MIL-T-60394A (AR)
AMENDMENT 2
1 August 1978
SUPERSEDING
AMENDMENT 1
7 May 1968

MILITARY SPECIFICATION

TAPE-PRESSURE-SENSITIVE ADHESIVE
FILM FOAM DOUBLE-COATED
(FOR USE WITH AMMUNITION)

This Amendment forms a part of Military Specification MIL-T-60394A (MU) dated 28 July 1967.

Add a new paragraph:

*1.2 Classification.- The tape covered by this specification shall be of the following types and classes as specified (See 6.1)

Type I - Regular
Type II - High Performance
Class 1 - High density-open cell
Class 2 - High density-closed cell

Delete paragraph 3.1 in its entirety and substitute the following:

*"3.1 Construction.- The tape shall consist of a high density, open or closed cell foam plastic backing, coated on both sides with a homogeneous, pressure-sensitive adhesive, applied in a smooth uniform layer throughout the length of the tape. The finished tape shall require no solvent, heat or other preparation prior to or after application to clean dry surfaces above freezing.

Paragraph 3.2, Physical Properties: Delete Table I in its entirety and substitute the new Table I on following page.

Paragraph 4.4.1: Delete "Code No. 04001, Major Defect" and substitute "Dynamic, Code No. 04001; Static.- Code No. 04002, Major Defects."

Test Method Paragraphs:

Paragraph 4.4.1.1: Add "e. Weights for static test, 2.5 kilograms each."

FSC 7510:

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:34Z
Check the source to verify that this is the current version before use.

TABLE I

TYPE	I		II		
PROPERTY	MINIMUM	MAXIMUM	MINIMUM	MAXIMUM	TEST PARAGRAPH
Dynamic Normal Tensile Pound Per Square Inch (psi)	15	--	25	--	4.4.1
Dynamic Normal Tensile (Aged) (psi)	9	--	25	--	4.4.1
Caliper (w/o liner) inches	0.021	0.045	0.021	0.045	4.4.2
Peel Adhesion unaged inches width/ozs.	45	--	45	--	4.4.3
Liner Removal Unaged oz/in	--	4.0	--	4.0	4.4.4
Aged oz/in	--	4.0	--	4.0	4.4.4
Holding Power Unaged minutes	2000	--	7000	--	4.4.5
Aged minutes	2000	--	7000	--	4.4.5
Static "Normal" Tensile hours	--	--	72	--	4.4.1
Compatibility (Reactivity) milliliters (see para. 6.3)	--	5	--	5	4.4.6

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:34Z
Check the source to verify that this is the current version before use.

Paragraph 4.4.1.3: Add the words "for Dynamic 'Normal' Tensile" after the word "Procedure" in the first line.

Paragraph 4.4.1.4: Add new paragraph as follows:

"4.4.1.4 Procedure for Static 'Normal' Tensile.- The 'T' blocks shall be cleaned by immersing in the MEK for 10 minutes and then removed and wiped dry with surgical gauze. The test specimen shall be placed, liner side down, on a flat horizontal surface. The one-inch square face of the 'T' block shall be contacted with the exposed adhesive surface of the specimen and pressed together. Using a razor or safety knife, the specimen shall be cut around the block so as to make the liner side of the specimen the exact dimensions of the block. The liner shall be removed and the 'T' block placed on its side with the 'T' section vertical. The other 'T' block shall be placed against the exposed adhesive, taking care that the two faces are in perfect alignment. The first mating is the only one possible, as once together the two blocks cannot be separated without damaging the specimen. If the first mating is not perfect, discard the specimen and repeat the above steps. Hang the mated 'T' blocks by the hole in one block so that it hangs free and add the 2.5 kilogram weight to the other block. Allow the loaded specimen to hang undisturbed. Time the specimen until the blocks separate due to failure of the tape. Remove the bulk of the foam from the blocks to place them in the MEK."

*Delete "FSC: 1375" and substitute "FSC-7510".

"The margins of this amendment are marked with an asterisk to indicate where changes (additions, modifications, corrections, deletions) from the previous amendment were made. This was done as a convenience only and the Government assumes no liability whatsoever, for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous amendment."

Custodian:
ARMY-AR

Preparing Activity
ARMY-AR

*Project Number 7510-A307

Source: https://assist.dla.mil - Downloaded: 2026-10-23T00:34Z
Check the source to verify that this is the current version before use.