[METRIC]

A-A-1225A
November 18, 1992
TO SUPERSEDE
A-A-1225
September 20, 1982

COMMERCIAL ITEM DESCRIPTION

PAPER, CARBON, DUPLICATING MACHINE

The General Services Administration, Office Supplies and Paper Products Commodity Center, New York, NY 10278, has authorized the use of this Commercial Item Description in lieu of Federal Specification UU-P-150, which is cancelled.

This description covers smudge-resistant carbon paper sheets for use in preparing duplicating masters.

1. Salient characteristics:

A. Paper used for base paper stock shall consist of bleached chemical wood, groundwood, or a similar base stock. Basis weight of the paper stock shall be not less than 51.805 grams per meter square (35 pounds (25 x 38-500)) when tested in accordance with TAPPI T410. The carbon paper sheet shall be 216mm x 279mm (8 1/2 x 11 inches) or 216mm x 356mm (8 1/2 x 14 inches) +/- 0.79mm (1/32 inch), as specified, including an uncoated edge 12.7mm (1/2 inch) wide across the short dimension. Color of the carbon shall be purple or black, as specified.

B. The base paper stock shall be coated with suitable waxes, dyes, and other necessary ingredients to ensure the quality and performance requirements. The carbon-coated side of the sheet shall be overcoated with a protective film which shall prevent the carbon surface from crystallizing, shall seal in the dye, and shall prevent smearing, smudging, soiling the hands, or discoloration of the master paper. Edges shall be sealed with a protective material to destroy permanently the aniline dyes.

Distribution Statement A:
Approved for public release;
distribution is unlimited.

FSC 7530

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:12Z
Check the source to verify that this is the current version before use.

C. The carbon paper shall have a smooth and calendered finish and shall give perfect release of the dye coating from the paper when impressed by type face, stylus or other means of transfer. Purple carbon paper, together with the master sheet, shall be capable of reproducing at least 300 clear, legible copies of good intensity. Black carbon paper shall be capable of reproducing at least 100 clear, legible copies of good intensity.

D. Bleaching: To obtain an acceptable brightness, a chemical bleaching process may be used. When specified, (See Section 6), the bleaching process shall not include the use of chlorine, chlorine dioxide, or hypochlorite. Certification of compliance shall be made available upon request by the Government.

E. Workmanship. The carbon paper shall be free from defects which might affect the appearance or quality of reproduction. Carbon coating shall be free of flaking, pinholes, wrinkles and other surface defects.

Table 1

Examine	Inspection Levels	AQLs (% defect)
Visual/Workmanship Defects	I	2.5
Dimensional Defects	S-3	4.0
Paper Characteristics	TAPPI	N/A
Preparation for Delivery	S-2	2.5

2. Quality Assurance Provisions. Responsibility for inspection. Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this commercial item description where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirement.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:12Z
Check the source to verify that this is the current version before use.

Sampling for examination and tests shall be performed in accordance with MIL-STD-105, using the plans as specified in Table 1, unless otherwise stated. For the purpose of sampling, a lot shall consist of duplicating paper. The sample unit shall be 1 duplicating paper for visual/workmanship and dimensional examination and one fully prepared shipping container for preparation for delivery examination, unless specified otherwise.

3. Regulatory requirements. The offeror/contractor is encouraged to use recovered materials in accordance with Public Law 94-580 to the maximum extent practicable.

4. Preservation, packaging, packing, labeling, and marking. Preservation, packaging, packing, labeling, and marking shall be as specified in the contract or order.

5. Application for copies of technical documents referenced herein: The issue date in effect on date of invitation for bids or request for proposal shall be apply.

   (1) TAPPI test methods are available from the Technical Association of the Pulp and Paper Industry, P.O. Box 105113, Atlanta, GA 30348.
   (2) MIL-STD-105 is available from Standardization Documents Order Desk, Bldg. 4D, 700 Robbins Ave., Philadelphia, PA 19111-5094.

6. Ordering Data. Purchasers should select the preferred options permitted herein, and include the following information in procurement documents:

   A) Packaging, packing and marking.
   B) Dimensions.
   C) Whether bleaching without use of chlorine, chlorine dioxide, or hypochlorite is required.

MILITARY INTERESTS:

DOD has waived coordination of this document

CIVIL AGENCY COORDINATING ACTIVITY:
COMMERCE-NIST

PREPARING ACTIVITY:
GSA-FSS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:12Z
Check the source to verify that this is the current version before use.