[INCH - POUND]
A-A-3150
March 4, 1998

COMMERCIAL ITEM DESCRIPTION

PILLOW, BED (LATEX FOAM AND POLYESTER FIBERFILL)

The General Services Administration has authorized the use of this commercial item description, for all Federal agencies.

1. SCOPE

1.1 Scope. This commercial item description (CID) covers requirements for one size and one type of bed pillow consisting of a flexible cellular latex foam envelope filled with polyester fiberfill and covered with a removable flame resistant cloth cover that closes at one end with a slide fastener.

2. SALIENT CHARACTERISTICS.

2.1. Design and construction. The design and construction of the pillow shall include all materials and processes necessary to produce a functional, durable, attractive finished bed pillow meeting the requirements stated herein.

2.1.1 Pillow insert. The pillow insert shall be a flexible cellular latex foam envelope filled, without void spaces at the edges and corners, with an inner core of 17 ± 1 ounces (482 ± 28 g) of first quality polyester fiberfill specifically designed as filling material for sleep pillows. The envelope walls shall be 1/2 ± 1/16 inch (1.3 ± 0.2 cm) thick. The seams shall be flexible and made in accordance with standard commercial practice. The foam shall be uniform and free from large internal voids perceptible on the exterior of the pillow insert by sight or touch. Bonded shredded foam or loose foam shall not be permitted.

2.1.1.1 Flexible cellular latex foam. The latex foam shall meet the requirements in Table I.

Table I. Physical requirements for flexible cellular latex foam.

Characteristic	Requirement	Test Method
Compression set	20%, maximum.	ASTM D 1055
Flexing resistance	250,000 cycles, no breakdown.	ASTM D 1055
Compression set, after flexing	10%, maximum.	ASTM D 1055
Indentation	25 - 40 lbf (111 - 178 N), tested on whole foam insert at the center.	ASTM D 1055
Indentation, after accelerated aging	35% change, maximum.	ASTM D 1055
Static fatigue	No cracking at the folded edge.	ASTM D 1055
Seam bond	The bond shall be stronger that the adjoining foam when separated by hand.	
Odor	Free from any pronounced odor.	
Fire resistance (see 2.3.1).	10, maximum. No running, dripping, or melting.	ASTM E-162

Beneficial comments, recommendations, additions, deletions, clarifications, etc. and any data which may improve this document should be sent to: General Services Administration, Engineering Branch (7FXEE), 819 Taylor Street, Fort Worth, TX 76102-6114.

FSC 7210

Source: https://assist.dla.mil -- Downloaded: 202610-26T08:30Z
Check the source to verify that this is the current version before use.

2.1.2 Removable pillow cover. The cover edges shall be parallel to the fabric grain. The cover shall close with a slide fastener not more than 2 inches (5 cm) shorter than the finished width of the pillow cover. All seams shall be straight, uniform, and sewn with sufficient stitches per inch to produce secure seams that do not slip or pull out. All stitching shall be uniform and evenly spaced. No raw edges shall be exposed on the finished cover. Seams shall not slip or pull out. All thread ends, when not caught in other seams and stitching, shall be secured to prevent unraveling.

2.1.2.1 Pillow cover fabric. The cover shall be made from 6.2 oz per sq yd (206.7 g per sq m) minimum weight, white, pre-shrunk, 100% cotton cloth treated with a flame resistant finish (see 2.3.2). The fabric shall be odor free, suitable for pillow covering, durable in appearance and function to repeated use and laundering, and soft and smooth enough to allow the finished pillow (pillow insert inside the cover) to slip easily into an appropriately sized pillow case without dragging or bunching. The cloth shall have not more than 1.5% residual shrinkage in either the warp or filling direction; a minimum breaking strength of 55 lbf (244.8 N) in both warp and filling directions; and a pH value of not less than 4.5 nor more than 8.0. Breaking strength may be determined before the cloth has been treated with a flame resistant finish, at the manufacturer's option.

2.1.2.2 Thread. Spun or multi-filament thread of a type appropriate for sleep pillow production and for the ticking shall be used for the cover. Thread color shall match the cloth color. The thread shall be durable in appearance and function to the care method appropriate for the finished pillow cover.

2.2 Dimensions. The insert and cover shall be rectangular in shape and have the dimensions shown in Table II. Length and width measurements shall be determined from end of seam to end of seam on the finished components. The cover shall be measured flat, before the insert is added. Pillow insert loft shall be measured with the finished insert in a relaxed state.

Table II. Minimum finished pillow component dimensions.

	Length, inches (cm) ± .05 in (±1.3 cm)	Width, inches (cm) ± .05 in (±1.3 cm)	Loft (thickness at center), inches (cm) ± .05 in (±1.3 cm)
Pillow Insert	23.5 to 24.5 (59.7 to 62.2)	16.5 to 17.5 (42.0 to 44.5)	6.0 to 7.0 (15.2 to 17.8)
Pillow Cover	27.5 (70.0)	22.25 (56.5)	NA

2.3 Flammability.

2.3.1 Foam envelope of pillow insert. The foam envelope shall have a fire resistance of 10, maximum, when tested in accordance with ASTM E-162, Standard Test Method for Surface Flammability of Materials Using a Radiant Heat Energy Source, using one inch (2.5 cm) hexagonal screen. The material shall exhibit no running, dripping or melting. The test specimen shall be 1 inch (2.5 cm) thick.

2.3.2 Pillow cover. The cloth shall pass flammability testing after a minimum of ten (10) launderings when laundered in accordance with AATCC 135 using machine washing and tumble drying procedures for sturdy cotton. The maximum average length of char or destroyed cloth shall not exceed 5-1/2 inches (14.0 cm) when tested in accordance with FED-STD-191, Test Method 5903.1. The cloth shall not continue flaming for more than two seconds after the flame is removed from the specimen.

2.4 Labels. Each pillow insert and cover shall have permanent, tear resistant label(s) marked with the following information: National Stock Number (NSN); pillow dimensions; fiber content of the cover; insert and filling material; care instructions appropriate for the pillow; and a label conforming to the legal requirements of the state of manufacture, if applicable. Manufacturer's name and trademark may be added to the permanent label(s), at the manufacturer's option. When allowed under state law, the information required under state regulation may be combined in the identification and care label. The label(s) shall be attached to an end seam. Multiple labels shall be layered in one area. All required information shall be completely visible after the label(s) is (are) sewn in. Marking shall be well defined and clearly legible. Label material and marking shall be durable to the care method appropriate for the pillow.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:30Z
Check the source to verify that this is the current version before use.

2.5 Workmanship. The finished pillow (insert and cover) shall conform to the quality of product established by this commercial item description and shall function as a comfortable, durable sleep pillow. The cover fabric shall be free from cuts, tears, mends, burns, thread pulls, or other fabric defects. The finished pillow (insert and cover) shall be clean, free from objectionable odor, and free of objectionable sound and crackling noise when the head is rested on the pillow. The cover shall fit smoothly on the finished pillow and shall fit so that the pillow is free to spread as required in use. The cover, when fitted over the insert, shall not pull so tightly that the fabric shows evidence of strain or that the stitching breaks or pulls loose. The finished pillow shall be free of any part assembled off grain or not aligned; corners not square; raw edges of any length; needle chews; puckered, twisted, pleated, uneven, or loose seams; or tight stitch tension (breaks when normal strain applied). Stitches shall be secure and uniform. The finished pillow insert shall be free of filling material on the outside. No defects affecting function, appearance, or serviceability shall be permitted.

2.6 Measurement system. The values stated in inch-pound units are to be regarded as the standard. The metric values stated in parenthesis are for information purposes only.

2.7 Metric products. Products manufactured to metric dimensions will be considered on an equal basis with those manufactured using inch-pound units, providing they fall within the tolerances specified and all other requirements of this document are met. If a product is manufactured to metric dimensions and those dimensions exceed the tolerances specified in the inch-pound units, a request should be made to the contracting officer to determine if the product is acceptable.

3. REGULATORY REQUIREMENTS.

3.1 Regulatory requirements. The offeror/contractor is encouraged to use recovered materials to the maximum extent practicable, in accordance with paragraph 23.403 of the Federal Acquisition Regulation (FAR).

4. QUALITY ASSURANCE PROVISIONS

4.1 Product conformance. The products provided shall meet the salient characteristics of this commercial item description, conform to the producer's own drawings, specifications, standards, and quality assurance practices and be the same product offered for sale in the commercial market. The government reserves the right to require proof of such conformance.

5. PACKAGING.

5.1 Packaging. Preservation, packing, and marking shall be as specified in the contract or purchase order.

6. NOTES.

6.1 Referenced documents. The documents referenced in this commercial item description shall be the issues in effect on the date of issuance of the invitation for bids or request for proposals unless otherwise specified. These documents form a part of this commercial item description to the extent specified. In the event of a conflict between this commercial item description and a document referenced herein, this commercial item description shall take precedence.

Copies of AATCC standards and test methods are available from American Association of Textile Colorists and Chemists, PO Box 12215, Research Triangle Park, NC 27709.

Copies of ASTM test methods are available from ASTM, 100 Barr Harbor Dr., West Conshohocken, PA 19428.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:30Z
Check the source to verify that this is the current version before use.

Copies of Federal standards, are available from the Federal Supply Service Bureau Specification Section (3FP-E), Specification Unit, Suite 8100, 470 E. L'Enfant Plaza, SW, Washington, DC 20407.

6.2 Ordering data. Purchaser should select the preferred options permitted herein and include the following information in procurement documents (if applicable).

a) Title, number, and date of this commercial item description.
b) The preservation, packing, and marking desired.

6.3 National stock number (NSN). NSN 7210-01-035-3342 corresponds to this commercial item description. This may not be the only NSN associated with the commercial item description.

MILITARY INTERESTS:

Military Coordinating Activity:

Custodians:
Air Force Code 99

Review Activities:
Air Force Codes 45, 03

CIVIL AGENCY COORDINATING ACTIVITIES:

PREPARING ACTIVITY:

GSA-FSS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:30Z
Check the source to verify that this is the current version before use.