INCH-POUND
MIL-L-83795B
3 Oct 1994
Superseding
MIL-L-83795A
31 May 1983

MILITARY SPECIFICATION

LAYOUT DYE, BLUE

This specification is approved for use by all
Departments and Agencies of the Department of Defense

1. SCOPE

1.1 Scope. This specification covers one type of blue layout dye to be applied to metal surfaces as a non-glare coating before scribing or marking of parts (see 6.1).

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation (see 6.2).

SPECIFICATIONS

Federal

PPP-B-621 - Box, Wood, Nailed and Lock-corner
PPP-B-636 - Box, Shipping Fiberboard
PPP-C-96 - Can, Metal, 28 Gage and Lighter
PPP-C-186 - Container, Packaging and Packing for Drugs, Chemicals and Pharmaceuticals

STANDARDS

Federal

FED-STD-313 Material Safety Data Sheets, Preparation and the Submission of
FED-STD-595 Color

Beneficial Comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Code (68) SA-ALC/SFSP, 1014 Billy Mitchell Blvd STE 1 Kelly AFB TX 78241-5603, by using the self-addressed standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A
FSC 6850
DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:47Z
Check the source to verify that this is the current version before use.

Military

MIL-STD-129 Marking for Shipment and Storage
MIL-STD-147 Palletized Unit Loads

(Unless otherwise indicated, copies of the federal and military specifications, standards, and handbooks are available from the Standardization Documents Order Desk, Building 4D 700 Robbins Avenue, Philadelphia PA 19111-5094 Copies required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.1.2 Other government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues are those cited in the solicitation.

DODISS - Department of Defense Index of Specifications and Standards

(The DODISS is available form the Standardization Documents Order Desk, the procuring activity or as directed by the contracting officer.)

Code of Federal Regulation 49 (49 CFR) - Transportation

(The Code of Federal Regulations and the Federal Register (FR) are for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402. When indicated, reprints of certain regulations may be obtained from the Federal agency responsible for issuance thereof.)

2.2. Other publications. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of the documents which are DoD adopted are those listed in the issue of the DODISS cited in the solicitation. Unless otherwise specified, the issues of the documents not listed in the DODISS are the issues of the documents cited in the solicitation (see 6.2).

AMERICAN SOCIETY FOR TESTING AND MATERIALS

ASTM Standards

D 56 Flash Point by Tag Closed Tester
D 1292 Standard Test Method for Odor in Water
E 29 Recommended Practices for Indicating Which Places of Figures are to be Considered Significant in Specified Limiting Values

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia PA 19103-1137.)

AMERICAN CHEMICAL SOCIETY (ACS) SPECIFICATIONS

ACS REAGENT CHEMICAL STANDARDS

(Application for copies should be addressed to the American Chemical Society, 1155 Sixteenth St., NW, Washington DC 20036.)

INTERNATIONAL CIVIL AVIATION ORGANIZATION (ICAO)

Technical Instructions for the Safe Transportation of Dangerous Goods by Air

(Application for copies should be addressed to International Civil Aviation Organization, Place de l'Aviation

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:47Z
Check the source to verify that this is the current version before use.

Internationale, 1000 Sheerbrooke St., W. Montreal, Quebec, Canada H3A 2R2.)

INTERNATIONAL AIR TRANSPORT ASSOCIATION (IATA)

Dangerous Goods Regulations

(Application for copies should be addressed to the International Air Transport Association, 2000 Peel St., Montreal, Quebec, Canada H3A 2R4.)

INTERNATIONAL MARITIME ORGANIZATION (IMO)

International Maritime Dangerous Goods Code (IMDGC)

(Application for copies should be addressed to the International Maritime Organization, 4 Albert Embankment, London SE1 7SR United Kingdom.)

(Industry association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 Layout dye.

3.1.1 General composition. The layout dye, flash point 55°F (12.8°C) minimum, shall conform to requirements of this specification and shall consist of a mixture of solvents and blue dye entirely suitable for the intended use of this product. (The flash point of 55°F (12.8°C) applies to layout dye destined for aerosol packaging before introduction into the aerosol container or contact with the propellant.) The liquid layout dye shall be completely homogeneous, without precipitation of solids, and without layering or separation of liquid components during use or storage. Composition of layout dye shall be at the option of the manufacturer except as limited by this specification. The layout dye shall not be corrosive to any metal alloys in common industrial use.

3.2 Toxicity. The product shall not have an adverse effect on the health of personnel or the environment when used in accordance with the manufacturers instructions.

3.3 Physical and chemical requirements.

3.3.1 Appearance. When applied to the surface to be coated, the product shall be of a deep blue color, shall provide a non-glare surface, and shall give the surface a uniform appearance and color. The blue color shall meet or exceed the blue color and appearance of Color Chip No. 25102, Table VII, FED-STD-595 (see 4.3.1). The layout dye shall be suitable for application by brush or spray methods.

3.3.2 Flash point. The flash point of the layout dye shall be 55°F (12.8°C) minimum, when tested as required in 4.3.2. (The flash point of 55°F (12.8°C) applies to layout dye destined for aerosol packaging before introduction into the aerosol container or contact with the propellant.)

3.3.3 Film thickness. Maximum film thickness of two layers of undiluted layout dye, when applied by use of a doctor blade, shall be 0.0098 inch (0.25 mm), when tested as required in 4.3.3. This film thickness requirement does not apply to layout dye in aerosol containers.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:47Z
Check the source to verify that this is the current version before use.

3.3.4 Drying time. When applied according to 3.3.3, the layout dye shall be dry to touch in no longer than two minutes, and shall be dry to scribe in no longer than five minutes, when tested as required in 4.3.4.

3.3.5 Resistance to flaking. After drying to scribe, as in 3.3.4, a sharp pointed scribing tool is used to make two lines intersecting at an angle of five degrees on a surface coated with layout dye, the coating will not peel or chip at the intersection of the two lines or in any other portion of the coated area, when tested as required in 4.3.5.

3.3.6 Adhesion of coating. The layout dye coating, when dry to scribe as in 3.3.4, shall not flake or scuff under maximum pressure which can be applied by thumb nail or by a wooden tongue depressor of the type commonly used in medicine.

3.3.7 Odor. The layout dye shall not have any offensive odors as tested in 4.3.6. The threshold odor number will be a maximum of 1 with a maximum odor intensity index of 0. This odor requirement does not apply to layout dye in aerosol containers.

3.3.8 Absorbance. The diluted layout dye shall have an absorbance of 0.50 to 0.60 units on a scale of 0 to 1, when tested as required in 4.3.7.

3.3.9 Viscosity. The layout dye shall have a draining time of 29 seconds to 32 seconds, at a temperature of 77°F (25°C), when tested as required in 4.3.8. This viscosity requirement does not apply to layout dye in aerosol containers.

3.3.10 Contents, non-aerosol containers. Contents of the screw top containers shall not be less than 1 gallon, 16.0 fluid ounces, 8.0 fluid ounces or 4.0 fluid ounces for the appropriate size container (see 6.2).

3.4 Pressurized container tests.

3.4.1 Leakage. When tested as specified in 4.3.10, the pressurized container shall not leak or become distorted. Containers shall be a commercial pressure-type generally known as aerosol containers of such construction as to assure acceptance of the finished package by common carriers operating in interstate commerce. The capacity shall be 16 fluid ounces with outage in accordance with generally recognized safe commercial practice.

3.4.2 Composition. The pressurized container shall contain 70 to 75 percent by weight layout dye and 25 to 30 percent by weight of isobutane/propane propellant. Sufficient propellant must be present to empty the container completely, in normal use. The net weight of the contents (layout dye and propellant) shall be no less than 12.0 ounces (avoirdupois) when tested as specified in 4.3.11.

3.5 Screw cap closure container tests.

3.5.1 Brush cap closures. Four fluid ounces (118.3 ml) and eight fluid ounce (226.6 ml) containers filled with layout dye will be provided with screw cap closures which incorporate a brush type applicator as an integral part of the closure. The bristles shall be 5/8 inch ± 1/16 inch long and 1/4 inch ± 1/16 inch wide and shall be made of natural goat hair or natural gray mixed horse hair. The hair shall be crimped into a suitable holder of sufficient length to permit the bristles to touch the bottom of the container with the top secured and attached to the screw cap in a manner which will meet the end use of applicator. Screw cap closures may be metal or plastic.

3.6 Material safety data sheets. A Material Safety Data Sheet shall be prepared in accordance with the requirements of FED-STD-313 (see 6.4).

3.7 Limiting values. The following applies to all specified limits in this specification: for purposes of determining conformance with these requirements, an observed value or a calculated value shall be rounded

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:47Z
Check the source to verify that this is the current version before use.

off "to the nearest unit" in the last right-hand place of figures used in expressing the limitation value, in accordance with ASTM Method E 29.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements (examinations and tests) as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this specification where such inspections are deemed necessary to ensure supplies and services conform to prescribed requirements. A certified test report shall be submitted to the Government procuring agency on each lot indicating test results verifying compliance with requirements of this specification.

4.1.1 Responsibility for compliance. All items shall meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of ensuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling inspection, as part of manufacturing operations, is an acceptable practice to ascertain conformance to requirements, however, this does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to accept defective material.

4.2 Quality conformance inspections.

4.2.1 Inspection of materials. The contractor shall insure that each lot of finished material furnished on the contract be sampled in accordance with 4.2.1.1, and subjected to all tests and inspection methods specified under 4.3.

4.2.1.1 Sampling. Sampling shall be in accordance with Table I. One or more defects shall be cause for rejection of the lot.

TABLE I. Sampling for tests and inspections.

Number of containers in lot	Number of sample containers
2 to 15	2
16 to 25	3
26 to 90	5
91 to 150	8
151 to 280	13
281 to 500	20
501 to 1200	32
1201 to 3200	50
3201 to 10000	80
10001 to 35000	125
35001 to 150000	200
150001 to 500000	315
500001 and over	500

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:47Z
Check the source to verify that this is the current version before use.

4.2.1.2 Lot definition. For the purpose of sampling, a lot shall consist of unit containers of the same size that have been filled with layout dye of the same type from one batch and which are presented for inspection at one time. A batch is defined as a homogeneous mixture of material manufactured by a single plant run through the same processing equipment during one continuous operation.

4.3 Test and inspection methods.

4.3.1 Appearance. The color and appearance of the layout dye coating on a metal surface, by visual comparison, shall meet or exceed the color of Color Chip No. 25102, Table VII, FED-STD-595.

4.3.2 Flash point. Determine the flash point of the layout dye using ASTM Method D 56 (Tag Closed Cup).

4.3.3 Film thickness. Determine film thickness using a micrometer calibrated in ten-thousandths of an inch and having a rachet type tightening screw for uniform closing. Measure over a flat, smooth finished section of stainless steel. Apply two layers of undiluted layout dye and allow to dry. Measure thickness of the layout dye coating on the same portion of the metal bar at which the original measurement was made.

4.3.4 Drying time. Dry to touch and dry to scribe requirements are applicable at an ambient temperature of 73.4°F ± 3.6°F (23° ±2°C), with no movement of ambient air during testing.

4.3.5 Resistance to flaking. To scribe lines, use a scriber, 0.046 inch in diameter, with a sharp point.

4.3.6 Odor. Odor shall be tested per ASTM Method D 1292.

4.3.7 Absorbance. Measure absorbance on a spectrophotometer at a wavelength of 586 nanometers, using a 10 millimeter square quartz cuvette cell. To make the test sample, dilute blue layout dye 1:2000 with ACS Grade Acetone. Follow manufacturer's instructions in regard to use of the spectrophotometer.

4.3.8 Viscosity. Determine viscosity of the layout dye using a No. G-1 Zahn Cup, at 77°F (25°C). Follow manufacturer's instructions in use of the Zahn Cup.

4.3.9 Contents, non-aerosol containers. Weigh a filled container, at room temperature to ± 0.01 gram. Empty the same container, rinse with ACS Grade Naphtha, and allow to dry thoroughly. Weigh the empty container to the nearest 0.10 gram and determine the net weight of contents (layout dye). Determine the number of grams (to the nearest ± 0.01 gram) per fluid ounce (or gallon) of layout dye. Use this density to convert the weight of the contents of the container to fluid ounces (or gallons). Contents less than the required fill shall constitute failure.

4.3.10 Leakage, pressurized containers. Using a filled pressurized can, spray the layout dye for three seconds and pause for two seconds. Repeat this operation five times. After spraying has been completed, submerge the can completely in water maintained at 113°F (45°C). Allow the can to remain for five minutes. The emission of bubbles shall indicate leakage. At the end of five minutes, remove the can from the water and examine it for distortion.

4.3.11 Composition, pressurized containers. Weigh the filled pressurized container(s) to the nearest 0.10 gram. Place container for a minimum of 24 hours in a cold box maintained at -13° ± 1.8°F (-25° ± 1°C).

WARNING

Wear protective goggles and gloves, when puncturing container. Pad container and clamp firmly in a vise, when puncturing. Do not allow can to become warmer, before puncturing.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:47Z
Check the source to verify that this is the current version before use.

Remove container, and immediately puncture. Allow can to warm up to room temperature in order to allow propellant to escape. After propellant has evaporated, weigh can and layout dye. Puncture a larger opening, without losing metal from container, and empty the can completely. Rinse container thoroughly, dry, and weigh to the nearest 0.01 gram. Calculate the weights of layout dye and propellant as follows:

$$A = \text{Weight of propellant (ounces)} = \frac{W_1 - W_2}{28.350}$$

$$\% \text{ Propellant} = \frac{A\ (100)}{12}$$

$$B = \text{Weight of layout dye (ounces)} = \frac{W_2 - W_3}{28.350}$$

$$\% \text{ Layout Dye} = \frac{B\ (100)}{12}$$

W_1 = Initial weight (container plus total content).
W_2 = Weight of container and layout dye after propellant has been allowed to evaporate.
W_3 = Weight of empty container.

"A" plus "B" shall be added together to determine compliance with 3.4.2

4.3.12 Packaging inspection. The container shall be examined as follows for the defects listed:

EXAMINATION	DEFECT
-Appearance, construction, and workmanship	Not in container specified, cracked, crushed or any defect affecting serviceability. Not clean; evidence of dirt, rust or foreign matter.
-Closures	Any leakage or seepage of contents in either an upright or horizontal position. Closure not as specified.
-Marking	Omitted, illegible, incorrect or not in accordance with contract requirements.

4.4 Examination of preparation for delivery. An examination shall be made to determine the packing, palletization and markings comply with Section 5.

Source: https://assist.dla.mil -- Downloaded: 202610-26T04:47Z
Check the source to verify that this is the currentversion before use.

EXAMINATION	DEFECT
-Packing	Container not as specified. Bulged, distorted or deteriorated containers.
-Palletization	Palletization not in accordance with contract requirements.
-Markings	Data illegible, incorrect, incomplete or not in accordance with contract requirements.

4.5 Rejection and retest. Rejected material shall not be resubmitted for acceptance without prior approval of the procuring activity. The application for resubmission shall contain full particulars concerning previous rejections and all measures taken to correct those defects. Samples for retest shall be taken from previously unopened products containers.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be Level "A" or "Industrial" as specified (see 6.2). Packaging shall also be in accordance with Code of Federal Regulation 49 (49 CFR), International Civil Aviation Organization (ICAO) "Technical Instructions for Safe Transport of Dangerous Goods by Air", International Air Transportation Association (IATA) "Dangerous Goods Regulations", and International Maritime Organization (IMO) "International Maritime Dangerous Goods Code (IMDGC)", as applicable to mode of transportation and destination. The Packaging shall meet the applicable performance tests in the aforementioned directives.

5.1.1 Level A.

5.1.1.1 Unit containers.

(a) Four fluid ounces (118.3 ml) of layout dye shall be packaged in a screw top container with brush top closure (see 3.5.1) conforming to Type VIII metal cans of PPP-C-96 or Group A, Class 2, Style 1, Grade optional, Closure A, plastic bottles of PPP-C-186. Containers shall also conform to the requirements of 49 CFR (DOT 2F) and United Nations (UN)/International requirements as stipulated in ICAO, IATA, and IMDGC (IP3/IC3) as applicable to mode of transportation and destination. The plastic bottles shall have a secondary closure of shrinkable tape applied to the closure. The shrinkable tape shall not react with or cause decomposition of the plastic container.

(b) Eight fluid ounces (236.6 ml) of layout dye shall be packaged in a screw top container with brush top closure (see 3.5.1) conforming to Type V, Class 4, metal cans of PPP-C-96 or Group A, Class 2, Style 1, Grade optional, plastic bottles of PPP-C-186. Containers shall also comply with the additional directives stipulated in 5.1.1.1 (a). The plastic bottles shall have a secondary closure of shrinkable tape applied to the closure. The shrinkable tape shall not react with or cause decomposition of the plastic container.

(c) Twelve fluid ounces (354.9 ml) of layout dye shall be packaged in a container conforming to Type IX, Class 4 (DOT 2P) or 5 (DOT 2Q) of PPP-C-96. Containers shall also conform to ICAO (1F.7, 1P.7A, 1F.7B), IATA (1C.7, 1C.7A) and IMDGC requirements as applicable to mode of transportation and destination. The dispenser shall be the aerosol type and shall have a finger pressure type dispensing device to produce the desired spray, so designed as to shut off when the finger pressure is released. The device shall be protected from accidental activation by the use of a snug-fitting metal or plastic protective cap.

(d) Sixteen fluid ounces (473.2 ml) shall be packaged in a metal container conforming to Type V, Class 4 of PPP-C-96. Containers shall also comply with the additional directives stipulated in 5.1.1.1 (a).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:47Z
Check the source to verify that this is the current version before use.

(e) One gallon (3.785 L) of layout dye shall be packaged in a screw top container conforming to Type V, Class 4, metal cans of PPP-C-96 or Group A, Class 2, Style 1, Grade optional, Closure A, plastic bottles of PPP-C-186. Containers shall also comply with the additional directives stipulated in 5.1.1.1 (a). The plastic bottles shall have a secondary closure of shrinkable tape applied to the closure. The shrinkable tape shall not react with or cause decomposition of the plastic container.

5.1.1.2 Intermediate packaging. Layout dye packaged as specified in 5.1.1.1 shall be intermediately packaged 12 to a box (except the one gallon size container described in 5.1.1.1 (e) above, which shall be packaged 4 to a box) in a snug-fitting fiberboard container conforming to Style RSC, Grade W5c of PPP-B-636. Full height, half-slotted style partitions fabricated of material equal to the strength of the fiberboard used for container construction shall be provided to form an individual snug-fitting cell for each unit container. Pads fabricated of material equal to the strength of the fiberboard used for container construction shall be positioned on the bottom and top of partitions. Pads shall not measure less than 1/4 inch less than the inside length and width of the intermediate container. The containers shall also conform to 49 CFR (DOT 12B), ICAO/IMDGC (4G) and IATA (T5A) as applicable to mode of transportation and destination.

5.1.2 Industrial packaging. Quantities of layout dye, as specified (see 6.2) shall be packaged in accordance with the directives stipulated in 5.1.1.1 (a) as applicable to mode of transportation and destination.

5.2 Packing. Packing shall be Level "A", "B" or "Industrial" as specified (see 6.2). The requirements of paragraph 5.1 also apply.

5.2.1 Level A. Layout dye, packaged as specified in 5.1.1.1 and 5.1.1.2, shall be packed for shipment in nailed wooden boxes conforming to Class 2, Style 4 1/2, Grade A, for a Type 2 average load of PPP-B-621, as specified (see 6.2). Containers shall also conform to 49 CFR (15B), ICAO/IMDGC (4C1) and IATA (T4A) as applicable to mode of transportation and destination. Closure shall be in accordance with requirements of applicable directive(s).

5.2.2 Level B. Layout dye, packaged as specified in 5.1.1.1 and 5.1.1.2 shall be packed for shipment in fiberboard box conforming to Type RSC, Grade V3c of PPP-B-636. Containers shall also conform to 49 CFR (DOT 12B), ICAO/IMDGC (4G) and IATA (T5A) as applicable to mode of transportation and destination. Closure shall be by taping in accordance with the requirements of applicable directive(s).

5.2.3 Industrial. Layout dye, packaged as specified in 5.1.2 in quantities as specified in the contract or order (see 6.2), shall be packed to insure carrier acceptance and safe delivery to the procuring activity. Containers shall be in compliance with 49 CFR, ICAO, IATA, and IMDGC as applicable to mode of transportation and destination.

5.3 Palletization. When specified (see 6.2), the layout dye shall be palletized in accordance with Load Type III of MIL-STD-147 except that for overseas shipments the overall height of the load shall not exceed 43 inches (109.2 cm).

5.4 Markings. In addition to special markings in 5.4.1 and any other markings required by the contract or order, marking shall be in accordance with 49 CFR, ICAO, IATA, and IMDGC as applicable to mode of transportation and destination.

5.4.1 Special markings. Each unit container shall be legibly marked to show the directions for use and each container of the material shall have the following CAUTION label:

Source: https://assist.dla.mil -- Downloaded: 202610-26T04:47Z
Check the source to verify that this is the currentversion before use.

WARNING

Extremely flammable. Keep from heat, sparks and open flames. Keep container closed when not in use. Use with adequate ventilation. Avoid prolonged or repeated contact with skin. Do not reuse container when empty. Dispose of properly.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. Layout dye, a fast-drying liquid, is used to provide a dark blue, non-glare coating on metal parts or assemblies before scribing.

6.2 Procuring data. Procuring activities should select from the options provided herein, and contracts or orders should include the following information.

(a) Title, number, and date of this specification.

(b) Level of packing and packaging required (see section 5).

(c) Inspection responsibility, if other than specified herein.

(d) Type and size of container required (see section 5).

(e) Issue of DODISS to be cited in the solicitation, and if required, the specific issue of individual documents referenced (see 2.1 and 2.2).

(f) Additional markings on unit containers and on outer shipping containers.

(g) Palletization, when specified.

6.3 Contractor data requirement. Data conforming to Data Item Description DI-NDTI-80809A will usually be required for delivery in connection with this specification. When so required, such data will be specified for delivery on a DD Form 1423 included in the contract.

6.4 Material safety data sheets. Contracting officers will identify those activities requiring copies of completed Material Safety Data Sheets prepared in accordance with FED-STD-313. The pertinent Government mailing addresses for submission of data are listed in FED-STD-313.

6.5 Changes from previous issue. Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extensiveness of the changes.

6.6 Subject term (key word) listing.

Layout dye
Fast-drying

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:47Z
Check the source to verify that this is the current version before use.

Custodian:

Air Force - 68

Review activities:
DLA - GS
Navy - AS

Using Activities:

Navy - AS, SH, MC

Preparing activity:

Air Force - 68

Project No. 6850-1077

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:47Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	1. DOCUMENT NUMBER	2. DOCUMENT DATE (YYMMDD)
	MIL-L-83795B	941003

3. DOCUMENT TITLE
Layout Dye Blue

4. NATURE OF CHANGE (Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle Initial)	b. ORGANIZATION	
c. ADDRESS (Include Zip Code)	d. TELEPHONE (Include Area Code) (1) Commercial (2) AUTOVON (If applicable)	7. DATE SUBMITTED (YYMMDD)

8. PREPARING ACTIVITY

a. NAME	b. TELEPHONE (Include Area Code)	
SA-ALC/SFSP	(1) Commercial (210) 925-7847	(2) AUTOVON 945-7847
c. ADDRESS (Include Zip Code) 1014 BILLY MITCHELL BLVD, STE 1 KELLY AFB, TX 78241-5603	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT: Defense Quality and Standardization Office 5203 Leesburg Pike, Suite 1403, Falls Church, VA 22041-3466 Telephone (703) 756-2340 AUTOVON 289-2340	

DD Form 1426, OCT 89 — Previous editions are obsolete. — 198/290

Source: https://assist.dla.mil -- Downloaded: 202610-26T04:47Z
Check the source to verify that this is the current version before use.