MIL-C-44187B
31 March 1988
SUPERSEDING
MIL-C-44187A
10 October 1985

MILITARY SPECIFICATION

CLOTH, LAMINATED, WATERPROOF AND MOISTURE VAPOR PERMEABLE

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This document covers a three-layered laminated cloth which is waterproof and moisture vapor permeable.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

* 2.1.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of these documents shall be those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation.

SPECIFICATIONS

FEDERAL

O-I-503	-	Insect Repellent, Clothing and Personal Application
P-D-245	-	Detergent, Laundry and Hand Dishwashing (Granular)
PPP-P-1136	-	Packaging of Coated (Plastic; Rubber) and Laminated Fabrics

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: U.S. Army Natick Research, Development, and Engineering Center, Natick, MA 01760-5014 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 8305

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 202610-22T00:27Z
Check the source to verify that this is the current version before use.

MILITARY

MIL-C-21852 - Cloth, Taffeta, Nylon

STANDARDS

FEDERAL

FED-STD-101 - Test Procedures for Packaging Materials
FED-STD-191 - Textile Test Methods
FED-STD-601 - Rubber: Sampling and Testing

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes

(Copies of specifications, standards, and handbooks required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

2.1.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this specification to the extent specified herein. Unless otherwise specified, the issues shall be those in effect on the date of the solicitation.

FEDERAL TRADE COMMISSION

Rules and Regulations Under the Textile Fiber Products Identification Act

(Copies may be obtained from the Federal Trade Commission, Correspondence Branch, Pennsylvania Avenue at Sixth Street, N.W., Washington, DC 20580.)

DRAWINGS

U.S. ARMY NATICK RESEARCH, DEVELOPMENT, AND ENGINEERING CENTER

2-1-1516B - Woodland Pattern - 60 inches

(Copies of drawings, publications, and other Government documents required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

* 2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted shall be those listed in the issue of the DODISS specified in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS shall be the issues of the nongovernment documents which are current on the date of the solicitation.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T00:27Z
Check the source to verify that this is the current version before use.

AMERICAN ASSOCIATION OF TEXTILE CHEMISTS AND COLORISTS (AATCC)

Chromatic Transference Scale

119 - Color Change Due to Flat Abrasion (Frosting): Screen Wire Method

(Copies should be obtained from the American Association of Textile Chemists and Colorists, P.O. Box 12215, Research Triangle Park, NC 27709-2215.)

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

D 618 - Conditioning of Plastics and Electrical Insulating Materials for Testing

D 2582 - Puncture-Propagation Tear Resistance of Plastic Film and Thin Sheeting

E 96 - Water Vapor Transmission of Materials, Procedure B and BW

(Copies should be obtained from the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103-1187.)

(Nongovernment standards and other publications are normally available from the organizations which prepare or which distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein, the text of this specification shall take precedence. Nothing in this specification, however, shall supersede applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 Standard sample. The printed laminated cloth shall match the standard sample for shade and appearance and shall be equal to or better than the standard with respect to all characteristics for which the standard sample is referenced (see 6.3).

3.2 First article. When specified in the contract or purchase order, a sample shall be subjected to first article inspection (see 4.3, 6.2, and 6.8).

3.3 Materials.

3.3.1 Base cloths.

3.3.1.1 Plain weave. The plain weave cloth shall be nylon, 2.8 $\pm$ 0.2 ounces per square yard Woodland Pattern Camouflage . The cloth shall be woven with a minimum of 101 ends per inch and 63 two-ply textured picks per inch.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T00:27Z
Check the source to verify that this is the current version before use.

3.3.1.2 Tricot knit. The tricot knit cloth shall be nylon, 1.5 ± 0.3 ounces per square yard, Olive Green 106. The cloth shall be knit on 2 bars using 40 denier multifilament and 15 denier monofilament yarn.

3.3.2 Plastic film. The plastic film shall be microporous polytetrafluoroethylene, weighing 0.5 ± 0.2 ounces per square yard.

3.3.3 Adhesive. The adhesive for laminating the layers together shall be such that the laminated cloth will meet the requirements of this document. The adhesive shall have no adverse health hazard when used as intended.

3.4 Laminated cloth. The cloth specified in 3.3.1.1 shall be laminated to one side of the plastic film specified in 3.3.2 and the cloth specified in 3.3.1.2 shall be laminated to the other side of the plastic film. The face side of the laminated cloth shall be the side with the cloth specified in 3.3.1.1. An approved water repellent finish shall be applied to the face side of the laminated cloth (see 3.5.1 and 6.4).

3.4.1 Color. The color of the face side of the laminated cloth shall be Woodland Pattern Camouflage. The color of the back side of the laminated cloth shall be OG 106. Both sides of the fabric shall match the respective side of the standard sample.

* 3.4.2 Matching. The color and appearance of the camouflage printed laminated cloth shall match the standard sample when viewed under filtered tungsten lamps that approximate artificial daylight and that have a correlated color temperature of 7500 ± 200K, with illumination of 100 ± 20 foot candles and shall be a good match to the standard sample under incandescent lamplight at 2300 ± 200K.

* 3.4.3 Colorfastness. The printed, laminated cloth shall meet the following colorfastness requirements when tested in accordance with 4.4.3 for the characteristics listed below:

Colorfastness characteristics	Requirement
Fastness to light (after 40 hrs) and fastness to laundering (after 3 cycles)	Equal to or better than the standard sample, or equal to or better than "good"
Fastness to perspiration	Equal to or better than the standard sample, or equal to or better than "good" 1/
Fastness to crocking	Equal to or better than the standard sample or not less than AATCC Chromatic Transference Scale Rating of 3.5 2/
Fastness to abrasion (Black 357 only)	Equal to or better than the standard sample

Source: https://assist.dla.mil -- Downloaded: 202610-22T00:27Z
Check the source to verify that this is the currentversion before use.

1/ Except the fastness of Dark Green 355 and Brown 356 shall be not less than "fair" when tested for fastness to alkaline perspiration.

2/ Except Black 357 shall show an AATCC Chromatic Transference Scale rating of not less than 1.0.

3.4.4 Pattern execution. The pattern shall reproduce the standard sample in respect to design, colors, and registration of the respective areas. The pattern repeat of the printed and laminated cloth shall be 27.25 + 1.25, - 2.50 inches in the warp direction. Each pattern area shall show solid coverage; skitteriness exceeding that shown by the standard sample in any of the printed areas will not be acceptable. When the standard sample is not referenced for pattern execution on design, the pattern of the base cloth shall match the standard Woodland Camouflage Pattern Drawing 2-1-1516B.

* 3.4.5 Spectral reflectance. The camouflage printed and water repellent treated side of the laminated cloth shall conform to the spectral reflectance requirements specified in table I when tested as specified in 4.4.3.

TABLE I. Spectral reflectance requirements

Wavelength nanometers	Reflectance values (percent)					
	Black 357		Light Green 354		Dark Green 355 and Brown 356	
	Min.	Max.	Min.	Max.	Min.	Max.
600	--	--	10	20	4	8
620	--	--	10	20	4	8
640	--	--	9	20	4	8
660	--	--	8	20	3	8
680	--	--	8	32	3	22
700	--	10	14	53	9	41
720	--	10	35	67	25	60
740	--	10	55	73	50	73
760	--	10	60	78	55	78
780	--	10	60	80	57	80
800	--	10	60	81	59	81
820	--	10	60	82	60	82
840	--	10	60	82	60	82
860	--	10	60	82	60	82

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T00:27Z
Check the source to verify that this is the current version before use.

* 3.5 Physical requirements. The laminated cloth shall conform to the requirements in table II when tested as specified in 4.4.3.

TABLE II. Physical requirements

Characteristics	Minimum	Maximum
Weight, oz/sq yd	--	5.9
Breaking strength, lbs:		
Warp	135	--
Filling	100	--
Tearing resistance, kgf:		
Warp	3.5	--
Filling	3.2	--
Moisture vapor transmission rate, $g/m^2/24$ hr:		
Procedure B		
Initial	600	--
After synthetic perspiration	600	--
Procedure BW		
Initial	3600	--
Hydrostatic resistance, psi:		
Initial	90	--
After strength of coating	80	--
After abrasion		
Face	80	--
Back	80	--
After insect repellent	80	--
Stiffness (warp only), cm	--	12.0

Source: https://assist.dla.mil -- Downloaded: 202610-22T00:27Z
Check the source to verify that this is the current version before use.

TABLE II. Physical requirements - Continued

Characteristics	Minimum	Maximum
Water permeability:		
Initial		no leakage
After synthetic perspiration		no leakage
After flex (70°F)		
Warp		no leakage
Filling		no leakage
After cold flex (-25°F)		
Warp		no leakage
Filling		no leakage

3.5.1 Water repellency. The laminated cloth shall be given an approved Quarpel type water repellent treatment on the face side of the cloth and shall conform to the water repellency requirements. The use of materials other than approved water repellents are prohibited (see 6.4).

3.5.2 Spray ratings. The results of the three individual determinations on the sample unit for spray rating shall be equal to or better than ratings 100, 90, 90 initially and the ratings shall be equal to or better than ratings of 90, 90, 80 after three launderings.

* 3.5.3 Resistance to organic liquids. The finished cloth shall show no wetting by n-tetradecane, initially and after three launderings. Different specimens shall be used for initial and after laundering specimens.

3.5.4 Resistance to delamination. Delamination between the cloth and film after five launderings shall not exceed 0.25 linear inches, when tested as specified in 4.5.5.

* 3.5.5 Dimensional stability. The shrinkage or elongation in the warp direction of the finished cloth shall not be greater than 4.5 percent for the individual sample unit and not greater than 4.0 percent for the lot average, and in the filling direction of the finished cloth, the shrinkage or elongation shall not be greater than 2.5 percent for the individual sample unit and not greater than 2.0 percent for the lot average when tested as specified in 4.4.3.

3.6 Width. The minimum overall width shall be as specified (see 6.2). Selvages shall be trimmed to give straight, uniform, fully laminated edges.

Source: https://assist.dla.mil -- Downloaded: 202640-22T00:27Z
Check the source to verify that this is the current version before use.

3.7 Length and put-up. Each roll shall contain no more than five pieces and no single piece shall be less than 10 yards in length. Acceptance of shorter lengths, if permitted, shall be based on the conditions stipulated in the contract or purchase order (see 6.2). The cloth shall be put-up on full width rolls as specified in 5.1.

3.8 Fiber identification. Each roll shall be labeled and ticketed for fiber content in accordance with the Textile Fiber Products Identification Act.

3.9 Workmanship. The laminated cloth shall conform to the quality of product established by this document. The occurrence of defects shall not exceed the applicable acceptable quality levels.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this document where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

* 4.1.1 Responsibility for compliance. All items must meet all requirements of sections 3 and 5. The inspection set forth in this document shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirement in the document shall not relieve the contractor of the responsibility of assuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling in quality conformance does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to acceptance of defective material.

4.1.2 Certificates of compliance. When certificates of compliance are submitted, the Government reserves the right to inspect such items to determine the validity of the certification.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).
b. Quality conformance inspection (see 4.4).

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T00:27Z
Check the source to verify that this is the current version before use.

4.3 First article inspection. When a first article is required (see 6.2), it shall be examined for the defects listed in table III and shall be tested for the characteristics specified in table IV. The presence of any defect or failure of any test shall be cause for rejection of the first article.

4.4 Quality conformance inspection. Unless otherwise specified, sampling for inspection shall be performed in accordance with MIL-STD-105.

4.4.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced documents unless otherwise excluded, amended, modified, or qualified in this document or applicable purchase document.

* 4.4.1.1 Plastic film overall weight test. The plastic film shall be tested in accordance with Method 5041 of FED-STD-191 except that each specimen shall be 25 square inches and shall be cut in diagonal fashion from each sample unit and may be tested under ambient conditions. The specimens shall be equally spaced across the full width of the sample unit no closer than 2 inches to the edges of the sample unit. The distance between the top of a specimen and the bottom of the next specimen shall be 3 inches. No two specimens shall overlap in the width or lengthwise direction. The sample unit shall be 1.5 yards full width of the plastic film. The lot shall be rejected if any specimen weighs less than 0.3 or greater than 0.7 ounces per square yard, or if the difference in weight between any two specimens in the sample unit is greater than 0.25 ounces per square yard. The sample size shall be in accordance with the following:

Lot size (yards)	Sample size (sample units)
800 or less	2
801 up to and including 22,000	3
22,001 up to and including 150,000	5

4.4.1.2 Certification. Components listed below shall be accepted on the basis of a contractor's certificate of compliance with the indicated requirements.

Component	Requirement paragraph
Plain weave nylon cloth	3.3.1.1
Tricot knit nylon cloth	3.3.1.2

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T00:27Z
Check the source to verify that this is the current version before use.

4.4.2 End item examination.

* 4.4.2.1 Yard-by-yard examination. The cloth shall be examined on both sides for the defects in table III. All defects found shall be counted regardless of their proximity to each other except where two or more defects represent a single local condition in which case only the more serious defect shall be counted. A continuous defect shall be counted as one defect for each warpwise yard or fraction thereof in which it occurs. The lot size shall be expressed in yards. The sample unit shall be 1 linear yard. The inspection level shall be II and the acceptance quality level (AQL), expressed in terms of defects per hundred units, shall be 4.0 for major defects and 10.0 for total (major and minor combined) defects for the face side of the laminated cloth and 4.0 for major defects and 10.0 for total (major and minor combined) defects for the back side of the laminated cloth, but with an AQL of no more than 6.5 for total combined major defects for the front and back sides of the laminated cloth. Any defects scored on one side of the laminated cloth shall not be scored on the opposite side. The number of rolls from which the sample yardage is to be selected shall be in accordance with table IV. The sample yardage shall be apportioned equally among the selected rolls.

TABLE III. End item visual defects

Defects	Classification	
	Major	Minor
Any hole, cut, or tear, including edges	X	
Abrasion resulting in a thin or weak place	X	
Multiple floats or skips, 1/2 inch or more in either warp or filling direction		X
Blisters, tunnels, or delamination of layers	X	
Crease or wrinkle resulting in doubling that cannot be corrected by manual pressure, adhesion of surfaces against each other, or any diagonal distortion of woven (face) fabric surface	X	
Any solid lump, defined as a slub C or 4, or knot which exceeds level C on the respective Sears Fabric Defect Scale (see 6.7)	X	

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T00:27Z
Check the source to verify that this is the current version before use.

TABLE III. End item visual defects - Continued

Defects	Classification	
	Major	Minor
Fabric edges rolled, folded, doubled, scalloped, or wavy	X	
Any spot, stain, or foreign matter 1/		X
Width less than minimum specified	X	
Any odor other than that which is characteristic of the laminating compound or water-repellent finish		X
Any color off shade, not uniform, mottled, or spotted 2/		X
Any tackiness	X	

1/ For the knit (back) side, any spot, stain, streak, off-shade area, or discoloration that is a result of the distortion of the knit when laminated or a result of uneven dyeing shall not be scored for this condition. Foreign matter shall be defined as waste, fly, or extraneous material that has been knit into fabric or spun into yarn.

2/ Woven (face) fabric side only.

TABLE IV. Sample size

Lot size in yards	Sample size in rolls
1,200 or less 1/	3
1,201 up to and including 3,200	5
3,201 up to and including 10,000	8
10,001 up to and including 35,000	13
35,001 up to and including 150,000	20
150,001 and over	32

1/ If lot contains fewer than three rolls, each roll in the lot shall be examined.

Source: https://assist.dla.mil -- Downloaded: 202610-22T00:27Z
Check the source to verify that this is the currentversion before use.

* 4.4.2.2 Length examination. During the yard-by-yard examination, each roll in the sample shall be examined for length. Any length found to be less than the minimum specified or more than 2 yards less than the length marked on the ticket shall be considered a defect with respect to length. The lot shall be unacceptable if two or more rolls in the sample are defective in respect to length, or if the total of the actual lengths of rolls in the sample is less than the total of the lengths marked on the tickets.

4.4.2.3 Shade and appearance examination. During the yard-by-yard examination, each roll in the sample shall be examined for shade and appearance. If any one component color in any roll of the sample is off shade or does not have the same appearance as the standard sample it shall be cause for rejection of the entire lot represented by the sample.

4.4.2.4 Roll identification examination. During the yard-by-yard examination, each roll in the sample shall be examined for proper identification. The lot shall be unacceptable if two or more rolls in the sample are not labeled or ticketed in accordance with the Textile Fiber Products Identification Act.

* 4.4.3 End item testing. The cloth shall be tested for the characteristics listed in table V. The methods of testing specified in FED-STD-191 wherever applicable and as listed in table V shall be followed. All test reports shall contain the individual values utilized in expressing the final results. The sample unit for all testing shall be 5 continuous yards full width of the finished cloth supplied on a tube to prevent folding. The lot shall be rejected if one or more sample units fail to meet the requirement specified. The maximum lot size shall be 150,000 linear yards. The sample size shall be in accordance with the following:

Lot size (yards)	Sample size (sample units)
800 or less	2
801 up to and including 22,000	3
22,001 up to and including 150,000	5

Source: https://assist.dla.mil -- Downloaded: 202610-22T00:27Z
Check the source to verify that this is the currentversion before use.

TABLE V. End item tests

Characteristic	Requirement paragraph	Test method 1/
Colorfastness to:		
Light	3.4.3	5660
Laundering (after 3 cycles)	3.4.3	5614 2/
Perspiration	3.4.3	5680
Crocking	3.4.3	5651
Abrasion	3.4.3	AATCC 119 3/
Spectral reflectance	3.4.5	4.5.1
Overall weight	3.5	5041
Breaking strength	3.5	5100 4/
Tearing resistance	3.5	ASTM D 2582 5/
Moisture vapor transmission rate		
Procedure B		
Initial	3.5	ASTM E 96 6/
After synthetic perspiration	3.5	4.5.8 and ASTM E 96 6/
Procedure BW		
Initial	3.5	ASTM E 96 7/
Hydrostatic resistance:		
Initial	3.5	5512 8/
After strength of coating	3.5	5972 9/and 5512 8/
After abrasion		
Face	3.5	5302 10/and 5512 8/
Back	3.5	5302 10/and 5512 8/
After insect repellent	3.5	11/
Stiffness (warp only), cm	3.5	5204
Water permeability		
Initial	3.5	5516 12/
After synthetic perspiration	3.5	4.5.7 and 5516 12/
After flex (70°F)		
Warp	3.5	4.5.2 and 5516 12/
Filling	3.5	4.5.2 and 5516 12/
After cold flex (-25°F)		
Warp	3.5	4.5.3 and 5516 12/
Filling	3.5	4.5.3 and 5516 12/

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T00:27Z
Check the source to verify that this is the current version before use.

TABLE V. Test Methods - Continued

Characteristic	Requirement paragraph	Test method 1/
Water repellency	3.5.1	13/
Spray rating		
Initial	3.5.2	5526
After 3 launderings	3.5.2	5552 and 5526
Resistance to organic liquid		
Initial	3.5.3	4.5.4
After 3 launderings	3.5.3	5552 and 4.5.4
Resistance to delamination	3.5.4	4.5.5
Dimensional stability	3.5.5	5552

1/ The face side of the laminated cloth shall be used to orient the test specimens in either the warp or filling direction as required by the applicable test method.

2/ Specimen size shall be 4 grams ± 0.1 gram.

3/ Except that the number of abrasion cycles shall be 300.

4/ Measurements shall be read from either dial or recording mechanism and a tensioning clamp shall not be required.

5/ Five warp and five filling specimens shall be tested in accordance with section 4 of FED-STD-191. Specimen size shall be 8 inches by 8 inches. Only one tear shall be made on a single specimen. The specimen shall be positioned with the face side toward the probe and with the designated yarns of the face fabric at right angles to the direction of tear. The test shall be conducted using carriage number 4 of (0.4536 kgs) and the standard drop height of 508 ± 2mm. If the tear is not straight on face side of the laminate, the result shall be considered invalid and another specimen shall be tested. The thickness of the specimen shall not be measured.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T00:27Z
Check the source to verify that this is the current version before use.

6/ The back side of the laminated cloth shall face the water, the free stream air velocity shall be 550 ± 50 FPM as measured 2 inches above the fabric specimen. The air flow shall be measured at least 2 inches from any other surface. The test shall be run for 24 hours and weight measurements shall be taken at only the start and completion of the test. At the start of the 24 hour test period, the air gap between the water surface and the back of the specimen shall be 3/4 ± 1/16 inch. Five initial and three after synthetic perspiration specimens shall be tested.

7/ The back side of the laminated cloth shall face the water. The free stream air velocity shall be 550 ± 50 FPM as measured 2 inches below the fabric specimen. The airflow shall be measured at least 2 inches from any other surface. The test shall be run for 2 hours and weight measurements shall be taken at only the start and completion of the test. Five specimens shall be tested. The specimen shall be sealed in any manner which prevents wicking and/or leaking of water out of the cup.

8/ The water pressure shall be applied to the face side of the laminated cloth. A taffeta fabric restraint, conforming to type III, class 1 of MIL-C-21852 shall be placed across the back of the laminate during testing. No area of the taffeta restraint may be used more than once.

9/ Except that the specimens shall be stretched at 20 pounds.

10/ The abrasion test shall be conducted in multidirectional mode using the face side of the laminate as the abradant. A load of 6 pounds shall be applied to the abradant. The test shall be completed at 10,000 cycles.

11/ Each of five 4 inch by 4 inch specimens shall be laid flat, face side up, on a glass plate 4 inches by 4 inches by 1/4 inch. Three drops of insect repellent conforming to type II, concentration A of O-I-503 shall be applied to the center of each specimen. A glass plate shall be placed on each specimen and a four pound weight placed on top. After 16 hours, remove the five specimens and test immediately in accordance with Method 5512 of FED-STD-191, with the water pressure being applied to the face side. A taffeta fabric restraint, conforming to type III, class 1 of MIL-C-21852 shall be placed across the back of the laminate during testing. No area of the taffeta restraint may be used more than once.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T00:27Z
Check the source to verify that this is the current version before use.

12/ The water permeability shall be measured as specified in Method 5516 of FED-STD-191, except that the face side of the laminated cloth shall contact the water. The hydrostatic head shall be 50 centimeters and shall be held for 5 minutes. The report shall only include measurement of the appearance of water drops. Leakage is defined as the appearance of water any place within the 4-1/2 inch diameter test area. The test may be performed using any device which tests the same specimen area at the equivalent pressure. In cases of dispute, the apparatus described in Method 5516 of FED-STD-191 shall be used.

13/ The contractor shall report the water repellents used and certify that no other material has been added.

* 4.4.3.1 Standard test conditions. Unless otherwise specified, results of physical tests obtained under testing conditions defined in FED-STD-191, ASTM-D-618, or FED-STD-601 will be acceptable except in cases of dispute and in the determination of moisture vapor transmission rate. In dispute cases, the tests shall be conducted with both the specimen and test apparatus under standard conditions as defined in FED-STD-191.

4.4.4 Packaging inspection. The inspection shall be in accordance with the quality assurance provisions of PPP-P-1136.

4.5 Methods of inspection.

* 4.5.1 Spectral reflectance test. Reflectance data shall be obtained from 600 to 860 nm relative to a barium sulfate standard, the preferred white reference standard. Other reference white standards may be used provided they are calibrated to an absolute white; e.g., Halon, magnesium oxide or vitrolite tile. The spectral bandwidth at 860 nm shall be less than 26 nm. Reflectance measurements shall be made using either the monochromatic or polychromatic mode of operation of a spectrophotometer (see 6.5). When the polychromatic mode is used, the spectrophotometer shall operate with the specimen diffusely illuminated with the full emission of a source that simulates either CIE Source A or CIE Source D65. Each shade of the pattern shall be measured as a single layer of laminate backed with six layers of unlaminated outer shell material of the same shade. Readings will be taken on a minimum of two different areas and the data averaged. The specimen shall be viewed at an angle no greater than 10 degrees from normal with specular component included. Photometric accuracy of the spectrophotometer shall be within 1 percent and the wavelength accuracy shall be within 2 nm. The standard aperture size used in the color measurement device shall be 1.0 to 1.25 inches in diameter. Any color having spectral reflectance values falling outside the limits at four or more of the wavelengths specified in table I shall be considered a test failure.

Source: https://assist.dla.mil -- Downloaded: 202610-22T00:27Z
Check the source to verify that this is the current version before use.

* 4.5.2 Water permeability after flex (70°F) test. One 8 inch by 12 inch area shall be cut from the sample unit with the 8 inch dimension in the indicated direction (warp or filling as applicable). The specimen shall be conditioned and flexed as specified in Method 2017 of FED-STD-101 except the specimen shall not be aged, the short edges shall not be heat sealed or otherwise joined, and the specimen shall be flexed for 1500 cycles. Two 6 inch by 8 inch specimens shall be cut from the 8 inch by 12 inch flexed specimen and tested for hydrostatic resistance in accordance with Method 5516 of FED-STD-191 with water pressure applied to the face side.

4.5.3 Water permeability after cold flex (-25°F) test. The water permeability after cold flex (-25°F) test shall be as specified in 4.5.2 except that the 8 inch by 12 inch specimen shall be mounted on the flex test apparatus, placed in a test chamber at -25°F for 1 hour, and then flexed in the test chamber at -25°F.

4.5.4 Resistance to organic liquid test. Place a small specimen of the cloth on smooth horizontal surface, face up. Using a pipette or eye dropper, gently deposit one drop of n-tetradecane on the surface of the specimen. After 30 seconds examine the specimen under light at an angle. Absence of light reflectance at the cloth drop interface shall be taken as evidence of wetting. Three specimens (or areas) taken at various locations across the sample unit shall be tested. Evidence of wetting on one or more specimens shall be considered a test failure.

4.5.5 Delamination test. Place 2 ± 0.2 pounds of the finished, laminated cloth (one sample unit, 24 inches by full width plus ballast) in a top-loading, commercially available, home-type washer set on the permanent press (10 minutes sudsing) cycle using a high water level (10 inches). The water temperature shall be warm (100° ± 10°F). Place 0.5 ounce of detergent conforming to type II of P-D-245 into the washer. The duration of each laundering cycle shall be 30 ± 5 minutes. After laundering, place sample and ballast in a commercially-available home-type dryer set on the permanent press cycle using medium heat (100° ± 10°F) and dry for approximately 15 minutes. Repeat laundering and drying cycle five times. After the fifth drying cycle, examine both sides of the laminated cloth for delamination. The sample shall be considered delaminated if the separation between any two plies exceeds 0.25 inch in any direction.

4.5.6 Exposure to synthetic perspiration procedure. The synthetic perspiration solution shall be made up in a 500 mL glass beaker by combining 3.0 grams sodium chloride, 1.0 gram trypticase soy broth powder, 1.0 gram normal propyl propionate, and 0.5 gram of liquid lecithin. Add 500 mL of distilled water, add a magnetic stirring bar, and cover the beaker. Place the beaker on a combination hot plate/magnetic stirrer apparatus. While stirring, heat the solution to 50°C until all ingredients are dissolved. While stirring, cool the solution to 35°C, remove cover, and dispense immediately

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T00:27Z
Check the source to verify that this is the current version before use.

with a pipette or other suitable measuring device. Dispense 2 mL of perspiration solution at 35°C onto the center of an 8 inch by 8 inch by 1/4 inch glass plate. Place a specimen on the glass plate with the knit side facing the glass. Dispense an additional 2 mL of the synthetic perspiration solution onto the center of the specimen. Place an 8 inch by 8 inch by 1/4 inch glass plate on top of the specimen with a 4 pound weight positioned in the center.

4.5.7 Water permeability after perspiration test. Three specimens, 8 inches by 8 inches, shall be cut and exposed to perspiration as specified in 4.5.6. After 16 hours, remove the specimens (do not rinse) and test after air drying for water permeability.

4.5.8 Moisture vapor transmission rate after perspiration test. Air dry the specimen used in 4.5.7. Cut out an appropriately sized specimen from the center and test for moisture vapor transmission rate.

5. PACKAGING

5.1 Put-up and preservation. Put-up and preservation shall be level A or Commercial as specified (see 6.2).

5.1.1 Levels A and Commercial. The cloth, shall be put-up and preserved in accordance with the applicable requirements of PPP-P-1136.

5.2 Packing. Packing shall be level A, B, or Commercial as specified (see 6.2).

5.2.1 Levels A, B, and Commercial. The cloth shall be packed in accordance with the applicable requirements of PPP-P-1136.

5.3 Marking. In addition to any special marking required in the contract or purchase order, shipments shall be marked in accordance with the requirements of PPP-P-1136.

6. NOTES

6.1 Intended use. The cloth is intended for use in the parka and trousers of the Extended Cold Weather Clothing System.

6.2 Ordering data. Acquisition documents should specify the following:

a. Title, number, and date of this document.
b. First article (see 3.2, 4.3, 6.8).
c. Width of cloth required (see 3.6).
d. Length required, if other than specified (see 3.7).
e. Selection of applicable levels of preservation and packaging (see 5.1 and 5.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T00:27Z
Check the source to verify that this is the current version before use.

6.3 Standard sample. For access to samples, address the contracting activity issuing the invitation for bids.

6.4 Quarpel water repellent. The "Quarpel type" water repellent treatment consists of the co-application of an emulsified fluorocarbon and a fluorocarbon extender. Approval of components and combinations is the responsibility of U.S. Army Natick Research, Development, and Engineering Center, Natick, MA 01760-5014 and is based on extensive tests, including those for toxicity which are not set forth in this document. Because of the time necessary to conduct full evaluation (approximately 6 months), only those chemical treatments already approved and so listed in the invitation for bids or request for proposals shall be considered acceptable for the related procurement.

6.5 Spectrophotometers. Suitable spectrophotometers for measuring spectal reflectance in the near-infrared are the Diano Hardy, Diano Match Scan, Hunter D54P-IR, Hunter VIS/NIR spectrocolorimeter, and Macbeth 1500 with IR option.

6.6 White standards. Barium sulphate of suitable quality for use as a white reference standard is available from the Eastman Kodak Company.

6.7 Fabric defect scales. Fabric Defect Replica Kits are available from Sears Roebuck and Company, Department 817, (ATTN: BSC 23-29), Sears Tower, Chicago, IL 60684.

6.8 First article. When a first article is required, it shall be inspected and approved under the appropriate provisions of FAR 52.209. The first article should be a preproduction sample. The contracting officer should specify the appropriate type of first article and the number of units to be furnished. The contracting officer should include specific instructions in all acquisition instruments regarding arrangements for selection, inspection, and approval of the first article.

* 6.9 Subject term (key word) listing.

Cloth, laminated, waterproof, moisture vapor permeable
Extended cold weather clothing system
Parka
Trousers

* 6.10 Changes from previous issue. The margins of this document are marked with an asterisk (*) to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only, and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content, as written, irrespective of the marginal notations and relationship to the last previous issue.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T00:27Z
Check the source to verify that this is the current version before use.

Custodians:

Army - GL
Navy - NU

Review activities:

Army - MD
Navy - MC
DLA - CT

Preparing activity:

Army - GL

Project No. 8305-0182

Source: https://assist.dla.mil -- Downloaded: 202610-22T00:27Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS. In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE ARMY

US Army Natick Research, Development, and
Engineering Center
Natick, MA 01760-5014

NO POSTAGE
NECESSARY
IF MAILED
IN THE
UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300
STRNC-ES

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 12062 WASHINGTON D. C.
POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Commander
US Army Natick Research, Development,
and Engineering Center
ATTN: STRNC-ES
Box 14A
Natick, MA 01760-5014

Source: https://assist.dla.mil -- Downloaded: 202640-22T00:27Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
MIL-C-44187B	Cloth, Laminated, Waterproof And Moisture Vapor Permeable

3a. NAME OF SUBMITTING ORGANIZATION

b. ADDRESS *(Street, City, State, ZIP Code)*

4. TYPE OF ORGANIZATION *(Mark one)*

- ☐ VENDOR
- ☐ USER
- ☐ MANUFACTURER
- ☐ OTHER *(Specify)*: _____

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T00:27Z
Check the source to verify that this is the current version before use.

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

NATICK OP, 1 Apr 84