FEDERAL SPECIFICATION

PASSIVATION TREATMENTS FOR CORROSION-RESISTING STEEL

This amendment, which forms a part of Federal Specification QQ-P-35B, dated April 5, 1973, was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

PAGE 6

4.4.1.2 (b) Delete in its entirety and substitute the following:

"b. The cleaned and dried parts shall be subjected to 95-100 percent humidity at 100°-115°F. in a suitable humidity cabinet for 24-26 hours."

Military Custodians:

Army - WC
Navy - SH
Air Force - 11

Civil Agency Coordination Activity:

GSA - FSS

Preparing activity:

Army - WC

Reviewer activities:

Army - AV, EL, GL, MI, MR, MU
Navy - AS, OS
Air Force - 80, 82
DSA - IS

User activities:

Army - AT, ME
Navy - None
Air Force - None

Source: https://assist.dla.mil -- Downloaded: 2026-10-25T20:03
Check the source to verify that this is the current version before use.