W-B-131L
January 16, 1978
SUPERSEDING
W-B-131K
April 23, 1975

FEDERAL SPECIFICATION

BATTERY, STORAGE: VEHICULAR, IGNITION, LIGHTING, AND STARTING

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers vehicular storage batteries of the lead acid type.

1.2 Classification. Vehicular storage batteries furnished under this specification shall be of the SAE battery type Nos. specified in table I and identified by a type designation No. (see 6.2).

1.2.1 Type designation No. Vehicular storage batteries covered by this specification shall be identified by a type designation No. formed as indicated below. This type designation No. is intended for cataloging and ordering purposes and not for surface printing on the vehicular battery.

W-B-131	-	1	-	9H3	-	D
Spec. No. (1.2.2)		Class of battery (1.2.3)		SAE type No. (1.2.4)		Wet or dry charged (1.2.5)

1.2.2 Vehicular battery specification No. W-B-131.

1.2.3 Class of vehicular batteries shall be designated as follows:

1 - Class 1 - Passenger car and light commercial, 12 volt.
2 - Class 2 - Heavy duty commercial, 12 volt.
3 - Class 3 - Passenger car and light commercial, 6 volt.
4 - Class 4 - Heavy duty commercial, 6 volt.
5 - Class 5 - Maintenance Free passenger car and light commercial, 12 volt.
6 - Class 6 - Maintenance Free heavy duty commercial, 12 volt.

1.2.4 The SAE type designation No. shall consist of the types specified in table I.

1.2.5 Dry or wet charged batteries shall be designated as follows:

D - Dry charged.
W - Wet charged.

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on the date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

FSC 6140

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:25Z
Check the source to verify that this is the current version before use.

Federal Standard:

Fed. Std. No. 123 - Marking for Shipment (Civil Agencies).

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

(Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Philadelphia, Washington, DC, Atlanta, Chicago, Kansas City, MO, Fort Worth, Houston, Denver, San Francisco, Los Angeles, and Seattle, WA.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standards:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply.

American Society for Testing and Materials (ASTM) Standard:

D 639 - Testing Battery Containers Made from Hard Rubber or Equivalent Materials.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

Battery Council International (BCI):

BCI Yearbook.

(Application for copies should be addressed to Battery Council International, 111 East Wacker Drive, Chicago, IL 60601.)

Society of Automotive Engineers, Inc., Publication:

SAE Handbook - Storage Battery Section (J537).

(Application for copies should be addressed to the Society of Automotive Engineers, Inc., Two Pennsylvania Plaza, New York, NY 10001.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:25Z
Check the source to verify that this is the current version before use.

National Motor Freight Traffic Association, Inc., Agent:

National Motor Freight Classification.

(Application for copies should be addressed to the American Trucking Associations, Inc., Traffic Department, 1616 P Street, N.W., Washington, DC 20036.)

Uniform Classification Committee, Agent:

Uniform Freight Classification.

(Application for copies should be addressed to the Uniform Classification Committee, Room 1106, 222 South Riverside Plaza, Chicago, IL 60606.)

3. REQUIREMENTS

3.1 Qualification. The batteries furnished under this specification shall be products which are qualified for listing on the applicable qualified products list at the time set for opening bids (see 4.2 and 6.2).

3.2 Materials. All material used in the construction of batteries purchased under this specification shall conform to standards of the best commercial practices. Active material, grid alloy or miscellaneous lead parts smelted from other batteries must be refined to remove impurities, prior to subsequent use in new batteries. Materials not specifically designated shall withstand the operational and environmental tests specified herein without adversely affecting battery performance.

3.3 Design and construction.

3.3.1 Dimensional limitations. Batteries shall be within the dimensional limitations specified in table I.

3.3.2 Containers. Containers shall be free of leaks, cracks, or other defects that would adversely affect performance. Containers shall be made of one piece construction and shall be made of nonabsorbent, acid-resistant, hard rubber or polypropylene plastic meeting the physical, chemical and electrical requirements specified (see 3.5.1).

3.3.3 Cell covers. Covers shall meet the same physical, chemical, and electrical requirements as the container material (see 3.5.1.3). Cell covers may be the one-piece or the multiple cell construction.

3.3.4 Sealing compound and heat sealing. The seal resulting from sealing by compound or heat shall be acid-resisting and shall maintain an unbroken seal between the cover and the container throughout the temperature range 0° to 150° F., and there shall be no adhesion or cohesion failures under any of the test conditions specified herein.

3.3.5 Filler plugs and electrolyte level. The cell covers shallprovide openings for each cell for filling plugs and the observation of electrolyte level. Normal electrolyte level shall be not less than 3.8 inch above the top of the separators, and be easily identifiable. The plugs may be of the screw, bayonet, gang or push-in type and shall incorporate baffles or other means of minimizing the splashing of electrolyte. The material in the plugs shall be nonabsorbent, acid-resistant, and have no adverse effect on the electrolyte. In addition, by design they shall be vented.

3.3.5.1 Classes 1, 2, 3, and 4 of vehicular batteries. The cell covers shall provide openings for each cell for filling plugs and the observation of electrolyte level. Normal electrolyte level shall be not less than 3/8 inch above the top of the separators, and be easily identifiable. The plugs may be of the screw, bayonet, gang or push-in type and shall incorporate baffles or other means of minimizing the splashing of electrolyte. The material in the plugs shall be nonabsorbent, acid-resistant, and have no adverse effect on the electrolyte. In addition, by design they shall be vented.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:25Z
Check the source to verify that this is the current version before use.

TABLE I. Battery classifications, dimensions, ratings, and assembly numbers

SAE battery type No.	BCI dimensional group size	Maximum overall dimensions, Inches: Length	Width	Height	Millimeters: Length	Width	Height	BCI Assembly figure number	Minimum performance rating: Reserve capacity minutes	Cold crank 0°F amps	Overcharge life units	Charge Acceptance amps	Amp-hour at 20-hr rate (a)
Class 1 - Passenger car and light commercial, 12 volt													
9HC0	20H	7.82	6.82	9.38	198	173	238	10	45	235	4	4.7	38
9H3	24H	10.25	6.82	9.38	260	173	238	10	70	300	5	6.0	50
9H3A	24H	10.25	6.82	9.38	260	173	238	10	98	365	7	7.3	60
9H3B	24H	10.25	6.82	9.38	260	173	238	10	110	410	8	8.2	70
9H5	27H	11.72	6.82	9.38	297	173	238	10	125	435	9	8.7	70
9H6	27H	12.03	6.82	9.40	305	173	240	10	130	430	11	8.6	75
9M1	21	8.54	6.82	8.19	216	173	208	10	60	255	5	5.1	44
9M3	24	10.25	6.82	8.88	260	173	225	10	52	240	5	4.8	40
9M6	27	12.04	6.82	8.88	306	173	225	10	105	355	9	7.0	70
9M3A	24	10.25	6.82	8.88	260	173	225	10	60	255	5	5.1	45
9M3B	24	10.25	6.82	8.88	260	173	225	10	75	305	5	6.1	50
9M3D	24	10.25	6.82	8.88	260	173	225	10	95	385	7	7.7	60
9M3E	24	10.25	6.82	8.88	260	173	225	10	105	430	8	8.6	61
9M3F	24	10.25	6.75	8.88	260	171	225	10	68	305	5	6.1	48
9MC3A	24	10.25	6.75	8.88	260	171	225	10	86	375	7	7.5	60
9MC3B	24	10.25	6.75	8.88	260	171	225	10	81	315	6	6.3	56
9MC6	27	12.00	6.75	8.75	304	171	222	10	105	400	9	8.0	67
9MJ3C	24C	10.25	6.82	8.88	260	173	225	10	75	285	5	5.7	53
9MJ3D	24C	10.25	6.79	8.67	260	172	220	10	95	385	7	7.7	60
9MJ3F	24C	10.25	6.82	8.88	260	173	225	10	98	335	8	6.7	61
9MJ3G	24C	10.25	6.82	8.90	260	173	226	10	110	410	8	8.2	62
9MJ3K	24C	10.25	6.79	8.76	260	172	222	10	110	385	8	7.7	70
9MJ6	27C	12.04	6.82	8.88	305	173	225	10	140	410	9	8.2	73
9MJ6A	27C	12.04	6.82	8.88	305	173	225	10	110	360	9	7.2	70
9MJ6B	27C	12.04	6.82	8.88	305	173	225	10	140	455	9	9.1	74
9T3	24T	10.25	6.82	9.75	260	173	248	10	105	370	9	7.0	70
9TJ3	24TC	10.25	6.82	9.75	260	173	247	10	113	380	9	7.6	70
10H7	27R	12.01	6.81	9.14	305	172	232	10	136	455	14	9.1	80
10H10	29HR	13.12	6.82	9.14	333	173	232	11	163	520	15	10.4	85
10M0	21R	8.99	6.84	8.97	228	173	227	11	72	290	5	5.8	45
10M3	24R	10.30	6.84	8.97	261	173	227	11	99	350	6	7.0	55
10M7	27R	12.01	6.81	8.95	305	172	227	11	125	430	9	8.6	70
10MJ3A	24R	10.27	6.81	8.97	261	173	228	11	135	455	15	9.1	
11M6	32N	14.25	5.50	8.91	361	140	226	11	115	350	9	7.0	70
13M2	3EE	19.32	4.35	8.88	490	110	225	11	85	290	7	5.8	60
13TC2	3ET	19.32	4.35	9.82	490	110	249	9	120	425	9	8.5	
14M2A	53	13.07	4.79	8.32	331	121	211	9	40	210	4	4.2	40
15M4	60	13.07	6.27	8.88	331	159	225	14	83	310	7	6.2	60
15M4A	60	13.07	6.27	8.88	331	159	225	12	110	360	9	7.2	70
15M4B	60	13.07	6.27	8.88	331	159	225	12	90	330	6	6.6	56
17H3	27HF	12.50	6.82	9.15	317	173	232	11F	125	435	9	8.7	70
17H3A	27HF	12.50	6.82	9.15	317	173	232	11F	136	425	15	8.5	80
17M1A	22HF	9.50	6.82	8.95	241	173	227	11F	72	290	5	5.8	45

(a) For reference purposes only

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:25Z
Check the source to verify that this is the current version before use.

TABLE I. Battery classifications, dimensions, ratings, and assembly numbers

SAE battery type No.	BCI dimensional group size	Maximum overall dimensions, Inches: Length	Width	Height	Maximum overall dimensions, Millimeters: Length	Width	Height	Assembly figure number	Minimum performance rating: Reserve capacity minutes	Cold crank 0°F amps	Overcharge life units	Charge Acceptance amps	Amp-hour at 20-hr rate (a)
Class 1 - Passenger car and light commercial, 12 volt (cont'd)													
17MJ1B	22FC	9.50	6.82	8.46	241	173	214	11F	60	275	5	5.5	45
17MJ1C	22FC	9.50	6.79	8.17	241	172	207	11F	75	305	5	6.1	50
17MJ1D	22FC	9.50	6.82	8.46	241	173	214	11F	50	260	5	5.2	40
17M2	24F	10.75	6.82	8.91	273	173	226	11F	99	330	6	6.6	55
17M2A	24F	10.75	6.82	8.91	273	173	226	11F	115	375	8	7.5	65
17M3A	27F	12.50	6.82	8.88	317	173	225	11F	136	455	15	9.1	80
17M3B	27F	12.50	6.82	8.91	317	173	226	11F	125	375	9	7.5	70
18M1	22NF	9.44	5.50	8.91	240	139	226	11F	52	245	5	4.9	40
18M3	29NF	13.00	5.58	9.00	330	141	228	11F	80	290	6	5.8	55
18M3A	29NF	13.00	5.50	9.00	330	139	228	11F	100	330	8	6.6	65
22MJ1	72	9.10	7.27	8.27	231	184	210	17	60	275	5	5.5	45
22MJ1A	72	9.10	7.27	8.77	231	184	222	17	60	275	5	5.5	
22MJ2	74	10.25	7.27	8.77	260	184	222	17	75	285	5	5.7	50
22MJ2A	74	10.25	7.27	8.77	260	184	222	17	98	335	8	6.7	60
22MJ2B	74	10.25	7.27	8.77	260	184	222	17	110	410	8	8.2	65
22MJ2C	74	10.25	7.27	8.77	260	184	222	17	140	455	9	9.1	73
22MJ3	77	12.04	7.27	8.77	305	184	222	17	110	360	9	7.2	73
22MJ3A	77	12.04	7.27	8.77	305	184	222	17	140	410	9	8.2	74
22MJ3B	77	12.04	7.27	8.77	305	184	222	17	142	455	9	9.1	75
25MJ1	22F	9.46	6.86	8.44	240	174	214	11L	65	290	8	5.8	45
25MJ1A	22F	9.46	6.86	8.44	240	174	214	11L	88	350	10	7.0	53
25MJ2	24F	10.75	6.86	8.94	273	174	227	11L	120	440	14	8.8	68
Class 2 - Heavy duty commercial, 12 volt													
9HC0(b)	20H	7.82	6.82	9.38	198	173	238	10	50	230	4	4.6	38
9H9(b)	30H	13.50	6.82	9.38	342	173	238	10	158	460	13	9.2	90
9H9A(b)	30H	13.50	6.81	9.21	342	172	233	10	175	580	13	11.6	95
20T4A	4D	21.25	8.75	10.88	539	222	276	8	285	640	9	12.8	150
20T4B	4D	21.25	8.75	10.88	539	222	276	8	310	800	9	16.0	153
20T6A	6D	21.25	10.00	10.88	539	254	276	8	350	800	10	16.0	168
20T8A	8D	21.25	11.13	10.88	539	282	276	8	430	900	13	18.0	200
Class 3 - Passenger car and light commercial, 6 volt													
1H2	2	10.38	7.13	9.38	263	181	238	2	220	560	7	11.2	120
1H2A	2	10.38	7.13	9.38	263	181	238	2	245	650	7	13.0	135
1H2B	2	10.38	7.13	9.38	263	181	238	2	295	775	7	15.5	140
1H3	3	11.75	7.13	9.38	298	181	238	2	245	650	7	13.0	130

(a) For reference purposes only.
(b) For impact test, these batteries shall be tested to the requirements for Class 1.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:25Z
Check the source to verify that this is the current version before use.

TABLE I. Battery classifications, dimensions, ratings, and assembly numbers

SAE battery type No.	BCI dimensional group size	Maximum overall dimensions, Inches: Length	Width	Height	Millimeters: Length	Width	Height	Assembly figure number	Minimum performance rating: Reserve capacity minutes	Cold crank 0°F amps	Overcharge life units	Charge Acceptance amps	Amp-hour at 20-hr rate (a)
Class 3 - Passenger car and light commercial, 6 volt (cont'd)													
1H4	4	13.13	7.13	9.38	333	181	238	2	275	700	9	14.0	150
1H4A	4	13.13	7.13	9.38	333	181	238	2	280	720	9	14.4	160
1M1	1	9.13	7.13	9.13	231	181	231	2	159	475	4	9.5	90
1M1A	1	9.13	7.13	9.13	231	181	231	2	185	545	4	10.9	115
1M2	2	10.38	7.13	9.13	263	181	231	2	192	520	6	10.4	110
1M3	3	11.75	7.13	9.13	298	181	231	2	222	550	7	11.0	133
1M4	4	13.13	7.13	9.13	333	181	231	2	256	600	9	12.0	150
1T4		13.03	7.04	9.52	330	178	241	2	380	860	18	17.2	
4H2	2N	10.00	5.57	9.00	254	141	228	1	170	495	4	9.9	90
8H2	2E	19.38	4.13	9.38	492	104	238	5	160	485	5	9.7	100
8H2A	2E	19.38	4.13	9.38	492	104	238	5	210	595	5	11.9	130
8T2	3EH	19.38	4.34	9.77	492	110	248	5	340	830	10	16.6	
8T3	4EH	19.38	5.00	9.77	492	127	248	5	420	880	13	17.6	
Class 4 - Heavy duty commercial, 6 volt													
2H5	5D	13.75	7.13	9.38	349	181	238	1	340	800	10	16.6	168
6T2	7D	15.94	7.63	10.88	405	193	276	2H	430	900	13	18.0	200
6T3A	7D	16.88	7.63	10.88	428	193	276	2H	430	900	13	18.0	200

(a) For reference purposes only.

Class 5 - Maintenance free batteries - passenger car and light commercial, 12 volt.													
71-275	71	8.19	7.05	8.51	208	179	216	17	60	275	NA	5.5	50
71-350	71	8.19	7.05	8.51	208	179	216	17	80	350	NA	7.0	48
72H-430	72H	9.10	7.05	8.51	231	179	216	17	100	430	NA	8.6	60
74-465	74	10.28	7.05	8.63	261	179	219	17	120	465	NA	9.3	70
22F-375	22F	9.50	6.88	8.25	241	174	209	11F	82	375	NA	10.0	50
24-270	24	10.25	6.75	8.75	260	171	222	10	120	470	NA	11.00	70
24F-470	24F	10.75	6.75	8.75	273	171	222	11F	120	470	NA	11.00	70
27-550	27	12.00	6.75	8.75	305	171	222	10	140	550	NA	12.0	80
27F-550	27F	12.50	6.75	8.75	317	171	222	11F	120	550	NA	12.0	80
77-550	77	12.00	7.00	8.63	305	177	219	17	140	550	NA	12.0	80
Class 6 - Maintenance free batteries - heavy duty commercial, 12 volt.													
24-475	24	10.25	6.81	8.75	260	173	222	10	120	475	NA	11.0	70
27-620	27	12.00	6.81	8.75	305	173	222	10	160	620	NA	14.0	90
31-475	31	13.13	6.80	9.18	333	172	233	10	120	475	NA	9.3	60
31-475(c)	31	13.13	6.80	9.38	333	172	233	11F	120	475	NA	9.3	60
31-620	31	13.13	6.80	9.18	333	172	233	10	160	620	NA	14.0	NA

NA - Not available.
(c) Furnished with top threaded terminals

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:25Z
Check the source to verify that this is the current version before use.

3.3.5.2 Classes 5 and 6 of maintenance free vehicular batteries. The cover of the battery shall provide no openings for the routine addition of water. The addition of water is not required on maintenance free batteries during normal service life. Provision for venting shall be accomplished by design.

3.3.6 Terminal seals. Terminal seals shall be provided to prevent leakage between terminals and battery cover or container and shall be acid-resistant.

3.3.7 Handles. Handles for particular types of batteries when required shall be specified (see 6.2). Attached handles shall be of good quality steel covered with an acid-resisting coating and securely attached to the end of the containers. Such handles shall not increase the dimensions of batteries over the limits specified. Acid-resistant cordage is also acceptable for handles. Cordage handles must meet a static pull requirement of 200 lbs.

3.3.8 Metal parts. All metal parts, other than lead alloys, shall be coated with lead, or otherwise treated to resist acid.

3.3.9 Internal construction.

3.3.9.1 Plates. Plates used in construction of batteries used in this specification shall be of the size, number, and thickness that will enable the battery to meet its electrical performance requirements as specified in table I.

3.3.9.2 Intercell connectors and post straps. Intercell connectors and post straps shall be in accordance with the Battery Materials Specifications as specified in BCI Yearbook. Also, the intercell connectors of 12 volt batteries shall not be exposed (excluding batteries recommended for motor coach or diesel engine use.)

3.3.9.3 Separators. The separators shall be of material that will enable the battery to meet all the performance requirements specified in table I.

3.3.9.4 Double insulation. When specified (see 6.2), double insulation shall be furnished in batteries of the types in which double insulation is commercially available. The double insulation shall be furnished in batteries recommended for motor coach or bus service. When a battery is built with double insulation, the cold activation, reserve capacity, and cold cranking requirements shall be reduced 15 percent.

Note: For the purpose of this specification, double insulation is defined as the use of a retaining sheet or perforated, porous material, including glass mats, between the positive plate and the customary single separator.

3.3.10 Terminals. Terminals shall be located as specified on the applicable assembly figures of table I. Polarity shall be plainly marked as follows: The positive terminal shall be identified by "POS," "P," or "+" on the terminal, on the cover or on the container adjacent to the terminal. The negative terminal shall be adjacent to the terminal. When tapered post terminals are specified, each post shall have a taper of 1-1/3 inches per foot, included angle, for a length of not less than 5/8 inch. The smaller diameter shall be 5/8 inch for the negative post and 11/16 inch for the positive post. For side terminals, both positive and negative terminals shall be designed to receive 3/8-16-2B threaded screw and restrict penetration to 0.34 in. (8.6mm) into case. For top threaded terminals, they shall be designed per figure 1 to receive 3/8 - 16 UNC-2B nuts.

3.3.11 Electrolyte. Unless otherwise specified (see 6.2), wet charged batteries shall be furnished with electrolyte that at full charge has a specific gravity of 1.265 + 0.010 at 80°F. Unless otherwise specified (see 6.2) electrolyte shall not be furnished with batteries shipped dry charged or moist charged.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:25Z
Check the source to verify that this is the current version before use.

3.3.12 Maintenance free. When specified, batteries shall be furnished as maintenance-free wet units having the following characteristics.

3.3.12.1 Internal construction. Grids shall contain not more than 0.001% antimony. Electrolyte reserve shall be such that watering of the batteries is not requried during normal service life.

3.3.12.2 External construction and venting system. The battery cover and vent system shall be designed to prevent electrolyte loss during service and to keep top of the battery free from electrolyte and corrosion. The cover shall be integrally assembled without vent caps or other readily removable parts which would allow fluid additions during normal service life or electrolyte loss through improper replacement.

3.3.12.3 Sealed side terminal batteries. Side terminals, where provided, shall be of the type which are to be mated with sealed terminal connectors to tightly secure and seal the termination from corrosion and thus assure a maintenance-free connection. See 3.3.10 for sealed terminal types.

3.4 Condition for shipment. Batteries purchased under this specification shall be shipped in one of the following conditions, as specified (see 6.2).

3.4.1 Batteries intended for immediate use of or wet storage with charging equipment. Wet charged batteries shall be filled with electrolyte (see 3.3.11) and shall be fully charged.

3.4.2 Batteries intended for storage in the unfilled state and without charging. Each of the following conditions is acceptable where storage in the unfilled state is intended.

3.4.2.1 Dry charged. Plates and separators of dry charged batteries shall be dry. When tested in accordance with 4.4.2.3, the moisture content of the plates shall not exceed 0.2 percent and the separators shall not exceed 1/7 percent except for plastic microporous, resin impregnated cellulose separators which shall not exceed 3 percent. The vent hole for each cell shall be closed by easily removeable, air-tight, and moisture-proof type seals, which shall be held firmly in place until removed. Seals for vent holes are not required when the battery is enclosed in a six sided box and sealed with weather resistant tape along the seams. Alternately, seals for vents are not required when the battery is enclosed and sealed in an air tight and moisture proof bag constructed of plastic film.

3.4.2.2 Moist charged. Plates and separators shall be moist. The filling hole of each cell shall be closed by easily removable, air-tight, and moisture-proof seals which shall be held firmly in place until removed. Batteries offered as moist charged must be manufactured using the procedures, techniques, and processes recognized as distinguishable from those used for wet charged and dry charged batteries. Air-tight and moisture-proof sealing of holes is required.

3.4.2.3 Water activated. Water activated batteries shall have the necessary sulphuric acid stored within each cell requiring only water for activation. The plates and separators shall be in dry condition (see 3.4.2.1) and the storage life shall be comparable to the dry charged and moist charged batteries. The filling holes of each cell shall be closed by easily removable, air-tight, and moisture-proof seals which shall be held firmly in place until removed.

3.4.2.4 Maintenance free. Maintenance free batteries shall be filled with electrolyte (see 3.3.11) and shall be fully charged.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:25Z
Check the source to verify that this is the current version before use.

3.5 Physical.

3.5.1 Containers.

3.5.1.1 Electrical breakdown. When tested as specified in 4.4.2.1.1, the container shall be free of leaks and other imperfections and shall show no evidence of being perforated or burned through.

3.5.1.2 Acid resistance. When tested as specified in 4.4.2.12, the material shall not increase in weight more than 1.5 percent or increase dimensionally greater than 2 percent. It shall show no evidence of blisters, cracks, or other visible damage.

3.5.1.3 Impact resistance. When tested as specified in 4.4.2.1.3 and 4.4.2.2, the minimum impact resistance requirement for containers and covers shall be as in table II.

3.5.1.3.1 Impact resistance. The minimum impact resistance values as indicated in table II shall apply to a test temperature of 80°F. This test temperature is applicable to both hard rubber and plastic materials.

TABLE II

Battery Service (From Table I)	Minimum Impact Resistance	
	Hard Rubber	Plastic
Classes 1 & 3	12 In. Lb. Avg. for short spans 12 In. Lb. Avg. for long spans No impact failure below 8 In. Lb.	50 In. Lb. Avg. for short spans 50 In. Lb. Avg. for long spans No single impact failure below 35 In. Lb.
Classes 2 & 4	20 In. Lb. Avg. for short spans 20 In. Lb. Avg. for long spans No impact failure below 16 In. Lb.	75 In. Lb. Avg. for short spans 75 In. Lb. Avg. for long spans No single impact failure below 50 In. Lb.

3.5.1.4 Bulge test. When tested as specified in 4.4.2.1.4, the bulge resistance of a hard rubber container shall not exceed 1/16 inch and for a plastic container shall not exceed 1/8 inch.

3.5.2 Covers. Cover material shall meet the minimum impact requirements specified for battery containers (see 3.5.1.3 and 4.4.2.2).

3.5.3 Leakage. When tested as specified in 4.4.2.4, each cell shall independently maintain a pressure of two pounds per square inch (psi) for a period of five seconds with a maximum loss of 0.1 psi. Evidence of any physical defect in the container, cover or seal between cover and container at the specified pressure or inability to attain that pressure shall constitute a failure. All failed batteries shall be rejected.

3.5.4 Vibration. When tested as specified in 4.4.2.5, 4.4.2.5.1, and 4.4.2.5.2, each battery shall survive 2 units of vibration, there shall be no flooding of electrolyte, the battery shall meet the leakage requirements of 3.5.3, the battery shall meet the cold cranking requirement for 0°F. when conducted at 80°F., and on external and internal examination there shall be no evidence of mechanical defects or leaks.

3.6 Electrical.

3.6.1 Cold activation at 30°F. (dry charged, moist charged, and water activated batteries only). When tested as specified in 4.4.3.1, the battery terminal voltage under load at the end of 15 seconds discharge shall be equivalent to 1.2 volts per cell or greater.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:25Z
Check the source to verify that this is the current version before use.

3.6.2 Reserve capacity. When tested inaccordance with 4.4.3.4, the average reserve capacity must equal or exceed the value in table I for the particular battery specified with no single value being less than 90 percent of the specified value. When a single battery is tested in accordance with the qualification procedure described in paragraph 4.2.2.2, the result obtained shall not be less than 90 percent of the specified value in table I.

3.6.3 Cold cranking test.

3.6.3.1 Cold cranking performance at 0°F. When tested in accordance with 4.4.3.5, the battery shall meet the minimum performance requirements specified in table I.

3.6.4 Overcharge life units. When tested in accordance with 4.4.3.6, the average life of the battery shall meet or exceed the minimum performance requirements specified in table I, with no single values less than one overcharge life unit below the specified value.

3.6.5 Charge rate acceptance test. When tested in accordance with 4.4.3.3, the average acceptance of the battery shall meet the minimum performance requirements specified in table I.

3.6.6 Retention of charge.

3.6.6.1 Classes 1, 2, 3, and 4 of vehicular batteries. When tested as specified in 4.4.3.7, the battery shall yield as a minimum, 75 percent of the reserve capacity specified in table I.

3.6.6.2 Classes 5 and 6 of maintenance free vehicular batteries. When tested as specified in 4.4.3.7, the battery shall yield as a minimum, 90 percent of the reserve capacity specified in table I.

3.6.7 Drycell internal resistance (dry charged and water activated batteries only). When tested as specified in 4.4.3.8, the average terminal-to-terminal resistance of each cell in both directions, after assembly in the container, shall be no less than 50,000 ohms. If each cell of the battery has a minimum resistance of 5,000,000 ohms after assembly in the container, the moisture test specified in 4.4.2.3 may be omitted.

3.7 Identification marking. The following data shall be molded on the sides, or cover ends of the container or applied to a permanent electrolyte resistant label or plate securely and permanently attached to the battery container and contain the following information:

Battery Identification Number
Cold Cranking at 0°F Rating (the test name or abbreviation thereof followed by the rating)
Manufacturer's Name or Identification

Date of manufacture (month, year) and plant of manufacture, if the same battery is manufactured at more than one plant, shall be legibly stamped or branded on the outside cell connector, top or side of the cover or container. A plate or label permanently affixed to the top or side of the outer cover or container, or a tag permanently affixed to the terminal post is acceptable. Coded information is acceptable as long as the key to the code is made available.

3.8 Instruction for placing battery into service. Instructions for placing the battery into service, as required, shall be provided with each battery. The instructions shall show the latest recommended date for placing the battery in service (if required) and shall include the specific gravity of electrolyte for filling (charged and dry) and charging instructions. The method for providing the instructions, shall be in accordance with the manufacturer's standard practice.

3.9 Workmanship. Containers, covers, and vent caps shall be free from cracks, lead, and broken parts. Leading burning or welding shall be homogeneous and free from blow holes or imperfect bonds between parts which have been burned or welded together. Handles and metallic parts shall be free of burrs, sharp edges, and corrosion. Marking shall be clear and distinct. The sealing compound shall not be cracked or separated from the holding surfaces.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:25Z
Check the source to verify that this is the current version before use.

3.10 Dry charged, moist charged, and water activated batteries. After activation in accordance with manufacturer's instructions, batteries shall meet the performance requirements specified in table I.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government.

4.2 Qualification.

4.2.1 Sampling for qualification. Sampling for qualification shall be as follows: (Sample selection will be conducted by a Government inspector.)

(1) To establish a class for a plant, including the qualification of the first battery type within that class, three sample batteries of a specified SAE battery type No. within the class shall be selected from production.

(2) To qualify additional SAE battery type Nos. within an established class, three sample batteries will be selected per battery SAE type per plant.

4.2.2 Qualification tests and inspections.

4.2.2.1 To establish a class. Two of the 3 sample batteries selected as specified in 4.2.1 subparagraph (1) shall be subjected to the tests in paragraphs 4.4.3.1 (if applicable), 4.4.3.4, and 4.4.3.5. After testing as above, the two battery samples shall be cut open and subjected to the Disassembly Inspection specified in 4.2.2.1.1. The untested third battery of the sample is also cut open and subjected to this inspection. The above qualification tests and inspections shall be conducted by the Government at a laboratory designated by the Standardization Division, Federal Supply Service, General Services Administration. In addition to the tests and inspections specified above, the battery shall conform with the requirements of paragraphs 3.2, 3.3.1 thru 3.3.10, 3.5.1 thru 3.5.4, 3.6.1 thru 3.6.7, 3.7, and 3.9 for each type by plant. For compliance with the requirements described above, no less than 5 batteries of each type shall be selected. Compliance shall be established by acting test by the Government, or by inspection of the manufacturer's test records (data to be no more than 6 months old).

4.2.2.1.1 Disassembly inspection. The sample batteries shall be inspected as follows:

(1) Each battery sample shall be given an external visual inspection for defects materials and workmanship.

(2) Battery cover(s) shall then be sawed off cutting through cell connectors and cells removed from the container.

(3) All burned connections shall be inspected for quality and then tested by twisting plate tabs or lugs.

(4) The alignment of plates and separators shall be checked in each cell.

(5) Plates shall be inspected for quality of pasting.

(6) Grids and separators shall be inspected for defects in materials and workmanship.

(7) Sediment space shall be inspected for amount of sediment present and the general quality of the active material shall be checked.

(8) Each battery shall be examined for defects as specified in 4.3.3.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:25Z
Check the source to verify that this is the current version before use.

4.2.2.2 To qualify additional SAE battery types within an established class. Two of the 3 sample batteries selected as specified in 4.2.1, subparagraph (2) shall be subjected to the disassembly inspection specified in 4.2.2.1.1. The third selected sample shall be subjected to the tests in paragraphs 4.4.3.4 and 4.4.3.5. After testing as above, the third battery shall be subjected to the disassembly inspection specified in 4.2.2.1. For the reserve capacity test, the reserve capacity for the battery must equal or exceed 90 percent of the value specified in table I. For the cold cranking test, the battery must equal or exceed the minimum performance specified in table I.

4.2.3 Failure to qualify. If any battery in the qualification sample fails to pass, the cold activation tese (4.4.3.1) or the cold cranking test (4.4.3.4) or the disassembly inspection or if the average reserve capacity as tested in 4.4.3.5 is less than that specified in table I the battery type shall not qualify.

4.3 Acceptance inspection.

4.3.1 Sampling for acceptance inspection. Unless otherwise specified, sampling shall be performed in accordance with the provisions set forth in MIL-STD-105 inspection level II.

4.3.2 Inspection lot. Inspection lot shall consist of batteries of one identification number from an identifiable production period, from one manufacturer, and one plant, submitted for acceptance.

4.3.3 Dimensional and visual examination and acceptable quality level. Each battery selected in accordance with 4.3.1 shall be examined for defects in accordance with table IV. The acceptable quality levels (AQL) on the basis of percent defective shall be as follows in table III.

TABLE III

Defect Classification	AQL
Major	1.5
Minor	4.0

4.3.3.1 Classification of defects. For examination purposes, defects shall be classified as specified in table IV.

TABLE IV. Classification of defects

Categories	Defects	Method of inspection
Major	Maximum dimensional limitation exceeded (see 3.3.1).	Scale
	Leaks or cracks in container (see 3.3.2).	Visual
	Covers not properly sealed to containers (see 3.3.4).	Visual
	Filler plugs and openings not as specified (see 3.3.5).	Visual
	Terminal seals not as specified (see 3.3.6).	Visual
	Location and polarity of terminal post not as specified (see 3.3.10).	Visual
	Terminal markings not as specified (see 3.3.10).	Visual
	Dimension of terminal post not as specified (see 3.3.10).	Gauge
	Specific gravity of electrolyte out of limits (charged and wet batteries only) (see 3.3.11 and 3.4.1).	Hydrometer
	Low electrolyte level (charged and wet only) (see 3.4.1).	Visual
	Vent holes not properly sealed (as applicable) (see 3.4.2).	Visual
	Loose terminal posts.	Visual
Minor	Improper markings (see 3.7).	Visual
	Missing instructions (see 3.8).	Visual
	Burrs or sharp edges (see 3.9).	Visual

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:25Z
Check the source to verify that this is the current version before use.

4.3.4 Test for acceptance. Each month during the contract while the batteries are in the process of manufacture, batteries from each plant shall be tested for cold activation, reserve capacity and cold cranking at 0°F. (see 4.4.3.1, 4.4.3.4, and 4.4.3.5). The sample for testing shall be selected in accordance with MIL-STD-105 inspection level S-1 from each Class (i.e., Classes 1, 2, 3, and 4 in table I). The applicable AQL shall be 6.5 percent defective for the tests in 4.4.3.1 and 4.4.3.5. Any battery failing to pass either 4.4.3.1 or 4.4.3.5 shall be considered defective. If the sample does not meet the average reserve capacity requirement it shall be considered to have failed. In case of failure, the contractor shall suspend offering all battery Types within the Class until corrective measures, as necessary, have been taken, and another sample of at least 20 batteries have been tested and passed.

4.4 Test procedures.

4.4.1 General.

4.4.1.1 Conditions. Tests shall be conducted under general laboratory conditions. Unless otherwise specified herein, tests shall be conducted at ambient room temperature of 80° ± 5°F.

4.4.2 Physical.

4.4.2.1 Containers.

4.4.2.1.1 Electrical breakdown. The electrical breakdown test shall be conducted as specified in ASTM D639 to determine conformance to 3.5.1.1. The voltage shall be 100 v/mil for hard rubber and 300 v/mil for plastic.

4.4.2.1.2 Acid resistance. The acid resistance test shall be conducted as specified in ASTM Standard D639 to determine conformance to 3.5.1.2.

4.4.2.1.3 Impact resistance. The impact resistance test for hard rubber containers shall be conducted as specified in ASTM D 639 to determine conformance to 3.5.1.3 with impact points and number of impacts as specified in the BCI Yearbook. The impact resistance test for plastic containers shall be conducted as specified in Plastic Container Cover, Testing Procedures BCI Yearbook, to determine conformance to 3.5.1.3. The test temperature for plastic containers shall be 80°F. ± 5°F.

4.4.2.1.4 Bulge resistance (container only). The bulge resistance test for hard rubber containers shall be conducted as specified in ASTM D639 to determine conformance to 3.5.1.4. The bulge resistance test for plastic containers shall be conducted as specified in "Plastic Container and Cover Testing Procedures," BCI Yearbook, to determine conformance with 3.5.1.4. The test temperature for plastic covers shall be 80°F. ± 5°F.

4.4.2.2 Impact resistance (covers).

4.4.2.2.1 Hard rubber covers. Three flat plate cell cover material specimens shall be molded and tested according to ASTM D639.

4.4.2.2.2 Plastic one-piece covers. Three whole covers shall serve as test specimens. The impact resistance test for covers shall be conducted as specified in Plastic Container and Cover "Testing Procedures," BCI Yearbook, to determine conformance to 3.5.1.3.

4.4.2.3 Moisture content of plates and separators. To determine conformance to 3.4.2.1.1, the plates and separators shall be removed from the battery, separated, and weighed. They shall be dried in an oven vented to the atomsphere at a temperature of 165° to 170°F. for 2 hours, until weight is constant. The plates and separators shall be reweighed and the percentage of moisture computed.

4.4.2.4 Leakage test. Two pounds per square inch shall be applied to each cell, individually, to establish compliance to 3.5.3.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:25Z
Check the source to verify that this is the current version before use.

4.4.2.5 Vibration. To determine conformance to 3.5.4.

4.4.2.5.1 Batteries with hard rubber cases. The batteries shall be tested as specified in SAE Standard J537, "Vibration test."

4.4.2.5.2 Batteries with plastic cases. The vibration test for plastic case batteries shall be as specified in SAE Standard J537, "Vibration test."

4.4.3 Electrical. The electrical tests shall be conducted in the sequence as listed below.

4.4.3.1 Cold activation test. This test shall apply to dry charged, moist charged and water activated batteries. The test shall be conducted as follows:

(a) Place the battery and electrolyte (1.265 ± 0.005 sp. gr. at 80°F.) in cold box at 30° F. ± 2°F. for at least 18 hours prior to test or until both battery and acid are at 30°F. ± 2°F. In the case of water activated batteries. The test shall be conducted as follows:

(b) Remove from cold box and immediately fill the battery with the cold electrolyte. For water activated batteries, fill with tap water chilled to 35 ± 2°F.

(c) Allow to stand 20 minutes after filling the last cell, then discharge the battery at 75 percent of the 0°F. cold performance rating. Measure the battery terminal voltage under load at end of 15 seconds. The battery shall meet the requirement of paragraph 3.6.1.

4.4.3.2 Conditioning. After being subjected to the test in 4.4.3.1 and prior to being tested further, the batteries shall be conditioned in accordance with the conditioning procedure specified in SAE J537.

4.4.3.2.1 Before each discharge the battery shall be charged according to the method given under conditioning in SAE J537.

4.4.3.3 Charge rate acceptance test. To determine conformance to 3.6.5, the charge rate acceptance test shall be conducted as specified in SAE Standard J537.

4.4.3.4 Reserve capacity rating. To determine conformance to 3.6.2, the reserve capacity test shall be conducted as specified in SAE Standard J537.

4.4.3.5 Cold cranking test at 0°F. To determine conformance to 3.6.3.1, the cold cranking test at 0°F. shall be conducted as specified in SAE Standard J537.

4.4.3.6 Overcharge life units. To determine conformance to 3.6.4, the overcharge life test shall be conducted as specified in SAE Standard J537.

4.4.3.7 Retention of charge. To determine conformance to 3.6.6, the battery shall be conditioned in accordance with 4.4.3.2 and allowed to stand on open circuit for 4 weeks in an ambient temperature of 75° ± 5°F. At the end of this period and without recharging, the battery shall be discharged at the reserve capacity rate in accordance with 4.5.3.4.

4.4.3.8 Dry cell internal resistance. To determine conformance to 3.6.7, the plate-to-plate resistance shall be measured with an ohm-meter, bridge, or other test instrument. The average of such resistance measured in both directions shall be calculated to determine conformance.

4.4.3.9 Inspection of preparation for delivery. Inspection of preparation for delivery shall be accomplished in accordance with MIL-B-208.

5. PREPARATION FOR DELIVERY

5.1 Packaging. The packaging shall be Level A or commercial as specified (see 6.2).

5.1.1 Level A. Charged and dry batteries shall be preserved and packaged in accordance with Level A specified in MIL-B-208.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:25Z
Check the source to verify that this is the current version before use.

5.1.2 Commercial. Charged and dry or wet batteries shall be preserved and packaged in accordance with normal commercial practice. The complete package shall be designed to protect the item against damage during shipment and storage.

5.2 Packing. The packing shall be level A or commercial as specified (see 6.2).

5.2.1 Level A. Charged and dry batteries shall be packed in accordance with Level A specified in MIL-B-208.

5.2.2 Commercial. Charged and dry and wet batteries packaged as specified in 5.1.2 shall be packed in fiberboard boxes to insure safe delivery at destination, to provide for safe redistribution by the initial receiving activity, and shall be acceptable by common carrier under National Motor Freight Classification or Uniform Freight CLassification.

5.3 Unitization. When shipments to Government depots are full car or truck load, the shipping containers shall be unitized for shipment and handling in accordance with normal commercial practice. The unitized load shall not exceed 2,500 lbs, in weight, 63 inches in height, 56 inches in length, and 45 inches in width.

5.4 Marking. Marking shall be in accordance with 5.4.1 or 5.4.2 as specified (see 6.2).

5.4.1 Civil agencies. Each shipping container and unitized loads (when applicable) shall be marked in accordance with Fed. Std. No. 123.

5.4.2 Military activities. Each shipping container and unitized loads (when applicable) shall be marked in accordance wtih MIL-STD-129.

6. NOTES

6.1 Intended use. The batteries covered by this specification are intended primarily for starting, lighting, and ignition service on passenger cars, motor-trucks, and motor-coaches equipped with regulated charging systems, but may be used for other purposes for which they are suitable.

6.2 Ordering data. Purchasers should select the preferred options permitted herein, and include the following information in procurement documents:

(a) Title, number, and date of this specification.
(b) Type designation No. (see 1.2).
(c) Whether QPL Listing is required (see 3.1).
(d) Handles, if required (see 3.3.7).
(e) Double insulation, if required (see 3.3.9.4).
(f) Specific gravity of electrolyte, is other than specified (see 3.3.11).
(g) Condition of battery at time of shipment (see 3.4.1, 3.4.2, and 6.3).
(h) When required, quantity and method of apckaging of electrolyte for charged and dry and moist charged batteries (see 3.3.11).
(i) Level of preservation and packaging and the level of packing required (see 5.1).
(j) Any special marking requirements (see 5.4).
(k) Unitization if required.

6.3 Batteries for immediate use. When batteries are being procured for immediate use, and when so specified (see 6.2), batteries may be procured in the charged and wet conditions.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:25Z
Check the source to verify that this is the current version before use.

Appendix 1

Cross Reference of Vehicle Batteries

NSN	W-B-131I	W-B-00131J	W-B-131K & L	wet or dry	BCI Group No.
6140-00-076-1774	-	17M1A, 17M1	W-B-131-1-17M1A-D	dry	22HF
184-3402	6D, 6G	20T6A	W-B-131-2-20T6A-D	dry	6D
184-3415	7D, 7G	6T3A	W-G-131-4-6T3A-D	dry	7D
190-9828	8D, 8G	20T8A, 20T8	W-B-131-2-20T8A-D	dry	8D
190-9831	4D, 4G	20T4A, 20T4	W-B-131-2-20T4A-D	dry	4D
190-9840	2E	8H2	W-B-131-3-8H2-D	dry	2E
191-8487	2M	1M2	W-B-131-3-1M2-W	wet	2
191-8490	3H	1H3	W-B-131-3-1H3-D	dry	3H
191-8502	3H	1H3	W-B-131-3-1H3-W	wet	3H
191-8505	6G, 6D	20T6A	W-B-131-2-20T6A-W	wet	6G
191-8506	1M	1M1	W-B-131-3-1M1-D	dry	1
191-8519	4H	1H4	W-B-131-3-1H4-D	dry	4
191-8522	2H, 1H	1H2, 3L2, 1H1	W-B-131-3-1H2-W	wet	2
195-5347	9D			dry	
195-5841	1M	1M1	W-B-131-3-1M1-W	wet	1
198-8573	2E	8H2	W-B-131-3-8H2-W	wet	2E
199-4988	7D, 7G	6T3A, 6T3	W-B-131-4-6T3A-W	wet	7D
199-4989	4D, 4G	20T4A, 20T4	W-B-131-2-20T4A-W	wet	4D
199-4991	8D, 8G	20T8A, 20T8	W-B-131-2-20T8A-W	wet	8D
397-2608	-	22MJ3B	W-B-131-1-22MJ2B-W	wet	74
397-2609	-	22MJ3A	W-B-131-1-22MJ3A-W	wet	77
397-2611	-	22MJ3	W-B-131-1-22MJ3-W	wet	77
397-2612	-	22MJ2C	W-B-131-1-22MJ2C-W	wet	74
397-2614	-	22MJ2B	W-B-131-1-22MJ2B-W	wet	74
397-2616	-	22MJ2A	W-B-131-1-22MJ2A-W	wet	74
397-2620	-	9H3B	W-B-131-1-9H3B-W	wet	24H
397-2622	-	9H6	W-B-131-1-9H6-W	wet	27H
397-2626	2SMA	9M3A	W-B-131-1-9M3A-W	wet	24
397-2630	-	9M3F	W-B-131-1-9M3F-W	wet	24
397-2633	-	9MC3A	W-B-131-1-9MC3A-W	wet	24
397-2636	-	9MC3B	W-B-131-1-9MC3B-W	wet	24
397-2641	-	9MJ3C	W-B-131-1-9MJ3C-W	wet	24C
397-2643	-	9MJ3D	W-B-131-1-9MJ3D-W	wet	24C
397-2645	-	9MJ3F	W-B-131-1-9MJ3F-W	wet	24C
397-2647	-	9MJ3G	W-B-131-1-9MJ3G-W	wet	24C
397-2649	-	9MJ3K	W-B-131-1-9MJ3K-W	wet	24C
397-2651	-	9MJ6	W-B-131-1-9MJ6-W	wet	27C
397-2653	-	9MJ6B	W-B-131-1-9MJ6B-D	dry	27C
397-2654	-	10H10	W-B-131-1-10H10-D	dry	29HR
397-2655	-	10M0	W-B-131-1-10M0-D	dry	21R
397-2656	-	10M3	W-B-131-1-10M3-D	dry	24R
397-2657	3EMB, 3EE 3EMA	13M2, 13M2A	W-B-131-1-13M2-D	dry	33EE
397-2658	-	15M4	W-B-131-1-15M4-D	dry	60
397-2659	-	15M4B	W-B-131-1-15M4B-D	dry	60
397-2660	-	17MJ1B	W-B-131-1-17MJ1B-D	dry	22FC
397-2662	-	17M1A, 17M1	W-B-131-1-17M1A-D	dry	22HF
397-2663	-	17H3A	W-B-131-1-17H3A-D	dry	27HF
397-2664	-	17H3	W-B-131-1-17H3-D	dry	27HF
397-2665	-	17MJ1C	W-B-131-1-17MJ1C-D	dry	22FC
397-2668	-	17MJ1D	W-B-131-1-17MJ1D-D	dry	22FC
397-2670	-	17M2A	W-B-131-1-17M2A-D	dry	24F
397-2671	-	22MJ1	W-B-131-1-22MJ1-D	dry	72
397-2677	-	22MJ2	W-B-131-1-22MJ2-D	dry	74
397-2678	-	22MJ2A	W-B-131-1-22MJ2A-D	dry	74
~~407-3398~~	-	~~1M1~~	~~W-B-131-3-1M1-D~~	~~dry~~	~~1~~
407-3434	-	22MJ3B	W-B-131-1-22MJ3B-D	dry	77
407-3435	-	22MJ3	W-B-131-1-22MJ3-D	dry	77
407-3440	-	10H7	W-B-131-1-10H7-D	dry	27R
434-5870	-	2H5	W-B-131-4-2H5-W	wet	5D

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:25Z
Check the source to verify that this is the current version before use.

Appendix 1

Cross Reference of Vehicle Batteries

NSN	W-B-131I	W-B-00131J	W-B-131K & L	wet or dry	BCI Group No.
6140-00-434-5871	-	2H5	W-B-131-4-2H5-D	dry	5D
434-5872	-	8H2A	W-B-131-3-8H2A-W	wet	2E
434-5873	-	8H2A	W-B-131-3-8H2A-D	dry	2E
434-5874	-	1M4	W-B-131-3-1M4-W	wet	4
434-5876	-	1M4	W-B-131-3-1M4-D	dry	4
434-5878	3M	1M3	W-B-131-3-1M3-D	dry	3
434-5880	3M	1M3	W-B-131-3-1M3-W	wet	3
434-5883	-	1M2	W-B-131-3-1M2-D	dry	2
434-5884	-	1M1A	W-B-131-3-1M1A-W	wet	1
434-5885	-	1M1A	W-B-131-3-1M1A-D	dry	1
434-5887	-	1H4A	W-B-131-3-1H4A-D	dry	4
434-5889	-	1H2B	W-B-131-3-1H2B-W	wet	2
434-5890	-	1H2B	W-B-131-3-1H2B-D	dry	2
434-5891	-	1H2A	W-B-131-3-1H2A-W	wet	2
434-5893	-	1H2A	W-B-131-3-1H2A-D	dry	2
434-5894	-	9MJ6A	W-B-131-1-9MJ6A-W	wet	27G
434-5897	-	9MJ6B	W-B-131-1-9MJ6B-W	wet	27C
434-5898	2STA	9TJ3, 9T3	W-B-131-1-9TJ3-W	wet	24T
434-5899	-	10H7	W-B-131-1-10H7-W	wet	27R
434-5900	-	10H10	W-B-131-1-10H10-W	wet	29HR
434-5901	-	10M0	W-B-131-1-10M0-W	wet	21R
434-5902	-	10M3	W-B-131-1-10M3-W	wet	24R
434-5907	-	15M4	W-B-131-1-15M4-W	wet	60
434-5908	-	15M4B	W-B-131-1-15M4B-W	wet	60
434-5909	-	17M1A, 17M1	W-B-131-1-17M1A-W	wet	22HF
434-5910	-	17H3A	W-B-131-1-17H3A-W	wet	27HF
434-5911	-	17H3	W-B-131-1-17H3-W	wet	27HF
434-5912	-	17MJ1B	W-B-131-1-17MJ1B-W	wet	22FC
434-5913	-	17MJ1C	W-B-131-1-17MJ1C-W	wet	22FC
434-5914	-	17MJ1D	W-B-131-1-17MJ1D-W	wet	22FC
434-5917	-	17M2A	W-B-131-1-17M2A-W	wet	24F
434-5918	-	22MJ1	W-B-131-1-22MJ1-W	wet	72
434-5920	-	22MJ2	W-B-131-1-22MJ2-W	wet	74
438-0208	-	20T4B	W-B-131-2-20T4B-W	wet	4D
438-0215	-	20T4B	W-B-131-2-20T4B-D	dry	4D
438-0299	-	9H9A	W-B-131-2-9H9A-D	dry	30H
446-6756	-	22MJ3A	W-B-131-1-22MJ3A-D	dry	77
446-6758	-	22MJ2C	W-B-131-1-22MJ2C-D	dry	74
446-6773	-	22MJ2B	W-B-131-1-22MJ2B-D	dry	74
446-6813	-	9H3B	W-B-131-1-9H3B-D	dry	24H
446-6818	-	9H6	W-B-131-1-9H6-D	dry	27H
446-6829	-	9M3	W-B-131-1-9M3-D	dry	24
446-6875	-	9M3A	W-B-131-1-9M3A-D	dry	24
446-6876	-	9M3F	W-B-131-1-9M3F-D	dry	24
446-6891	-	9MC3A, 9MC3	W-B-131-1-9MC3A-D	dry	24
446-6906	-	9MC3B	W-B-131-1-9MC3B-D	dry	24
446-7007	-	9MJ3C	W-B-131-1-9MJ3C-D	dry	24C
446-7017	-	9MJ3D	W-B-131-1-9MJ3D-D	dry	24C
446-7019	-	9MJ3F	W-B-131-1-9MJ3F-D	dry	24C
446-7037	-	9MJ3K	W-B-131-1-9MJ3K-D	dry	24C
446-7038	-	9MJ6	W-B-131-1-9MJ6-D	dry	27C
446-7064	-	9MJ6A	W-B-131-1-9MJ6A-D	dry	27C
473-1565	-	9MJ3G	W-B-131-1-9MJ3G-D	dry	24C
473-1603	-	9H9A	W-B-131-2-9H9A-W	wet	30H
473-1804	2STA	9TJ3, 9T3	W-B-131-1-9TJ3-D	dry	24T
504-0968	4NA	11M4	W-B-131-1-11M4A-D	dry	29NF
538-9980	5NA	11M6, 11m6A, 11M4, 11M4A	W-B-131-1-11M6-W	wet	32N

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:25Z
Check the source to verify that this is the current version before use:

Appendix 1

Cross Reference of Vehicle Batteries

NSN	W-B-131I	W-B-00131J	W-B-131K & L	wet or dry	BCI Group No.
6140-00-538-9984	3SMA	9M6, 9MC6	W-B-131-1-9MC6-D	dry	27
538-9986	2SMC	9M3D	W-B-131-1-9M3D-D	dry	24
539-8486	2SMC	9M3D	W-B-131-1-9M3D-W	wet	24
539-8488	3SMA	9M6, 9MC6	W-B-131-1-9MC6-W	wet	27
539-8491	4H	1H4	W-B-131-3-1H4-D	dry	4
539-8507	5NA	11M6, 11M6A 11M4, 11M4A	W-B-131-1-11M6-D	dry	32N
585-4891	2SHA	9H3	W-B-131-1-9H3-D	dry	24H
605-9181		1H4A	W-B-131-1-1H4A-W	wet	4
643-0486	1H	1H1	W-B-131-3-1H1-D	dry	1
643-0495	2SMB	9M3B	W-B-131-1-9M3B-D	dry	24
643-0496	2N, 3NR	4M2, 4M3, 5M3	W-B-131-3-4M2-W	wet	2N
643-0497	2SMB	9M3B	W-B-131-1-9M3B-W	wet	24
643-0498	3N, 3NR	4M3, 5M3	W-B-131-3-4M2-D	dry	3N
643-0502	3KMA	15M4	W-B-131-1-15M4-D	dry	60
729-8974	3MSA	10M7	W-B-131-1-10M7-D	dry	27R
729-8975	3MSA	10M7	W-B-131-1-10M7-W	wet	27R
829-9714	2SM	9M3	W-B-131-1-9M3-W	wet	24
822-0397	18M1	18M1	W-B-131-1-18M1-D	dry	22NF
822-0409	18M1	18M1	W-B-131-1-18M1-W	wet	22NF
822-0410	14M2A	14M2A	W-B-131-1-14M2A-D	dry	53
822-0411	14M2A	14M2A	W-B-131-1-14M2A-W	wet	53
822-0414	4NFB	18M3A	W-B-131-1-18M3A-D	dry	29NF
822-0415	4NFB	18M3A	W-B-131-1-18M3A-W	wet	29NF
822-0418	3SHA	9H5, 9HC5	W-B-131-1-9H5-W	wet	27H
822-0419	3SHA	9H5, 9HC5	W-B-131-1-9H5-D	dry	27H
836-1280	3KMB	15M4A	W-B-131-1-15M4A-D	dry	60
836-1281	3KMB	15M4A	W-B-131-1-15M4A-W	wet	60
836-1282	3EMB, 3EE, 3EMA	13M2, 13M2A	W-B-131-1-13M2A-W	wet	3EE
864-7458	2H, 2L, 2F	1H2, 3L2	W-B-131-3-1H2-D	dry	2
889-1134	17M2	17M2	W-B-131-1-17M2-W	wet	24F
984-0068	17M2	17M2	W-B-131-1-17M2-D	dry	24F
984-0069	2SHA	9H3	W-B-131-1-9H3-W	wet	24H
984-0142	9H9	9H9	W-B-131-2-9H9-W	wet	30H
984-0143	9H9	9H9	W-B-131-2-9H9-D	dry	30H
984-0146	17M3A, 17M3	17M3A	W-B-131-1-17M3A-W	wet	27F
984-0147	17M3A, 17M3	17M3A	W-B-131-1-17M3A-D	dry	27F
984-0149	-	13TC2	W-B-131-1-13TC2-D	dry	3ET
984-0153	5NB	11M6A	W-B-131-1-11M6A-D	dry	5NB
984-0154	3MFA	17M3B	W-B-131-1-17M3B-W	wet	27F
984-0155	3MFA	17M3B	W-B-131-1-17M3B-D	dry	27F
984-0158	2SMD	9M3E	W-B-131-1-9M3E-W	wet	24
984-0159	2SMD	9M3E	W-B-131-1-9M3E-D	dry	24
984-0162	2SHB	9H3A, 9HC3A	W-B-131-1-9H3A-W	wet	24H
984-0163	2SHB	9H3A, 9HC3A	W-B-131-1-9H3A-D	dry	24H
984-0166	4NFA	18M3	W-B-131-1-18M3-W	wet	29NF
984-0167	4NFA	18M3	W-B-131-1-18M3-D	dry	29NF

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:25Z
Check the source to verify that this is the current version before use.

Maintenance Free Battery Reference

NSN	W-B-131L(SAE No.)	Wet or Dry	BCI Group No.
6140-01-031-6873	W-B-131-1-71-275	Wet	71
01-032-3617	W-B-131-1-71-350	Wet	71
01-031-6874	W-B-131-1-72H-430	Wet	72H
01-031-6875	W-B-131-1-74-465	Wet	74
01-032-3619	W-B-131-1-22F-375	Wet	22F
01-031-6876	W-B-131-1-24F-470	Wet	24F
01-031-6877	W-B-131-1-27-550	Wet	27
01-031-6878	W-B-131-1-27F-550	Wet	27F
01-031-6883	W-B-131-1-77-550	Wet	77
01-031-6879	W-B-131-1-24-475	Wet	24
01-031-6880	W-B-131-1-27-620	Wet	27
01-032-1326	W-B-131-1-31-475*	Wet	31
01-031-6882	W-B-131-1-31-620	Wet	31

* Top threaded terminals

FIGURE 1

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:25Z
Check the source to verify that this is the current version before use.

MILITARY INTEREST

Custodians:

Army - AT
Navy - YD
Air Force - 82

Review activities:

Army - ~~SC~~, EL
Air Force - 11

User activity:

Navy - WP, MC

PREPARING ACTIVITY:

GSA-FSS

CIVIL AGENCIES COORDINATING ACTIVITIES:

COMMERCE - NBS
DC GOVT - DCG
POSTAL - POS
USDA - AFS
GSA - FSS

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See Section 2 of this specification to obtain extra copies and other documents referenced herein. Pri[illegible] cents each.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:25Z
Check the source to verify that this is the current version before use..