MIL-P-50573C (AR)
AMENDMENT 4
22 September 1987
SUPERSEDING
AMENDMENT 3
8 August 1986

MILITARY SPECIFICATION

PROJECTILE, 155MM, HE, ROCKET ASSISTED M549 & M549A1 FORWARD (AHH) PROPELLANT GRAIN FOR

This Amendment forms a part of Military Specification MIL-P-50573C (AR), dated 20 June, 1979, and is approved for use within the US Army Armament Munitions and Chemical Command and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 3

3.5.1 Delete ".359 minimum" and substitute ".345 minimum".

PAGE 5

* 3.10 Add the following new subparagraph:

3.10.3 Alternate test method

3.10.3.1 Plus 140° F. The average of three (3) maximum compression readings from each casting shall be no less than 890 lbs. and the average of three (3) deformation readings from each casting shall be no less than 53 percent when tested as specified in 4.4.3.4 and 4.5.4.1.

3.10.3.2 Minus 40° F. The average of three (3) maximum compression readings from each casting shall be no less than 6,990 lbs. and the average of three (3) deformation readings from each casting shall be no less than 5.25 percent when tested as specified in 4.4.3.4 and 4.5.4.1.

PAGE 9

* 4.4.1.b Change "or more than 1 months production of rocketgrains" to "or more than 2 months production of rocket grains".

PAGE 11

4.4.2.2 Add the following Major defect:

"105. Offset of Bevel, Max (3 places, 120° apart)- 0.40% 3.2 Gage".

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:29Z
Check the source to verify that this is the current version before use.

4.4.2.3 Add the following Critical defect:

"1. Excessive cracks, foreign material or porosity, 100% 3.6.2 Visual".

Major Defect 101: Delete in its entirety.

Major Defect 103: Delete in its entirety and substitute the following:

"103. Inhibitor separation - 100% 3.7 Visual".

* 4.4.3.4 Delete paragraphs 4.4.3.4.1 and 4.4.3.4.2 and substitute the following:

"4.4.3.4.1 Plus 140° F (See 3.10.1 or 3.10.3.1). Major defect. Three samples will be randomly selected from the lot. If possible, no two samples will be taken from the same casting solvent sublot. These samples shall be tested for maximum compression load and deformation as specified in 4.5.4 or 4.5.4.1. The lot shall be rejected if the average of the three specimens from any casting fails to meet the requirements of 3.10.1 or 3.10.3.1.

4.4.3.4.2 Minus 40° F (See 3.10.2 or 3.10.3.2). Major defect. Three samples will be randomly selected from the lot. If possible, no two samples will be taken from the same casting solvent sublot. These samples shall be tested for compression load and deformation as specified in 4.5.4 or 4.5.4.1. The lot shall be rejected if the average of the three specimens from any casting fails to meet the requirements of 3.10.2 or 3.10.3.2."

* 4.5.4 Add the following new subparagraph:

"4.5.4.1 Physical properties - alternate test method - Each specimen and specimen support shall conform to the requirements of Figure 1. The specimen shall be conditioned at the required temperature plus or minus 5° F for three hours, minimum. The specimen shall be removed from the conditioning box and inserted between the fixture posts with

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:29Z
Check the source to verify that this is the current version before use.

steel cylinders the same diameter as the specimen placed above and below the specimen forming one continous concentric cylinder. The specimen shall be tested using a cross head speed of 2 inches per minute. The total time elapsed from removing the speciment from the conditioning box to the completion of each test shall be 1 $\pm$ 1/2 minutes. All compression tests shall be conducted in a room that is maintained at 70° F $\pm$ 5° F."

The margins of this amendment are marked with an asterisk of vertical line to indicate where changes (additions, modifications, corrections, deletions) from the previous amendment were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous amendment.

Custodian:
Army - AR

Preparing activity:
Army - AR

(Project 1320-A985)

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:29Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:29Z
Check the source to verify that this is the current version before use.