MIL-I-62521(AT)
22 July 1987
SUPERSEDING
(see 6.5)

# MILITARY SPECIFICATION

## INSULATION, FLOOR-MAT, THERMAL-BARRIER

This specification is approved for use within the US Army Tank-Automotive Command, Department of the Army, and is available for use by all Departments and Agencies of the Department of Defense.

## 1. SCOPE

1.1 Scope. This specification covers floor-mat insulation with thermal-barrier properties.

## 2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications and standards. The following specifications and standards form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of these documents shall be those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: US Army Tank-Automotive Command, ATTN: AMSTA-GDS, Warren, MI 48397-5000, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document, or by letter.

AMSC N/A FSC 5640
DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:45Z
Check the source to verify that this is the current version before use.

SPECIFICATIONS
FEDERAL

| | |
|---|---|
| VV-F-800 | - Fuel Oil, Diesel. |

MILITARY

| | |
|---|---|
| MIL-L-2104 | - Lubricating Oil, Internal Combustion Engine, Tactical Service. |
| MIL-G-3056 | - Gasoline, Automotive, Combat. |
| MIL-C-46168 | - Coating, Aliphatic Polyurethane, Chemical Agent Resistant. |

STANDARDS
MILITARY

| | |
|---|---|
| MIL-STD-105 | - Sampling Procedures and Tables for Inspection by Attributes. |
| MIL-STD-130 | - Identification Marking of US Military Property. |
| MIL-STD-810D | - Environmental Test Methods and Engineering Guidelines. |
| MIL-STD-45662 | - Calibration System Requirements. |

(Copies of specifications, standards, handbooks, drawings, publications, and other Government documents required by the contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted shall be those listed in the issue of the DODISS specified in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS shall be the issue of the nongovernment documents which is current on the date of the solicitation.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

| | |
|---|---|
| ASTM C177 | - Steady-State Thermal Transmission Properties by Means of the Guarded Hot Plate. |
| ASTM D412 | - Rubber Properties in Tension. |
| ASTM D624 | - Rubber Property - Tear Resistance. |
| ASTM D903 | - Peel or Stripping Strength of Adhesive Bonds. |
| ASTM D4158 | - Abrasion Resistance of Textile Fabrics (Uniform Abrasion Method). |

(Application for copies should be addressed to American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)



Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:45Z
Check the source to verify that this is the current version before use.

SOCIETY OF AUTOMOTIVE ENGINEERS (SAE)

SAE J369 - Flammability of Automotive Interior Material - Horizontal Test Method.

(Information as to the availability of the above standard may be obtained from the Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.)

(Nongovernment standards and other publications are normally available from the organizations which prepare or which distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein, the text of this specification shall take precedence. Nothing in this specification, however, shall supersede applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 First article. Unless otherwise specified (see 6.2), the contractor shall furnish insulation samples which shall be subjected to first article inspection (see 4.4). First article inspection samples, properly marked with identifying information, shall be a sample of the insulation to be furnished to the Government. All subsequent insulation delivered to the Government shall conform to these samples in all of their pertinent physical and performance attributes.

3.2 Materials. The materials shall be as specified herein. The insulation when used within the performance parameters of 3.4, except when burning, shall not contain any materials which would cause adverse effects on the health of the personnel (see 4.8.1).

3.2.1 Composition. The insulation shall be a composite consisting of the following.

3.2.1.1 Vinyl. The cover material shall be 0.040- to 0.045-inch-thick deep-twist grain vinyl (see 4.8.1).

3.2.1.2 Barrier. The barrier shall be bonded between the vinyl and the foam. The barrier shall weigh 0.8 pound per square foot, and shall have a specific gravity of 2.5 $\pm$ 5 percent (see 4.8.1).

3.2.1.3 Foam. The foam shall be 0.50-inch-thick closed-cell foam insulation (see 4.8.1).

3.2.2 Recycled, virgin and reclaimed materials. There are no requirements for the exclusive use of virgin materials; however, all materials shall be new and unused. The use of recycled or reclaimed (recovered) materials is acceptable provided that all other requirements of this specification are met (see 6.3.1).



Source: https://assist.dla.mil -- Downloaded: 202640-23T01:45Z
Check the source to verify that this is the current version before use.

3.3 Design and construction.

3.3.1 Configuration. The configuration of the insulation shall be as specified in the acquisition document or as specified on the applicable assembly drawing (see 4.8.2 and 6.2).

3.3.2 Color. The color of the vinyl shall be green 383 per MIL-C-46168 (see 4.8.2).

3.4 Performance.

3.4.1 Adhesion strength. The adhesion strength of the vinyl to the barrier and the barrier to the foam at a 180 degree peel shall be not less than 2.2 pounds per linear inch (see 4.8.3).

3.4.2 Thermal conductivity. The thermal conductivity of the insulation shall be not greater than 0.35 British thermal unit (Btu)/[(hour)(square foot)(degrees Fahrenheit/inch)] (see 4.8.4).

3.4.3 Tear resistance.

3.4.3.1 Insulation. The tear resistance of the insulation shall be not less than 25 pounds force per inch (ppi) (see 4.8.5.1).

3.4.3.2 Barrier/vinyl. The tear resistance of the barrier/vinyl shall be not less than 130 ppi (see 4.8.5.2).

3.4.4 Tensile strength.

3.4.4.1 Insulation. The tensile strength of the insulation shall be not less than 100 pounds force per square inch (psi) (see 4.8.6.1).

3.4.4.2 Barrier/vinyl. The tensile strength of the barrier/vinyl shall be not less than 500 psi (see 4.8.6.2).

3.4.5 Abrasion resistance. There shall be not more than a 0.025-percent weight loss of the insulation when tested as specified in ASTM D4158 (see 4.8.7).

3.4.6 Flammability. The burning rate of the insulation shall be not greater than 2 inches per minute (see 4.8.8).

3.4.7 Environmental.

3.4.7.1 High temperature. The insulation shall remain physically stable when exposed to a temperature of 250 degrees Fahrenheit (°F) (see 4.8.9).

3.4.7.2 Low temperature. The insulation shall remain physically stable when exposed to a temperature of -40°F (see 4.8.10).

3.4.7.2.1 Low temperature (cold bend). After being cold soaked at -30°F, the insulation shall evidence no cracks while bent 180 degrees around a 1-inch mandrel (see 4.8.10.1).



Source: https://assist.dla.mil -- Downloaded: 202640-23T01:45Z
Check the source to verify that this is the current version before use.

3.4.7.3 Chemical resistance.

3.4.7.3.1 Gasoline. The insulation shall evidence not more than 3 percent shrinkage after immersion in gasoline conforming to MIL-G-3056 (see 4.8.11.1).

3.4.7.3.2 Diesel fuel. The insulation shall evidence no shrinkage after immersion in diesel fuel conforming to VV-F-800 (see 4.8.11.2).

3.4.7.3.3 Lubricating oil. The insulation shall evidence no shrinkage after immersion in lubricating oil conforming to MIL-L-2104 (see 4.8.11.3).

3.5 Identification marking. Identification marking shall be in accordance with MIL-STD-130 (see 4.8.2).

3.6 Workmanship. Insulation shall be uniform in quality and free of foreign matter, cracks, tears, cuts, or any other defect that will affect its life, serviceability, or appearance. Workmanship shall be such as to ensure insulation which is in conformance to this specification (see 4.8.2).

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order (see 6.2), the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform or witness any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items must meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of assuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling in quality conformance does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to acceptance of defective material.

4.1.2 Inspection equipment. Unless otherwise specified in the contract (see 6.2), the contractor is responsible for the provision and maintenance of all inspection equipment necessary to assure that supplies and services conform to contract requirements. Inspection equipment must be capable of repetitive measurements to an accuracy of 10 percent of the measurement tolerance. Calibration of inspection equipment shall be in accordance with MIL-STD-45662.



Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:45Z
Check the source to verify that this is the current version before use.

4.2 Classification of inspection:

a. First article inspection (see 4.4).
b. Quality conformance inspections (see 4.5).
   1. Examination (see 4.5.2).
   2. Tests (see 4.5.3).
c. Control tests (see 4.6).

4.3 Inspection conditions. Unless otherwise specified (see 6.2), all inspections shall be conducted under the following conditions:

a. Air temperature 73 ± 18°F
b. Barometric pressure 28.5 + 2.0 inches mercury (Hg)
   - 3.0
c. Relative humidity 50 ± 30 percent

4.4 First article inspection. Unless otherwise specified (see 6.2), the Government shall select insulation samples produced under the production contract (see 6.2) for first article inspection. First article samples shall be inspected as specified in table I. Approval of first article samples by the Government shall not relieve the contractor of his obligation to supply insulation that is fully representative of those inspected as first article samples. Any changes or deviation of the production units from the first article samples shall be subject to the approval of the contracting officer.

4.4.1 First article inspection failure. Test item deficiencies during, or as a result of, first article inspection shall be cause for rejection of the items until evidence has been provided by the contractor that corrective action has been taken to eliminate the deficiency. Any deficiency found during, or as a result of, first article inspection shall be evidence that the insulation already produced prior to completion of first article inspection is similarly deficient unless contrary evidence satisfactory to the contracting officer is furnished by the contractor. Such deficiencies on all items shall be corrected by the contractor. The Government will not accept products until first article inspection is completed to the satisfaction of the Government.



Source: https://assist.dla.mil -- Downloaded: 202610-23T01:45Z
Check the source to verify that this is the current version before use.

TABLE I. Classification of inspections.

| Title | Requirement | Inspection | First article | Quality conformance | | Control |
|---|---|---|---|---|---|---|
| | | | | Examination | Tests | |
| Materials | 3.2 thru 3.2.1.3 | 4.8.1 | X | | X | |
| Defects (see 4.5.2 and table II) | 3.3.1, 3.3.2, 3.5, and 3.6 | 4.8.2 | X | X | | |
| Adhesion strength | 3.4.1 | 4.8.3 | X | | | X |
| Thermal conductivity | 3.4.2 | 4.8.4 | X | | | X |
| Tear resistance | 3.4.3 | 4.8.5 | X | | | X |
| Tensile strength | 3.4.4 | 4.8.6 | X | | | X |
| Abrasion resistance | 3.4.5 | 4.8.7 | X | | | X |
| Flammability | 3.4.6 | 4.8.8 | X | | | X |
| High temperature | 3.4.7.1 | 4.8.9 | X | | | X |
| Low temperature | 3.4.7.2 | 4.8.10 | X | | | X |
| Low temperature (cold bend) | 3.4.7.2.1 | 4.8.10.1 | X | | | X |
| Chemical resistance | 3.4.7.3 | 4.8.11 | X | | | |

4.5 Quality conformance inspections.

4.5.1 Sampling.

4.5.1.1 Lot formation. An inspection lot shall consist of all the insulation manufactured during an identifiable production period (not exceeding 24 hours), from one manufacturer, submitted at one time for acceptance.

4.5.1.2 Sampling for examination. Samples for quality conformance examination shall be selected in accordance with general inspection level II of MIL-STD-105.

4.5.2 Examination.

4.5.2.1 Acceptable quality level. Each sample selected in accordance with 4.5.1.2 shall be examined to determine conformance to the following acceptable quality levels (AQL) on the basis of percent defective:

| Classification | AQL |
|---|---|
| Major | 1.0 |
| Minor | 2.5 |

4.5.2.2 Classification of defects. For examination purposes, defects shall be classified as listed in table II.



Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:45Z
Check the source to verify that this is the current version before use.

TABLE II. Classification of defects.

| Category | Defect | Method of examination |
|---|---|---|
| Critical | None | |
| Major | AQL 1.0% Defective | |
| 101 | Dimensions, out of tolerance (see 3.3.1). | SIE 1/ |
| 102 | Faulty workmanship affecting performance (see 3.6). | Visual |
| Minor | AQL 2.5% Defective | |
| 201 | Color not as specified (see 3.3.2). | Visual |
| 202 | Identification marking, improper (see 3.5) | Visual |
| 203 | Faulty workmanship affecting appearance (see 3.6). | Visual |

1/ SIE = Standard Inspection Equipment.

4.5.3 Tests. Each insulation sample shall be subjected to the quality conformance tests specified in table I.

4.6 Control tests. Control tests shall be conducted on 1 insulation sample from each lot of 200 units consecutively produced, except that not more than 1 test shall be performed in a 3-month period, not less than 1 test in a 6-month period. The insulation sample shall be subjected to the tests specified in table I.

4.7 Failure. Failure of any sample to pass any of the specified quality conformance or control tests shall be cause for the Government to refuse acceptance of the production quantity represented, until action taken by the contractor to correct defects and prevent recurrence has been approved by the Government.

4.8 Methods of inspection.

4.8.1 Materials. Conformance to 3.2 through 3.2.1.3 shall be determined by inspection of contractor records providing proof or certification that processing and materials conform to requirements. Applicable records shall include specifications, receiving inspection records, processing and quality control standards, vendor catalogs and certifications, industry standards, test reports, and rating data.

4.8.2 Defects. Conformance to 3.3.1, 3.3.2, 3.5, and 3.6 shall be determined by examination for the defects listed in table II. Examination shall be visual, tactile, or by measurement with SIE.

4.8.3 Adhesion strength. To determine conformance to 3.4.1, the adhesion strength of the vinyl to the barrier and the barrier to the foam shall be tested as specified in ASTM D903.



Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:45Z
Check the source to verify that this is the current version before use.

4.8.4 Thermal conductivity. To determine conformance to 3.4.2, the insulation shall be tested as specified in ASTM C177.

4.8.5 Tear resistance.

4.8.5.1 Insulation. To determine conformance to 3.4.3.1, the insulation shall be tested as specified in ASTM D624, die C.

4.8.5.2 Barrier/vinyl. To determine conformance to 3.4.3.2, the barrier/vinyl shall be tested as specified in ASTM D624, die C.

4.8.6 Tensile strength.

4.8.6.1 Insulation. To determine conformance to 3.4.4.1, the insulation shall be tested as specified in ASTM D412, die A.

4.8.6.2 Barrier/vinyl. To determine conformance to 3.4.4.2, the barrier/vinyl shall be tested as specified in ASTM D412, die A.

4.8.7 Abrasion resistance. To determine conformance to 3.4.5, the insulation shall be tested as specified in ASTM D4158. The load shall be 500 grams and the number of cycles shall be 1000.

4.8.8 Flammability. To determine conformance to 3.4.6, the insulation shall be tested as specified in SAE J369.

4.8.9 High temperature. To determine conformance to 3.4.7.1, the insulation shall be tested as specified in MIL-STD-810D, method 501.2, procedure I, at 250°F for seven 24-hour periods.

4.8.10 Low temperature. To determine conformance to 3.4.7.2, the insulation shall be tested as specified in MIL-STD-810D, method 502.2, precedure I, at -40°F for 4 hours.

4.8.10.1 Low temperature (cold bend). To determine conformance to 3.4.7.2.1, the insulation shall be tested as specified in MIL-STD-810D, method 502.2, procedure II, at -30°F for 4 hours. After the 4-hour period, the insulation shall be bent around a 1-inch mandrel and examined for evidence of cracks.

4.8.11 Chemical resistance.

4.8.11.1 Gasoline. To determine conformance to 3.4.7.3.1, a 4- by 14-inch specimen of insulation shall be immersed for 24 hours in gasoline conforming to MIL-G-3056. After the 24-hour period, the specimen shall be removed and allowed to stand for 1 hour at room temperature. After this 1-hour period, the speciman shall be measured for any skrinkage.



Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:45Z
Check the source to verify that this is the current version before use.

4.8.11.2 Diesel fuel. To determine conformance to 3.4.7.3.2, a 4- by 14-inch specimen of insulation shall be immersed for 24 hours in diesel fuel conforming to VV-F-800. After the 24-hour period, the specimen shall be removed and allowed to stand for 1 hour at room temperature. After this 1-hour period, the specimen shall be examined for evidence of shrinkage.

4.8.11.3 Lubricating oil. To determine conformance to 3.4.7.3.3, a 4- by 14-inch specimen of insulation shall be immersed for 24 hours in lubricating oil conforming to MIL-L-2104. After the 24-hour period, the specimen shall be removed and allowed to stand for 1 hour at room temperature. After this 1-hour period, the specimen shall be examined for evidence of shrinkage.

## 5. PACKAGING

5.1 Preservation, packaging, packing, and marking. Preservation, packaging, packing, and marking for the desired level shall be in accordance with the applicable packaging standard or packaging data sheet specified by the contracting authority (see 6.2).

## 6. NOTES

6.1 Intended use. This insulation is intended to be used as floor-mat insulation in military vehicles.

6.2 Ordering data. Acquisition documents should specify the following:

a. Title, number, and date of this specification.
b. If first article samples are not required (see 3.1).
c. Configuration of the insulation or title, number, and date of the applicable drawing (see 3.3.1).
d. If responsibility for inspection shall be other than as specified (see 4.1).
e. If responsibility for inspection equipment shall be other than as specified (see 4.1.2).
f. If inspection conditions shall be other than as specified (see 4.3).
g. If first article inspection is not required (see 4.4).
h. Number of samples to be selected for first article inspection (see 4.4).
i. Applicable levels of preservation, packaging, packing, and marking (see 5.1).

6.3 Definitions.

6.3.1 Recovered materials. "Recovered materials" means materials that have been collected or recovered from solid waste (see 6.3.2).

6.3.2 Solid waste. "Solid waste" means (a) any garbage, refuse, or sludge from a waste treatment plant, water supply treatment plant, or air pollution control facility; and (b) other discarded material, including solid, liquid, semisolid, or contained gaseous material resulting from industrial, commercial, mining, and agricultural operations, and from



Source: https://assist.dla.mil -- Downloaded: 202610-23T01:45Z
Check the source to verify that this is the current version before use.

community activities. It does not include solid or dissolved material in domestic sewage, or solid or dissolved material in irrigation return flows or industrial discharges which are point sources subject to permits under section 402 of the Clean Water Act, (33 U.S.C. 1342 et seq.), or source, special nuclear, or byproduct material as defined by the Atomic Energy Act of 1954 (42 U.S.C. 2011 et seq.) (Source: Federal Acquisition Regulations, section 23.402).

6.4 Subject term (key word) listing.

Floor Mat
Insulation
Thermal Barrier

6.5 Supersession data. This military specification supersedes AM General Corporation specification AMG 192, revision A, dated 16 May 1984.

Custodian:
Army - AT

Preparing activity:
Army - AT

(Project No. 5640-A444)



Source: https://assist.dla.mil -- Downloaded: 202610-23T01:45Z
Check the source to verify that this is the currentversion before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:45Z
Check the source to verify that this is the current version before use.

**INSTRUCTIONS**: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

*NOTE*: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

*(Fold along this line)*

*(Fold along this line)*

DEPARTMENT OF THE ARMY

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 12062 WASHINGTON, D.C.

POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Commander
US Army Test and Evaluation Command
ATTN: DRSTE-AD-M
Aberdeen Proving Ground, MD 21005

inspection records shall ... the inspection record

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:45Z
Check the source to verify that this is the current version before use.

(TO DETACH THIS FORM, CUT ALONG THIS LINE.)

# STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

*(See Instructions – Reverse Side)*

| 1. DOCUMENT NUMBER | 2. DOCUMENT TITLE |
|---|---|
| | |

| 3a. NAME OF SUBMITTING ORGANIZATION | 4. TYPE OF ORGANIZATION *(Mark one)* |
|---|---|
| | ☐ VENDOR |
| b. ADDRESS *(Street, City, State, ZIP Code)* | ☐ USER |
| | ☐ MANUFACTURER |
| | ☐ OTHER *(Specify)*: _____ |

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

| 7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional | b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional |
|---|---|
| c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional | 8. DATE OF SUBMISSION *(YYMMDD)* |
| | |

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE

Source: https://assist.dla.mil -- Downloaded: 202610-23T01:45Z
Check the source to verify that this is the current version before use.