INCH-POUND
MIL-STD-1276F
14 January 2000
SUPERSEDING
MIL-STD-1276E
18 May 1993

DEPARTMENT OF DEFENSE INTERFACE STANDARD

LEADS FOR ELECTRONIC COMPONENT PARTS



AMSC N/A FSC 5999

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T23:35Z
Check the source to verify that this is the current version before use.

FOREWORD

1. This standard is approved for use by all Departments and Agencies of the Department of Defense.

2. Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Defense Supply Center, Columbus, ATTN: DSCC-VAT, PO Box 3990, Columbus, OH 43216-5000, or telephone (614) 692-0542, or facsimile (FAX) (614) 692-6939.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T23:35Z
Check the source to verify that this is the current version before use.

CONTENTS

PARAGRAPH		PAGE
1.	SCOPE	1
1.1	Scope	1
1.2	Classification	1
1.2.1	Type designator	1
1.2.1.1	Cross section	1
1.2.1.2	Nominal size	1
1.2.1.3	Composition	1
1.2.1.4	Final finish	1
1.2.1.5	Underplating	1
2.	APPLICABLE DOCUMENTS	3
2.1	General	3
2.2	Government documents	3
2.2.1	Specifications, standards, and handbooks	3
2.3.	Non-Government publications	3
2.4.	Order of precedence	4
3.	DEFINITIONS	5
3.1	Definitions	5
4.	GENERAL REQUIREMENTS	6
4.1	Preferred methods of assembly	6
4.2	Solderability	7
4.3	Thickness	7
4.4	Adhesion	7
4.5	Porosity	7
4.6	Recycled, recovered, or environmentally preferable materials	7
4.7	Workmanship in finishes	7
5.	DETAILED REQUIREMENTS	8
5.1	Composition	8
5.2	Final finish	9
5.2.1	Underplating	10
5.2.1.1	Gold plating	10
5.2.1.2	Composition F, G, and K	10
5.2.1.3	Hot solder dip	10
5.2.1.4	Composition A, B, J, and X	10
6.	NOTES	11
6.1	Intended use	11
6.2	Precaution	11
6.3	Removal of gold plating before soldering	11
6.4	Passive nickel	11
6.5	Cross reference	11
6.6	Environmentally preferable material	12
6.7	Cleanliness	13
6.8	Supersession data	13
6.9	Subject term (key word) listing	13
6.10	Changes from previous issue	13

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T23:35Z
Check the source to verify that this is the current version before use.

TABLES

TABLE I	Nominal size	2
TABLE II	Preferred methods of assembly	6
TABLE III	Chemical Composition	8
TABLE IV	Cross reference of lead types	11
TABLE V	EPA top seventeen hazardous materials	12
TABLE VI	Supersession data for final finishes	13

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T23:35Z
Check the source to verify that this is the current version before use.

1. SCOPE

1.1 Scope. This standard establishes the method of identifying, specifying, and limiting to a minimum the combinations of basic materials, the thickness and composition of the plating used therewith, and the sizes of wire and flat wire (ribbon) leads on electronic and electrical parts when they are to be soldered or welded during assembly in equipment.

1.2 Classification.

1.2.1 Type designation. The type designation will be in the following format:

L	W	(X.XX)	D	-	21	-	A1
Lead	Cross-section (see 1.2.1.1)	Nominal size (see 1.2.1.2)	Composition (see 1.2.1.3)	Dash	Final finish (see 1.2.1.4)	Dash	Under-plating (see 1.2.1.5)

1.2.1.1 Cross section. The lead cross section will be identified by a single letter symbol as follows:

R - Rectangular.
S - Square.
W - Wire (round or circular).
X - Other (as specified).

1.2.1.2 Nominal size. The lead size will be identified by the nominal diameter or nominal diagonal in millimeters (within parentheses) or inches (without parentheses). See table I for a list of suggested nominal sizes.

1.2.1.3 Composition. The lead composition will be identified by a single letter symbol as specified in 5.1.

1.2.1.4 Final finish. The final finish for leads will be identified by a two-number code as specified in 5.2.

1.2.1.5 Underplating. The underplating type and thickness will be identified by a one or two digit alpha-numeric code as specified in 5.2.1.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T23:35Z
Check the source to verify that this is the current version before use.

TABLE I. Nominal size (for information only).

Wire size AWG (B and S)	Diameter in inches	Diameter in millimeters
1	0.289	7.34
2	0.257	6.53
3	0.229	5.82
4	0.204	5.18
5	0.181	4.60
6	0.162	4.11
7	0.144	3.65
8	0.128	3.25
9	0.114	2.90
10	0.101	2.57
11	0.090	2.29
12	0.080	2.03
13	0.072	1.83
14	0.064	1.63
15	0.057	1.45
16	0.050	1.27
17	0.045	1.14
18	0.040	1.02
19	0.035	0.89
20	0.032	0.81
21	0.028	0.71
22	0.025	0.64
23	0.022	0.56
24	0.020	0.51
25	0.017	0.43
26	0.015	0.38
27	0.014	0.36
28	0.012	0.30
29	0.011	0.28
30	0.010	0.25
31	0.008	0.20
32	0.008	0.20
33	0.007	0.18
34	0.006	0.15
35	0.005	0.13
36	0.005	0.13
37	0.004	0.10
38	0.004	0.10
39	0.003	0.08
40	0.003	0.08

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T23:35Z
Check the source to verify that this is the current version before use.

2. APPLICABLE DOCUMENTS

2.1 General. The documents listed in this section are specified in sections 3, 4, and 5 of this standard. This section does not include documents cited in other sections of this standard or recommended for additional information or as examples. While every effort has been made to ensure the completeness of this list, document users are cautioned that they must meet all specified requirements documents cited in sections 3, 4, and 5 of this standard, whether or not they are listed.

2.2 Government documents.

2.2.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DoDISS) and supplement thereto, cited in the solicitation.

SPECIFICATION

FEDERAL

QQ-N-290 - Nickel Plating (Electrodeposited).
QQ-S-365 - Silver Plating, Electrodeposited; General Requirements for.

DEPARTMENT OF DEFENSE

MIL-C-26074 - Coatings, Electroless Nickel, Requirements for.
MIL-N-46025 - Nickel Bar, Flat Wire (Ribbon) and Strip (for Electronic Use).

STANDARDS

DEPARTMENT OF DEFENSE

MIL-STD-202 - Test Methods for Electronic and Electronic and Electrical Component Parts.
MIL-STD-750 - Test Methods for Semiconductor Devices.
MIL-STD-883 - Test Methods and Procedures for Microelectronics.

(Unless otherwise indicated, copies of the above specifications, standards, and handbooks are available from the Defense Automated Printing Service, Building 4D (DPM-DODSSP), 700 Robbins Avenue, Philadelphia, PA 19111-5094.)

2.3 Non-Government publications. The following document(s) form a part of this document to the extent specified herein. Unless otherwise specified, the issues of the documents which are DoD adopted are those listed in the issue of the DoDISS cited in the solicitation. Unless otherwise specified, the issues of documents not listed in the DoDISS are the issues of the documents cited in the solicitation.

AMERICAN NATIONAL STANDARDS

J-STD-006 - Requirements for Electronic Grade Solder Alloys and Fluxed and Non-Fluxed Solid Solders for Electronic Soldering Applications.

(Application for copies should be addressed to the Institute for Interconnecting and Packaging Electronic Circuits (IPC), 7380 N. Lincoln Avenue, Lincolnwood, IL 60646.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T23:35Z
Check the source to verify that this is the current version before use.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

ASTM B5	-	Standard Specification for Electrolytic Tough-Pitch Copper Refinery Shapes.
ASTM B122	-	Standard Specification for Copper-Nickel-Tin Alloy, Copper-Nickel-Zinc Alloy (Nickel Silver), and Copper-Nickel Alloy Plate, Sheet, Strip and Rolled Bar.
ASTM B170	-	Standard Specification for Oxygen-Free Electrolytic Copper-Refinery Shapes.
ASTM B322	-	Standard Practice for Cleaning Metals Prior to Electroplating.
ASTM B343	-	Standard Practice for Preparation of Nickel for Electroplating with Nickel.
ASTM B465	-	Standard Specification for Copper-Iron Alloy Plate, Sheet, Strip, and Rolled Bar.
ASTM B487	-	Standard Practice for Measurement of Metal and Oxide Coating Thickness by Microscopical Examination of a Cross-section.
ASTM B488	-	Electrodeposited Coatings of Gold for Engineering Uses.
ASTM B545	-	Standard Specification for Electrodeposited Coatings of Tin.
ASTM B571	-	Standard Practice for Adhesion of Metallic Coating.
ASTM B592	-	Standard Specification for Copper-Zinc-Aluminum-Cobalt or Nickel-Alloy Plate, Sheet, Strip, and Rolled Bar, Specification for.
ASTM B735	-	Standard Test Method for Porosity in Gold Coatings on Metal Substrates by Nitric Acid.
ASTM B741	-	Standard Test Method for Porosity in Gold Coatings on Metal Substrates by Paper Electrography.
ASTM F15	-	Standard Specification for Iron-Nickel-Cobalt Sealing Alloy.
ASTM F29	-	Standard Specification for Dumet Wire for Glass-to-Metal Seal Applications.
ASTM F30	-	Standard Specification for Iron-Nickel Sealing Alloy.

(Application for copies should be addressed to the American Society for Testing and Materials, 100 Barr Harbor Drive, West Conshohocken, PA 19482-2959.)

SOCIETY OF AUTOMOTIVE ENGINEERS

AMS 2418	-	Plating, Copper
AMS P-81728	-	Plating, Tin-Lead (Electrodeposited)

(Application for copies should be addressed to the Society of Automotive Engineers, Inc. (SAE), 400 Commonwealth Drive, Warrendale, PA 15096-0001).

2.4 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T23:35Z
Check the source to verify that this is the current version before use.

3. DEFINITIONS

3.1 Definitions. This section is not applicable to this standard.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T23:35Z
Check the source to verify that this is the current version before use.

4. GENERAL REQUIREMENTS

4.1 Preferred methods of assembly. The preferred methods of assembly shall be in accordance with table II.

TABLE II. Preferred methods of assembly.

Composition (see 5.1)	Underplating (see 5.2l.1)	Final finish (see 5.2)											
		01	21	22	32	34	41	43	51	52	61	71	72
A	A	---	S,W	S,W	S	S	S	S	S	S	W	S	S
"	B	---	S,W	S,W	"	"	"	"	"	"	"	"	"
"	C	---	---	---	"	"	"	"	"	"	"	"	"
B	A	---	S,W	S,W	"	"	"	"	"	"	"	"	"
"	B	---	S,W	S,W	"	"	"	"	"	"	"	"	"
"	C	---	---	---	"	"	"	"	"	"	"	"	"
C	A	---	---	---	"	"	"	"	"	"	"	"	"
"	B	---	---	---	"	"	"	"	"	"	"	"	"
"		---	---	---	"	"	"	"	"	"	"	"	"
"	P	---	---	---	"	"	"	"	"	"	"	"	"
"	N	W	---	---	"	"	"	"	"	"	"	"	"
D	A	---	S,W	S,W	"	"	"	"	"	"	"	"	"
"	B	---	S,W	S,W	"	"	"	"	"	"	"	"	"
"	C	---	---	---	"	"	"	"	"	"	"	"	"
"	P	---	---	---	"	"	"	"	"	"	"	"	"
"	N	---	---	---	"	"	"	"	"	"	"	"	"
E	A	---	S,W	S,W	"	"	"	"	"	"	"	"	"
"	B	---	S,W	S,W	"	"	"	"	"	"	"	"	"
"	C	---	---	---	"	"	"	"	"	"	"	"	"
"	P	---	---	---	"	"	"	"	"	"	"	"	"
"	N	---	---	---	"	"	"	"	"	"	"	"	"
F	A	---	S,W	S,W	"	"	"	"	"	"	"	"	"
"	B	---	S,W	S,W	"	"	"	"	"	"	"	"	"
"	C	---	---	---	"	"	"	"	"	"	"	"	"
"	P	---	---	---	"	"	"	"	"	"	"	"	"
G	A	---	S,W	S,W	"	"	"	"	"	"	"	"	"
"	B	---	S,W	S,W	"	"	"	"	"	"	"	"	"
"	C	---	---	---	"	"	"	"	"	"	"	"	"
"	P	---	---	---	"	"	"	"	"	"	"	"	"
H	A	---	S,W	S,W	"	"	"	"	"	"	"	"	"
"	B	---	S,W	S,W	"	"	"	"	"	"	"	"	"
"	C	---	---	---	"	"	"	"	"	"	"	"	"
"	P	---	---	---	"	"	"	"	"	"	"	"	"
"	N	---	---	---	"	"	"	"	"	"	"	"	"
J	A	---	S,W	S,W	"	"	"	"	"	"	"	"	"
"	B	---	S,W	S,W	"	"	"	"	"	"	"	"	"
"	C	---	---	---	"	"	"	"	"	"	"	"	"
K	A	---	S,W	S,W	"	"	"	"	"	"	"	"	"
"	B	---	S,W	S,W	"	"	"	"	"	"	"	"	"
"	C	---	---	---	"	"	"	"	"	"	"	"	"
"	P	---	---	---	"	"	"	"	"	"	"	"	"
L	A	---	---	---	"	"	"	"	"	"	"	"	"
"	B	---	---	---	"	"	"	"	"	"	"	"	"
"					"	"	"	"	"	"	"	"	"
"	P	---	---	---	"	"	"	"	"	"	"	"	"
"	N	---	---	---	"	"	"	"	"	"	"	"	"
M					"	"	"	"	"	"	"	"	"
"					"	"	"	"	"	"	"	"	"
"	C	---	---	---	"	"	"	"	"	"	"	"	"
"	P	---	---	---	"	"	"	"	"	"	"	"	"
"	N	---	---	---	"	"	"	"	"	"	"	"	"

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T23:35Z
Check the source to verify that this is the current version before use.

TABLE II. Preferred methods of assembly - Continued.

Composition (see 5.1)	Underplating (see 5.2l.1)	Final finish (see 5.2)											
		01	21	22	32	34	41	43	51	52	61	71	72
N					S	S	S	S	S	S	W	S	S
"					"	"	"	"	"	"	"	"	"
"	C	---	---	---	"	"	"	"	"	"	"	"	"
"	P	---	---	---	"	"	"	"	"	"	"	"	"
"	N	W	---	---	"	"	"	"	"	"	"	"	"
W	A	---	S,W	S,W	"	"	"	"	"	"	"	"	"
"	B	---	S,W	S,W	"	"	"	"	"	"	"	"	"
"					"	"	"	"	"	"	"	"	"
"	P	---	---	---	"	"	"	"	"	"	"	"	"
"	N	---	---	---	"	"	"	"	"	"	"	"	"
X	As specified in the acquisition document.												

S = Solder
W = Weld

4.2 Solderability. When specified in the acquisition documents, leads shall meet the following solderability requirements.

a. Discrete semiconductor devices: Test method 2026 of MIL-STD-750.

b. Microelectronics: Test method 2003 of MIL-STD-883.

c. Other electronic and electrical component parts: Test method 208 of MIL-STD-202.

4.3 Thickness. When specified in the acquisition document, the thickness of the final finish and underplating shall be determined in accordance with ASTM B487 or ASTM B567.

4.4 Adhesion. When specified in the acquisition document, the adhesion of the final finish and underplating shall be determined in accordance with ASTM B571 or method 2025 of MIL-STD-883.

4.5 Porosity. When specified in the acquisition document, there shall be no evidence of porosity for final finishes 21, 22, and 61 when tested in accordance with ASTM B735 or ASTM B741.

4.6 Recycled, recovered, or environmentally preferable materials. Recycled, recovered, or environmentally preferable materials should be used to the maximum extent possible provided that the material meets or exceeds the operational and maintenance requirements, and promotes economically advantageous life cycle costs.

4.7 Workmanship in finishes. All plating or primary finishes or underplating shall be deposited in such a way that the plating is applied to a clean, nonoxidized metal surface that is free from defects that will be detrimental to the utility, form, fit, function, or protective value of the finish. Where surface cleaning, deoxidation, activation, or undercoating are used, the material or device so treated must proceed immediately to the primary finish process in order to maintain the ability to overplate effectively.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T23:35Z
Check the source to verify that this is the current version before use.

5. DETAILED REQUIREMENTS

5.1 Composition. The specified lead composition (see 1.2.1.3) shall conform to the requirements of the applicable documents and table as follows:

A - Copper-iron-phosphorus-zinc alloy (194 alloy): ASTM B465 (see 5.2.1.4).

B - Copper-iron-phosphorus-cobalt-tin alloy (195 alloy), 97 percent Cu, 1.5 percent Fe, 0.1 percent P, 0.8 percent Co, and 0.6 percent Sn (see 5.2.1.4).

C - Copper (oxygen free): ASTM B170, grade 1 or grade 2.

D - Copper-clad nickel-iron alloy (Dumet): ASTM F29.

E - Copper-nickel-tin alloy (725 alloy), 88.2 percent Cu, 9.5 percent Ni, and 2.3 percent Sn: ASTM B122.

F - Iron-nickel alloy (52 alloy): ASTM F30 (see 5.2.1.2).

G - Iron-nickel alloy (42 alloy): ASTM F30 (see 5.2.1.2).

H - Copper-aluminum-silicon-cobalt alloy (638 alloy), 95.0 percent Cu, 2.8 percent Al, 1.8 percent Si, and 0.4 percent Co.

J - Copper-zinc-aluminum-cobalt alloy (688 alloy): ASTM B592 (see 5.2.1.4).

K - Iron-nickel-cobalt alloy: ASTM F15 (see 5.2.1.2).

L - Copper, Electrolytic tough - pitch: ASTM B5.

M - Steel, nickel clad, 8 percent nickel, clad by weight.

N - Nickel: MIL-N-46025 (for ribbon leads) or table III (for round-wire leads.)

W - Steel, copper-clad: ASTM B452 (except that the percent of conductivity shall be a minimum of 16 percent.)

X - Other composition as specified in the acquisition document (see 5.2.1.4).

TABLE III - Chemical composition

Element	Percent 1/
Nickel 2/	99.0 min
Iron	0.30
Copper	0.20
Manganese	0.35
Carbon	0.15
Silicon	0.20
Sulfur	0.008

1/ Maximum unless otherwise indicated.
2/ Cobalt counting as nickel.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T23:35Z
Check the source to verify that this is the current version before use.

5.2 Final finish. The final finish for leads (see 1.2.1.4) shall conform to the following as applicable:

01 - No finish. Lead is supplied with no external finish.

21 - Gold plating, electrodeposited, in accordance with ASTM B488, type 2. The thickness of the gold plating shall be 100 to 300 microinches. When specified, under-plating shall be in accordance with 5.2.1.1.

22 - Gold plating, electrodeposited, in accordance with ASTM B488, type 2. The thickness of the gold plating shall be 50 to 100 microinches. When specified, under-plating shall be in accordance with 5.2.1.1.

32 - Tin-lead plating, electrodeposited, in accordance with AMS-P-81728. Composition shall be 50 to 70 percent tin (remainder lead). The thickness shall be 300 to 900 microinches (22.9 µm).

34 - Fused (reflowed) tin-lead plated, electrodeposited, in accordance with AMS-P-81728. Composition shall be 50 to 70 percent tin (remainder lead). The tin-lead thickness after fusing (or reflow), shall not be less than 100 microinches (2.54 µm) at any single point. The average thickness of all points measured shall be 300 (7.62 µm) to 500 microinches (12.7 µm).

41 - Acid-tin-lead plating, electrodeposited, in accordance with ASTM B545. Thickness shall be 300 (7.62 µm) to 500 microinches (12.7 µm). Minimum lead content shall be 3 percent.

43 - Matte-tin-lead plating, electrodeposited, in accordance with ASTM B545. The thickness shall be 300 (7.62 µm) to 500 microinches (12.7 µm). The matte-tin plating shall contain no more than 0.05 percent by weight codeposited organic material measured as elemental carbon. Minimum lead content shall be 3 percent.

45 - Acid-tin-lead plating, electrodeposited, in accordance with ASTM B545. Thickness shall be 100 (2.54 µm) to 300 microinches (7.62 µm). Minimum lead content shall be 3 percent.

46 - Matte-tin-lead plating (low organic content), electrodeposited, in accordance with ASTM B545. The thickness shall be 100 (2.54 µm) to 300 microinches (7.62 µm). The matte-tin plating shall contain no more than 0.05 percent by weight codeposited organic material measured as elemental carbon. Minimum lead content shall be 3 percent.

51 - Hot solder dip. The composition shall be Sn60PB40A, Sn63Pb37A, or Sn62PB36AgO2C in accordance with J-STD-006. The coating shall have a minimum thickness of 200 microinches as measured at the crest. Hot solder dip finish may be used over final finish types 21, 22, 32, 34, 41, 43, 45, 46, 61, 71, and 72. When specified (see 1.2.1.5), electroless nickel under-plating may be used in accordance with 5.2.1.3.

52 - Hot solder dip. The composition shall be Sn60PB40A, Sn63Pb37A, or Sn62PB36AgO2C in accordance with J-STD-006. Thickness shall be 60-200 microinches as measured at the crest. Hot solder dip finish may be used over final finish types 21, 22, 32, 34, 41, 43, 45, 46, 61, 71, and 72. When specified (see 1.2.1.5), electroless nickel underplating may be used in accordance with 5.2.1.3.

61 - Nickel plating, electrodeposited, in accordance with QQ-N-290. Thickness shall be 50 (1.27 µm) to 150 microinches (3.81 µm). The nickel plating shall be nonbrightened and low stress.

71 - Silver plating, electrodeposited, in accordance with QQ-S-365, type II, grade B. Thickness shall be 150 (3.81 µm) to 350 microinches (8.89 µm).

72 - Silver plating, electrodeposited, matte, nonbrightened, in accordance with QQ-S-365, type I. Thickness shall be 150 (3.81 µm) to 350 microinches (8.89 µm).

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T23:35Z
Check the source to verify that this is the current version before use.

5.2.1 Underplating. The underplating (see 1.2.1.5) shall conform to the following requirements:

A - Nickel electrolytic.

1 - 60 (1.52 µm) to 150 microinches (3.81 µm) thick.
2 - 100 (2.54 µm) to 300 microinches (7.62 µm) thick.
3 - 20 (0.50 µm) to 60 microinches (1.52 µm) thick.

B - Nickel, electroless (not to be used on flexible or semirigid leads).

1 - 100 (2.54 µm) to 200 microinches (5.08 µm) thick.
2 - 50 (1.27 µm) to 120 microinches (3.04 µm) thick.

C - Copper, electrodeposited.

1 - 60 (1.52 µm) to 150 microinches (3.81 µm) thick.
2 - 150 (3.81 µm) to 300 microinches (7.62 µm) thick.
3 - 20 (0.50 µm) to 60 microinches (1.52 µm) thick.

P - Palladium-nickel Alloy

1 - 50 (1.27 µm) to 100 microinches (2.54 µm) thick.

N - No underplating.

5.2.1.1 Gold plating. A copper plus electrodeposited nickel or electrodeposited nickel underplating is required on all leads with gold plating as the final finish in accordance with AMS 2418.

5.2.1.2 Compositions F, G, and K. All leads with composition F, G, or K (see 5.1) shall have an underplating prior to final finish.

5.2.1.3 Hot solder dip. When specified for use under hot solder dip lead finish (see 5.2), the electroless nickel underplating shall be in accordance with MIL-C-26074. The thickness shall be as designated in 5.2.1.B.

5.2.1.4 Compositions A, B, J, and X. All leads with compositions A, B, J. or X (see 5.1) shall have a copper or nickel underplate of 100 microinches (2.54 µm) minimum.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T23:35Z
Check the source to verify that this is the current version before use.

6. NOTES

(This section contains information of a general or explanatory nature which may be helpful, but is not mandatory.)

6.1 Intended use. Documents conforming to the requirements of this standard are intended for use of identifying, specifying, and limiting to a minimum the combinations of basic materials, the thickness and composition of the plating used therewith, and the sizes of wire and flat wire (ribbon) leads on electronic and electrical parts when they are to be soldered or welded during assembly in equipment.

6.2 Precaution. Substitution of any type of lead for the existing leads on electronic component parts should not be made in a parts specification without first determining the effect of this substitution on the performance and solderability characteristics of the component part.

6.3 Removal of gold plating before soldering. Prior to equipment assembly, gold plated leads will have the gold removed before soldering by single or double dipping into a flowing or nonflowing hot solder of sufficient volume to assure complete gold removal.

6.4 Passive nickel. If there is a delay after the application of nickel strike, where the nickel surface may have become passive, the nickel will be reactivated followed by gold plating. Reactivation of the nickel surface should be in accordance with the appropriate section of the latest ASTM standards. (Reference: ASTM B322, "Cleaning Metals Prior to Electroplating"; and ASTM B343, "Preparation of Nickel for Electroplating with Nickel".)

6.5 Cross reference. A cross reference of discontinued and superseding lead types appears in table IV. Where MIL-STD-1276B designations are specified, the cross referenced MIL-STD-1276C designations may be used.

TABLE IV. Cross reference of lead types.

Superseding type			Discontinued type
MIL-STD-1276C			MIL-STD-1276B
Composition	Final finish	Underplating	
C	3	---	C (tin plated)
C	4	---	C (tin-lead plated)
D	2a	A1	D
F	2a	A1	F
K	2a	A1	K
N	1	---	N-1
N	2a	---	N-2
N	3	---	N-3 (tin plated)
N	4	---	N-4 (tin-lead plated)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T23:35Z
Check the source to verify that this is the current version before use.

TABLE IV. Cross reference of lead types - Continued.

Superseding type	Discontinued type
MIL-STD-1276D	MIL-STD-1276C
Composition	Composition
A	Not available
B	Not available
C	C
D	D
E	Not available
F	F
G	G
H	Not available
J	Not available
K	K
L	C_1
M	Not available
N	N
W	W
X	X
Underplating (same as revision C with the addition of C and P)	
Final finish	Final finish
01	1
21	2a
22	2b
31	3
32	4
33	Not available
34	Not available
51	5a
52	5b
61	6
71	7
72	Not available

6.6 Environmentally preferable material. Environmentally preferable materials should be used to the maximum extent possible that the material meets or exceeds the operational and maintenance requirements, and promotes economically advantageous life cycle costs. Table XIII lists the Environmental Protection Agency (EPA) top seventeen hazardous materials targeted for major usage reduction. If any of these hazardous materials are required, it is recommended that it be used only when other materials cannot meet performance requirements.

TABLE V. EPA top seventeen hazardous materials.

Benzene	Dichloromethane	Tetrachloroethylene
Cadmium and compounds	Lead and compounds	Toluene
Carbon Tetrachloride	Mercury and compounds	1,1,1 - Trichloroethane
Chloroform	Methyl Ethyl compounds	Trichloroethylene
Chromium and compounds	Methyl Isobutyl Ketone	Xylenes
Cyanide and compounds	Nickel and compounds	

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T23:35Z
Check the source to verify that this is the current version before use.

6.7 Cleanliness. The last step in any component manufacturing process should be cleaning to remove residues such as fluxes.

6.8 Supersession data. Final finishes 31, 33, 35, and 36 are deleted, effective with revision E of this standard. These pure tin finishes may cause "tin whiskers" growth leading to shorts and intermittents, especially in low power (5 mA and below) applications. For additional information on this matter, refer to ASTM B545 ("Standard Specification for Electrodeposited Coating of Tin.") Replacement finish codes are 41, 43, 45, and 46 respectively, as described in 1.2.1.4, 5.2, and table V.

TABLE VI. Supersession data for final finishes.

Superseded (old) finish code (MIL-STD-1276D)	Superseding (new) finish code (MIL-STD-1276E)
31	41
33	43
35	45
36	46

6.9 Subject term (key word) listing.

Final finish
Plating
Terminals
Underplating

6.10 Changes from previous issue. Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extensiveness of the changes.

Custodians:
Army - CR
Navy - EC
Air Force - 11
DLA - CC

Review activities:
Navy - AS, CG, MC, SH
Air Force - 99

Preparing activity:
DLA - CC

(Project 5999-0362)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T23:35Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.

2. The submitter of this form must complete block1s 4, 5, 6, and 7, and send to preparing activity.

3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	**1. DOCUMENT NUMBER** MIL-STD-1276F	**2. DOCUMENT DATE** (YYMMDD)

3. DOCUMENT TITLE
LEADS FOR ELECTRONIC COMPONENT PARTS

4. NATURE OF CHANGE (Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle initial)	b. ORGANIZATION	
c. ADDRESS (Include Zip Code)	d. TELEPHONE (Incl Area Code) (1) Commercial (2) DSN (If applicable)	7. DATE SUBMITTED (YYYYMMDD)

8. PREPARING ACTIVITY

a. NAME Defense Supply Center, Columbus ATTN: VAT	b. TELEPHONE (Include Area Code) (1) Commercial (614) 692-0542 (2) DSN 850-0542
c. ADDRESS (Include Zip Code) P.O. Box 3990 Columbus, OH 43216-5000	**IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT:** Defense Standardization Program Office (DLSC-LM) 8725 John J. Kingman Road, Suite 2533 Fort Belvoir, Virginia 22060-6221 Telephone (703) 767-6888 DSN 427-6888

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T23:35Z
Check the source to verify that this is the current version before use.