METRIC

A-A-58044A
27 October 2011

SUPERSEDING
A-A-58044
30 June 1995

COMMERCIAL ITEM DESCRIPTION

N-METHYLPYRROLIDONE

The General Services Administration has authorized the use of this commercial item description for all federal agencies.

1. SCOPE. This commercial item description covers N-methylpyrrolidone for cold-wipe removal of overspread and/or overspray of polysulfide sealants and epoxy adhesives from aircraft and aerospace ground equipment surfaces. See Table I for pertinent information.

Table I. Description

Chemical Abstract Service (CAS) Registry No:	872-50-4
CAS Registry Name:	1-Methyl-2-Pyrrolidone
Synonym:	N-Methylpyrrolidone

Comments, suggestions, or questions on this document should be addressed to AFPA/AFTT, 2430 C Street, Bldg 70, Area B, Wright-Patterson AFB OH 45433-7632 or e-mailed to AFPET.AFTT@wpafb.af.mil. Since contact information can change, you may want to verify the currency of this address information using the ASSIST Online database at https://assist.daps.dla.mil.

AMSC N/A FSC 6810

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:59Z
Check the source to verify that this is the current version before use.

2. SALIENT CHARACTERISTICS.

2.1 Workmanship. The product shall consist of a stable, homogenous fluid free from dirt, fibers, lint, chips, and/or other foreign matter. The material shall not contain any amount of any chlorinated compounds, phosphates, abrasives, chromates, phenols, cresols, amines, petroleum hydrocarbons, lead, mercury, cadmium, chromium, sodium chloride, urea, sodium, sulfates, nitrates, nitrites, any ozone depleting compounds, or any of the targeted chemicals listed in the EPA 33/50 Program final report, EPA-745-R-99-004, March, 1999.

2.2 Physical properties. The product shall exhibit the physical and chemical properties described in Table II and 2.4 when tested in accordance with the methods listed.

Table II. Tests.

Component	Limit	Method
Assay, % by wt, min	99.0	Gas Chromatography
Water, % by wt, max	0.1	ASTM E 1064
Color, Pt-Co units, max	100	ASTM D 1209
γ-Butyrolactone, % by wt, max	Report	Gas Chromatography
Foreign matter	None allowed	Visual
Nonvolatile residue, % by wt, max [1]	0.10	Section 2.3
[1/] This requirement does not apply to product that has been purified by vacuum distillation.		

2.3 Nonvolatile residue. Transfer 10 ± 1 grams of product to the round bottom flask of a Kugelrohr apparatus. Assemble the apparatus and operate at 1 to 2 mm Hg and 65 ± 2°C for 60 ± 5 minutes. Calculate the weight percent gravimetrically.

2.4 Corrosion. The material shall be tested in accordance with ASTM F 483 (Total Immersion Corrosion). Test panels shall be prepared from cold-rolled sheet carbon steel and sheet aluminum conforming to SAE AMS 5046C and SAE AMS-QQ-A-250, respectively. Steel panels shall be fabricated from 1020 alloy. Aluminum test panels shall be fabricated from 2024 and 7075 alloy. The product shall not cause etching, accretion, or pitting corrosion; nor any discoloration or dulling of the panels; nor cause a weight change of an average of three test panels greater than that shown in Table III.

Table III. Maximum allowable weight change.

Alloy	Average of 3 Panels Weight Loss, Max (mg/cm^2/168 hrs)
2024 clad aluminum	0.5
7075 clad aluminum	0.05
1020 steel	0.05

3. PRODUCT CONFORMANCE PROVISIONS.

3.1 Contractor certification. The contractor shall certify and maintain substantiating evidence that the product offered meets the salient characteristics of this Commercial Item Description, and that the product conforms to the producer's own drawings, specifications, standards, and quality assurance practices, and be the same product offered for sale in the commercial marketplace. The government

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:59Z
Check the source to verify that this is the current version before use.

reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise stipulated by the provisions of the contract.

4. PACKAGING.

4.1 Preservation, packaging, packing and marking. The preservation, packaging, packing, labeling, and marking shall be as specified in the contract or order.

5. NOTES.

5.1 Part or identification number. The following part identification numbering procedure is for government purposes and does not constitute a requirement for the contractor.

This example describes a part numbering system for CID A-A-58044.

AA58044 - 100

└── Size of container in liters.

5.2 Source of documents.

5.2.1 ASTM documents. Documents are available through ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA, 19428-2959. Electronic copies of ASTM standards may be obtained through http://www.astm.org.

5.2.2 Society of Automotive Engineers (SAE) Documents. Documents are available through SAE International, 400 Commonwealth Drive, Warrendale, PA, 15096-0001. Electronic copies of these SAE standards may be obtained through http://www.sae.org.

5.3 Key Words.

1-Methyl-2-Pyrrolidine

NMP

Custodians:
Air Force - 68
DLA - GS

Preparing Activity:
Air Force – 68

(Project 6810-2011-008)

Note: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information using the ASSIST Online database at https://assist.daps.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:59Z
Check the source to verify that this is the current version before use.