INCH-POUND

MIL-B-63524A(AR)
AMENDMENT 1
21 December 1993

MILITARY SPECIFICATION

BATTERY, HED, SINGLE CELL, PRIMARY RESERVE

This amendment forms a part of Military Specification MIL-B-63524A(AR), dated 12 January 1988, and is approved for use by the US Army Armament, Munitions and Chemical Command, and is available for use by all Department and Agencies of the Department of Defense.

3.10.1 Accelerated storage aging verification. Add the following paragraph:

"3.10.1 Accelerated storage aging verification. All HED Battery (Dwg. 9328787) samples for First Article Testing shall be conditioned for 21 days at 215°F + 5°F prior to testing for the requirements of 3.3, 3.4, 3.5, 3.11, 3.12 and 3.13. During production, a continuous sample of 5 batteries per hour shall be taken from each lot and subjected to 215°F + 5°F for 21 days. If after conditioning, the batteries meet the non-activation voltage requirements of 3.3, lot acceptance samples will be taken from the production lot and subjected to lot acceptance testing. If after conditioning the batteries do not meet the non-activation voltage requirement of 3.3, then the entire lot shall be rejected."

PAGE 5

3.14.1 Ampul blank annealing. Add the following paragraph:

3.14.1 Ampul blank annealing. A light shone through the ampul blank after undergoing the annealing process shall be clear and not show colors of the spectrum when examined as specified in paragraph 4.4.4.1."

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T03:03Z
Check the source to verify that this is the current version before use.

PAGE 7

4.3.4 Battery, HED, Single Cell Primary Reserve, Under "Battery, Single Cell, Primary Reserve:

Add: "Accelerated storage aging, 438, 3.10.1".

Delete "Non-activation voltage, 126, 3.3, 4.4.6.1" and substitute "Non-activation voltage, 438-1-2, 3.3, 4.4.6.1".

PAGE 9

4.4.2.1 Battery, HED, Single Cell Primary Reserve:

Add: "113 Accelerated storage aging verification, 4.4, 3.10.1".

Add: "114 Flatness incorrect, 0.40%, 3.2, Gage".

PAGE 26

4.4.2.18 Ampul Blank:

Add: "109 Improper stress relief 1/, --, 3.14.1, 4.4.4.1".

Under Notes, Add: "1/ Sample shall be as specified in 4.4.4.1".

PAGE 32

4.4.4.1 Process control of ampul blank annealing. Add the following paragraph:

"4.4.4.1 Procss control of ampul blank annealing. In place of the normal sampling associated with the classification of defects, at startup, a sample of at least 25 annealed ampul blanks shall be examined using a polaroscope or equivalent for the requirements of 3.14.1. In addition, a sample of 5 blanks shall be selected each hour during the annealing process production run. If any defects are found during startup, continue selecting until 25 consecutive annealed ampuls pass. If any defects are found during the production run, that portion of the run will be screened until the last 5 acceptable units. Furthermore, all found defects shall be removed from the lot. A down time of more than 2 hours will require a startup requalification."

Custodian:
Army-AR

Preparing activity:
Army-AR

(Project 1345-A629)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T03:03Z
Check the source to verify that this is the current version before use.