MILITARY SPECIFICATION

BAG, WATERPROOF, CHEMICAL-BIOLOGICAL MASK, M1Al

This specification is approved for use by all Department-and Agencies of Department of Defense.

1. SCOPE

1.1 This specification covers one type of chemical-biological mask waterproof bag.

2. APPLICABLE DOCUMENTS

2.1 Government documents. The following documents, of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

SPECIFICATIONS

FEDERAL

UU-T-106	Tape, Pressure-Sensitive Adhesive, Masking, Paper.
PPP-B-621	Box, Wood, Nailed and Lock Corner
PPP-B-601	- Boxes, Wood, Cleated-Plywood.
PPP-B-636	Box, Fiberboard.

MILITARY

MIL-B-131 - Barrier Material, Water Vaporproof, Flexible, Heat-Sealable.

STANDARDS

FEDERAL

FED-STD-406 - plastics: Methods of Testing

FSC 4240

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:59Z
Check the source to verify that this is the current version before use.

STANDARDS

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-sTD-129 - Marking for Shipment and Storage.
MIL-STD-147 -- Palletized and Containerized Unit Loads 40 inch x 48 inch Pallets, Skids, Runners or Pallet Type Base.

DRAWINGS

US ARMY ARMAMENT COMMAND

EDGEWOOD ARSENAL

D5-75-13 - Bag, Waterproof, Chemical-Biological Mask, M1Al

(Copies of specifications, standards, drawings, and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

3. REQUIREMENTS

3.1 Materials. All materials cited on Drawing D5-75-13 and its subsidiary drawings shall conform to the specifications listed thereon, or to the specific characteristics set forth on the drawings.

3.2 Assembly. The M1A1 Bag shall consist of a waterproof bag (D5-75-13) and a retainer bag (B5-75-17).

3.3 Bag leakage. The plastic bag shall not leak when tested as specified in 4.4.4.1.

3.4 Marking. The bag shall be marked in accordance with Drawing D5-75-13 and no more than five characters may be illegible when tested as specified in 4.4.4.2.

3.5 Seal strength. The bag seal and seal edge shall withstand a minimum pull of 13,0 pounds when tested as specified in 4.4.4.3.

3.6 Preproduction. Prior to the start of regular production, a preproduction sample of bags shall be produced in accordance with this specification for examination and test (see 4.3).

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:59Z
Check the source to verify that this is the current version before use.

3.7 Workmanship. The bag shall be free from damage (cuts, tears, abrasions, or punctures) and foreign matter (dirt, grease, or oil). The seals shall be uniform, continuous, and free from wrinkles and bubbles.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility?; for inspection.

4.1.1 Supplier's responsibility. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved. by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to specified requirements.

4.1.2 Government's responsibility. Tests specified by 4.4.4.3 will be observed by the Government.

4.1.3 Objective evidence. The supplier shall provide objective evidence acceptable to the contracting officer that the requirements of 3.1 and section 5 for which specific inspection has not been provided in this specification have been satisfied.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

(a) Preproduction inspection (see 4.3).
(b) Quality conformance inspection (see 4.4).

4.3 Preproduction inspection.

4,3.1 Sample. A preproduction sample of 50 bags shall be produced, using the same methods, material, and equipment as will be used during regular production.

4.3.2 Inspection procedure. Each bag from the preproduction lot shall be examined and tested for all requirements of the drawings and of this specification.

4,3.3 Tests. Tests shall be conducted as specified in 4.4.4.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:59Z
Check the source to verify that this is the current version before use.

4.3.4 Acceptance/rejection criteria. The preproduction sample shall meet the examination and tests specified by 4.3.2 to be acceptable. The acceptance number is zero, The supplier shall obtain written approval. from the contracting officer before proceeding with regular production.

4.4 Quality conformance inspection.

4.4.1 Lotting. A lot shall consist of the bags produced during one work shift, by one manufacturer, at one plant, from the same materials, under essentially the same manufacturing conditions. However, no more than one lot of vinyl film shall be represented in any one lot of finished bags.

4.4.2 Sampling.

4.4.2.1 For examination and nondestructive tests. Sampling shall be conducted in accordance with MIL-STD-105, For defect 101, level I shall be used. For defect 107, level S-4 shall be used.

4.4.2.2 For destructive tests. Sampling for seal strength shall be conducted in accordance with MIL-STD-105, level S-1.

4.4.3 Inspection procedure.

4.4.3.1 For examination and nondestructive tests. Sample bags shall be examined in accordance with the classification of defects and MIL-STD-105.

4,4.3,2 For destructive tests. Sample bags shall be tested in accordance with 4.4.4.3 and MIL-STD-105, using an AQL of 2.5 percent defective for each test.

4.4,3.3 Classification of defects,

(a) Bag, waterproof, Chemical-Biological mask, M1A1 (Dwg D5-75-13).

Categories	Defects	Acceptance standards
Critical:	None defined	
Major:	AQL 0.25 percent defective	
101	Bag leakage	4.4.4.1
	AQL 1.0 percent defective	
102	Component missing or in-correctly assembled	

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:59Z
Check the source to verify that this is the current version before use.

4.4.3,3 Classification of defects (cent'd).

(a) Bag, waterproof, Chemical-Biological mask, M1A1 (Dwg D5-75-13).

Categories	Defects	Acceptance standards
Major:	AQL 1.0 percent defective	
103	Snap fastener inoperative	4.4,4.2
104	Bag overall dimensions	
105	Radii	
106	Stiffener dimensions	
107	Bag marking	
108	Workmanship (3.7)	

(b) Retainer, bag (Dwg B5-75-17).

Categories	Defects
Critical:	None defined
Major:	AQL 1.0 percent defective
101	Retainer bag dimensions

4.4.4 Tests. Tests shall be conducted as follows:

4.4.4.1 Bag leakage. Support each bag to be tested in an upright position by means of at least four widemouth clamps attached to the open end. Fill the bag with water to a depth of 12 inches. To avoid condensation of water from the surrounding air the water should be at approximately room temperature. Let the water-filled bag stand 15 minutes and examine the outside of the bag for leakage.

4.4.4.2 Marking. Submerge each bag to be tested in water at 75° ± 5°F for 30 minutes so that the printing will be wet. Remove the bag from the water and wipe dry. Within four minutes after removing from the water, apply five inches of 1/2 by 6-inch strips of masking tape conforming to type II of UU-T-106 at right angles to the printed lines so that at least 45 letters are covered. Place the bag on a hard smooth surface and roll a 10-pound, hard-surfaced, hinged roller with a diameter of approximately five inches over the applied strips three times. The roller shall travel at approximately 12 inches per 10 seconds. A strip of paper may be applied to the adhesive side of the extending l-inch section of the tape to prevent adhesion to the

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:59Z
Check the source to verify that this is the current version before use.

bag during rolling, Immediately after application, double back the free end of the tape at about 180 degrees and peel the tape slowly and evenly from the bag. Examine the printing for compliance with 3.4.

4.4.4.3 Seal strength. Seal strength shall be determined as specified in method 1013, method B of FED-STD-406 using a pendulum (Scott) type of machine, except that no autographic stress strain curve is needed. The test specimens shall be 1 inch wide. The seam shall be at the center of the specimen and perpendicular to the center line. The specimen shall be prepared for peel stress (bonding strength) by placing one strip of film (centered) on top of another and sealing one end, leaving the free ends to be gripped in the jaws of the testing machine.

5* PREPARATION FOR DELIVERY

5.1 Preservation and packaging, level A.

5.1.1 Unit packaging. A retainer bag (B5-75-17) shall be put inside of each waterproof bag.

5.1.2 Intermediate package. Twenty bags, processed as specified in 5.1.1, shall be further packaged in a style RSC, type CF, variety SW, grade W5C or V3C, class, weather resistant fiberboard box conforming to PPP-B-636, having inside dimensions of 16-3/4 inches by 15 inches by 2-3/4 inches, length, width, and dpeth respectively. The bags shall be laid flat in the box with the opened end of each bag alternately staggered. Fiber pads, 16 by 14 inches, fabricated from same material as the box shall be included as necessary to make a tight pack. The box shall be closed by taping in accordance with closure method IV in the appendix to PPP-B-636.

5.2 Packing, Levels shall be as specified (see 6.2).

5.2.l Level A. Ten intermediate packages, 5.1.2, shall be packed in either an overseas type cleated plywood box conforming to PPP-B-601, style I, grade A, type I (easy load) and 0-50 pound load limit, or a nailed wood box conforming to PPP-B-621, class 2, style 4, Grade A, 0-50 pound load limit and the 1 (easy load). The box shall have inside dimensions of 32-3/4 inches by 15-1/2 inches by 17-1/4 inches, length, width, and depth respectively, The box shall be closed in accordance with the appendix to the applicable box specification,

5.2.2 Level B, Ten intermediate packages, 5.1.2, shall be packed as specified in 5.2.1, except that the box shall be a weather resistant fiberboard box conforming to PPP-B-636, style RSC, type CF, variety SW, grade W5C

Source: https://assist.dla.mil -- Downloaded: 2026l0-22T20:59Z
Check the source to verify that this is the currentversion before use.

or V3C, and type I (easy load). The box shall be closed and reinforced in accordance with the requirements in the appendix to PPP-B-636. Closure shall be in accordance with method V closure requirements and reinforced in accordance with the requirements for class weather resistant boxes, using either non-metallic strapping or tape banding.

5.2.3 Level C. The waterproof bags, packaged as specified in 5.1, shall be packed to prevent damage in shipment from the supply source to the first receiving activity for immediate use or further processing. Shipping containers shall be in compliance with the rules and regulations applicable to the mode of transportation.

5.3 Marking. In addition to the marking required by the contract or order, intermediate packages (5.1.2) and shipping containers (5.2.1, 5.2.2 and 5.2.3) shall be marked in accordance with MIL-STD-129. All marking on the preservative treated Shipping Containers (5.2.1) shall be clear, legible, and permanent.

5.4 Palletization. When specified in the contract or order (see 6.2), waterproof bags, packed as specified in 5.2.l and 5.1.2, shall be palletized in accordance with MIL-STD-147, and marked in accordance with MIL-STD-129 (standard marking procedure for palletized unit loads).

6. NOTES

6.1 Intended use. The M1Al Bag is intended to be used for waterproofing protective masks.

6.2 Ordering data. Procurement documents should specify the following:

(a) Title, number, and date of this specification,
(b) Level and type of packing required.
(c) Palletization.
(d) Preproduction.

(1) Time allowed for supplier submission of samples for Government test and evaluation after award of contract.
(2) Name and address of test facility and shipping instructions when testing is performed by the Government.
(3) Time required for the Government to notify the supplier whether or not to proceed with production.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:59Z
Check the source to verify that this is the current version before use.

6.3 Supersession data. This specification supersedes Edgewood Arsenal Purchase Description I97-54-1098A, dated 9 October 1968.

Custodian:

Army-EA

Preparing activity:

Army - EA

Project No. 4240-A554

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:59Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 22-R255

INSTRUCTIONS: This sheet is to be filled out by personnel, either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments and suggestions submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or serve to amend contractual requirements.

SPECIFICATION

ORGANIZATION

CITY AND STATE | CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO *(If "yes", in what way?)*

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity - Optional)* | DATE

DD FORM 1 JAN 66 1426 REPLACES EDITION OF 1 OCT 64 WHICH MAY BE USED.

Source: https://assist.dla.mil -- Downloaded: 20260410-22T20:59Z
Check the source to verify that this is the current version before use.

FOLD

POSTAGE AND FEES PAID

OFFICIAL BUSINESS

Commander
Edgewood Arsenal
Attn: SAREA-TS-S
Aberdeen Proving Ground, MD 21010

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:59Z
Check the source to verify that this is the current version before use.