FED. SUP CLASS
2620

THE TIRE SHALL BE IN ACCORDANCE WITH THE APPLICABLE REQUIREMENTS OF MIL-R-7726 EXCEPT AS SPECIFIED HEREIN

SIZE	TYPE	PLY RATING	STATIC LOAD RATING LBS.	INFL. PRESS. PSI MIN.	BURST PRESS. PSI MIN.	BEAD WIDTH IN. MAX.	WEIGHT POUNDS MAX.	STATIC UNBAL OZ-IN MAX.	TREAD	MOLD SKID DEPTH MIN.	DEFLEC +3% -4%
26x6.6	1/TT	14	10,000	225	790	1.60	33.6	13	3/RIB	.30	32.0%
26x6.6	2/TL	14	10,000	225	790	1.75	38.0	13	3/RIB	.30	32.0%
26x6.6	1/TT	16	12,000	270	950	1.70	35.7	13	3/RIB	.30	32.0%
26x6.6	2/TL	16	12,000	270	950	1.85	39.9	13	3/RIB	.30	32%

1/TT TUBETYPE TIRE

2/TL TUBELESS TIRE

3/AT LEAST THREE BUT NOT MORE THAN SEVEN CONTINUOUS CIRCUMFERENTIAL RIBS

RIM DATA:

WIDTH BETWEEN FLANGES (INCH)	LEDGE DIAMETER (INCH)	FLANGE HEIGHT (INCH)	MIN. LEDGE WIDTH (INCH)	MIN. FLANGE WIDTH (INCH)	FLANGE RADIUS (INCH)	HEEL RADIUS (INCH)	FLANGE EDGE RADIUS (INCH)
5.00	14.00	1.00	.688	1.62	.50	.250	.125

14 PLY RATING - (HIGH PERFORMANCE)

THIS TIRE SHALL BE SUITABLE FOR USE AND PROVIDE REASONABLE SERVICE LIFE DURING ALL NORMAL OPERATIONS AT TAKE-OFF SPEEDS OF NOT MORE THAN 160 MPH AND LANDING SPEEDS OF NOT MORE THAN 140 MPH ON ALL TYPES OF RUNWAYS AND ON AIRCRAFT CARRIERS.

THE TIRE SHALL WITHSTAND WITHOUT FAILURE THE FOLLOWING TESTS:

TIRE 1:

DYNAMIC TEST - THE TIRE SHALL SATISFACTORILY WITHSTAND 50 HIGH SPEED (120-90 MPH) AND 50 LOW SPEED (90-0 MPH) LANDINGS AS DESCRIBED IN SPECIFICATION MIL-T-5041.

TIRE 2:

GOVT LAB TEST - THIS TIRE SHALL BE REBUILT FROM THE SAME BATCH AS TEST TIRE 1 AND SHALL BE IDENTICALLY PROCESSED. THIS TIRE SHALL NOT BE CONTRACTOR TESTED AND SHALL BE PROVIDED FOR GOVERNMENT LABORATORY TESTING.

SECTION - A REPRESENTATIVE SECTION OF TIRE 1 AND TIRE 2 SHALL BE SUBMITTED TO A GOVERNMENT LABORATORY AS SPECIFIED IN MS 3377.

16 PLY RATING - (200 MPH)

THIS TIRE SHALL BE SUITABLE FOR USE AND PROVIDE REASONABLE SERVICE LIFE DURING ALL NORMAL OPERATIONS AT TAKE-OFF SPEEDS OF NOT MORE THAN 200 MPH AND LANDING SPEEDS OF NOT MORE THAN 160 MPH ON ALL TYPES OF RUNWAYS AND ON AIRCRAFT CARRIERS.

TIRE 1:

DYANAMIC TEST - THE TIRE SHALL WITHSTAND WITHOUT FAILURE 50 CYCLES OF TEST A, 50 CYCLES OF TEST B AND 50 CYCLES OF TEST C.

TEST A - THE TIRE SHALL BE LANDED AGAINST A FLYWHEEL ROTATING AT A PERIPHERAL SPEED OF 23 MPH AND TAXIED AT THIS SPEED FOR A DISTANCE OF 10,000 FT. LOAD DURING THE TAXI TO BE MAINTAINED AT 12,000 LBS. IMMEDIATELY AFTER COMPLETION OF THE TAXI ROLL THE FLYWHEEL SHALL BE ACCELERATED FROM ZERO MPH TO 200 MPH IN 50 SECONDS AT A CONSTANT ACCELERATION RATE OF APPROXIMATELY 5.88 FT/SEC/SEC AT WHICH TIME THE TIRE SHALL BE UNLANDED. THE ROLL DISTANCE FOR THE ACCELERATION PART OF THE TEST IS APPROXIMATELY 7,350 FT. THE INFLATION PRESSURE SHALL BE VARIED AS NECESSARY TO OBTAIN A STATIC DEFLECTION OF 32% ON THE FLYWHEEL SURFACE AT A LOAD OF 12,000 LBS. THE LOAD SHALL BE MAINTAINED AT 12,000 LBS FOR THE FIRST 10 SECONDS OF THE ACCELERATION TEST AND THEN DECREASED LINEARLY WITH TIME TO 1,200 LBS AT THE INSTANT OF UNLANDING.

TEST B - THE TIRE SHALL BE LANDED AGAINST A FLYWHEEL ROTATING AT A PERIPHERAL SPEED OF 160 MPH. THE FLYWHEEL SPEED SHALL BE DECREASED FROM 160 MPH TO 50 MPH IN 30 SECONDS AT A CONSTANT DECELERATION RATE OF APPROXIMATELY 5.4 FT/SEC/SEC. THE FLYWHEEL SPEED SHALL THEN BE DECREASED FROM 50 MPH TO 20 MPH IN 26 SECONDS AT A CONSTANT DECELERATION RATE OF APPROXIMATELY 1.7 FT/SEC SEC. THE ROLL DISTANCE FOR THE LANDING PART OF THIS TEST IS APPROXIMATELY 5900 FT. THE FLYWHEEL SHALL IMMEDIATELY BE ACCELERATED TO 23 MPH AND REMAIN AT THAT SPEED UNTIL THE TIRE HAS TAXIED 10,000 FT, AT WHICH TIME THIS TIRE SHALL BE UNLANDED. THE LOAD SHALL INCREASE FROM 0 TO 3000 LBS IN 1 TO 3 SECONDS AND THEN INCREASE LINEARLY WITH TIME TO A VALUE OF 11,500 LBS IN 30 TO 40 SECONDS. THE LOAD SHALL THEN BE MAINTAINED AT 11,500 LBS UNTIL THE TIRE IS UNLANDED.

(A) REVISED AND REDRAWN

APPROVED 18 FEB 1969 REVISED (A) 29 DEC 1981

This standard has been approved by the NAVAL AIR SYSTEMS COMMAND Department of the NAVY and shall be used by that activity. All other military activities are required to employ this standard where suitable.

P.A. NAVY - AS Other Cust	TITLE: TIRE, PNEUMATIC, AIRCRAFT, REBUILT, 26x6.6 (200 MPH/HIGH PERFORMANCE) TYPE VII (NAVY)	MILITARY STANDARD MS 3383(AS)
PROCUREMENT SPECIFICATION MIL-R-7726	SUPERSEDES:	SHEET 1 OF 2

DD FORM 672-1 (Limited coordination) PREVIOUS EDITIONS OF THIS FO IM ARE OBSOLETE. PROJECT NO. 2620-N221 PLATE NO. 17709

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T13:03Z
Check the source to verify that this is the current version before use.

TEST C - CAMBER TEST AS FOLLOWS:

C_1 - OUTBOARD CAMBER

1. ACCELERATE FLYWHEEL TO 20 MPH AND MAINTAIN THIS SPEED THROUGHOUT THE TEST.

2. LAND THE TIRE AGAINST THE FLYWHEEL IN A POSITION 15° OUTBOARD CAMBER AND LOAD THE TIRE TO 14,500 LBS WITHIN 4 SECONDS. MAINTAIN THIS LOAD UNTIL A ROLL DISTANCE OF 2300 FEET HAS BEEN COVERED.

C_2 - INBOARD CAMBER

SAME AS TEST C_1 EXCEPT THAT THE LOAD SHALL BE APPLIED FROM A DIRECTION TO PROVIDE FOR 15° INBOARD CAMBER.

TIRE 2:

GOVT LAB TEST - THIS TIRE SHALL BE REBUILT FROM THE SAME BATCH AS TEST TIRE 1 AND SHALL BE IDENTICALLY PROCESSED. THIS TIRE SHALL NOT BE CONTRACTOR TESTED AND SHALL BE PROVIDED FOR GOVERNMENT LABORATORY TESTING.

SECTION - A REPRESENTATIVE SECTION OF TIRE 1 AND TIRE 2 SHALL BE SUBMITTED TO A GOVERNMENT LABORATORY AS SPECIFIED IN MS 3377.

AIR RETENTION - THE TUBELESS TIRE SHALL BE INFLATED TO A PRESSURE OF 340 PSI FOR 14PR AND 450 PSI FOR 16 PR AND ALLOWED TO STAND FOR A PERIOD OF 4 HOURS AT WHICH TIME THE PRESSURE DROP DUE TO GROWTH SHALL BE REPLACED. THE TIRE SHALL THEN STAND FOR AN ADDITIONAL 12 HOURS AT WHICH TIME THE PRESSURE SHALL BE MEASURED AND THE TIRE INSPECTED. THE AIR PRESSURE LOSS SHALL NOT EXCEED 5 PERCENT AND THE TIRE SHALL NOT REVEAL ANY APPEARANCE OR PERFORMANCE DEFECTS, SUCH AS SIDEWALL BLISTERS, TREAD SEPARATION, ETC.

NOTES:

1. REFERENCED DOCUMENTS SHALL BE OF THE ISSUE IN EFFECT ON DATE OF INVITATION FOR BIDS, OR REQUEST FOR PROPOSAL EXCEPT THAT REFERENCE ADOPTED INDUSTRY STANDARDS SHALL GIVE THE DATE OF THE ISSUE ADOPTED.

2. FOR DESIGN FEATURE PURPOSES, THIS STANDARD TAKES PRECEDENCE OVER PROCUREMENT DOCUMENTS REFERENCED HEREIN.

APPROVED 18 FEB 1969 REVISED (A) FOR CHANGES SEE SHEETS 1 AND 2

This standard has been approved by the NAVAL AIR SYSTEMS COMMAND Department of the NAVY and shall be used by that activity. All other military activities are required to employ this standard where suitable.

P.A. NAVY - AS Other Cust	TITLE: TIRE, PNEUMATIC, AIRCRAFT, REBUILT; 26x6.6 (200 MPH/HIGH PERFORMANCE) TYPE VII (NAVY)	MILITARY STANDARD MS 3383(AS)
PROCUREMENT SPECIFICATION MIL-R-7726	SUPERSEDES:	SHEET 2 OF 2

DD FORM 672-1 (Limited coordination) PREVIOUS EDITIONS OF THIS FORM ARE OBSOLETE. PLATE NO. 17709

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T13:03Z
Check the source to verify that this is the current version before use.