MILITARY SPECIFICATION

TRINITRORESORCINOL (STYPHNIC ACID)

This Amendment forms a part of Military Specification MIL-T-50611 (MU), dated 6 May 70, and is approved for use within the U.S. Army Armament, Munitions and Chemical Command and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 3

3.2 Table I, Chemical and Physical Properties:

Add:

Property	Type I	Type II	Test paragraph
Moisture, alternate, percent (for on-site use to produce lead styphnate only)	20% min.	20% min.	4.5.1

NOTE: "On-site use" applies to the trinitroresorcinol manufactured on a facility and to be used on that same facility and will not be packaged and shipped to another facility."

AMSC N/A

FSC 1376

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:31Z
Check the source to verify that this is the current version before use.

PAGE 5

4.5.1 Test Procedure, moisture: Delete "Transfer 3 grams of the sample to a tared weighing dish (6 cm in diameter). Break up any lumps with a spatula, cover the weighing dish and weigh the dish plus sample. Uncover the dish and heat at 68 ± 2 degrees C for 8 to 16 hours. Cool in desiccator containing drierite or anhydrone and weigh. Calculate the percent moisture as follows:" and substitute the following:

"Transfer 2-6 grams of the sample to a tared weighing dish. Break up any lumps with a spatula, cover the weighing dish and weigh the dish plus sample. Uncover the dish and heat at 68 ± 2 degrees C for a minimum of 4 1/2 hours. Cool in a desiccator containing a suitable desiccant (drierite, anhydrone, etc.) and weigh. Calculate the percent moisture as follows:"

PAGE 10

4.5.8 Sulfate: Delete "Transfer 5 grams of the dried sample to a 250 ml. beaker", and substitute the following:

"If a dried sample is not available, transfer 6 to 8 grams of a wet sample to a porcelain dish, a watch glass, or a conductive container at least 5 cm in diameter. Break up any lumps with a conductive spatula. Heat uncovered at 68 ± 2 degrees C for a minimum of 4.5 hours. Cool for a minimum of 15 minutes in a desiccator.

Transfer approximately 4 to 6 grams of the dried sample to a tared, 250 ml beaker."

Delete "$\frac{42.02\ (A-B)}{B}$" and substitute "$\frac{42.02\ (A-B)}{W}$".

Custodian:
Army-AR

Preparing activity:
Army-AR

(Project 1376-A466)

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:31Z
Check the source to verify that this is the current version before use.