INCH-POUND
A-A-59709A
September 13, 2021
SUPERSEDING
A-A-59709
December 11, 2001

COMMERCIAL ITEM DESCRIPTION

CLOTH, BUNTING, NYLON; AND NYLON AND WOOL

The General Services Administration has authorized the use of this Commercial Item Description (CID) for all Federal Agencies.

1. SCOPE. This document covers nylon and nylon and wool bunting cloth used on woman's Garrison Cap and the Union Jack Flag.

2. CLASSIFICATION. The cloth shall be in the following types and classes:

2.1 Types.

Type I - 100 percent nylon filament

Class A - Lightweight
Class B - Heavyweight

Type II - 75 percent nylon (staple) and 25 percent wool

3. SALIENT CHARACTERISTICS

3.1 Material.

3.1.1 Nylon (Type I only). The Type I bunting material shall be bright, high tenacity, and continuous nylon filament.

3.1.2 Nylon (Type II only). The Type II bunting material shall be bright staple nylon. The material shall not contain waste reused, nor reclaimed nylon fiber.

Beneficial comments, recommendations, additions, deletions, clarifications, etc. and any data that may improve this document should be sent to: Attn: DLA Troop Support, 700 Robbins Avenue, Philadelphia, PA 19111-5096. Since contact information can change, verify the currency of the address information using Acquisition Streamlining and Standardization Information System (ASSIST) online database https://assist.dla.mil.

AMSC N/A FSC 8305

DISTRIBUTION STATEMENT A. Approved for public release. Distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:24Z
Check the source to verify that this is the current version before use.

3.1.3 Wool (Type II only). The wool top for the Type II bunting material shall be fleece wool, pulled wool, or any combination thereof not lower in grade than 44s U.S. Standard when tested in accordance with U.S Standards for Grades of Wool. In the event of a dispute the wool grade shall be determined by the width (wedge) method. A variation of plus or minus 5 percent content for either fiber shall be permitted. The use of noils, laps, or any other manufacturing by-product is prohibited.

3.2 Yarn.

3.2.1 Type I bunting.

3.2.1.1 Class A. The warp yarn for Class A cloth shall be single end 70 nominal denier. The filling yarn shall be two-ply 70 nominal denier or 140 nominal denier singles.

3.2.1.2 Class B. The yarn for Class B cloth shall be either 200 or 210 nominal denier single yarn in both the warp and filling direction.

3.2.2 Type II bunting. The yarns for the Type II bunting cloth shall be a blend of 75 percent nylon staple and 25 percent wool two-ply for both warp and the filling direction. A variation of plus or minus five (5) percent content for either fiber shall be permitted. The yarns shall be spun from combed top on the Bradford, French or American System.

3.3 Weave. The cloth shall be a plain weave. The selvages shall be an oxford weave with two (2) ends weaving as one (1). When shuttleless looms are used, the requirement for selvage shall not apply.

3.4 Standard sample. Unless otherwise indicated, the finished cloth shall match the standard sample for shade and appearance, and shall, be equal to or better than the standard sample with respect to all characteristics for which the standard sample is referenced.

3.4.1 Color. The color of the finished cloth shall be as specified in the contract or purchase order (see 7.6) and shall meet the colorfastness requirements when tested as specified in 3.5.

3.4.1.1 Visual shade matching. The color and appearance of the cloths shall match the standard sample when viewed using the AATCC EP9, Evaluation Procedure for Visual Assessment of Color Difference of Textiles, Option C (see 7.5), with sources simulating artificial daylight D_{65} illuminant with a color temperature of 7500 (± 200) K illumination of 100 (± 20) foot candles, and shall be a good match to the standard sample under incandescent lamplight at 2856 (± 200) K.

3.5 Physical and colorfastness requirements. The finished bunting cloth shall meet the physical and colorfastness requirements specified in Table I when tested in accordance with the test methods specified in Table I.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:24Z
Check the source to verify that this is the current version before use.

TABLE I. Physical and colorfastness requirements.

Characteristic	Type I		Type II	Test Method
	Class A	Class B		
Fiber identification				
Nylon	See 3.1.1	See 3.1.1	See 3.1.2	AATCC TM20 (see 7.4)
Wool	-	-	See 3.1.3	AATCC TM20 (see 7.4)
Fiber content				
Nylon (Type I)	See 3.1.1	See 3.1.1		AATCC TM20A (see 7.4)
Nylon and wool (Type II)	-	-	See 3.2.2	AATCC TM20A (see 7.4)
Weight (oz./yd^2) (min.)	2.5	3.6	4.8	ASTM D3776/D3776M, Option A
Yarns per inch (min.)				ASTM D3775
Warp	106	72	32	
Filling	76	56	30	
Breaking strength (lbs) (min.)				ASTM D5034
Warp	125	225	115	
Filling	155	152	100	
Colorfastness (min.):				
Light (after 40 AFU or 170 kJ/(m^{2}nm)@420 nm) 1/	3-4	3-4	3-4	AATCC TM16.3, Opt 3, 2/
Water	3-4	3-4	3-4	AATCC TM107, 3/
Salt water	3-4	3-4	3-4	AATCC TM106, 3/
Crocking	3.5	3.5	3.5	AATCC TM8, 4/
pH (range)	5.0-8.5	5.0-8.5	4.0-8.0	AATCC TM81

1/ AFU - AATCC Fading Units
2/ Rating using AATCC EP1, Evaluation Procedure for Gray Scale for Color Change
3/ Rating using AATCC EP1, Evaluation Procedure for Gray Scale for Color Change and AATCC EP2, Evaluation Procedure for Gray Scale for Staining
4/ Rated using the AATCC EP8, Evaluation Procedure for AATCC 9-Step Chromatic Transference Scale

3.6 Width. For Government procurements only, the width of the finished cloth shall be as specified in the contract or purchase order and shall be the minimum acceptable width exclusive of the selvage.

3.7 Length and put-up. For Government procurement only, unless otherwise specified (see 7.6), the cloth shall be furnished in continuous lengths of not less than 40 yards and shall be put-up full width on rolls.

3.8 Fiber identification. Each roll of finished cloth shall be labeled or ticked for fiber content in accordance with the 16 CFC Part 303 of Rules and Regulations under the Textile Fiber Products Identification Act. (see 7.1.2)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:24Z
Check the source to verify that this is the current version before use.

3.8.1 Wool identification (Type II only). The finished cloth containing wool shall be labeled in accordance with Wool Products Labeling Act (see 7.1.2).

3.9 Toxicity. The finished cloth shall not present a health hazard and shall show compatibility with prolonged, direct skin contact when tested as specified in 3.9.1. Chemicals recognized by the Environmental Protection Agency (EPA) as human carcinogens shall not be used (see 7.2.4).

3.9.1 Toxicity test. When required, (see 7.6) an acute dermal irritation study and a skin sensitization study shall be conducted. When the results of these studies indicate the material is not a sensitizer or irritant, a Repeat Insult Patch Test shall be performed in accordance with the Modified Draize Procedure (see 7.2.5). If toxicity requirement (see 3.9) can be demonstrated with historical use data, on the finishing treatments used, toxicity testing may not be required (see 7.6).

3.10 Workmanship. The finished cloth shall conform to the quality of product established by this document. The occurrence of defects shall not exceed the contractor's own quality assurance standards and the quality assurance standards defined by the technical data in the bid package.

4. REGULATORY REQUIREMENTS. Unless otherwise specified, the offeror/contractor is encouraged to use recovered, recycled, bio based, and environmentally preferable materials to the maximum extent practicable, in accordance with paragraph 23.403, 23.404(b) of the Federal Acquisition Regulation FAR, or the sustainable acquisition of EO 13693; as applicable. (See 7.2.4).

5. PRODUCT CONFORMANCE PROVISIONS.

5.1 Product conformance. The cloth shall meet the salient characteristics of this commercial item description, conform to the producer's own drawings, specifications, standards, and quality assurance practices, and be the same product that is offered for sale in the commercial marketplace. The Government reserves the right to require proof of such conformance.

5.2 Market acceptability. The finished cloth must have been sold to the government or commercial market.

5.3 End item inspection procedures. Sampling for inspection shall be conducted in accordance with ASQ/ANSI Z1.4 - Sampling Procedures and Tables for Inspection of Attributes (see 7.2.2).

5.4 Visual examination. The finished cloth shall be examined for the defects listed below as defined in ASTM D3990:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:24Z
Check the source to verify that this is the current version before use.

TABLE II. Visual examination defects.

Cloth: Any hole, cut, or tear; broken or missing yarn; smash; float, mispick, harness skip, or other misweave; hitchback, stripback; open or thin place, crack (warp or filling); knot or slub; loose, slack, or tight yarn; abrasion mark, tender or weak spot, embedded crease or wrinkle; filling bar, coarse filling, or mixed filling; spot, stain, streak or dirty yarn, overall uncleanness or soiled; foreign matter; shade not as specified, shading defects – side to side, side to center or end to end; finish not equal to standard sample; mottled, cloudy, streaky.
Label: Label missing, incorrect, or illegible. Fiber identification marking omitted. Required information missing from the label.
Packaging: Not packaged in accordance with the contract or purchase order.

5.5 Acceptance criteria. Acceptance criteria shall be as specified in the contract or purchase order (see 7.6).

6. PACKAGING. Preservation, packing and marking shall be as specified in the contract or purchase order (see 7.6).

7. NOTES.

7.1 Source of Government documents.

7.1.1 Copies of Government documents are available online at https://quicksearch.dla.mil.

7.1.2 16 CFC Part 303 of Rules and Regulations under the Textile Fiber Products Identification Act and the Wool Products Labeling Act are available online at https://www.ftc.gov.

7.1.3 United States Standards for Grades of Wool are available online at https://ams.usda.gov.

7.2 Source of non-Government documents.

7.2.1 AATCC test methods are available online at https://aatcc.org.

7.2.2 ASQ/ANSI Z1.4 – Sampling Procedures and Tables for Inspection of Attributes are available online at https://asq.org.

7.2.3 ASTM Standards are available online at https://www.astm.org.

7.2.4 EPA and EO 13693 information is available online at https://www.epa.gov.

7.2.5 Repeat insult patch test. Modified Draize Procedure - Principles and Methods of Toxicology, A Wallace Hayes (editor) are available online at https://www.crcpress.com.

7.3 Intended use. The cloth shall be used for flags and caps.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:24Z
Check the source to verify that this is the current version before use.

7.4 Certificate of compliance. The contracting activity may select to accept a certificate of compliance for stated requirement.

7.5 Visual shade matching. In 2017, Option A of AATCC EP9, Evaluation Procedure for Visual Assessment of Color Difference of Textiles was changed to Option C. NOTE: In case of confusion, the viewing geometry should be "The specimen plane and illumination source will be parallel to each other and aligned so that the light flux is incident at the center of the specimen plane, which is set at a 35 (± 5º) angle relative to the horizontal. The observer will view the specimens at a 90º angle, relative to the plane of the specimens".

7.6 Ordering data. The contract or order should specify the following:

a. Title, number, and date of this commercial item description
b. Type and Class of cloth required (see 2.1)
c. Color of cloth required (see 3.4.1)
d. Length put-up required (see 3.7)
e. Labeling information (see 3.8)
f. Toxicity requirement (see 3.9)
g. Product conformance (see 5.1)
h. Acceptance criteria (see 5.5)
i. Packaging requirements (see 6.)

7.7 Key words.

Caps
Union Jack Flag

MILITARY INTERESTS:

Custodians:
Army - GL
Navy - NU
Air Force - 11

Review Activities:
Army - IH
Navy - MC, OS, SH

CIVIL AGENCY COORDINATING ACTIVITY:

GSA – FAS

Preparing Activity:
DLA - CT

(Project 8305-2021-023)

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using ASSIST Online database at https://assist.dla.mil/.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:24Z
Check the source to verify that this is the current version before use.