INCH-POUND

A-A-59759
17 November 2004

COMMERCIAL ITEM DESCRIPTION

SORBENT, HAZARDOUS MATERIAL (HM)

The General Services Administration has authorized the use of this commercial item description, for all federal agencies.

1. SCOPE. This commercial item description (CID) covers sorbents of various shapes and sizes used in HM spill response on Navy ships. This material is used to contain and sorb HM spills on Navy ships.

2. CLASSIFICATION.

2.1 Type. The sorbent material shall conform to the following types:

2.1.1 Type I. Type I sorbent materials are loose, unconsolidated particles of sorbent material.

2.1.2 Type II. Type II sorbent materials are pads or sheets where length and width dimensions greatly exceed the thickness.

2.1.3 Type III. Type III sorbent materials are pillows that are encased in outer fabric or netting, where length and width dimensions exceed the thickness.

2.1.4 Type IV. Type IV sorbent materials are socks that are encased in outer fabric or netting, where length dimensions greatly exceed all other dimensions.

3. SALIENT CHARACTERISTICS.

3.1 Design.

3.1.1 Materials. Sorbents shall be composed of materials that fulfill the requirements contained herein. Materials shall not be soluble or react chemically with sorbed HM when used for their intended purpose. Manufacturers shall clearly state which chemicals or type of chemicals, if any, should not be used in combination with the sorbent.

Beneficial comments, recommendations, additions, deletions, clarifications, etc. and any data that may improve this document should be sent to: Commander, Naval Sea Systems Command, ATTN: SEA 05Q, 1333 Isaac Hull Avenue, SE, Stop 5160, Washington Navy Yard DC 20376-5160 or emailed to commandstandards@navsea.navy.mil, with the subject line "Document Comment". Since contact information can change, you may want to verify the currency of this address information using the ASSIST Online database at http://assist.daps.dla.mil.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:26Z
Check the source to verify that this is the current version before use.

3.1.2 Size.

3.1.2.1 Type I. Type I sorbents shall be a uniform, loose, granular material having not less than 90 ±2 percent weight retention when tested in accordance with the following test method.

a. Weigh a 0.0045-pound sample and shake for 5 minutes through a mechanical No. 100 U.S. Standard Sieve or in a shallow pan.
b. Light air circulation shall be present during testing, so that particles, which become airborne, do not settle on the original sample.
c. Air circulation may be supplied in light winds (5 mph) or a light upward draft originating no further than 3 feet from the sample.
d. After five minutes, re-weigh sample and determine percent retention.

3.1.2.2 Type II. Type II sorbents shall be supplied in sheets with a minimum dimension of 12 inches by 12 inches and a maximum dimension of 24 inches by 24 inches.

3.1.2.3 Type III. Type III sorbents shall be supplied as individual pillows. Type III sorbents shall have a minimum area of 80 $in^2$, where neither side is more than 2.5 times larger than the other, and a maximum area of 576 $in^2$, with maximum dimensions of 24 inches by 24 inches. Type III sorbents shall have a maximum thickness of 3 inches.

3.1.2.4 Type IV. Type IV sorbents shall be those which have a length that greatly exceeds other dimensions (i.e., socks or booms). Type IV sorbents shall be individually supplied with a minimum length of 24 inches, a maximum length of 48 inches, and a maximum diameter of 3 inches.

3.1.3 Strength. The strength of the sorbent shall be determined by the following test method:

a. Attach a sample of the sorbent to a tension tester or attach one end of the sample to a continuous reading hanging scale with weights attached to the other end.
b. Run the tension tester or continuously add weights until complete ripping or destruction occurs.
c. Measure the weight at which complete ripping or destruction occurs.

3.1.3.1 Type I. N/A

3.1.3.2 Type II. Type II sorbents shall withstand a minimum of 2 pounds of force when tested by the method listed in 3.1.3. For Type II sorbents a sample of the outer fabric shall be used.

3.1.3.3 Type III. Type III sorbents shall withstand a minimum of 1 pound of force when tested by the method listed in 3.1.3. For Type III sorbents a sample of the outer fabric shall be used.

3.1.3.4 Type IV. Type IV sorbents shall withstand a minimum of 1 pound of force when tested by the method listed in 3.1.3. For Type IV sorbents a sample of the outer fabric shall be used.

3.1.4 Construction.

3.1.4.1 Type I. Type I sorbents shall not become airborne in quantities, which create a nuisance to the user. Type I sorbents shall be of a dense material that will not move in light winds (5 mph) and shall easily pour to contain the spill movement.

3.1.4.2 Type II. Type II sorbents shall be constructed so that sorbent layers (if applicable) are not easily separated from each other.

3.1.4.3 Type III. Type III sorbents shall not release internal sorbent materials in quantities, which create a nuisance to the user. The internal material shall not compress or greatly move while contained in the outer fabric.

3.1.4.4 Type IV. Type IV sorbents shall not release internal sorbent materials in quantities, which create a nuisance to the user. Type IV sorbents shall be flexible enough to bend around the perimeter of the spill and create a barrier to block the spill movement. The internal material shall not compress or greatly move while contained in the outer fabric.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:26Z
Check the source to verify that this is the current version before use.

3.2 Performance characteristics.

3.2.1 General. All sorbent types shall sorb a variety of different HM and shall not be specific to any categories of HM.

3.2.2 Sorption. The amount of fluid sorbed shall be determined by the following test method. Test results from ASTM F716 or F726 may also be accepted in lieu of the following test:

a. Weigh a sample of sorbent and record this weight. In a dish, large enough to completely contain the sorbent sample and test fluid, put the test fluid in the dish and put the sorbent on top of the test fluid. The test fluid shall be supplied in enough quantity to saturate the sorbent sample.
b. After 15 minutes, remove the sorbent and allow the fluid to drip until cessation (less than 1 drop per minute).
c. Place the sorbent on a tared weighing pan. Record the weight.
d. Subtract the weight of the sorbent (Step a) from the weight of sorbent and the fluid (Step c).
   (1) Divide this value by the weight of the sorbent (Step a) to determine the ratio of the weight sorbed.
   (2) Multiply this value by the density of the fluid to determine the volume of the fluid sorbed.

3.2.2.1 Type I. Type I sorbents shall have a minimum sorption of three times its weight and shall not drip while containing this quantity when tested by the method listed in 3.2.2.

3.2.2.2 Type II. Type II sorbents shall have a minimum effective pickup of 0.24 gallon per pad and shall not drip while containing this quantity when tested by the method listed in 3.2.2. Type II sorbents shall not deform and shall allow for complete removal of sorbent while containing the minimum effective pickup.

3.2.2.3 Type III. Type III sorbents shall be used in their entirety in the test listed in 3.2.2. Type III sorbents shall have a minimum effective pickup of 1 gallon per pillow and shall not drip while containing this quantity. Type III sorbents shall not deform and shall allow for complete removal of sorbent while containing the minimum effective pickup. The sorption of HM to the outer fabric and the initial layers of internal sorbent shall not create a barrier preventing sorption on the innermost layers.

3.2.2.4 Type IV. Type IV sorbents shall be used in their entirety in the test listed in 3.2.2. Type IV sorbents shall have a minimum effective pickup of 1 gallon per sock and shall not drip while containing this quantity. Type IV sorbents shall not deform and shall allow for complete removal of sorbent while containing the minimum effective pickup. The sorption of HM to the outer fabric and the initial layers of the internal sorbent shall not create a barrier preventing sorption on the innermost layers.

3.3 Flammability. All types of sorbents shall be nonflammable when tested in accordance with ASTM D2859, Methenamine Pill Test; or UL 94; or a simple rating of noncombustible and flashpoint in accordance with ASTM D92, Cleveland Open-Cup Test.

3.4 Environmental considerations. Sorbents shall not be toxic to aquatic life and waterfowl and shall have no adverse effects on the health of personnel when used for their intended purpose. Sorbents shall not of themselves or in combination with the HM pollute waters or shoreline either chemically or physically when used for their intended purpose.

4. REGULATORY REQUIREMENTS. The offeror/contractor is encouraged to use recovered materials to the maximum extent practicable, in accordance with paragraph 23.403 of the Federal Acquisition Regulation (FAR).

5. PRODUCT CONFORMANCE.

5.1 Product conformance. The products provided shall meet the salient characteristics of this Commercial Item Description, conform to the producer's own drawings, specifications, standards, and quality assurance practices, and be the same product offered for sale in the commercial marketplace. The government reserves the right to require proof of such conformance.

5.2 Market acceptability. The manufacturers of the item must have been producing a product meeting the requirements contained herein for at least 2 years.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:26Z
Check the source to verify that this is the current version before use.

6. PACKAGING. Preservation, packing, and marking shall be as specified in the contract or order.

7. NOTES.

7.1 Part or identifying number (PIN). The following PIN procedure is for government purposes and does not constitute a requirement for the contractor.

This example describes a part numbering system for CID A-A-59759:

AA59759-1

| PIN CODE | TYPE |
|---|---|
| 1 | I |
| 2 | II |
| 3 | III |
| 4 | IV |

7.2 Source of documents.

7.2.1 ASTM Standards are available from ASTM International, 100 Barr Harbor Dr., West Conshohocken, PA 19428, or www.astm.org.

7.2.2 The Federal Acquisition Regulation may be obtained from the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402 or online at http://www.arnet.gov/far.

7.2.3 Underwriters Laboratories Inc. (UL) standards are available from COMM 2000, 1414 Brook Drive, Downers Grove, IL 60515, or online at www.ul.com.

7.3 Ordering data. The contract or order should specify the following:

a. CID document number, revision, and CID PIN.
b. Product conformance provisions.
c. Quantity required.
d. Packaging requirements.

7.4 Key words.

Cleanup
Granular
Hazardous Material
Pad
Pillow
Sock
Sorbent
Spill



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:26Z
Check the source to verify that this is the current version before use.

MILITARY INTERESTS

Custodians:
Navy - SH
Air Force - 99

Review Activities:
Air Force - 84
DLA - GS, GS3

CIVIL AGENCY COORDINATING ACTIVITY:
GSA - FSS

Preparing Activity:
Navy - SH
(Project 4235-0002-000)



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:26Z
Check the source to verify that this is the current version before use.