INCH-POUND
A-A-59759A
March 17, 2020
SUPERSEDING
A-A-59759
November 17, 2004

COMMERCIAL ITEM DESCRIPTION

SORBENT, HAZARDOUS MATERIAL (HM) AND OIL

The General Services Administration has authorized the use of this commercial item description for all federal agencies.

1. SCOPE. This Commercial Item Description (CID) covers sorbents of various shapes and sizes used in the hazardous material (HM) and oil spill response kits. These sorbents are used to contain and sorb HM and oil spills onboard and overboard Navy ships and submarines.

2. CLASSIFICATION.

2.1 Type. The sorbent material shall conform to the following types:

2.1.1 Type I. Type I sorbent materials are loose, unconsolidated particles of sorbent material, also referred to as granular. (NOTE: Type I sorbent shall not be used, and the ship shall not replenish type I sorbent if the ship supply is exhausted. Unused type I sorbents can be offloaded as ordinary trash while in port. Type I sorbents should not be processed in solid waste equipment nor should they be disposed of over board. No further requirements are provided for type I sorbents within this document.)

2.1.2 Type II. Type II sorbent materials are pads or sheets where length and width dimensions greatly exceed the thickness.

2.1.3 Type III. Type III sorbent materials are pillows that are encased in outer fabric or netting, where length and width dimensions exceed the thickness.

2.1.4 Type IV. Type IV sorbent materials are socks that are encased in outer fabric or netting, where length dimensions greatly exceed all other dimensions.

2.1.5 Type V. Type V sorbent materials are sweeps, pads, or sheets connected along their length by reinforced stitching or fabric, where length dimensions greatly exceed all other dimensions. Type V sorbent material is also known as a boom and is primarily used for overboard oil spills.

3. SALIENT CHARACTERISTICS.

3.1 Design.

3.1.1 Materials. Sorbents shall be composed of materials that fulfill the requirements contained herein. Materials shall not be soluble or react chemically with sorbed HM when used for their intended purpose. Manufacturers shall clearly state which chemicals or type of chemicals, if any, should not be used in combination with the sorbent.

3.1.2 Size.

3.1.2.1 Type I. N/A.

Beneficial comments, recommendations, additions, deletions, clarifications, etc. and any data that may improve this document should be sent to: Commander, Naval Sea Systems Command, ATTN: SEA 05S, 1333 Isaac Hull Avenue, SE, Stop 5160, Washington Navy Yard DC 20376-5160 or emailed to CommandStandards@navy.mil, with the subject line "Document Comment". Since contact information can change, you may want to verify the currency of this address information using the ASSIST Online database at https://assist.dla.mil.

FSC 4235

DISTRIBUTION STATEMENT A. Approved for public release. Distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:26Z
Check the source to verify that this is the current version before use.

3.1.2.2 Type II. Type II sorbents shall be supplied in pads with a minimum dimension of 12 by 12 inches and a maximum dimension of 24 by 24 inches.

3.1.2.3 Type III. Type III sorbents shall be supplied as individual pillows. Type III sorbents shall have a minimum area of 80 square inches, where neither side is more than 2.5 times larger than the other, and a maximum area of 576 square inches, with maximum dimensions of 24 by 24 inches. Type III sorbents shall have a maximum thickness of 3 inches.

3.1.2.4 Type IV. Type IV sorbents shall be those which have a length that greatly exceeds other dimensions (e.g., socks). Type IV sorbents shall be individually supplied with a minimum length of 24 inches, a maximum length of 48 inches, and a maximum diameter of 3 inches.

3.1.2.5 Type V. Type V sorbents shall be supplied in lengths with a maximum width of 24 inches and a maximum length of 100 feet.

3.1.3 Strength. The strength of sorbent types II, III, IV, and V shall be determined using the applicable methods detailed within the subsections of the Dynamic Degradation Test of ASTM F726.

NOTE: ASTM F726 classifies sorbents differently than the classification used in this CID. Refer to table I for clarification.

TABLE I. Type conversion.

Sorbent	A-A-59759 Types	ASTM F726 Types
Granular	Type I	Type II
Pads	Type II	Type I
Pillows	Type III	Type IIIa
Socks	Type IV	Type IIIb
Sweeps, Booms	Type V	Type IV

3.1.3.1 Type I. N/A.

3.1.3.2 Type II. The surface area of the type II sorbent test sample shall not be reduced by more than 25 percent due to deterioration when tested using the method listed in ASTM F726. For type II sorbents, a sample of the outer fabric shall be used.

3.1.3.3 Type III. The inner filler material and the outer fabric layer comprising type III sorbents shall be tested independently. Ten percent or more of the inner filler material shall not sink in the test solvent when using the method detailed in ASTM F726. The surface area of the type III sorbent outer fabric test sample shall not be reduced by more than 25 percent due to deterioration when tested using the method listed in ASTM F726.

3.1.3.4 Type IV. The inner filler material and the outer fabric layer comprising type IV sorbents shall be tested independently. Ten percent or more of the inner filler material shall not sink in the test solvent when using the method detailed in ASTM F726. The surface area of the type IV sorbent outer fabric test sample shall not be reduced by more than 25 percent due to deterioration when tested using the method listed in ASTM F726.

3.1.3.5 Type V. The inner filler material and the outer fabric layer comprising type V sorbents shall be tested independently. Ten percent or more of the inner filler material shall not sink in the test solvent when using the method detailed in ASTM F726. The surface area of the type V sorbent outer fabric test sample shall not be reduced by more than 25 percent due to deterioration when tested using the method listed in ASTM F726.

3.1.4 Construction.

3.1.4.1 Type I. N/A.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:26Z
Check the source to verify that this is the current version before use.

3.1.4.2 Type II. Type II sorbents shall be constructed so that sorbent material layers (if applicable) are not easily separated from each other upon agitation (e.g., when being transported) or when left stationary.

3.1.4.3 Type III. Type III sorbents shall not release internal sorbent material outside the outer fabric layer upon agitation (e.g., when being transported) or when left stationary. The internal material shall not compress or displace while contained in the outer fabric.

3.1.4.4 Type IV. Type IV sorbents shall not release internal sorbent material outside the outer fabric layer upon agitation (e.g., when being transported) or when left stationary. Type IV sorbents shall be flexible enough to bend around the perimeter of the spill and create a barrier to block the spill movement. The internal material shall not compress or displace while contained in the outer fabric.

3.1.4.5 Type V. Type V sorbents shall be constructed so that sorbent layers (if applicable) are not easily separated from each other. Type V sorbents shall be reinforced along the length with either double row stitching with nylon rope or nylon fabric. Type V sorbents shall have connections on the ends of the length for attaching other sweeps or rope.

3.2 Performance characteristics.

3.2.1 General. All sorbent types shall sorb a variety of different HM and shall not be specific to any categories of HM. Commercial off-the-shelf sorbents designed to sorb different HM types (e.g., lube oil, paint, etc.) are designated as “universal” and “HAZMAT” or “HM”. These designations can also sorb oil.

3.2.2 Sorption. The Oil Adsorption-Short Test detailed in ASTM F726 shall be the test used to determine sorption performance. Subsections of ASTM F726 describe the test method applicable to each sorbent type.

3.2.2.1 Type I. N/A.

3.2.2.2 Type II. Type II sorbents shall have a minimum sorbency of 1,100 percent by weight per pad when tested using the ASTM weight sorption method referenced above (see 3.2.2) applicable to pads. Type II sorbents shall not deform and shall allow for complete removal of sorbent while containing at least the minimum quantity required for a sorbency of 1,100 percent by weight.

3.2.2.3 Type III. Type III sorbents shall have a minimum sorbency of 700 percent by weight per pillow when tested using the ASTM weight sorption method referenced above (see 3.2.2) applicable to pillows. Type III sorbents shall not deform and shall allow for complete removal of sorbent while containing at least the minimum quantity required for a sorbency of 700 percent by weight.

3.2.2.4 Type IV. Type IV sorbents shall have a minimum sorbency of 600 percent by weight per sock when tested using the ASTM weight sorption method referenced above (see 3.2.2) applicable to socks. Type IV sorbents shall not deform and shall allow for complete removal of sorbent while containing at least the minimum quantity required for a sorbency of 600 percent by weight.

3.2.2.5 Type V. Type V sorbents shall have a minimum sorbency of 900 percent by weight per sweep when tested using the ASTM weight sorption method referenced above (see 3.2.2) applicable to sweeps. Type V sorbents shall not deform and shall allow for complete removal of sorbent while containing at least the minimum quantity required for a sorbency of 900 percent by weight.

3.3 Buoyancy.

3.3.1 Type I, II, III, and IV. N/A.

3.3.2 Type V. Type V sorbents shall achieve a minimum buoyancy to weight (B/W) ratio of 2:1 when using the test method described in the “Test Method” section of ASTM F2682.

3.4 Flammability. All types of sorbents shall be nonflammable when tested in accordance with the Methenamine Pill Test of ASTM D2859, UL 94, or a simple rating of noncombustible and flashpoint in accordance with the Cleveland Open-Cup Test of ASTM D92.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:26Z
Check the source to verify that this is the current version before use.

3.5 Environmental considerations. Sorbents shall not be toxic to aquatic life and waterfowl and shall have no adverse effects on the health of personnel when used for their intended purpose. Sorbents shall not of themselves or in combination with the HM or oil pollute waters or shoreline either chemically or physically when used for their intended purpose.

3.6 Off-gassing. The sorbents shall be evaluated for off-gassing in accordance with the requirements of 3.6.1. Based on the circumstances of use and the chemical nature of the sorbents, the Navy will determine whether off-gas testing is required or if an administrative assessment is acceptable. In order to be considered acceptable for use in submarines, the sorbents shall be assigned to either the "Permitted" or "Limited" category.

3.6.1 Off-gassing verification. The sorbents shall be evaluated for off-gassing in accordance with S9510-AB-ATM-010 chapter titled "Material Control Program" (see 3.6 and 7.3). If the Navy determines that off-gas testing is required, testing shall be conducted at a test facility approved by the Technical Authority. The Navy will review the off-gas test results and assign a usage category. Additionally, the Navy will assign a usage category if an administrative review is conducted in lieu of off-gas testing.

4. REGULATORY REQUIREMENTS. The offeror/contractor is encouraged to use recovered materials to the maximum extent practicable, in accordance with paragraph 23.403 of the Federal Acquisition Regulation (FAR).

5. PRODUCT CONFORMANCE PROVISIONS.

5.1 Product conformance. The products provided shall meet the salient characteristics of this CID, conform to the producer's own drawings, specifications, standards, and quality assurance practices, and be the same product offered for sale in the commercial marketplace. The government reserves the right to require proof of such conformance.

5.2 Sampling. Bid samples shall be as specified (see 7.4).

5.3 Examination. The bid sample sorbents shall be examined for compliance with the requirements specified in table II. Non-compliance with any specified requirements or the presence of one or more defects lessening required efficiency shall constitute cause for rejection.

TABLE II. Examination for expected product conformance.

Major Defect Number	Defect	Reference Paragraph	Method of Examination
101	Material not as specified	3.1.1	Visual/Doc
102	Pad sorbent not as specified	3.1.2.2, 3.1.3.2, 3.1.4.2, 3.2.2.2, 3.3	Visual/Doc/SIE
103	Enclosed sorbent (pillow type) not as specified	3.1.2.3, 3.1.3.3, 3.1.4.3, 3.2.2.3, 3.3	Visual/Doc/SIE
104	Enclosed sorbent (sock type) not as specified	3.1.2.4, 3.1.3.4, 3.1.4.4, 3.2.2.4, 3.3	Visual/Doc/SIE
105	Enclosed sorbent (sweep type) not as specified	3.1.2.5, 3.1.3.5, 3.1.4.5, 3.2.2.5, 3.3	Visual/Doc/SIE

NOTES:
1. Doc = Documentation
2. SIE = Standard Inspection Equipment

5.4 Tests. Bid sample testing for type II, III, and IV sorbents shall be conducted in accordance with the procedures described in ASTM F726. Bid sample testing for type V sorbent shall be conducted in accordance with the procedures described in ASTM F2682.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:26Z
Check the source to verify that this is the current version before use.

5.5 Ambient test conditions. Test conditions (testing location temperature, humidity, and air pressure) for bid samples shall be conducted in accordance with the procedures defined in the conditioning section of ASTM F726. All contaminated material resulting from the test shall be disposed of properly.

5.6 Market acceptability. The manufacturers of the item must have been producing a product meeting the requirements contained herein for at least 2 years.

6. PACKAGING. Preservation, packing, and marking shall be as specified in the contract or order.

7. NOTES.

7.1 Part or identification number (PIN). The following PIN procedure is for government purposes and does not constitute a requirement for the contractor. Table III describes the part numbering system for A-A-59759:

TABLE III. Part numbering system.

AA	59759	-	X
Prefix for CID	CID Number	-	Type (see code below)

Pin Code	Type
1	I
2	II
3	III
4	IV
5	V

Example: A type I sorbent would be PIN AA59759-1.

7.2 Source of documents.

7.2.1 ASTM International. ASTM standards are available from ASTM International, 100 Barr Harbor Dr., P.O. Box C700, West Conshohocken, PA 19428-2959 or online at www.astm.org.

7.2.2 FAR. The FAR may be obtained from the Superintendent of Documents, U.S. Government Publishing Office, Washington, DC 20402 or online at https://www.acquisition.gov/far.

7.2.3 Naval Sea Systems Command (NAVSEA) Publication. S9510-AB-ATM-010, Nuclear Powered Submarine Atmosphere Control Manual; chapter titled “Material Control Program” is available by email request to CommandStandards@navy.mil.

7.2.4 Underwriters Laboratories, Inc. (UL). UL standards are available from COMM 2000, 151 Eastern Avenue, Bensenville, IL 60106 or online at www.comm-2000.com.

7.3 Material certification. Materials to be installed or carried in submarines are to be controlled to prevent off-gassing, which contaminates the submarine’s atmosphere and can result in health hazards to personnel or deleterious effects on machinery. These controls are administered through the Submarine Material Control Program, which is described in the Nuclear Powered Submarine Atmosphere Control Manual, S9510-AB-ATM-010 chapter titled “Material Control Program.” Under the Submarine Material Control Program, all materials considered for use on submarines require certification and assignment of a usage category. Under the certification process, candidate materials are selected by Navy activities or contractors, and a request for certification is submitted to Commander, Naval Sea Systems Command, ATTN: SEA 05S, 1333 Isaac Hull Avenue, SE, Stop 5160, Washington Navy Yard, DC 20376-5160 or emailed to CommandStandards@navy.mil. The certification request is accompanied by detailed information, including descriptions of the material, method of application, usage, and storage. A chemical analysis is conducted, which can be accomplished through off-gas testing. If off-gas testing is required, it must be conducted in a Government approved laboratory. Information pertaining to this test requirement may be obtained from Commander, Naval Sea Systems Command, ATTN: SEA 05S, 1333 Isaac Hull Avenue, SE,

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:26Z
Check the source to verify that this is the current version before use.

Stop 5160, Washington Navy Yard, DC 20376-5160 or emailed to CommandStandards@navy.mil. Based on the chemical analysis results, a usage category is assigned to the material defining whether, and to what extent, the material may be used on submarines.

7.4 Ordering data. The contract or order should specify the following:

a. CID document number, revision, and CID PIN.
b. Product conformance provisions.
c. Bid sample requirements.
d. Quantity required.
e. Packaging requirements.

7.5 Key words.

Boom
Cleanup
Disposal
Granular
Pad
Pillow
Sheet
Sock
Spill
Sweep

CONCLUDING MATERIAL

MILITARY INTERESTS:

Custodian:
Navy – SH

Review Activities:
DLA – GS, GS3

CIVIL AGENCY COORDINATING ACTIVITY:
GSA – FAS

Preparing Activity:
Navy – SH
(Project 4235-2020-001)

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:26Z
Check the source to verify that this is the current version before use.