MIL-C-915/57A
1 August 1972
SUPERSEDING 1/
MIL-C-915/57(SHIPS)
20 March 1972

MILITARY SPECIFICATION SHEET

CABLE, ELECTRICAL, TYPE 1SAU

(A) This specification is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for procuring the cable described herein shall consist of this document and the latest issue of Specification MIL-C-915.

REQUIREMENTS:

Qualification required.

Construction

First - Copper conductor, ASTM B-286, size 20-7, uncoated. Maximum diameter 0.039 inch.

(A) Second - Polyethylene insulation, natural, type II, class L, grade 3 of L-P-390. Minimum thickness 0.012 inch. Diameter over insulation 0.060 inch, minimum.

A Third - Clear polyamide jacket on each conductor, type III, grade E or type IV of MIL-M-20693. Nominal thickness 0.003 inch.

Fourth - Braided shield of AWG No. 36 uncoated copper. Braid angle of 30 to 35 degrees; minimum coverage of 85 percent.

A Fifth - Shield insulation of one polyester tape, type G of MIL-I-631, plus a jacket of clear polyamide, type III, grade E or type IV of MIL-M-20693. Nominal thickness of 0.003 inch. Standard Identification Code, applied by method 2.

- Alternate shield insulation of two polyester tapes, type G of MIL-I-631, sealed. Standard Identification Code, applied by method 2, on inner tape.

- Diameter over completed conductors 0.110 inch nominal.

Sixth - The required number of singles (see details) cabled with a lay not greater than 24 times the pitch diameter of the layer. Cabling sequence shall be consecutive, starting with No. 1, from center outward.

Seventh - Binder tape applied helically with overlap.

A Eighth - Standard thermoplastic jacket (gray). Minimum thickness 0.050 inch. Cable surface marking required.

A Details

Type and size	Number of condrs.	Overall diameter	
		Min. (inch)	Max. (inch)
1SAU-44	44	0.910	0.990

EXAMINATION AND TESTS:

(A) Basic electrical:	Requirements:
Conductor resistance - At 25°C., ohms/1000 ft., maximum.	10.71
Voltage withstand - Volts, rms, minimum	
Conductor to shield	2000
Shield to shield.	500

1/ Requirements formerly covered on MIL-C-24145/17.

(A) Denotes changes.

FSC 6145

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:13Z
Check the source to verify that this is the current version before use.

	Requirements:
Group A:	
Visual and dimensional	
Capacitance - pF/ft. at 1 kHz, maximum	72
Group B:	
Physicals (unaged)	
Insulation (conductor)	
Tensile strength - psi, minimum.	1400
Elongation - Percent, minimum.	300
Jacket (cable)	
Tensile strength - psi, minimum.	1800
Elongation - Percent, minimum.	225
Group C:	
Physicals (aged)	
Insulation (conductor)	
Air oven	
Elongation - Percent of unaged, minimum	60
Jacket (cable)	
Hot oil immersion	
Tensile strength - psi, minimum	1400
Elongation - Percent, minimum	50
Permanence of printing (jacket) - Cycles, minimum.	250

QUALIFICATION INSPECTION

Qualification inspection shall include basic electrical plus all of Groups A, B and C.

UNIT ORDERING LENGTHS: 1000 feet (nominal)

(A) Custodians:
Army - MI
Navy - SH
Air Force - 80

(A) Review activities:
Army - EL, MI, AV
Navy - EC
Air Force - 80

(A) User activities:
Army - ME, MU, WC
Navy - CG

Preparing activity:
Navy - SH
(Project 6145-0609-43)

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:13Z
Check the source to verify that this is the current version before use.