MIL-C-915/59B
5 April 1973
SUPERSEDING 1/
MIL-C-915/59A
1 August 1972

MILITARY SPECIFICATION SHEET

CABLE, ELECTRICAL, TYPE 1SU

This specification sheet is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for procuring the cable described herein shall consist of this document and the latest issue of Specification MIL-C-915.

REQUIREMENTS:

Qualification required.

Construction

(B)

First - Copper conductors, tin coated, ASTM B-286 size 20-7 (maximum diameter 0.039 inch), and AWG No. 18 (7 X 0.0152 inch) (maximum diameter 0.050 inch). For 1SU-36, thirty-two size 20-7 and four AWG No. 18 conductors. For 1SU-60, sixty size 20-7 conductors.

Second - Polyethylene insulation, natural, type II class L, grade 3 of L-P-390. Minimum wall thickness 0.014 inch.

Third - Clear polyamide jacket on each conductor, type III, grade E or type IV of MIL-M-20693. Nominal thickness 0.003 inch.

Fourth - Braided shield of AWG No. 36 uncoated copper. Braid angle of 30 to 35 degrees; minimum coverage of 85 percent.

(B)

Fifth - Shield insulation of one polyester tape, type G of MIL-I-631, plus a jacket of clear polyamide, type III grade E or type IV of MIL-M-20693. Nominal thickness of 0.003 inch. Standard Identification Code, applied by method 2. (NOTE: The four size AWG No. 18 conductors shall be numbers 1 through 4.)

- Alternate shield insulation of two polyester tapes, type G of MIL-I-631, sealed. Standard Identification Code, applied by method 2, on inner tape. (NOTE: The four size AWG No. 18 conductors shall be numbers 1 through 4.)

Sixth - The required number of singles cabled with a lay not greater than 15 times the pitch diameter of the layer. Cabling sequence shall be consecutive, starting with No. 1, from center outward.

Seventh - Binder tape applied helically with overlap.

Eighth - Standard thermoplastic jacket (gray). (See details for thickness.) Cable surface marking required.

Details

Type and size	(B) Condr. size	Diameter over comp. condr. nom. (inch)	Cable jacket thick. min. (inch)	Overall diameter	
				Min. (inches)	Max. (inches)
1SU-36	AWG No. 18 20-7	0.127 .115	0.060	0.910	0.985
1SU-60	20-7	.115	.080	1.210	1.310

1/ Requirements formerly covered on MIL-C-24145/19.

(B) Denotes changes.

FSC 6145

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:13Z
Check the source to verify that this is the current version before use.

EXAMINATION AND TESTS:

	Requirements:
Basic electrical:	
Conductor resistance - At 25°C., ohms/1000 ft., maximum	
ASTM B-286 Size 20-7	10.93
Size AWG No. 18	7.20
Voltage withstand - Volts, rms, minimum	
Conductor to shield	2200
Shield to shield	500
Group A:	
Visual and dimensional	
Capacitance - At 1 kHz, pF/ft., maximum	72
Group B:	
Cold bending, cable - At minus 30° ± 2°C. maximum mandrel diameter, 12 times max. cable diameter	No damage
Physicals (unaged)	
Insulation (conductor)	
Tensile strength - psi, minimum	1400
Elongation - Percent, minimum	300
Jacket (cable)	
Tensile strength - psi, minimum	1800
Elongation - Percent, minimum	225
Group C:	
Physicals (aged)	
Insulation (conductor)	
Air oven	
Elongation - Percent of unaged, minimum	60
Jacket (cable)	
Hot oil immersion	
Tensile strength - psi, minimum	1400
Elongation - Percent, minimum	50
Permanence of printing (jacket) - Cycles, minimum	250

QUALIFICATION INSPECTION

Qualification inspection shall include basic electrical plus all of Groups A, B and C.

UNIT ORDERING LENGTHS:

All sizes: 1000 feet (nominal)

Custodians:
Army - MI
Navy - SH
Air Force - 80

Review activities:
Army - EL, MI, AV
Navy - EC
Air Force - 80

User activities:
Army - ME, MU, WC
Navy - CG

Preparing activity:
Navy - SH
(Project 6145-0648-17)

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:13Z
Check the source to verify that this is the current version before use.