MIL-C-915/61A
1 August 1972
SUPERSEDING 1/
MIL-C-915/61(SHIPS)
20 March 1972

MILITARY SPECIFICATION SHEET

CABLE, ELECTRICAL, TYPE S2S

(A) This specification is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for procuring the cable described herein shall consist of this document and the latest issue of Specification MIL-C-915.

REQUIREMENTS:

Qualification required.

Construction (watertight)

(A) First - High strength conductor, 7/.016 inch, tin coated (max. dia. 0.050 inch).
(A) Second - Butyl rubber insulation. Nominal thickness 0.060 inch.
(A) Third - Braided shield of AWG No. 34, tin coated, copper clad steel having 30 percent minimum conductivity.

NOTE: Shield to be 6 ends per carrier, 16 carriers, 11.5 picks per inch.

(A) Fourth - Butyl rubber insulation. Nominal thickness 0.060 inch.
(A) Fifth - Braided shield of AWG No. 34, tin coated, copper clad steel having 30 percent minimum conductivity.

NOTE: Shield to be 8 ends per carrier, 24 carriers, 11.5 picks per inch.

Sixth - Double layer jacket, minimum total thickness 0.065 inch. Inner layer 0.020 inch nominal wall butyl rubber insulation; outer layer arctic type polychloroprene (black) bonded to the inner layer. Cable surface marking required.

NOTE: Completed cable diameters: minimum 0.480 inch, maximum 0.500 inch.

EXAMINATION AND TESTS:

	Requirements:
Basic electrical:	
Conductor resistance - At 25°C., ohms/1000 ft., maximum.	20.45
Voltage withstand - Volts, rms, minimum	
Conductor to inner shield	1500
(A) Shield to shield.	1500
Insulation resistance - Megohms/1000 ft., minimum	
Conductor to inner shield	500
Shield to shield.	500
Outer shield to water	250
Group A:	
Visual and dimensional	
(A) Hydrostatic (open end) - Leakage at 1000 psi, 6 hrs., (Test each shipping length).	Zero
Capacitance - At 1 kHz, pF/ft., maximum.	37 ± 1

1/ Requirements formerly covered on MIL-C-24145/21.

(A) Denotes changes.

FSC 6145

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:13Z
Check the source to verify that this is the current version before use.

	Requirements:
Group B:	
(A) Cold bending, cable - At minus 30° ± 2°C., 4-inch maximum diameter mandrel	No damage
Breaking strength - Pounds, minimum.	150
Physicals (unaged)	
Insulation	
Tensile strength - psi, minimum.	700
Elongation - Percent, minimum.	350
Jacket (outer layer)	
Tensile strength - psi, minimum.	1800
Elongation - Percent, minimum.	300
Set - Inch, maximum.	3/8
Group C:	
Physicals (aged)	
Air pressure heat	
Insulation	
Tensile strength - Percent of unaged, minimum	50
Elongation - Percent of unaged, minimum	50
Permanence of printing (jacket) - Cycles, minimum.	250

QUALIFICATION INSPECTION

Qualification inspection shall include basic electrical plus all of Groups A, B and C plus the following:

Pressure cycling (1000 psi)	
Capacitance - At 1 kHz, pF/ft.	37 + 3 - 1
Insulation resistance:	
Outer shield to water - Megohms/1000 ft., minimum. (measured before, after, and at one week intervals during 90 days immersion in tap water at room temperature.)	50

UNIT ORDERING LENGTHS: 500 feet (nominal)

(A) Custodians:
Army - MI
Navy - SH
Air Force - 80

(A) Review activities:
Army - EL, MI, AV
Navy - EC
Air Force - 80

(A) User activities:
Army - ME, MU, WC
Navy - CG

Preparing activity:
Navy - SH
(Project 6145-0609-58)

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:13Z
Check the source to verify that this is the current version before use.