MIL-C-915/63A
1 August 1972
SUPERSEDING[1/]
MIL-C-915/63(SHIPS)
20 March 1972

MILITARY SPECIFICATION SHEET

(A) CABLE, ELECTRICAL, 300 VOLTS, TYPE 2U

(A) This specification is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for procuring the cable described herein shall consist of this document and the latest issue of Specification MIL-C-915.

REQUIREMENTS:

Qualification required.

Construction

First - Copper conductor, tin coated, ASTM B-286 size 26-7. Maximum diameter 0.020-inch.

(A) Second - Polyethylene insulation, type II, class L, grade 4 of L-P-390. Nominal thickness 0.012-inch. Telephone Identification Code, applied by method 3. Diameter over insulation 0.045 nominal.

(A) Third - Insulation jacket of clear polyamide, type III, grade E or type IV of MIL-M-20693, nominal thickness 0.003-inch.

Fourth - Two conductors cabled together to form a pair, with nominal lay of 1-1/2 inches.

(A) Fifth - The specified number of pairs (see details) cabled together with lay not greater than 16 times the pitch diameter of the layer. Cabling sequence shall be consecutive, starting with pair number 1, from center outward.

Sixth - Binder tape of polyester, type G of MIL-I-631, applied helically with overlap.

Seventh - Braided shield of AWG No. 34 tin coated copper. Minimum coverage of 88 percent.

(A) Eighth - Standard thermoplastic jacket (gray). (See details for thickness.) Cable surface marking required.

(A) Details

Type and size	Number of pairs	Cable jacket thickness nominal (inch)	Overall diameter	
			Min. (inch)	Max. (inch)
2U-10	10	0.050	0.450	0.480
2U-15	15	.050	.530	.560
2U-19	19	.050	.550	.580
2U-30	30	.050	.670	.700
2U-45	45	.050	.830	.870
2U-60	60	.065	.920	.960

1/ Requirements formerly covered on MIL-C-24145/23.

(A) Denotes changes.

FSC 6145

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:14Z
Check the source to verify that this is the current version before use.

EXAMINATION AND TESTS:

	Requirements:
Basic electrical:	
(A) Conductor resistance - At 25°C., ohms/1000 ft., maximum.	45.19
Voltage withstand - Volts, rms, minimum	
Conductor to conductor.	2000
Conductor to shield	1000
Group A:	
Visual and dimensional	
(A) Characteristic impedance - At 1 MHz, ohms.	135 ± 15
Group B:	
(A) Cold bending, cable - At minus 30° ± 2°C., maximum mandrel diameter twelve times cable diameter	No damage
(A) Bending endurance - At 25° ± 2°C., cycles, minimum	25
Physicals (unaged)	
Insulation	
Tensile strength - psi, minimum.	1400
Elongation - Percent, minimum.	300
Jacket (cable)	
Tensile strength - psi, minimum.	1800
Elongation - Percent, minimum.	225
Group C:	
Physicals (aged)	
Insulation	
Air oven	
Elongation - Percent, of unaged, minimum.	60
Jacket (cable)	
Hot oil immersion	
Tensile strength - psi, minimum	1400
Elongation - Percent, minimum	50
Permanence of printing (jacket) - Cycles, minimum.	250

QUALIFICATION INSPECTION

Qualification inspection shall include basic electrical plus all of Groups A, B and C.

UNIT ORDERING LENGTHS:

All sizes: 1000 feet (nominal)

(A) Custodians:
Army - MI
Navy - SH
Air Force - 80
(A) Review activities:
Army - EL, MI, AV
Navy - EC
Air Force - 80
(A) User activities:
Army - ME, MU, WC
Navy - CG

Preparing activity:
Navy - SH
(Project 6145-0609-46)

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:14Z
Check the source to verify that this is the current version before use.