MIL-C-915/63C
18 June 1985
SUPERSEDING
MIL-C-00915/63B(SH)
25 January 1982
MIL-C-915/63A
1 August 1972

MILITARY SPECIFICATION SHEET

CABLE, ELECTRICAL, 300 VOLTS, TYPE 2U (INCLUDING VARIATION TYPE 2UA)

This specification sheet is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for acquiring the cable described herein shall consist of this document and the latest issue of MIL-C-915.

This cable can be manufactured in two variations: 2U (unarmored) and 2UA (armored).

REQUIREMENTS:

Qualification required.

Construction (non-watertight)

First - Copper conductor, tin coated, in accordance with ASTM B 286, size 26-7. Maximum diameter 0.020 inch.

Second - Polyethylene insulation, type II, class L, grade 4 in accordance with L-P-390. Nominal thickness 0.012 inch. Telephone identification code applied by method 3. Diameter over insulation 0.045 nominal.

Third - Insulation jacket of clear polyamide in accordance with ASTM D 4066, nominal thickness 0.003 inch.

Fourth - Two conductors cabled together to form a pair, with nominal lay of 1-1/2 inches.

Fifth - The specified number of pairs (see table I) cabled together with lay not greater than 16 times the overall diameter of the layer. Cabling sequence shall be consecutive, starting with pair no. 1, from center outward.

Sixth - Binder tape of polyester, type G in accordance with MIL-I-631, applied helically with overlap.

Seventh - Braided shield of AWG no. 34 tin coated copper. Minimum coverage of 88 percent.

FSC 6145

DISTRIBUTION STATEMENT A Approved for public release; distribution unlimited

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:14Z
Check the source to verify that this is the current version before use.

Construction variant for type 2U

Eighth - Special thermoplastic jacket (gray). (See table I for thickness.) Cable surface marking required.

Construction variant for type 2UA

Eighth - Special thermoplastic jacket (gray). (See table I for thickness.)
Ninth - Braided metal armor and paint.

TABLE I. Details.

Size 1/	Number of pairs	Cable jacket thickness (nominal) (inch)	Overall diameter (inches)			
			Type 2U		Type 2UA	
			Minimum	Maximum	Minimum	Maximum
10	10	0.050	0.450	0.480	0.500	0.530
15	15	.050	.530	.560	.580	.610
19	19	.050	.550	.580	.600	.630
30	30	.050	.670	.700	.720	.750
45	45	.050	.830	.870	.880	.920
60	60	.065	.920	.960	.970	1.010

1/ Types 2U and 2UA.

EXAMINATION AND TESTS:

	Requirements
Basic electrical:	
Conductor resistance - ohms/1000 feet, at 25°C, maximum.	45.19
Voltage withstand - volts, root mean square, minimum	
Conductor to conductor.....	2000
Conductor to shield.....	1000
Insulation resistance - megohms/1000 feet, minimum	
Conductor to conductor.....	2000
Conductor to shield.....	1000
Group A:	
Visual and dimensional.....	No failure
Characteristic impedance - at 1 MHz, ohms.....	135 ± 15

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:14Z
Check the source to verify that this is the current version before use.

EXAMINATION AND TESTS: (Continued)

	Requirements
Group B:	
Cold bending, cable - at minus 30 ± 2°C, maximum mandrel diameter 12 times cable diameter.....	No damage
Bending endurance - at 25 ± 2°C, cycles, minimum.....	25
Physicals (unaged)	
Insulation	
Tensile strength - lbf/in^2, minimum.....	1400
Elongation - percent, minimum.....	300
Jacket (cable)	
Tensile strength - lbf/in^2, minimum.....	2300
Elongation - percent, minimum.....	250
Group C:	
Physicals (aged)	
Insulation	
Air oven	
Elongation - percent of unaged, minimum..	60
Jacket (cable)	
Air oven (168 hours at 136°C)	
Tensile strength - percent of unaged, minimum.....	80
Elongation - percent of unaged, minimum..	60
Hot oil immersion	
Tensile strength - percent of unaged, minimum.....	75
Elongation - percent of unaged, minimum..	50
Permanence of printing (jacket) type 2U only - cycles, minimum.....	250
Armor - conformance to material, construction and coverage, type 2UA.....	No failure
Shield-conformance to material coverage and construction	No failure

QUALIFICATION INSPECTION:

Qualification inspection shall include basic electrical, all of groups A, B and C, plus the following:

Jacket durometer (type A) hardness, minimum.....	80

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:14Z
Check the source to verify that this is the current version before use.

UNIT ORDERING LENGTHS: All sizes 1000 feet (nominal).

Revision letters are not used to denote changes due to the extensiveness of the changes.

NOTE: Not for Air Force use.

Custodians:
Army - MI
Navy - SH

Review activities:
Army - CR, ER
Navy - EC
DLA - IS

User activities:
Army - AL, AR, ME
Navy - CG

Preparing activity:
Navy - SH
(Project 6145-0885-58)

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:14Z
Check the source to verify that this is the current version before use.