MIL-C-915/64A
1 August 1972
SUPERSEDING
MIL-C-915/64(SHIPS)
20 March 1972
MIL-C-24145/24C(SHIPS)
15 November 1971

MILITARY SPECIFICATION SHEET

(A) CABLE, ELECTRICAL, 600 VOLTS, TYPE 2WAU

(A) This specification is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for procuring the cable described herein shall consist of this document and the latest issue of Specification MIL-C-915.

REQUIREMENTS:

Qualification required.

Construction (Watertight)

First - Copper conductor, tin coated, ASTM B-286 size 22-7. Maximum diameter 0.033 inch.
(A) Second - Polyethylene insulation, type II, class L, grade 4 of L-P-390. Minimum thickness 0.020-inch. Telephone Identification Code, applied by method 3.
(A) Third - Insulation jacket of clear polyamide, type III, grade E or type IV of MIL-M-20693. Nominal thickness 0.004-inch.
Fourth - Two conductors cabled together to form a pair, with nominal lay of 1-1/2 inches.
Fifth - Forty pairs cabled together, with a lay not greater than 16 times the pitch diameter of the layer. Cabling sequence shall be consecutive, starting with pair No. 1, from center outward. Nonfibrous fillers shall be employed to form a firm, well-rounded assembly.
(A) Sixth - Binder tape, applied helically with overlap. 1/
Seventh - Braided shield of AWG No. 34 tin coated copper. Minimum coverage of 85 percent.
Eighth - Binder tape applied helically with overlap.
(A) Ninth - Standard thermoplastic jacket (gray). Nominal thickness 0.060-inch. Cable surface marking required. Overall diameter, see details.

(A) Details

Type and size	No. of pairs	Overall diameter	
		Min. inches	Max. inches
2WAU-40	40	1.320	1.370

EXAMINATION AND TESTS:

	Requirements:
Basic electrical:	
(A) Conductor resistance - At 25°C., ohms/1000 ft., maximum	17.71
Voltage withstand - Volts, rms, minimum,	
Conductor to shield.	2500
(A) Shield to water.	1000
Insulation resistance - Megohms/1000 ft., minimum	
Conductor to conductor	5000

1/ Since the capacitance of all pairs should be approximately the same, it may be necessary to apply a greater thickness of insulation to conductors in the outer layer, because of their proximity to the overall shield braid. For the same reason, the first binder tape should be one having good electrical properties.

(A) Denotes changes

FSC 6145

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:14Z
Check the source to verify that this is the current version before use.

	Requirements:
Group A:	
Visual and dimensional	
Capacitance - At 1 MHz, pF/ft., maximum,	
Grounded capacitance	30
Mutual capacitance	20
(A) Watertightness - Leakage at 25 psi for 6 hours, cubic inches, maximum	1.0
Group B:	
(A) Cold bending, cable - At 0° ± 2°C., mandrel maximum diameter twelve times cable diameter	No damage
Physicals (unaged)	
Insulation	
Tensile strength, psi, minimum	1400
Elongation, percent, minimum	300
Jacket (cable)	
Tensile strength, psi, minimum	1800
Elongation, percent, minimum	225
Group C:	
Physicals (aged)	
Insulation	
Air oven	
Elongation, percent of unaged, minimum	60
Jacket (cable)	
Hot oil immersion	
Tensile strength, psi, minimum	1400
Elongation, percent, minimum	50
Permanence of printing (jacket) - Cycles, minimum	250
Cable filler removability	

QUALIFICATION INSPECTION

Qualification inspection shall include basic electrical plus all of Groups A, B and C plus the following:

(A) Cable aging and compatibility (95° ± 3°C.)	No failure

UNIT ORDERING LENGTH:
1000 feet (nominal).

(A) Custodians:
Army - MI
Navy - SH
Air Force - 80

(A) Review activities:
Army - EL, MI, AV
Navy - EC
Air Force - 80

(A) User activities:
Army - ME, MU, WC
Navy - CG

Preparing activity:
Navy - SH
(Project 6145-0609-59)

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:14Z
Check the source to verify that this is the current version before use.