MIL-C-915/65A
1 August 1972
SUPERSEDING 1/
MIL-C-915/65(SHIPS)
20 March 1972

MILITARY SPECIFICATION SHEET

CABLE, ELECTRICAL, TYPE 1SMWU

(A) This specification is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for procuring the cable described herein shall consist of this document and the latest issue of Specification MIL-C-915.

REQUIREMENTS:
Qualification required.

Construction (Watertight)

First - Copper conductor, ASTM B-286, size 22-7, tin coated. Maximum diameter 0.033 inch.

(A) Second - Polyethylene insulation, white, type II, class L, grade 4 of L-P-390. Nominal thickness 0.027 inch.

(A) Third - Jacket on each conductor of clear polyamide, type III, grade E, or type IV of MIL-M-20693. Nominal thickness 0.003 inch. Standard Identification Code, applied by method 1.

Fourth - Braided shield of AWG No. 36 tin coated copper. Braid angle of 30 to 35 degrees; minimum coverage of 85 percent.

(A) Fifth - Shield insulation of one polyester tape, type G of MIL-I-631, plus a jacket of clear polyamide, type III, grade E or type IV of MIL-M-20693. Nominal thickness of 0.003 inch.

- Alternate shield insulation of two polyester tapes, type G of MIL-I-631, sealed.

(A) Sixth - The required number of singles (see details) cabled together with a lay not greater than 24 times the pitch diameter of the layer. Cabling sequence to be consecutive, starting with No. 1, from center outward. Non-fibrous fillers shall be employed.

Seventh - Binder tape applied helically with overlap.

(A) Eighth - Standard thermoplastic jacket (gray). Jacket thickness, 0.050 inch, nominal. Cable surface marking required.

(A)

Details

Type and size	Number of condrs.	Overall diameter	
		Min. (inch)	Max. (inch)
1SMWU-70	70	1.465	1.555

EXAMINATION AND TESTS:

	Requirements:
Basic electrical;	
(A) Conductor resistance - Ohms/1000 ft. at 25°C., maximum	17.71
Voltage withstand - Volts, rms, minimum	
Conductor to shield	5000
Shield to shield	500
Capacitance - pF/ft. at 1 kHz, maximum	35

1/ Requirements formerly covered on MIL-C-24145/27.

(A) Denotes changes.

FSC 6145

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:14Z
Check the source to verify that this is the current version before use.

	Requirements:
Group A:	
Visual and dimensional	
(A) Watertightness - Leakage at 25 psi, cubic inch, 6 hrs. maximum . . .	1.0
Group B:	
(A) Cold bending, cable - At 0° ± 2°C., (mandrel diameter 20 inches, maximum).	No damage
Physicals (unaged)	
Insulation (conductor)	
Tensile strength - psi, minimum.	1400
Elongation - Percent, minimum.	300
Jacket (cable)	
Tensile strength - psi, minimum.	1800
Elongation - Percent, minimum.	225
(A) Drip - At 75° ± 1°C.	Zero
Attenuation - At 400 MHz, db/100 ft.; maximum.	18
Group C:	
Physicals (aged)	
Insulation (conductor)	
Air oven	
Elongation - Percent of unaged, minimum	60
Jacket (cable)	
Hot oil immersion	
Tensile strength - psi, minimum	1400
Elongation - Percent, minimum	50
Permanence of printing (conductor) - Cycles, minimum	50
Permanence of printing (jacket) - Cycles, minimum.	250
Cable filler removability	

QUALIFICATION INSPECTION

Qualification inspection shall include basic electrical plus all of Groups A, B and C plus the following:

(A) Cable aging and compatibility (95° ± 3°C.)	No failure

UNIT ORDERING LENGTH: 1000 ft. (nominal)

(A) Custodians:
Army - MI
Navy - SH
Air Force - 80

(A) Review activities:
Army - EL, MI, AV
Navy - EC
Air Force - 80

(A) User activities:
Army - ME, MU, WC
Navy - CG

Preparing activity:
Navy - SH
(Project 6145-0609-47)

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:14Z
Check the source to verify that this is the current version before use.