MIL-C-915/71B
5 April 1973
SUPERSEDING
MIL-C-915/71A
1 August 1972

MILITARY SPECIFICATION SHEET

CABLE, ELECTRICAL, 1000 VOLTS, MULTICONDUCTOR, TYPE MNW

This specification sheet is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for procuring the cable described herein shall consist of this document and the latest issue of Specification MIL-C-915.

REQUIREMENTS:
Qualification required.

Construction

First - Copper conductor, uncoated, Navy Standard size 2(7).
Second - Polypropylene insulation, black, 0.015-inch nominal thickness. Standard Identification Code, applied by method I.
Third - The required number of conductors (see Details), cabled together with a lay not greater than 24 times the pitch diameter of the layer, except that the lay of the two outer layers for size 44 shall not be greater than 18 times the pitch diameter of the layer. Cabling sequence shall be consecutive, starting with No. 1, from the center outward. Fibrous fillers as required in order to form a firm, well-rounded assembly.
Fourth - Binder-tape of 0.002-inch thick corrugated polyester, type G of MIL-I-631.
Fifth - Standard thermoplastic jacket (gray). Cable jacket thickness 0.050-inch nominal. Cable surface marking required.

Details

Type and size	Number of conductors	Overall diameter maximum (inch)	Cold bending mandrel diameter, maximum (inches)
MNW-7	7	0.390	3
MNW-10	10	.480	3
MNW-14	14	.515	4
MNW-19	19	.560	4
MNW-24	24	.650	5
MNW-30	30	.685	5
MNW-37	37	.740	6
MNW-44	44	.840	7

EXAMINATION AND TESTS

	Requirements:
Basic electrical:	
Voltage withstand - Volts, rms, minimum	3000
Insulation resistance - Megohms/1000 ft. at 25°C., max.	10,000
Conductor resistance - Ohms/1000 ft. at 25°C., max.	6.44
Group A:	
Visual and dimensional	

(B) Denotes changes.

FSC 6145

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:15Z
Check the source to verify that this is the current version before use.

	Requirements:
Group B:	
Abrasion resistance - scrapes, minimum	250
Cold bending, cable - (See details for mandrel diameter)	No damage
Physicals (unaged)	
(B) Insulation (Note 1)	
Tensile strength - psi, minimum	4000
Elongation - percent, minimum	200
Jacket	
Tensile strength - psi, minimum	1800
Elongation - percent, minimum	225
Group C:	
Permanence of printing (conductors) - cycles, minimum	25
Permanence of printing (jacket) - cycles, minimum	250
Flammability - Inches, maximum	2
Physicals (aged)	
(B) Insulation (Note 1)	
Air oven	
Tensile strength - percent of unaged, minimum	80
Elongation - percent of unaged, minimum	70
Jacket	
Hot oil immersion	
Tensile strength - psi, minimum	1400
Elongation - inches, minimum	1

(B) Note 1: Stretch rate shall be 2 inches per minute.

QUALIFICATION INSPECTION

Qualification inspection shall consist of basic electrical plus all of Groups A, B and C plus the following:

Cold working (minus 20° ± 2°C.)	No damage

UNIT ORDERING LENGTHS:

Type and Size	Feet (nominal)
MNW-7	1500
MNW-10	1500
All other sizes	1000

Custodians:
Army - MI
Navy - SH
Air Force - 80

Review activities:
Army - EL, MI, AV
Navy - EC
Air Force - 80

User activities:
Army - ME, MU, WC
Navy - CG

Preparing activity:
Navy - SH
(Project 6145-0648-19)

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:15Z
Check the source to verify that this is the current version before use.