MIL-C-915/73A
1 August 1972
SUPERSEDING
MIL-C-915/73(SHIPS)
20 March 1972

MILITARY SPECIFICATION SHEET

CABLE, ELECTRICAL, 3000 VOLTS, TYPES SRW, DRW AND TRW

(A) This specification is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for procuring the cable described herein shall consist of this document and the latest issue of Specification MIL-C-915.

REQUIREMENTS:

Qualification required.

Construction (watertight)

First - Copper conductor, uncoated, Navy standard size 4(7).
Second - Separator, polyester, type G of MIL-I-631, opaque white, applied either helically or longitudinally to give 100 percent coverage.
(A) Third - Cross-linked thermosetting polyethylene insulation, colored black. Nominal thickness 0.080-inch. Standard Identification Code applied by method 1, on two-conductor and three-conductor cables only.
Fourth - The required two or three conductors cabled with a lay not greater than 24 times the pitch diameter. Either non-fibrous or a combination of non-fibrous and fibrous fillers shall be used to form a firm, well-rounded assembly.
Fifth - Binder tape applied helically with overlap for two and three conductor cables only.
(A) Sixth - Standard thermoplastic jacket (gray). 0.050 inch nominal thickness. Cable surface marking required.

Note: Manufacturer's marker tape may be omitted from single conductor cable.

(A) Details

Cable type	Number of conductors	Overall diameter maximum (inch)	Conductor resistance at 25°C. max./1000 ft. (ohms)	Cold bending mandrel maximum diameter (inch)
SRW	1	0.400	2.46	3
DRW	2	.670	2.51	5
TRW	3	.710	2.51	7

EXAMINATION AND TESTS:

	Requirements:
Basic electrical:	
Conductor resistance - Ohms/1000 ft., maximum	See details
Voltage withstand - Volts, rms, minimum	8000
(A) Insulation resistance - Megohms/1000 ft., minimum	9500
Group A:	
Visual and dimensional	
Watertightness - (See MIL-C-915, table for limits of water leakage)	

(A) Denotes changes.

FSC 6145

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:16Z
Check the source to verify that this is the current version before use.

	Requirements:
Group B:	
Cold bending, cable - (See details for mandrel diameter)	No failure
Physicals (unaged)	
Insulation	
Tensile strength - Psi, minimum	1800
Elongation - Percent, minimum	250
Jacket	
Tensile strength - Psi, minimum	1800
Elongation - Percent, minimum	225
Group C:	
Permanence of printing (conductor) (types DRW and TRW) -	
(A) Cycles, minimum	25
Permanence of printing (jacket) - Cycles, minimum	250
Cable filler removability	2
Flammability - inches, maximum	30
Heat distortion - percent of unaged, maximum	Zero
(A) Drip - At 95° + 1°C.	
Physicals (aged)	
Insulation	
Air oven	
Tensile strength - Percent of unaged, minimum	75
Elongation - Percent of unaged, minimum	75
Jacket	
Hot oil immersion	
Tensile strength - Psi, minimum	1400
Elongation - Inches, minimum	1

QUALIFICATION INSPECTION

Qualification inspection shall include basic electrical, all of groups A, B and C plus the following:

(A) Cable aging and compatibility (125° ± 5°C.)	No failure

UNIT ORDERING LENGTHS:

Type SRW, 2500 feet nominal
Types DRW and TRW, 2000 feet nominal

(A) Custodians:
Army - MI
Navy - SH
Air Force - 80

(A) Review activities:
Army - EL, MI, AV
Navy - EC
Air Force - 80

(A) User activities:
Army - ME, MU, WC
Navy - CG

Preparing activity:
Navy - SH
(Project 6145-0609-62)

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:16Z
Check the source to verify that this is the current version before use.