MILITARY SPECIFICATION SHEET

CABLE, ELECTRICAL, TYPE 4NW8

This specification is approved for use by the Naval Sea Systems Command and is available for use by all Departments and Agencies of the Department of Defense.

The complete requirements for procuring the cable described herein shall consist of this document and the latest issue of Specification MIL-C-915.

REQUIREMENTS:

First article required.

Construction

First - Copper conductor, uncoated, size AWG-8 (7 x 0.0486-inch).

Second - Separator, polyester type G of MIL-I-631, opaque white, applied either helically or longitudinally to give 100 percent coverage.

Third - Cross-linked thermosetting polyeth lene insulation, colored black. Nominal thickness 0.045-inch. Standard Identification Code applied by me od 1.

Fourth - Four conductors cabled together with a lay not greater than 24 times the pitch diameter. Either non-fibrous or a combination of non-fibrous and fibrous fillers shall be used to form a firm, well-rounded assembly.

Fifth - Binder tape of 0.002 inch thick, corrugated polyester, type G of MIL-I-631.

Sixth - Standard thermoplastic jacket (gray). Nominal thickness 0.050-inch. Maximum overall diameter 0.740-inch. Cable surface marking required.

EXAMINATION AND TESTS:

Basic electrical:	Requirements:
Conductor resistance - At 25° Celsius (C) ohms/1000 feet, maximum	0.679
Voltage withstand - Condr. to condr., volts, root mean square (rms), minimum	4500
Insulation resistance - Megohms/1000 feet, minimum	4200

Group A:

Visual and dimensional.

Group B:

Cold bending, cable - 6-inch mandrel diameter, maximum	No damage
Physicals (unaged)	
Insulation	
Tensile strength - pounds per square inch gage (lb/in^2g), minimum	1800
Elongation - percent, minimum	250
Jacket	
Tensile strength - lb/in^2g, minimum	1800
Elongation - percent, minimum	225

Group C:

Permanence of printing, (conductor) - cycles, minimum	25
Permanence of printing, (jacket) - cycles, minimum	250
Cable filler removability	
Flammability - inches, maximum	2
Heat distortion - percent of unaged, maximum	30

FSC 6145

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:16Z
Check the source to verify that this is the current version before use.

	Requirements:
Drip - At 95° ± 1°C.	Zero
Physicals (aged)	
Insulation	
Air oven	
Tensile strength - percent of unaged, minimum.	75
Elongation - percent of unaged, minimum	75
Jacket	
Hot oil, immersion	
Tensile strength - lb/in^2g, minimum	1400
Elongation - inches, minimum.	1

FIRST ARTICLE INSPECTION

First article inspection shall include basic electrical plus all of Groups A, B and C plus the following:

Cold working (minus 20° ± 2°C)	No damage
Cable aging and compatibility (125° ± 5°C)	No failure

UNIT ORDERING LENGTH: 1500 feet (nominal)

Preparing activity:
Navy - SH
(Project 6145-N257)

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:16Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers/ vendors who are prospective suppliers of the product are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?

☐ YES ☐ NO *(If "Yes", in what way?)*

4. REMARKS

SUBMITTED BY *(Printed or typed name and address - Optional)*

TELEPHONE NO.

DATE

DD FORM 1 JAN 72 1426 REPLACES EDITION OF 1 JAN 66 WHICH MAY BE USED

S/N 0102-014-1802

☆ U.S. GOVERNMENT PRINTING OFFICE: 1972—714-863/3404 2-1

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:16Z
Check the source to verify that this is the current version before use.

FOLD

COMMANDER
NAVAL SHIP ENGINEERING CENTER
CENTER BUILDING - SEC 6124
PRINCE GEORGES CENTER
HYATTSVILLE, MARYLAND 20782

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

POSTAGE AND FEES PAID
DEPARTMENT OF NAVY

DOD 316

U.S.MAIL

COMMANDER
NAVAL SHIP ENGINEERING CENTER
CENTER BUILDING - SEC 6124
PRINCE GEORGES CENTER
HYATTSVILLE, MARYLAND 20782

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:16Z
Check the source to verify that this is the current version before use.