INCH-POUND

MIL-C-915/87A
29 September 1989
SUPERSEDING
MIL-C-915/87
18 June 1985

MILITARY SPECIFICATION SHEET

CABLE, POWER ELECTRICAL, TWISTED TRIAD, NO. 16 GAUGE, FLUOROPOLYMER INSULATION, FOR SUBMARINE OUTBOARD USE ONLY (NOT FOR INBOARD USE), TYPE 1TR-16

This specification sheet is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specificaiton sheet and the issue of the following specification listed in that issue of the Department of Defense Index of Specifications and Standards (DoDISS) specified in the solicitation: MIL-C-915.

REQUIREMENTS:

Qualification required.

Construction

First - Copper conductor, tin coated, AWG size 16, class B stranding.

Second - Insulation of ethylene tetrafluoroethylene (ETFE). Nominal wall thickness 0.010 inch. Maximum overall diameter 0.082 inch.

Third - Three insulated conductors, one black, one white, and one red, twisted together with a nominal lay of 2-1/2 inches to form a triad.

Fourth - Cable jacket of black polyether polyurethane applied so as to completely fill the triad valleys. The cable jacket material shall be B.F. Goodrich Co. ESTANE 58300 or 58863; Mobay Chemical Co. TEXIN 985A. Nominal wall thickness 0.100 inch. Overall diameter to be 0.380 to 0.400 inch.

AMSC N/A FSC 6145

DISTRIBUTION STATEMENT A: Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 202640-16T12:18Z
Check the source to verify that this is the current version before use.

EXAMINATION AND TESTS:

	Requirements
Basic electrical:	
Conductor resistance - at 20°C, ohms/1000 feet, maximum	4.24
Voltage withstand - volts, root mean square, minimum	
Conductor to conductor	2000
Conductor to water	2000
Insulation dielectric (on 100 percent of insulated conductor) - test in accordance with MIL-W-81381, using a test voltage of 8.0 kV (peak), minimum.	
Insulation resistance - megohms/1000 feet, minimum	5000
Group A:	
Visual and dimensional	No failure
Group B:	
Cold bending, cable - at minus 40 ± 2°C over a 3-inch diameter mandrel	No damage
Physicals (unaged)	
Insulation	
Tensile strength - lbf/in², minimum	5000
Elongation - percent, minimum	150
Cable jacket	
Tensile strength - lbf/in², minimum	4000
Elongation - percent, minimum	500
Group C:	
Physicals (aged)	
Insulation	
Air oven (168 hours at 180°C)	
Tensile strength - percent of unaged, minimum	80
Elongation - percent of unaged, minimum.	90
Cable jacket	
Air oven (168 hours at 80°C)	
This test shall be in accordance with MIL-C-915	No failure
Hot oil immersion	
Tensile strength, percent of unaged, minimum	60
Elongation, percent of unaged, minimum	80

QUALIFICATION INSPECTION:

Qualification inspection shall include basic electrical, plus all of groups A, B and C.

UNIT ORDERING LENGTH: 500 feet (minimum).

Source: https://assist.dla.mil -- Downloaded: 202610-16T12:18Z
Check the source to verify that this is the current version before use.

NOTE: Not for Air Force use.

Revision letters are not used to denote changes due to the extensiveness of the changes.

Custodians:
Army - MI
Navy - SH

Review activities:
Army - CR, ER
Navy - EC
DLA - IS

User activities:
Army - AL, AR, ME
Navy - CG

Preparing activity:
Navy - SH
(Project 6145-1127-24)

Source: https://assist.dla.mil -- Downloaded: 202640-16T12:18Z
Check the source to verify that this is the current version before use.