MILITARY SPECIFICATION SHEET

CABLE, ELECTRICAL, ONE SHIELDED TWISTED PAIR NO. 16 GAUGE, FLUOROPOLYMER INSULATION, FOR SUBMARINE OUTBOARD USE ONLY (NOT FOR INBOARD USE), TYPE 1SPR-16

This specification sheet is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for acquiring the cable described herein shall consist of this document and the latest issue of MIL-C-915.

REQUIREMENTS:

Qualification required.

Construction

First - Copper conductor, tin coated, AWG size 16, class B stranding.

Second - Insulation of ethylene tetrafluoroethylene (TEFZEL). Nominal wall thickness 0.010 inch. Maximum overall diameter 0.082 inch.

Third - Two insulated conductors, one black and one white, twisted together with a lay of 1-1/4 ± 1/8 inches.

Fourth - Rubber filler in order to form a firm, round assembly. Filler shall be capable of removal from the assembly without damaging the conductor insulation.

Fifth - Braided shield of AWG no. 36 tin coated copper. Braid angle of 35 degrees minimum; coverage of 85 percent, minimum.

Sixth - Separator tape of polyester, applied helically with overlap.

Seventh - Cable jacket of black polyether polyurethane. The cable jacket material shall be B.F. Goodrich Co. ESTANE 58300 or 58863, Mobay Chemical Co. TEXIN 985A or equal. Nominal wall thickness 0.090 inch. Overall diameter to be 0.380 to 0.400 inch.

FSC 6145

DISTRIBUTION STATEMENT A Approved for public release; distribution unlimited

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:18Z
Check the source to verify that this is the current version before use.

EXAMINATION AND TESTS:

	Requirements
Basic electrical:	
Conductor resistance - at 20°C, ohms/1000 feet, maximum.	4.24
Voltage withstand - volts, root mean square, minimum	
Conductor to conductor	2000
Conductor to shield	1000
Shield to water	500
Insulation dielectric (on 100 percent of insulated conductor) - test in accordance with MIL-W-81381, using a test voltage of 8.0 kV (peak), minimum.	
Insulation resistance - megohms/1000 feet, minimum	5000
Group A:	
Visual and dimensional	No failure
Group B:	
Cold bending, cable - at minus 40 ± 2°C over a 3-inch diameter mandrel	No damage
Physicals (unaged)	
Insulation	
Tensile strength - lbf/in^2, minimum	5000
Elongation - percent, minimum	100
Cable jacket	
Tensile strength - lbf/in^2, minimum	5000
Elongation - percent, minimum	500
Group C:	
Physicals (aged)	
Insulation	
Air oven (168 hours at 180°C)	
Tensile strength - percent of unaged, minimum	80
Elongation - percent of unaged, minimum	90
Cable jacket	
Air oven (168 hours at 80°C)	
This test shall be in accordance with MIL-C-915	No failure
Hot oil immersion	
Tensile strength, percent of unaged, minimum	90
Elongation, percent of unaged, minimum	80
Shield-conformance to material coverage and construction	No failure

Source: https://assist.dla.mil -- Downloaded: 202640-16T12:18Z
Check the source to verify that this is the currentversion before use.

QUALIFICATION INSPECTION:
Qualification inspection shall include basic electrical, plus all of groups A, B and C.

UNIT ORDEF G LENGTH: 500 feet (minimum).

NOTE: Not for Air Force use.

Custodians:
Army - MI
Navy - SH

Preparing activity:
Navy - SH
(Project 6145-0886-09)

Review activities:
Army - CR, ER
Navy - EC
DLA - IS

User activities:
Army - AL, AR, ME
Navy - CG

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:18Z
Check the source to verify that this is the current version before use.