MIL-C-915/58B
5 April 1973
SUPERSEDING 1/
MIL-C-915/58A
1 August 1972

MILITARY SPECIFICATION SHEET

CABLE, ELECTRICAL, 600 VOLTS, TYPE MWF

This specification sheet is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for procuring the cable described herein shall consist of this document and the latest issue of Specification MIL-C-915.

REQUIREMENTS:
Qualification required.

Construction (Watertight)

(B)

First - Copper conductor, AWG No. 18 (7 X 0.0152 inch), tin coated. Maximum diameter 0.050-inch.
Second - Insulation of synthetic rubber or cross-linked polyethylene. Nominal thickness 0.020-inch.
Third - Jacket of clear polyamide, type III grade E, or type IV, of MIL-M-20693, nominal thickness 0.005-inch. Standard identification code, applied by Method 1.
Fourth - The required number of conductors (see details) cabled together with a maximum lay of 20 times the pitch diameter of the layer. Cabling sequence to be consecutive, starting with No. 1, from the center outward. Fillers as necessary in order to form a firm, round assembly. Fillers shall be non-fibrous.
Fifth - Binder tape applied helically with overlap.
Sixth - Arctic type neoprene jacket, black. (See details for thickness.) Cable surface marking required.

Details

Type and size	Number of conductors	Cable jacket thickness nominal (inch)	Overall diameter	
			Minimum (inches)	Maximum (inches)
MWF-7	7	0.060	0.480	0.500
MWF-10	10	.065	.605	.635
MWF-14	14	.065	.605	.635
MWF-19	19	.085	.710	.745
MWF-24	24	.085	.800	.836
MWF-30	30	.110	.905	.945
MWF-37	37	.110	1.005	1.045

EXAMINATION AND TESTS:

	Requirements:
Basic electrical:	
Voltage withstand - Volts, rms, minimum	
Conductor to conductor.	2000
Conductor to water.	1000
Conductor resistance - Ohms/1000 ft. at 25°C., maximum	6.87

1/ Requirements formerly covered on MIL-C-24145/18.

(B) Denotes changes.

FSC 6145

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:13Z
Check the source to verify that this is the current version before use.

	Requirements:
Group A:	
Visual and dimensional	
Hydrostatic (open end)(on every shipping length) - Leakage at 1000 psi, in 6 hrs. cu. in., maximum	0
Group B:	
Physicals (unaged)	
Insulation (conductor)	
Synthetic rubber	
Tensile strength - psi, minimum	700
Elongation - Percent, minimum	350
Cross-linked polyethylene	
Tensile strength - psi, minimum	1800
Elongation - Percent, minimum	350
Jacket (cable)	
Tensile strength - psi, minimum	1800
Elongation - Percent, minimum	300
Set - Inch, maximum	3/8
Group C:	
Physicals (aged)	
Insulation (conductor)	
Synthetic rubber	
Oxygen pressure	
Tensile strength - Percent of unaged, minimum	75
Elongation - Percent of unaged, minimum	75
Air pressure heat	
Tensile strength - Percent of unaged, minimum	50
Elongation - Percent of unaged, minimum	50
Cross-linked polyethylene	
Air oven	
Tensile strength - Percent of unaged, minimum	80
Elongation - Percent of unaged, minimum	80
Air pressure heat	
Tensile strength - Percent of unaged, minimum	50
Elongation - Percent of unaged, minimum	50
Permanence of printing (conductor) - Cycles, minimum	50
Permanence of printing (jacket) - Cycles, minimum	250
Cold working (minus 54° ± 2°C.)	No damage
Cable filler removability	

QUALIFICATION INSPECTION

Qualification inspection shall include basic electrical plus all of Groups A, B and C plus the following:

Cable aging and compatibility (125° ± 5°C.)	No failure
Cold working (minus 54° ± 2°C.)	

UNIT ORDERING LENGTHS:

Size	Feet (nominal)
7	1000
10	1000
14	500
19	500
24	500
30	500
37	500

Custodians:
Army - MI
Navy - SH
Air Force - 80

Review activities:
Army - EL, MI, AV
Navy - EC
Air Force - 80

User activities:
Army - ME, MU, WC
Navy - CG

Preparing activity:
Navy - SH
(Project 6145-0648-16)

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:13Z
Check the source to verify that this is the current version before use.