GGG-P-831e
INTERIM AMENDMENT-4
June 28, 1973
SUPERSEDING
Interim Amendment-3
February 5, 1971

INTERIM AMENDMENT

TO

FEDERAL SPECIFICATION

PUNCHES; CENTER, COOPERS', DRIVE PIN, ALIGNING, AND PRICK

This Interim Amendment was developed by Standardization Division, Federal Supply Service, General Services Administration, Washington, D. C. 20406, based upon currently available technical information. It is recommended that Federal agencies use it in procurement and forward recommendations for changes to the preparing activity at the address shown above.

The General Services Administration has authorized the use of this interim amendment as a valid exception to Federal Specification GGG-P-831e, dated January 27, 1966.

PAGE 1

Paragraph 2.1, under "Federal Standards:" Delete "Fed. Std. No. 102 - Preservation, Packaging, and Packing Levels."

PAGE 2

After paragraph 3.2, add:

"3.2.1 Hardness. The striking end of all punches shall not exceed Rockwell "C" 50 when tested as specified in paragraph 4.4.9."

Paragraph 3.7.1: Delete first sentence and substitute:

"Punches, when ordered in encased sets, shall be furnished in durable wooden or plastic boxes, fabric wraps, plastic wraps, or rolls, as specified (see 6.1)."

Paragraph 3.7.1.1: At end of first sentence delete the period and add "and withstand the drop test specified in 4.4.11."

Paragraphs 3.7.1.2 and 3.7.1.3: Delete and substitute:

"3.7.1.2 Plastic boxes. The boxes and covers shall be of plastic that will withstand the flammability test as specified for plastic wraps or rolls in 4.4.10, and not be damaged when subjected to the drop test specified in 4.4.11.

3.7.1.3 Fabric wraps or rolls. Fabric wraps or rolls shall be of good quality, durable material such as canvas or duck, and provided with durable ties.

3.7.1.4 Plastic wraps or rolls. Plastic wraps or rolls shall be of good quality plastic or plastic-coated cloth. The wraps or rolls shall be provided with snap fasteners or durable ties. The wraps or rolls shall be capable of withstanding the test specified in 4.4.10."

FSC 5120

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:42Z
Check the source to verify that this is the currentversion before use.

PAGE 3

Paragraph 3.8.1: Delete last sentence and substitute:

"Class A punches shall possess a Rockwell "C" hardness of 50 to 63 within a minimum of 1/2 inch from the point end (see 4.4.9)."

PAGE 5

Paragraph 3.10: Delete last sentence and substitute:

"Type VIII, classes A, B, and C punches shall have a Rockwell "C" hardness of 50 to 63 throughout their point length."

PAGE 7

Paragraph 3.11: Delete last sentence and substitute:

"Type IX punches shall have a Rockwell "C" hardness of 50 to 63 throughout a minimum of 75 percent of the taper length from the point of the taper."

Paragraph 3.12: Delete fifth sentence and substitute:

"The point end shall have a Rockwell "C" hardness of 50 to 63 within a minimum of 1/2 inch from the point end."

PAGE 8

Paragraph 3.13: Delete and substitute:

"3.13 Workmanship. Punches shall be well proportioned, well balanced, new, and clean. Knurling, when utilized, shall be well defined. The working end shall be sharp and suitably ground having either a sharp point, or ground to the point diameter specified. Punches shall be free from any defects which may impair their serviceability, durability, or appearance."

Paragraph 4.4.1: Delete and substitute the new paragraph as follows:

"4.4.1 Performance test for type II, classes A and B center punches. Test impressions shall be made in steel plate (free of scale) at least 1/4 inch thick with a hardness between 25 and 30 on the Rockwell "C" scale. A machinists' hammer in accordance with table XA shall be used and the test punch struck as squarely as possible with at least 25 (light to medium) blows producing at least 10 different indentations in the test bar. Punches shall be considered to have failed if either the striking end or point breaks, deforms, dulls, spalls, or cracks during this test. Note: Points of class B automatic center punches shall be removed and secured in a separate steel shank of suitable size and tested with an 8 ounce machinists' hammer for purposes of this test.

TABLE XA.

Punch size	Body size	Hammer weight
	Inches	Ounces
0	3/16	8
2	1/4	8
4	5/16	8
5	3/8	16
7	1/2	16
10	5/8	24

"

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:42Z
Check the source to verify that this is the current version before use.

PAGE 9

Paragraphs 4.4.4 and 4.4.5: Delete and substitute 4.4.4:

"4.4.4 Performance test for type VIII, classes A, B, or C punches. The sample punches shall be tested by placing the punch end against an anvil or hardened piece of steel and striking the head end six times while in the vertical position with the applicable machinist hammer (see table below).

For class A punches; (see table V)	sizes 1, 2, and 3; use 6 oz. hammer
	sizes 4, 5, 10, and 6; use 10 oz. hammer
	sizes 7, 8, and 9; use 14 oz. hammer
For class B punches; (see table VI)	sizes 0, 1, and 1a; use 4 oz. hammer
	sizes 1, 2, and 3; use 8 oz. hammer
	sizes 4, 5, and 6; use 16 oz. hammer
For class C punches; (see table VII)	sizes 1, 1a, and 2; use 8 oz. hammer
	sizes 3, 4, and 5; use 1 lb. hammer
	sizes 6 and 8; use 1-1/2 lb. hammer

Punches shall demonstrate the ability to resist breakage, deformation, spalling, or cracking."

Paragraph 4.4.6: Delete and substitute:

"4.4.6 Performance test for type X, prick punch. Sample punches shall be tested under service conditions on steel plate (free of scale) at least 1/8 inch thick with a hardness between 25 and 30 on the Rockwell "C" scale. A machinists' hammer in accordance with table XB shall be used and the test punch struck as squarely as possible with at least 25 (light to medium) blows producing at least 10 different indentations in the test bar. Punches shall be considered to have failed if either the striking end or point breaks, deforms, dulls, spalls, or cracks during this test.

TABLE XB.

Punch size	Body size	Hammer weight
	Inches	Ounces
1	1/4	8
1A	5/16	8
2	3/8	16
3	1/2	16

"

PAGE 11

Following paragraph 4.4.10, insert new paragraph 4.4.11 as follows:

"4.4.11 Drop test. Each of the sample boxes (complete with tools) selected in accordance with 4.2, shall be dropped to land on its base five times by free fall from a height of four feet onto a concrete floor or slab. At completion of this test, the box and method of holding the contents in place shall not show damage that will be detrimental to use or serviceability."

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:42Z
Check the source to verify that this is the current version before use.

Paragraph 6.1, subsection "(e)": Delete and substitute:

"(e) Whether sets shall be furnished in wooden boxes, plastic boxes, fabric wraps, plastic wraps, or rolls (see 3.7.1)."

Paragraph 6.2: Delete in its entirety.

GSA GC 14-364

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:42Z
Check the source to verify that this is the current version before use.