INCH-POUND

A-A-54793
8 January 1993

COMMERCIAL ITEM DESCRIPTION

BOXES, SETUP (Mailing, Dental)

The General Services Administration has authorized the use of this Commercial Item Description as a replacement for Military Specification MIL-B-37173 which is cancelled.

This Commercial Item Description covers paperboard setup boxes of the full telescoping design, for use in mailing dental products.

Salient characteristics:

Shall be assembled paperboard setup boxes, suitable for dental laboratories to mail dental models, try-ins, and finished prosthetic products.

Shall be of the following sizes (length x depth x height) as specified (see Table I and "Ordering data"):

Size 1. Large size - 6 x 4 x 3-3/4 inches

Size 2. Small size - 4-1/8 x 3-7/16 x 2-9/16 inches

Shall be of full telescoping design. Each box shall consist of a base and a telescoping cover. The base and telescoping cover shall each be of one piece construction from paperboard blanks that are cut and scored to provide the required size. The paperboard used shall be laminated kraftboard with a 0.056 to 0.062 inch thickness. The paperboard shall be composed of natural sulfate fiber or a composition of 70% sulfate and 30% reworked kraft. The minimum bursting strength of the paperboard shall be 300 points based on testing procedures included in the Quality Assurance Provisions segment of this document.

AMSC N/A FSC 8115

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:38Z
Check the source to verify that this is the current version before use.

Shall provide boxes with inside dimensions for the base component as specified in Table I:

Table I. Inside dimension of base (inches ± 10%)

Size	Length	Depth	Height
1	6	4	3-3/4
2	4-1/8	3-7/16	2-9/16

The inside dimensions of the telescoping cover for each specified size base shall be similar to the outside dimensions of the base.

Shall provide box components (base and telescoping cover) that are assembled from paperboard blanks that are crease-scored to give additional strength. The scoring applied to the paperboard shall not cut the paperboard surface. The box components shall be constructed and assembled with joints that are either butted or lapped as herein after specified. Metal fasteners shall be used and clinched to secure the butted or lapped joints. The metal fasteners shall be suitably protected from corrosion.

Shall provide boxes with butted joints that are constructed and assembled so that the edges (for both base and cover components) meet at their joints and are secured by means of metal edge stays. The metal stays shall extend 1/8 to 1/4 inch from the ends of the joints.

Shall provide boxes with lapped joints that are constructed and assembled in accordance with the following:

The base component includes flaps that are extensions of the ends and are crease-scored to fold and meet at the inside center of the sides along the long dimension without overlapping. The flaps on each side shall be secured to the side by means of at least three staples. A staple shall be applied near each corner, and the third staple shall be applied in the middle to overlap both ends of the flaps and fasten them together.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:38Z
Check the source to verify that this is the current version before use.

The cover component includes flaps that are extensions of the sides and are crease-scored to fold and meet at the inside center of the ends without overlapping. The flaps on each end shall be secured to the ends by means of at least three staples. A staple shall be applied near each corner, and the third staple shall be applied in the middle to overlap with both ends of the flaps and fasten them together.

Shall provide telescoping covers that include a thumb notch or cutout on opposite sides along the long dimension. The exterior of the telescoping cover shall be permanently and legibly marked with the name or registered trademark of the manufacturer, the box size, and the words "RE-USE CONTAINER".

Workmanship. The setup boxes shall be free from defects which detract from their appearance or impair their serviceability.

Unit. Each (EA). One box, of the size specified, constitutes one unit.

QUALITY ASSURANCE PROVISIONS.

Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of three years after delivery of the supplies to which such records relate.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:38Z
Check the source to verify that this is the current version before use.

Inspection. Inspection, as used herein, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

Examination and Testing. Examination and testing shall be conducted on the setup boxes in accordance with commercial practice. The sampling for examination and testing shall be in accordance with commercial practice.

Testing for bursting strength. Testing shall be conducted to determine the bursting strength of the paperboard being supplied.

Sampling for testing. Sampling for testing of the paperboard shall be in accordance with MIL-STD-105 and an S-1 inspection level. The unit of product shall be the paperboard which shall be traceable to a specific lot number.

Conditioning of samples. Before testing the paperboard samples shall be conditioned to atmospheric conditions as indicated in TAPPI T402os.

Apparatus. Based on using Mullen or Cady type apparatus, the bursting strength test shall consist essentially of clamping a paperboard sample and applying hydraulic pressure so as to burst a hole through the paperboard. The fiberboard sample shall be clamped between two surfaces having concentric circular apertures of approximately one (1) square inch area (1.20 inch diameter). Hydraulic pressure shall be applied through a rubber diaphragm, that is secured to one of the circular apertures so as to burst a hole through the paperboard sample exposed to the opening. The pressure required to burst the paperboard sample shall be recorded by means of a pressure gauge calibrated to read in pounds per square inch. The testing apparatus shall be hand or motor driven, and the hydraulic system shall be filled with glycerine and maintained free from entrapped air when in use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:38Z
Check the source to verify that this is the current version before use.

Testing procedure. The pre-conditioned paperboard sample shall be firmly clamped to the testing apparatus to prevent slipping. The bursting strength of the paperboard sample shall be determined by applying pressure by action of a motor drive or a handwheel. Six punctures shall be made, three from each side of the board. If a paperboard sample slips during testing, the results of that testing shall be disregarded. The average of six testing results determined for each sample shall not be less than 300 points. The acceptance number shall be zero if the average bursting strength on any sample falls below 300 points.

Alternate testing. Testing procedures and apparatus, different from those specified herein, may be used for determining bursting strength if they provide the equivalent quality assurance to that which is specified. The contracting officer has the option of accepting or rejecting the alternate testing. If the contracting officer determines that the alternate testing does not represent acceptable quality assurance, the test procedures set forth herein shall be applicable.

Metric products. Products manufactured to metric dimensions will be considered on an equal basis with those manufactured using inch-pound units, providing they fall within the tolerances specified using conversion tables contained in the latest revision of Federal Standard No. 376, and all other requirements of this document are met.

If a product is manufactured to metric dimensions and those dimensions exceed the tolerances specified in the inch/pound units, a request should be made to the contracting officer to determine if the product is acceptable.

The contracting officer has the option of accepting or rejecting the product.

Contractor Certification. The contractor shall certify and maintain substantiating evidence that the product offered meets the salient characteristics of this Commercial Item Description, and that the product conforms to the producers' own drawings, specifications, standards, and quality assurance practices. The government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:38Z
Check the source to verify that this is the current version before use.

Regulatory requirements.

Federal Food, Drug, and Cosmetic Act. If the product covered by this document has been determined by the U.S. Food and Drug Administration to be under its jurisdiction , the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of the Federal Food, Drug, and Cosmetic Act, as amended, and regulations promulgated thereunder. In addition, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of all other applicable Federal, State, and local statutes, ordinances, and regulations.

Recovered material. The offeror/contractor is encouraged to use recovered material in accordance with Federal Acquisition Regulation Subpart 23.4 to the maximum extent practical.

Preservation, packaging, packing, labeling, and marking. Unless otherwise specified, preservation, packaging, and packing shall be to a degree of protection to preclude damage to containers and/or contents thereof under normal shipping conditions, handling, etc., involving shipment from the supply source to the receiving activity, plus reshipment from receiving activity, and shall conform to applicable carrier's rules and regulations. Intermediate and exterior package quantities and labeling and marking shall be as specified in the contract and/or order.

Other publications.

Technical Association of the Pulp and Paper Industry (TAPPI)

TAPPI T402os	Standard Conditioning and Testing Atmospheres for Paper, Board, Pulp Handsheets and Related Products.

(Application for copies should be addressed to the Technical Association of the Pulp and Paper Industry, Dunwoody Park, Atlanta, GA 30341.)

Ordering data. (Size box required, intermediate/exterior package quantities, labeling, and marking must be specified in the contract and/or order.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:38Z
Check the source to verify that this is the current version before use.

NOTE: The following National Stock Numbers are covered by this document:

NSN	Item Identification
8115-00-511-5750	BOX, SETUP, Mailing, Dental, Large.
8115-00-511-5751	BOX, SETUP, Mailing, Dental, Small.

MILITARY INTERESTS:

Custodians:

Army-MD
Navy-MS
Air Force-03

PREPARING ACTIVITY:

DoD-MB

Agent:

DLA-DM

CIVIL AGENCY COORDINATING ACTIVITIES:

VA-OSS
USPHS
FDA-MPQAS

Project No. 8115-0538

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:38Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8 In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	1. DOCUMENT NUMBER A-A-54793	2. DOCUMENT DATE (YYMMDD) 8 JANUARY 1993

3. DOCUMENT TITLE
BOXES, SETUP (MAILING, DENTAL)

4. NATURE OF CHANGE *(Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)*

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle Initial)	b. ORGANIZATION	
c. ADDRESS (Include Zip Code)	d. TELEPHONE (Include Area Code) (1) Commercial (2) AUTOVON (If applicable)	7. DATE SUBMITTED (YYMMDD)

8. PREPARING ACTIVITY

a. NAME	b. TELEPHONE (Include Area Code) (1) Commercial (2) AUTOVON
c. ADDRESS (Include Zip Code)	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT: Defense Quality and Standardization Office 5203 Leesburg Pike, Suite 1403, Falls Church, VA 22041-3466 Telephone (703) 756-2340 AUTOVON 289-2340

Source: https://assist.dla.mil - Downloaded: 2026-10-26T09:38Z
Check the source to verify that this is the current version before use.