P-P-556d
May 7, 1963

SUPERSEDING
Int. Fed. Spec. P-P-00556c (Army-QMC)
November 1, 1961 and
Fed. Spec. P-P-556a
April 4, 1939

FEDERAL SPECIFICATION

POLISH, METAL

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers polishes for use on copper, brass, nickel and chrome (see 6.1).

1.2 Classification.

1.2.1 *Types and classes.* Metal polish shall be of one grade and of the following types and classes, as specified (see 6.2):

Type II.—Liquid
- Class 1—Strong acting
- Class 2—Mild acting

Type III.—Paste
- Class 1—Strong acting
- Class 2—Mild acting

2. APPLICABLE SPECIFICATIONS, STANDARDS, AND OTHER PUBLICATIONS

2.1 Specifications and standards. The following specifications and standards, of the issues in effect on date of invitations for bids, form a part of this specification to the extent specified herein.

Federal Specification:

PPP-C-96—Cans, Metal, 28 Gage and Lighter.

Federal Standards:

Fed. Std. No. 102—Preservation, Packaging, and Packing Levels.

Fed. Std. No. 123—Marking for Domestic Shipment (Civilian Agencies).

Fed. Test Method Std. No. 141—Paint, Varnish, Lacquer, and Related Materials: Methods of Inspection, Sampling, and Testing.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications, Standards and Handbooks at the prices listed in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington 25, D. C.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Washington, D. C., Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, and Auburn, Washington.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications, Standards, and Handbooks from established distribution points in their agencies.)

FSC 7930

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:17Z
Check the source to verify that this is the current version before use.

Military Standards:

MIL-STD-105—Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129—Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement function should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following document forms a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitations for bids shall apply.

American Society For Testing And Materials Standard:

D-1172-56—Method of Test for pH of Aqueous Solutions of Soaps and Detergents.

(Copies of ASTM Standards may be obtained from the American Society for Testing and Materials, 1916 Race Street, Philadelphia 3, Pennsylvania.)

3. REQUIREMENTS

3.1 Material. Polishes shall contain suitable cleaning agents and finely divided abrasives.

3.1.1 *Non-acceptable materials.* The metal polishes shall not contain benzol or chlorinated hydrocarbon solvents, mineral acids, cyanides, grit, or other ingredients having a detrimental effect on metals.

3.1.1.1 *Certification.* A certificate shall be submitted by the contractor to the contracting officer verifying that the product which he intends to furnish shall contain no benzol or chlorinated hydrocarbon solvents, mineral acids, or other ingredients which would have a detrimental or corrosive effect on the specific metals to be polished. The certificate shall be accompanied by actual test, inspection, or other verifiable quality data.

3.2 Form and stability.

3.2.1 *Type II.* Type II polish shall be a uniform liquid and shall not contain any sediment that cannot be readily put into suspension by thorough shaking as specified in table II.

3.2.2 *Type III.* Type III polish shall be a uniform paste free from lumps and shall show no liquid separation when tested as specified in table II.

3.3 Chemical and physical requirements. The polish shall conform to the requirements shown in table I when tested as specified in table II.

TABLE I. *Chemical and physical requirements*

Properties	Type II				Type III	
	Class 1		Class 2		Classes 1 and 2	
	Minimum	Maximum	Minimum	Maximum	Minimum	Maximum
Matter nonvolatile at 105°C. percent	25	—	7	—	30	—
pH value	2.2	10.5	2.2	10.5	2.2	10.5
Abrasive content, percent	18.0	—	4.0	—	25.0	—
Fineness; percent of material passing thru:						
No. 200 sieve	100	—	100	—	100	—
No. 270 sieve	99	—	99	—	99	—
Flash point	100°	—	100°	—	100°	—
Cyanides	None		None		None	

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:17Z
Check the source to verify that this is the current version before use.

3.4 **Performance.**

3.4.1 *Polishing capability (types II and III, classes* 1 *and* 2). The polish shall produce an initial gloss of not less than 550 gloss units when tested as specified in table II.

3.4.2 *Tarnish removal and metal weight loss due to polishing.*

3.4.2.1 *Types II and III, class* 1. The polish shall remove tarnish and produce a gloss of not less than 550 gloss units in 200 revolutions and the weight loss shall not exceed 0.08 gram when tested as specified in table II.

3.4.2.2 *Types II and III, class* 2. The polish shall remove tarnish and produce a gloss of not less than 550 gloss units in 800 revolutions and the weight loss shall not exceed 0.05 gram when tested as specified in table II.

3.4.3 *Chemical activity.*

3.4.3.1 *Chemical activity on tarnished brass (types II and III, class* 1). The polish shall produce a gloss not less than 100 gloss units when tested as specified in table II.

3.4.3.2 *Chemical activity on untarnished brass (types II and III, classes* 1 *and* 2). The polish shall not reduce the gloss more than 20 gloss units and the weight loss shall not exceed 0.0010 gram when tested as specified in table II.

3.4.4 *Gloss retention (types II and III, classes* 1 *and* 2). Polished brass panels shall retain 95 percent of the gloss when tested as specified in table II.

3.5 **Workmanship.**

3.5.1 *Type II.* Type II polish shall be a clean homogeneous mixture in liquid form.

3.5.2 *Type III.* Type III polish shall be a clean uniform mixture in paste form.

3.6 **Quality.** The quality of the metal polish shall conform to the levels established herein. The occurrence of defects shall not exceed the number permitted under the acceptable quality levels (AQLs) specified in section 4 for any examinations and tests of materials, components and end item, as applicable.

4. SAMPLING, INSPECTION, AND TEST PROCEDURES

4.1 **Responsibility for inspection.** Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.2 **Sampling for inspection and tests.** Sampling for inspection and tests shall be in accordance with the provisions of MIL-STD-105, except where otherwise indicated. For purposes of sampling for inspection, a lot shall consist of all material of the same type, form, and construction from the same manufactured batch.

4.2.1 *Inspection of components and materials.* In accordance with 4.1 the supplier shall be responsible for insuring that the quality assurance provisions for components or materials shall be in accordance with this specification and with referenced subsidiary specifications to the extent applicable. In the event of conflict, this specification shall govern.

4.3 **Inspection of the end item.**

4.3.1 *Examination of the end item.* The end item shall be examined in accordance with the classification of defects in the applicable sub-paragraphs at the inspection levels (AQLs) set forth in 4.3.1.5. Random

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:17Z
Check the source to verify that this is the current version before use.

samples shall be drawn from each lot of end items in the same size container for examination for visual, contents and preparation for delivery defects. The lot size for purposes of determining the sample size, in accordance with MIL-STD-105, shall be expressed in units of filled primary containers of the same capacity, consisting of metal polish manufactured in one batch for the examination in 4.3.1.1, 4.3.1.2 and 4.3.1.3, and in units of shipping containers for examination under 4.3.1.4.

4.3.1.1 *Examination of the primary container.* The sample unit for this examination shall be one filled primary container.

Examine	Defect
Construction	Not type specified (see 5.1).
Closure	Not type specified; imperfect.
Seal	No inner seal (see 5.1.1.1).
Exterior coating	Not as specified (see 5.1.1.1).
Workmanship	Dented, dirty; any other defect affecting serviceability; any leaking of contents.
Markings	Missing, incomplete, incorrect, not as specified (see 5.3.1).

4.3.1.2 *Examination of contents of the primary container.* The sample unit for this examination shall be the contents of one filled primary container.

Examine	Defect
Workmanship	Not clean, contains foreign material.

4.3.1.3 *Examination of the end item for net contents.* The sample unit for this examination shall be one filled primary container. The average net contents per container shall be not less than specified or indicated for all sample units examined.

4.3.1.4 *Examination of the end item for defects in preparation for delivery.* An examination shall be made to determine that markings, materials, workmanship and contents comply with the requirements of section 5 of this specification. The sample unit shall be one shipping container, fully packed, selected just prior to the closing operation. Closed shipping containers, fully prepared for delivery shall be examined for closure defects.

Examine	Defect
Markings	Incorrect, incomplete, illegible, omitted; of improper size, sequence, or method of application; not in accordance with contract requirements.
Material	Any nonconforming component; component missing, damaged, or otherwise defective, affecting serviceability.
Workmanship	Inadequate application of components such as: Incomplete closure of case liners, container flaps; loose or inadequate sealing, strapping, or stapling.
	Bulged or distorted containers.
Contents	Number of intermediate packages per shipping container is more or less than required.
	Number of primary containers per intermediate package is less than specified.

4.3.1.5 *Inspection levels and acceptable quality levels (AQLs) for examinations.* The inspection levels and the acceptable quality levels (AQLs) expressed in defects per 100 units shall be as follows:

Examination paragraph	Inspection level	AQL
4.3.1.1	I	2.5
4.3.1.2	I	2.5
4.3.1.3	L-4	—
4.3.1.4	L-4	4.0

4.3.2 *Testing of the end item.* The end item shall be tested for the characteristics specified in table I in accordance wth test methods specified in table II. The lot size for test purposes shall be the number of containers of the same type filled with metal polish of the same type and class from a single manufactured batch. The sample unit shall be 1 quart of type II or 1 pound of type III polish. The sample size shall be five. Each sam-

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:17Z
Check the source to verify that this is the current version before use.

TABLE II. *Instructions for testing of end item*

CHARACTERISTIC	Specification reference		Requirements applicable to		Number determinations per unit sample	Results reported as	
	Requirement	Test method paragraph	Sample unit	Lot aver.		Pass or fail[1]	Numerically to nearest[2]
Matter nonvolatile at 105°C., percent	Table I	4.4.1	X		1		1
pH value	Table I	4.4.2	X		1		0.1
Abrasive content, percent	Table I	4.4.3	X		1		1
Fineness of abrasive:							
Material passing No. 200 sieve, percent	Table I	4.4.4	X		1	X	
Material passing No. 270 sieve, percent	Table I	4.4.4	X		1		1
Flash point °F.	Table I	4.4.5	X		1		1
Cyanides	Table I	4.4.8	X		1	X	
Form and stability	3.2	4.4.7	X		1	X	
Polishing capability:							
Types II and III, class 1 and 2	3.4.1	4.4.6.4	X		1		
Tarnish removal and metal weight loss due to polishing:							
Types II and III, class 1	3.4.2.1	4.4.6.6.1	X		1		1 gloss unit and 0.01g
Types II and III, class 2	3.4.2.2	4.4.6.6.2	X		1		1 gloss unit and 0.01g
Chemical activity on tarnished brass:							
Types II and III, class 1	3.4.3.1	4.4.6.8	X		1		1 gloss unit
Chemical activity on untarnished brass							
Types II and III, classes 1 and 2	3.4.3.2	4.4.6.9	X		1		1 gloss unit and 0.001g
Gloss retention:							
Types II and III, classes 1 and 2	3.4.4	4.4.6.7	X		1		1

[1] If failure is indicated, report description of numerical point of failure, applicable.
[2] Test reports shall include all values on which results are based.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:17Z
Check the source to verify that this is the current version before use.

ple shall be taken from a different container. A single determination shall be made on each sample unit for all characteristics. The lot shall be unacceptable if there is any evidence of failure to meet any characteristic applicable to the sample unit.

4.4 Test procedures.

4.4.1 *Nonvolatile matter.* Accurately weigh 12-15 grams of polish in a tared flat bottom dish about 8 cm. in diameter provided with a tightly fitted cover. Remove the cover and place sample over a steam bath until the bulk of volatile matter has evaporated, and then place in an oven maintained at 100° ± 2.5°C. for 4 hours. Cool in a dessicator, replace cover and weigh residue. Repeat the drying until weight is constant. Calculate percent nonvolatile matter as follows:

$$\text{Percent nonvolatile matter} = \frac{\text{weight of residue}}{\text{weight of polish}} \times 100$$

4.4.2 *pH.* Type II polish shall be tested undiluted and type III as a 50 percent dispersion in distilled water. Determine pH with a suitable pH meter in accordance with ASTM Standard D1172-56.

4.4.3 *Abrasive content.* Accurately weigh 10-12 grams of polish in a tared centrifuge tube. Dilute and disperse polish to 100 ml. with hot alcohol or hot distilled water and then centrifuge at approximately 2000 r.p.m. for 5 minutes. Decant liquid carefully so as not to lose solid matter. Repeat twice the above procedure of dilution, dispersion, centrifuging and decanting. Following the third treatment, place residual solids in an oven maintained at 100° ± 2.5°C. for 4 hours. Cool in a dessicator and weigh residue. Repeat the drying until weight is constant. Calculate percent abrasive matter as follows:

$$\text{Percent abrasive content} = \frac{\text{weight of residue}}{\text{weight of polish}} \times 100$$

4.4.4 *Sieve test.* Weigh approximately 50 grams of the polish and place into an 800-ml. beaker. Dilute polish to 500 ml. with hot alcohol or hot distilled water, cover with a watchglass and digest on a steam bath for 1 hour. Vigorously stir to disperse solid matter and pour liquid and solid matter through a No. 200 sieve and then wash with hot distilled water. Determine visually if all solid matter passes through the No. 200 sieve. Repeat above procedure with another sample of polish and pass through a No. 270 sieve. Wash material retained on No. 270 sieve with hot distilled water until no more solids pass through. Dry sieve contents at 100° ± 2.5°C. for 1 hour, cool and transfer solid particles to a tared container. Weigh and calculate percent passing through the No. 270 sieve as follows:

$$\text{Percent passing through No. 270 sieve} = \frac{\text{Sample weight — weight retained on No. 270 sieve}}{\text{sample weight}} \times 100$$

4.4.5 *Flash point.* The flash point (open cup) shall be determined on the sample in accordance with method 4294 of Fed. Test Method Std. No. 141.

4.4.6 *Performance.*

4.4.6.1 *Test materials.*

4.4.6.1.1 *Test panels.* Smooth, half hard, yellow brass panels, each 2 inches in diameter and 1/4 inch thick shall be used. The yellow brass alloy shall consist of 64 to 68 percent copper and the remainder zinc and shall have a hardness of 72 to 78 on the Rockwell B scale.

4.4.6.1.2 *Wool cloth.* Cloth, (see 6.5.1), 100 percent virgin wool, unbleached, weighing approximately 6 ounces per square yard.

4.4.6.2 *Test equipment.*

4.4.6.2.1 *Polishing apparatus.* The polishing apparatus (Schiefer Abrasion Machine or equivalent) (see 6.5.2) shall abrade a

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:17Z
Check the source to verify that this is the current version before use.

plane area of a specimen uniformly from every azimuthal direction. The apparatus shall consist essentially of a motor, a belt drive-gear mechanism through which the motor rotates two shafts with approximately the same angular velocity, 250 r.p.m., each about its axis. The axes are spaced 1 inch apart and are parallel. One shaft rotates the abradant while the other rotates the specimen in the same direction but at a slightly different speed which prevents the same element of the abradant from acting on the same area of the specimen during each rotation. The weight of the abradant upon the specimen shall be 6.5±0.5 pounds. (This includes weight of abradant accessory and cloth.)

4.4.6.2.2 *Polishing apparatus attachments.*

4.4.6.2.2.1 *Abradant accessory.* This attachment (see 6.5.2.1) shall be capable of firmly holding a circular piece of cloth approximately 5-1/4 inches in diameter. The attachment shall include a screw device by which the attachment can be readily connected to the abradant shaft of the Schiefer Abrasion Machine.

4.4.6.2.2.2 *Specimen accessory.* This attachment (see 6.5.2.1) shall be capable of firmly holding a 2 inch diameter, 1/4 inch thick, brass disk and contain a screw device by which the attachment can be readily connected to the specimen shaft of the Schiefer Abrasion Machine.

4.4.6.2.3 *Glossmeter.* A glossmeter (Photovolt Glossmeter Model 660 or equivalent, see 6.5.3) capable of measuring the 45 degree specular gloss of metallic surfaces in the range of 0 to 700 gloss units (in terms of a perfect mirror as 1000 gloss units) by proper standardization.

4.4.6.3 *Preparation of test panels.* Eight brass disks (2 inch diameter) shall be hand polished using either the test polish or another effective metal polish until all etchings or other marks have been removed.

4.4.6.4 *Initial polishing of test panels.* A clean 5-1/4 inch circle of wool cloth shall be attached to the abradant shaft accessory. There shall be no wrinkles in the fabric surface. Attach a prepared untarnished brass disk (4.4.6.3) to the specimen shaft accessory. Place 1 ml. of metal polish on the brass disk and lower the abradant shaft until the woolen cloth is resting on the brass specimen. Set the Schiefer Machine counter to zero and commence polishing. The polishing operation shall be interrupted every 50 revolutions and 1 ml. of polish shall be applied to the brass panel until a total of 500 revolutions have been completed. The brass panel shall then be removed from the specimen shaft accessory and wiped free of polish with a clean piece of wool followed by washing with soap and warm water and then dried with soft tissue paper. The above procedure shall be repeated for each of the eight brass test panels except that two of the polished panels shall be wiped clean with a dry woolen cloth and shall not be washed or rinsed with water. These panels shall be used for gloss retention as specified in 4.4.6.7.

4.4.6.4.1 *Gloss of polished panels.* The gloss of the eight polished test panels shall be determined in accordance with 4.4.6.4.2. Average the values to obtain a gloss value.

4.4.6.4.2 *Gloss determinations.* Specular gloss (45 degree) determinations shall be accomplished with the Photovolt Glossmeter Model 660 including the 45-degree 660M Search Unit or equivalent. It is preferable to standardize the Glossmeter using a high gloss working standard consisting of a mirror of reasonable stability. If such a mirror is not available, the Carrara black gloss standard furnished with the Photovolt 660M Search Unit can be used for standardizing the glossmeter in accordance with the Photovolt operating instructions. The glossmeter standardization shall be checked with the standard before each gloss determination. All gloss readings shall be taken at approximately the center of each test panel.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:17Z
Check the source to verify that this is the current version before use.

4.4.6.5 *Tarnishing of test panels.* Four panels, polished as specified in 4.4.6.4 shall be uniformly tarnished by exposure to wet ammonia vapors under controlled conditions. Ten ml. of concentrated ammonium hydroxide (28-30 percent NH_3) shall be mixed with thirty ml. of warm distilled water so that the final temperature of the solution is 100° ± 1°F. This solution shall be poured into a 180-ml. electrolytic high-form beaker, or other glass container approximately 2 inches in diameter and 4-1/2 inches high. The beaker shall be placed in a constant temperature bath maintained at 100° ± 1°F. such that the level in the bath is between 1/2 to 1 inch of the top of the beaker. The brass panel previously immersed in distilled water at 100°F. to attain the same temperature shall be quickly wiped dry with soft tissue paper and then shall be placed polished side down over the mouth of the beaker of ammonium hydroxide. The specimen shall remain exposed to the ammonia vapors for 150 seconds. The specular gloss of the tarnished brass shall not exceed 5 gloss units when measured as specified in 4.4.6.4.2. Weigh the tarnished brass panel to 0.0001 gram. This tarnishing procedure shall be repeated for each of the four panels using a freshly prepared ammonia solution for each of the panels.

4.4.6.6 *Tarnish removal and gloss restoration.* A tarnished panel, 4.4.6.5, and piece of clean wool cloth shall be attached to the Schiefer Abrasion Machine in accordance with the procedure outlined in 4.4.6.4. Two tarnished panels shall be polished as follows:

4.4.6.6.1 *Types II and III, class* 1 *metal polishes.* Each panel shall be polished for a total of 200 revolutions, interrupting the polishing operation every 50 revolutions and applying 1 ml. of test polish to the specimen surface.

4.4.6.6.2 *Types II and III, class* 2 *metal polishes.* Each panel shall be polished for a total of 800 revolutions, interrupting the polishing operation every 50 revolutions and applying 1 ml. of test polish to the specimen surface. Determine the gloss of both panels, in accordance with 4.4.6.4.2 and average the results to obtain a gloss value. Weigh each panel and determine the weight loss as the difference in weight between the tarnished panel and the polished panel. Average the weight loss of the two panels.

4.4.6.7 *Gloss retention.* Average the gloss readings of the two polished unwashed panels, prepared as outlined in 4.4.6.4, and age the two panels in a dessicator over anhydrous calcium chloride for 24 hours. Determine the gloss of each panel, in accordance with 4.4.6.4.2 and then average the gloss values. Calculate the gloss retention as follows:

$$\text{Percent gloss retention} = \frac{\text{Average specular gloss after aging (see 4.4.6.7)}}{\text{Average specular gloss before aging (see 4.4.6.4)}} \times 100$$

4.4.6.8 *Chemical activity on tarnished panels, types II and III, class* 1. Lightly spread approximately 5 ml of polish over the surface of a tarnished panel, prepared in accordance with 4.4.6.5, and allow to stand at room temperature (68°-80°F.) for 60 minutes. Wash polish from the panel in a stream of hot tap water, lightly brushing with a camels hair brush to facilitate polish removal. Then wash panel clean with soap and water and dry with soft tissue paper. The above procedure shall be used for each of two tarnished panels. Determine the gloss of each panel, in accordance with 4.4.6.4.2 and average the results.

4.4.6.9 *Chemical activity on polished, untarnished panels, (types II and III), (classes* 1 *and* 2). Determine the weight of two polished panels, prepared as outlined in 4.4.6.4, and repeat the treatment as described in 4.4.6.8. After drying determine the gloss of each treated panel in accordance with the method described in 4.4.6.4.2 and then average the values. Weigh each panel and de-

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:17Z
Check the source to verify that this is the current version before use.

termine the weight loss as the difference in weight between the polished panel and the chemically acted upon panel, 4.4.6.9. Average the weight losses of the two panels.

4.4.7 *Form and stability.* In the case of type II polish, the containers as received in the laboratory shall be allowed to stand at rest for 24 hours, after which they shall be thoroughly shaken and the contents poured into glass bottles and the containers examined for presence of any caked abrasive material which remains therein. The glass bottles shall be corked and thoroughly shaken and the polish observed for uniformity. Type III polish samples shall be examined for uniformity and liquid separation.

4.4.8 *Cyanides.* A mixture containing 5 ml. of polish and 5 ml. of distilled water shall be tested with litmus paper. If necessary, add sodium hydroxide solution to make the mixture alkaline. Then add three drops each of ferrous sulfate and ferric chloride (10 percent solutions) mix and heat to a temperature of 120°F. in a hot water bath. Make the mixture acid to litmus by the addition of hydrochloric acid. If cyanides are present a blue precipitate is formed.

5. PREPARATION FOR DELIVERY

(Fed. Std. No. 102 shall be referred to for definitions and application of the various levels of packaging and packing for civil agency procurements.)

5.1 Packaging. Packaging shall be level A or C, as specified (see 6.3 and 6.6).

5.1.1 *Level A.*

5.1.1.1 *Type II.* The liquid metal polish shall be furnished in 1 pint, 1 quart, or 1 gallon (see 6.3) oblong cans conforming to type V, class 4 with inner seal, exterior coating plan A of PPP-C-96, except that 0.25-pound electrolytic tinplate, ternplate, or blackplate shall not be used. One pint cans shall be packaged in accordance with the interior packaging requirements in the Appendix of PPP-C-96.

5.1.1.2 *Type III.* The paste metal polish shall be furnished in 2 ounce or 1 pound (see 6.3) round cans conforming to type V, class 1 or 2, exterior coating plan A of PPP-C-96, except that 0.25-pound electrolytic tinplate, ternplate, or blackplate shall not be used. The filled cans of polish shall then be packaged in accordance with the interior packaging requirements in the Appendix of PPP-C-96.

5.1.2 *Level C.* The metal polish shall be packaged in accordance with the industry's practice.

5.2 Packing. Packing shall be level A, B, or C, as specified (see 6.3).

5.2.1 *Level A.* Metal polish of one type and class, packaged as specified in 5.1, shall be packed in fiberboard shipping containers in accordance with the overseas packing requirements in the Appendix of PPP-C-96.

5.2.2 *Level B.* Metal polish of one type and class, packaged as specified in 5.1, shall be packed in fiberboard shipping containers in accordance with the domestic packing requirements in the Appendix of PPP-C-96.

5.2.3 *Level C.* Metal polish, packaged as specified in 5.1 shall be packed in a manner to insure carrier acceptance and safe delivery at destination at the lowest transportation rate for such supplies. Containers shall be in accordance with rules or regulations of carriers applicable to the mode of transportation.

5.3 Marking.

5.3.1 *Labeling.* Unit containers shall be provided with clear and concise instructions for the use of the polish including the precautionary words "NOT FOR USE ON ALUMINUM AND SILVER". In addition, the

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:17Z
Check the source to verify that this is the current version before use.

statement "CAUTION-COMBUSTIBLE MIXTURE" in 10-point type (minimum) shall appear on the label for the products having flash points from 100° to 300°F.

5.3.2 *Civil agencies.* In addition to the labeling specified in 5.3.1 and any special marking required by the contract or order, interior packages and shipping containers shall be marked in accordance with Fed. Std. No. 123.

5.3.3 *Military requirements.* In addition to the labeling specified in 5.3.1 and any special marking required by the contract or order, interior packages and shipping containers shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 Intended use. Metal polish covered by this specification is intended for general cleaning and polishing of copper, brass, chrome, and nickel but not aluminum or silver. Class 1 polish is intended for use on heavily tarnished surfaces or where a minimum of effort is desired. Class 2 polish is intended for use on lightly tarnished surfaces where a mild action is desired.

6.2 Deletion data. Type I, powder polish has been deleted from this specification because of lack of interest in the item and the superior performance of the liquid and paste type polishes (types II and III).

6.3 Ordering data. Purchasers should exercise any desired options offered herein and procurement documents should specify the following:

(*a*) Title, number, and date of this specification.

(*b*) Type and class required.

(*c*) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).

(*d*) Quantity of liquid or paste polish desired (see 5.1.1.1 and 5.1.1.2).

6.4 Transportation description. Transportation descriptions and minimum weights applicable to this commodity are:

Rail:

Compound, polishing, not otherwise indexed by name.
Carload minimum weight 36,000 pounds.

Motor:

Compound polishing, not otherwise indexed.
Truckload minimum weight 36,000 pounds, subject to Rule 115, National Motor Freight Classification.

6.5 Testing materials and equipment.

6.5.1 *Wool cloth.* Cloth, wool, 100 percent virgin, unbleached. Appoximately 47 ends and 41 picks per inch and approximately 6 ounces per square yard. Botany, wool, Style 404 or equal.

6.5.2 *Polishing apparatus.* Schiefer Abrasion Testing Machine, Frazier Precision Instrument Company, 8913 Glenville Road, Silver Spring, Maryland.

6.5.2.1 *Polishing apparatus attachments.*

Abradant accessory—Accessory No. 4 in Schiefer Abrasion Testing Machine brochure.

Specimen accessory—attachment for holding 2 inch diameter specimens similar to accessory No. 8 in Schiefer Abrasion Testing Machine brochure.

6.5.3 *Glossmeter.* Photovolt Photoelectric Glossmeter Model 660 with the Photovolt 660M Search Unit. Photovolt Corporation, New York 10, New York.

6.6 For civil agencies. When level B packaging is required, level A packaging shall be specified.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:17Z
Check the source to verify that this is the current version before use.

Notice. When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

MILITARY CUSTODIANS:

Army—GL

Navy—Sh

Air Force—MOA

OTHER INTERESTS:

Army—M

Navy—Wep MC

//

Copies of this specification may be purchased f ents each.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:17Z
Check the source to verify that this is the current version before use.