P-P-567b

MAY 20, 1958

SUPERSEDING
Int. Fed. Spec. P-P-00567a(GSA-FSS)
June 15, 1956 and
Fed. Spec. P-P-567
June 23, 1943

FEDERAL SPECIFICATION

POLISH, SHOE; PASTE

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. — The polish covered by this specification is intended primarily for the cleaning and polishing of leather footwear and other leather articles.

1.2 Classification.

1.2.1 *Grade and type.*—The polish covered by this specification shall be of one grade and one type.

2. APPLICABLE SPECIFICATIONS, STANDARDS, AND OTHER PUBLICATIONS

2.1 Specifications and standards.—The following specifications and standards, of the issues in effect on date of invitation for bids, form a part of this specification.

Federal Specifications:

PPP-B-636—Boxes, Fiber.

Federal Standards:

Fed. Std. No. 102—Preservation, Packaging, and Packing Levels.

Fed. Std. No. 123—Marking for Domestic Shipment (Civilian Agencies).

Fed. Test Method Std. No. 791—Lubricants, Liquid Fuels, and Related Products; Methods of Testing.

(Activities outside the Federal Government may obtain copies of Federal Specifications and Standards as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington 25, D. C.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, Los Angeles, Seattle, and Washington, D. C.

(Federal Government activities may obtain copies of Federal Specifications and Standards and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standards:

MIL-STD-105 — Sampling Procedures and Tables for Inspection by Attributes.

MIL-STD-129 — Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring agency or as directed by the contracting officer.)

2.2 Other publications. — The following publication, of the issue in effect on date of invitation for bids, forms a part of this specification:

Consolidated Freight Classification Rules.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:18Z
Check the source to verify that this is the current version before use.

(Application for copies should be addressed to the Consolidated Classification Committee, 202 Chicago Union Station, Chicago 6, Ill.)

3. REQUIREMENTS

3.1 Material.—Shoe polish shall be a uniform blending of wax and suitable solvents to form a paste. The product shall be substantially free of lumpiness, granulation, grit, extraneous matter, and shrinkage.

3.2 Color.—Shoe polish shall be furnished in one of the following colors as specified: black, tan, brown, or oxblood.

3.3 Consistency. — The polish shall be a nonflowing smooth paste over a temperature range of 40° F. to 100° F. with not more than a few drops of solvent separating when tested as specified in 4.4.1.

3.4 Wax content.—The wax content shall be not less than 25 percent when tested as specified in 4.4.2.

3.5 Melting point of wax. — The melting point of the wax in the product shall be not less than 150° F. when tested as specified in 4.4.3.

3.6 pH value.—The pH value of a water extract of the polish tested as specified in 4.4.4 shall be not less than 5.0 nor more than 7.5.

3.7 Properties of the volatile solvents.

3.7.1 *Flash point.*—The volatile solvents tested as specified in 4.4.5 shall have a flash point not less than 90° F.

3.7.2 *Initial boiling point.*—The initial boiling point of the volatile solvents shall be not less than 290° F. when tested as specified in 4.4.6.

3.8 Performance.—The polish shall be capable of being readily applied to smooth leather, and the film left on the leather shall be capable of drying hard within 5 minutes. Buffing of the film shall produce a hard glossy surface free from any greasiness or stickiness when tested as specified in 4.4.7.

4. SAMPLING, INSPECTION, AND TEST PROCEDURES

4.1 Sampling for lot acceptance.

4.1.1 *Inspection lot.*—For purposes of sampling, a lot shall consist of all polish manufactured as one batch and offered for delivery at one time.

4.1.2 *Sampling for inspection of filled containers.*—A random sample of filled containers shall be taken from each lot by the Government inspector in accordance with Military Standard MIL–STD–105 at inspection level I and acceptable quality level (AQL) = 2.5 percent defective to verify compliance with all stipulations of this specification regarding fill, closure, marking, and other requirements not involving tests.

4.1.3 *Sampling for tests.*—From each inspection lot the Government inspector shall take 8 containers at random which shall be sealed, marked, and forwarded to the testing laboratory designated by the bureau or agency concerned.

4.2 Inspection.

4.2.1 *Inspection of filled containers.*—Each sample filled container selected in accordance with 4.1.2 shall be examined by the Government inspector for defects of the container and the closure, for evidence of leakage, and for unsatisfactory markings. Each sample filled container shall also be weighed to determine the amount of the contents. Any container in the sample having one or more defects, or under required fill, shall be rejected, and if the number of defective containers in any sample exceeds the acceptance number for the appropriate sampling plan of Military Standard MIL–STD–105 the lot represented by the sample shall be rejected. Rejected lots may be resubmitted for acceptance tests provided that the contractor has removed or repaired all nonconforming containers.

4.3 Lot acceptance tests. — The sample specimens selected in accordance with 4.1.3 shall be subjected separately to the tests

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:18Z
Check the source to verify that this is the current version before use.

specified in 4.4. If any specimen fails in one or more of these tests the lot shall be rejected. Rejected lots may be resubmitted for acceptance tests provided the contractor has removed or reworked all nonconforming products.

4.4 Test procedures.

4.4.1 *Consistency.*—An original container of polish shall be maintained at 40° F. for 2 hours. Examine and note whether any liquid has separated from the paste. Note whether the paste is soft and smooth to the touch and capable of readily being taken up with a brush or cloth without "crumbling". Tilt the container and note whether any of the material flows or "runs". Repeat the procedure specified above, using the same can of polish, except that the shoe polish shall be maintained at a temperature of 100° F. for 2 hours and note results as above. The separation of not more than a few drops of the liquid, which is reabsorbed when the paste is permitted to cool, shall be considered as meeting this test.

4.4.2 *Wax content.*—All of the polish from an original container shall be steam distilled. (The solvent which distills over shall be separated from the water in a funnel, then completely dehydrated by adding 1 gram anhydrous copper sulfate for each 5 ml. of solvent, shaking, and filtering through dry filter paper for use in the tests in 4.4.5 and 4.4.6.) The wax remaining in the still shall be freed of water by the following technique: Take up in chloroform (see note); separate in funnel from excess water; add 1 gram of anhydrous copper sulfate for each 5 grams of wax; pour off chloroform from the copper sulfate; wash the copper sulfate with two successive portions of chloroform which has previously been dried with anhydrous copper sulfate, using about 15 ml. for each wash and combine these washings with the main chloroform extract. Evaporate the chloroform and dry the residue of wax to constant weight.

Note.—Carbon tetrachloride may be used in lieu of chloroform.

4.4.3 *Melting point of wax.* — Bring the wax previously freed from water and solvent to a temperature slightly above its melting point. Dip a thermometer into the melted wax so that the bulb is completely covered. Remove the thermometer after 5 seconds, rotate slowly in a vertical position, and before the wax has quite solidified remove the excess drop of wax on the bottom of the bulb by touching it with the hand. After letting the wax on bulb solidify, place the thermometer in a test tube 6 x 1 inches and cork loosely so that the bulb is 1 inch from the bottom of the tube. Suspend the tube in a beaker of water so that the bottom of the tube is about 1 inch above the bottom of the beaker. Gradually raise the temperature of the water to about 15° below the probable melting point and then raise the temperature at a rate of 1° to 1½° per minute until a drop of clear wax forms on the bottom of the bulb. The temperature at which this occurs is the melting point.

4.4.4 *pH.*—Five grams of the shoe polish shall be added, with constant stirring to 100 ml. of freshly boiled distilled water in a beaker. Raise the temperature until wax is melted, stirring constantly for 10 minutes. Cool the mixture to 25° C. ± 5°, pour off the water from the cake of solidified wax and measure its pH with a glass electrode.

4.4.5 *Flash point of the solvent.*—Shall be determined with a tag closed cup tester, as described in method 1101.4 of Fed. Test Method Std. No. 791.

4.4.6 *Initial boiling point of the solvent.*—Place 20 ml. of the vehicle in a 100-ml. Engler (single arm) distillation flask. Insert a thermometer through a stopper centrally in the neck of the flask and to such a height that the top of the bulb is on a level with the entrance to the side outlet tube. Connect the outlet tube with a condenser cooled with iced water. Heat at a uniform rate so regulated that the first drop of condensate falls from the condenser in not less than 5 nor more than 10 minutes. The reading of the ther-

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:18Z
Check the source to verify that this is the current version before use.

mometer when the first drop falls shall be recorded as the initial boiling point.

4.4.7 *Performance.* — A piece of smooth, clean, unpolished leather, one square foot or more in area, shall be used for this test. The application of the polish to the leather shall be made as directed by the manufacturer with room temperature conditions prevailing throughout the test. Examine for film characteristics, ease of application and shine.

5. PREPARATION FOR DELIVERY

The definitions and applications of the levels of packaging and packing shall be in accordance with Federal Standard No. 102.

5.1 Packaging.

5.1.1 *Level B.*—The shoe polish shall be packaged in suitable commercial round metal containers. Net weight of the unit container shall be 1½ ounces (avoirdupois). Twelve unit containers shall be intermediate packaged in a suitable cardboard box.

5.1.2 *Level C.*—The shoe polish shall be packaged in containers conforming to the manufacturer's practice.

5.2 Packing.

5.2.1 *Level B.*—One dozen boxes containing twelve unit containers each shall be packed in a fiber box conforming to Federal Specification PPP–B–636, type I or II, class 1, style RSC.

5.2.2 *Level C.*—Shoe polish packaged in accordance with level B or C, as specified, shall be packed in containers in a manner to insure safe delivery and acceptance at destination. Containers shall comply with the Consolidated Freight Classification Rules or other carrier regulations applicable to the mode of transportation.

5.3 Marking.

5.3.1 *Civil agencies.*—Unit and shipping containers shall be marked as specified in Federal Standard No. 123.

5.3.2 *Military agencies.*—Unit and shipping containers shall be marked in accordance with Military Standard No. 129.

6. NOTES

6.1 Ordering data.—Purchasers should exercise any desired options offered herein. (See 3.2, 5.1, 5.2, 5.3.)

6.2 Basis of purchase.—The material shall be purchased by units of 1½ ounces net weight (avoirdupois).

6.3 Transportation description.—Transportation description applicable to this item is:

Dressing, Shoe

Carload minimum weight 36,000 pounds.

Truckload minimum weight 36,000 pounds.

Notice. — When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

MILITARY INTERESTS:
Army—Q
Air Force.

Copies of this specification may be purchased for cents each.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:18Z
Check the source to verify that this is the current version before use.