[METRIC]
A-A-1270
April 16, 1996
SUPERSEDING
MMM-A-180C Cl A
August 6, 1979

COMMERCIAL ITEM DESCRIPTION

ADHESIVE, POLYVINYL ACETATE EMULSION, GENERAL PURPOSE

The General Services Administration has authonzed the use of this commercial item description as a replacement for Federal Specification MMM-A-180C Class A, for all Federal Agencies

1 SCOPE This commercial item descnption covers a nonflammable, nontoxic, water based polyvinyl acetate emulsion (also known as "white glue"), that dnes clear to form strong bonds on almost all porous and semi-porous matenals This adhesive is for general office or household indoor use for bonding lightweight fabncs, paper, light wood or bookbinding

2 SALIENT CHARACTERISTICS

2 1 Appearance and application properties The adhesive, in a freshly opened container shall be smooth, uniform and free from lumps, skins or foreign matter It shall flow and spread evenly and smoothly when applied by brushing, roller coating or dipping

2 2 The product shall meet the requirements in Table I

TABLE I

Characteristic	Minimum	Maximum	Test[1]
Viscosity, cp	2000	6000	ASTM D 1084 Method B
pH	4	6	ASTM E 70
Compression shear strength, maple blocks, kPa (psi)	17200 (2500)	—	ASTM D 905
Tension shear strength, birch plywood[2], kPa (psi)	2750 (400)	—	ASTM D 906

[1] Manufacturer may use tests shown in this table or an equivalent test to verify compliance to those requirements The tests listed will be used in case of dispute.
[2] 3mm thick basswood may be used in lieu of birch plywood

2 3 Prohibited material The product shall not contain (other than trace impurity amounts, not to exceed 06% liquid wt), any of the following hydrolyzable chlorine derivatives, ethylene based glycol ethers and their acetates, any carcinogen, as defined in 29 CFR 1910 1200, any of the 17 target chemicals on the EPA 33/50 program list, [These chemicals are benzene, cadmium & compounds, carbon tetrachloride, chloroform, chromium & compounds, cyanides, lead & compounds, mercury & compounds, methyl ethyl ketone, methyl isobutyl ketone, methylene chloride, nickel & compounds, tetrachloroethylene, toluene, trichloroethane, trichloroethylene, and xylenes], nor any ozone depleting compound [as listed in the Federal Register notice of July 30, 1992 (57 Fed Reg 33753), which include chlorofluorocarbons, halons, carbon tetrachloride, methyl chloroform, and hydrochlorofluorocarbons]

2 4 Freeze/thaw stability Store a sample of the product at -18°C (0°F) for 18 hours Remove from freezer and restore to a temperature of 24°C (75°F) without stirring This constitutes one freeze-thaw cycle After 5 freeze thaw cycles, the sample shall meet all appearance and application properties and all requirements in Table I

Beneficial comments, recommendations, additions, deletions, clanfication's, etc and any data which may improve this document should be sent to General Services Administration, Engineering and Commodity Management Division (10FTE), 400 15th St SW, Auburn, WA 98001

FSC 8040

DISTRIBUTION STATEMENT A: Approved for public release Distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:12Z
Check the source to verify that this is the current version before use.

2 5 Storage life After storing a sample of adhesive at 24°C (75°F) for 18 months, the sample shall meet all appearance and application properties and all requirements in Table I There shall be no evidence of any biological growth

3 QUALITY ASSURANCE PROVISIONS

3 1 Commercial Quality The products provided shall conform to the producer's own drawings, specifications, standards, and quality assurance practices and be the same product offered for sale in the commercial market. The government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract

4 PACKAGING
The packaging and packing shall be as specified in the contract or order

5 NOTES

5 1 Intended use This product corresponds to Class A of MMM-A-180 It is for general purpose bonding of paper, fabrics and wood Not for use on photos, bare metal or joints subjected to heat, soaking or high stress

5.2 Referenced documents

Federal Regulations
29 CFR Part 1910 1200
The code of Federal Regulations (CFR) is for sale mail order by the Superintendent of Documents, ATTN New Order, PO Box 371954, Pittsburgh, PA 15250-7954

ASTM Methods
ASTM D 905 - Strength Properties of Adhesive Bonds in Shear by Compression Loading
ASTM D 906 - Strength Properties of Adhesives in Plywood Type Construction in Shear by Tension Loading
ASTM D 1084 - Viscosity of Adhesives
ASTM E 70 - pH of Aqueous Solutions with the Glass Electrode
ASTM standards are available from the American Society for Testing and Materials, 100 Barr Harbor Drive West Conshocken, PA 19428-2959 The issue of the ASTM test methods in effect on the date of the solicitation shall be used to determine compliance with these requirements

EPA 33/50 Program Information on the EPA 33/50 program is available from US EPA 33/50 Program (TS-792A), 401 M Street SW, Washington, DC 20460

MILITARY INTEREST

COORDINATING ACTIVITY
Army - MR, Navy - AS,Air Force - 99
REVIEW ACTIVITIES
Army - AR , Air Force 84
USER ACTIVITIES
Army - AT, EA, Navy YD

CIVIL AGENCY INTEREST

OORDINATING ACTIVITY
GPO

PREPARING ACTIVITY
GSA-FSS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:12Z
Check the source to verify that this is the current version before use.