A-A-863A
May 30, 1996
Superseding
A-A-863
March 1, 1984

COMMERCIAL ITEM DESCRIPTION

ADHESIVE, RUBBER, FOR PAPER BONDING

The General Services Administration has authorized the use of this commercial item description by all federal agencies.

1. SCOPE. This commercial item description covers rubber-based adhesives used for bonding papers, maps, drawings, and charts.

2. CLASSIFICATION.

2.1 Type I - Solvent based
Type II - Water based emulsion

2.2 Class 1 - Permanent
Class 2 - Repositionable

2.3 Form A - Bulk liquids
Form B - Aerosol

3. SALIENT CHARACTERISTICS.

3.1 Appearance - The adhesive shall be transparent or translucent. The adhesive shall be clear when dried although it may be colorless or lightly colored when in wet state. The adhesive shall not cause permanent warping, discoloration, or staining in the paper.

3.2 Workmanship - The adhesive shall be smooth and uniform in consistency and free from dirt, lumps, and coarse particles. The adhesive shall also be free from all defects that will affect performance and serviceability or present a hazard to the user.

3.3 Class 1, Permanent bonding - Products shall be able to produce bonds with standard bond typing paper strong enough to cause fibers to be embedded in the glue line when pulled apart after drying.

Beneficial comments, recommendations, additions, deletions, clarifications, etc. and any other data which may improve this document should be sent to: General Services Administration, GSA Center (10FTE), Auburn, Washington 98001.

FSC 8040

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:10Z
Check the source to verify that this is the current version before use.

3.4 Class 2, Repositionable bonding - Adhesives shall remain tacky after solvent evaporation. Adhesives shall allow bonded material to be lifted off the glue line and repositioned without loss of bond strength. However, no fibers will be left in the glue line when pulled apart after solvent evaporation.

3.5 Viscosity - The viscosity of the adhesive shall be not less than 2500 centipoise nor more than 5000 centipoise when tested in accordance with ASTM D 1084, Method B, using a Brookfield RVF viscometer (or equivalent) with a #2 spindle and a velocity of 4 rpm.

3.6 Form B, Aerosol - Products shall be capable of producing a uniform spray pattern that is free of lumps or excessively big drops. The cans shall be adequately pressurized with a non-ozone depleting propellant capable of expelling at least 95% of the contained adhesive.

3.7 Drying time - Type I solvent products shall be dry in 10 minutes or less. Type II water based products shall be dry in 30 minutes or less.

3.8 Solvent and propellant properties - Solvents used shall not be photochemically reactive, foul-odored, toxic, or contain ozone depleting substances.

4. REGULATORY REQUIREMENTS.

4.1 The offeror/contractor is encouraged to use recovered materials to the maximum extent practicable in accordance with paragraph 23.403 of the Federal Acquisition regulation.

5. QUALITY ASSURANCE PROVISIONS.

5.1 Product conformance. The products provided shall meet the salient characteristics of this commercial item description, conform to the producer's own drawings, specifications, standards, and quality assurance practices and be the same product offered for sale in the commercial marketplace. The government reserves the right to require proof of such conformance.

6. PACKAGING. Packaging, preservation, packing, and marking shall be as specified in the contract or purchase order.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:10Z
Check the source to verify that this is the current version before use.

7. NOTES.

7.1 Copies of ASTM standards are available from the American Society for Testing and Materials, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

Preparing Activity:
GSA-FSS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:10Z
Check the source to verify that this is the current version before use.