MILITARY SPECIFICATION

PROJECTILE, 155MM, HE, ROCKET ASSISTED M549, MOTOR BODY BONDING ASSEMBLY FOR

This amendment forms a part of Military Specification MIL-P-50569C (AR), dated 01, June 1982, and is approved for use by the US Army Armament Munitions and Chemical Command and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 25

Delete paragraph 4.4.3.8.1 in its entirety and substitute the following:

"4.4.3.8.1 Salt spray. After qualification in accordance with TT-C-490, two (2) salt spray samples shall be taken each week, one during the first 30 minutes of production and a second at any other time. Failure to comply with the requirements of the applicable drawing shall be cause for taking the corrective action prescribed in TT-C-490."

PAGE 28

4.5.5, line 6: Delete "M185 or".

Delete paragraph 4.5.6.1 in its entirety and substitute the following:

"4.5.6.1 Salt spray testing. Salt spray testing shall be accomplished on production projectiles or sectioned projectiles that were acceptable at the time of painting and were sectioned subsequent to painting. If sectioned projectiles are used, sectioning shall be accomplished to allow testing of all major areas of the projectiles on an alternating basis. The salt spray test shall be performed utilizing the equipment and procedures specified by Federal Test Method Standard No. 141 and TT-C-490 with the exception that test samples shall be selected in accordance with 4.4.3.8.1 and test samples shall be dried in accordance with Drawing 9235997."

Custodian:
Army - AR

Preparing activity:
Army - AR

(Project 1320-A763)

FSC 1320

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:29Z
Check the source to verify that this is the current version before use.