MIL-W-50577C (AR)
AMENDMENT 3
6 AUGUST 1982
SUPERSEDING
AMENDMENT 2
9 MARCH 1981

MILITARY SPECIFICATION

WARHEAD, 155MM, M549A1
BONDING ASSEMBLY

This amendment forms a part of Military Specification MIL-W-50577C (AR), dated 20 June 1979 and is approved for use by the U.S. Army Armament Research and Development Command, and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 19

Delete paragraph 4.4.3.4 in its entirety.

* Add 4.4.5 as follows:

"4.4.5 Steel quality. Steel supplied shall comply with MIL-S-50783, except that macroetch quality shall be per MIL-STD-1459. The quality of the steel as indicated by the macroetch results shall be equal to, or better than A5, B3 and C8 with defects D1, D3, D4, D5, D6, D7 or D8 unacceptable. Manufacturer shall provide a certification that the applicable MIL-S-50783, and macroetch requirements have been met."

PAGE 21

* Delete paragraph 4.5.3.4 and substitute the following in its place:

"4.5.3.4 Operator qualifications. For operation of ultrasonic equipment, personnel shall be qualified and certified in accordance with MIL-STD-410, Level I. For set-up and calibration of ultrasonics equipment, personnel shall be qualified and certified in accordance with MIL-STD-410, Level II, in all respects but need not include experience."

FSC 1320

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:30Z
Check the source to verify that this is the current version before use.

* Delete paragraph 4.5.9.3 and substitute the following in its place:

"4.5.9.3 Operator qualifications. For operation of eddy current equipment, personnel shall be qualified and certified in accordance with MIL-STD-410, Level I. For set-up and calibration of eddy current equipment, personnel shall be qualified and certified in accordance with MIL-STD-410, Level II, in all respects but need not include experience."

4.5.10.1, delete this paragraph in its entirety and substitute the following:

"4.5.10.1 Salt spray testing. Salt Spray testing shall be conducted on production warheads or sectioned warheads that were acceptable at the time of painting and were sectioned subsequent to painting. If sectioned warheads are used, sectioning shall be accomplished to allow testing of all major areas of the warheads on an alternating basis. The salt spray test shall be performed utilizing the equipment and procedures specified by Federal Test Method Standard No. 141 and TT-C-490 with the exception that test samples shall be dried in accordance with Dwg. 9235995 in lieu of the drying cycle specified in TT-C-490. Salt Spray samples shall be selected alternately, one during the first 30 minutes of production (early morning) and then one randomly at different times of the day.

The margins of this amendment are marked with an asterisk to indicate where changes from the previous amendment were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous amendment.

Custodian:
Army - AR

Preparing activity:
Army - AR

(Project 1320-A655)

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:30Z
Check the source to verify that this is the current version before use.