NOTE: The document identifier and heading has been changed on this page to reflect that this is a performance specification. There are no other changes to this document. The document identifier on subsequent pages has not been changed, but will be changed the next time this document is revised.

METRIC
DOD-PRF-24648
AMENDMENT 1
5 March 1991

PERFORMANCE SPECIFICATION

PRIMER COATING, ZINC DUST PIGMENTED FOR EXTERIOR STEEL SURFACES (METRIC)

This amendment forms a part of DOD-P-24648, dated 16 July 1985, and is approved for use by all Departments and Agencies of the Department of Defense.

PAGE 3

2.2, ASTM: Delete "ASTM D 1748 - Standard Test Method for Rust Protection by Metal Preservatives in the Humidity Cabinet (DoD adopted)."

2.2, ASTM: Add "ASTM D 2247 - Standard Test Method for Testing Coated Metal Specimens at 100% Relative Humidity".

2.2: Delete "South Coast Air Quality Management District" in its entirety.

PAGE 4

3.2.2: Delete and substitute the following:

"3.2.2 Volatiles. The volatile portion of each component and mixed components of the primer shall have a maximum volatile organic content (VOC) of 340 grams solvent per liter of paint (2.8 pounds per gallon)."

AMSC N/A
FSC 8010
DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:38Z
Check the source to verify that this is the current version before use.

3.2.3: Delete and substitute the following:

"3.2.3 Thinners. When the liquid vehicle portion of the primer cannot be thinned with water, the manufacturer of that primer shall specify a suitable solvent (see 4.11)."

3.4, last line: Delete last word "rejection".

3.4, last line: Add "and removal from the qualified products list (QPL). Qualification is based on one year satisfactory performance when tested in accordance with 4.8.14."

PAGE 5

3.4.1, subparagraphs (1) and (2): Delete and substitute the following:

"(1) One mist coat of formula 150 of MIL-P-24441. One full coat of either formula 151 or 150 of MIL-P-24441. Two coats of formula 20 of DOD-E-699.

(2) One mist coat of formula 150 of MIL-P-24441. One full coat of either formula 151 or 150 of MIL-P-24441. Two coats of haze gray, DOD-E-24635, color number 26270."

PAGE 6

3.12, line 2: Delete "sandblasted" and substitute "abrasive blasted".

3.12, fifth line: Delete the last word "shall" and substitute "may".

PAGE 14

4.8.10, third line: Delete "ASTM D 1748" and substitute "ASTM D 2247".

4.8.12, second line: After "panel shall be coated" add "as specified in 3.4.1(e)."

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:38Z
Check the source to verify that this is the current version before use.

PAGE 15

4.8.14, sixth line: After "film failure" delete "other than a moderate change in appearance".

PAGE 17

5.3.2: Delete and substitute the following:

"5.3.2 Special marking. In addition to other markings required on the containers, there shall be the following statement: "The volatile organic content of primer in this container does not exceed 340 grams solvent per liter of paint"."

PAGE 18

6.4: Delete in its entirety.

Custodiams:
Army - ME
Navy - SH
Air Force - 99

Review activities:
Army - MR
Navy - AS, YD

User activities:
Navy - CG, MC

Preparing activity:
Navy - SH
(Project 8010-0426)

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:38Z
Check the source to verify that this is the current version before use.