MIL-S-43753C
25 August 1987
SUPERSEDING
MIL-S-43753B
31 December 1981

MILITARY SPECIFICATION

SAFETY CLOTHING, HIGH VISIBILITY

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This document covers a safety ensemble which consists of vest, leg bands, sleevelets, arm bands, and helmet band. The ensemble provides the wearer high visibility to approaching vehicle operators in both day and night conditions.

* 1.2 Classification. The safety clothing shall be of the following types and styles as specified (see 6.2):

Type VI	- Vest, High Visibility
Style 1	- Knitted
Style 2	- Woven
Type VII	- Leg Band, High Visibility (pair)
Type VIII	- Sleevelet, High Visibility (pair)
Style 1	- Knitted
Style 2	- Woven
Type IX	- Arm Band, High Visibility (pair)
Type X	- Helmet Band, High Visibility

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: U.S. Army Natick Research, Development and Engineering Center, Natick, MA 01760-5014, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 8415

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:13Z
Check the source to verify that this is the current version before use.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

* 2.1.1 Documents. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents shall be those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation.

SPECIFICATIONS

FEDERAL

A-A-50083	- Bag, Plastic, Folded Garment
JJ-W-155	- Webbing, Textile, (Cotton, Elastic)
DDD-L-20	- Label: For Clothing, Equipage, and Tentage, (General Use)
PPP-B-636	- Boxes, Shipping, Fiberboard

MILITARY

MIL-W-5664	- Webbing, Textile, Elastic
MIL-F-21840	- Fastener Tapes, Hook and Pile, Synthetic
MIL-L-35078	- Loads, Unit: Preparation of Semiperishable Subsistence Items; Clothing, Personal Equipment and Equipage; General Specification For
MIL-T-43548	- Thread, Polyester Core: Cotton-, Rayon-, or Polyester-Covered
MIL-C-43708	- Cloth, Coated or Cloth, Laminated, Reflective

STANDARDS

FEDERAL

FED-STD-191	- Textile Test Methods
FED-STD-751	- Stitches, Seams, and Stitchings

MILITARY

MIL-STD-105	- Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129	- Marking for Shipment and Storage
MIL-STD-147	- Palletized Unit Loads
MIL-STD-731	- Quality of Wood Members for Containers and Pallets

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:13Z
Check the source to verify that this is the current version before use.

2.1.2 Other Government documents. The following other Government documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues shall be those in effect on the date of the solicitation.

DRAWINGS

U.S. ARMY NATICK RESEARCH, DEVELOPMENT AND ENGINEERING CENTER

2-3-433	- Safety Clothing, High Visibility; Vest
2-3-434	- Vest Details
2-3-435	- Safety Clothing, High Visibility; Arm Band and Leg Band
2-3-436	- Safety Clothing, High Visibility; Sleevelet and Helmet Band

(Copies of documents required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

* 2.2 Other publications. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted shall be those listed in the issue of the DODISS specified in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS shall be the issues of the nongovernment documents which are current on the date of the solicitation.

THE COLOR ASSOCIATION OF THE UNITED STATES

Standard Color Card of America

(Application for copies should be addressed to the Color Association of the United States, 343 Lexington Avenue, New York, NY 10016-0927.)

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

D 1424 - Tear Resistance of Woven Fabrics by Falling-Pendulum (Elmendorf) Apparatus
D 3951 - Standard Practice for Commercial Packaging

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103-1187.)

(Technical society and technical association documents are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:13Z
Check the source to verify that this is the current version before use.

* 2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document shall take precedence. Nothing in this document, however, shall supersede applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 Standard sample. The fluorescent coated cloth shall match the standard sample with respect to all characteristics for which the standard sample is referenced (see 6.3).

3.2 First article. When specified in the contract or purchase order, a sample shall be subjected to first article inspection (see 4.3, 6.2, and 6.4).

3.3 Materials (see 6.5).

* 3.3.1 Reflective cloth. The reflective cloth shall conform to either type I, class 2 or type II, class 1 of MIL-C-43708; except the put-up (type I, class 2) and flame resistance (type II, class 1) requirements shall not apply.

3.3.2 Fluorescent mesh cloth. The fluorescent mesh cloth shall be knitted or woven as specified (see 6.2) from polyvinyl chloride coated polyester yarns, and shall conform to the requirements in table I when tested as specified in 4.4.1. The fluorescent mesh cloth is used in the vest and in the sleevelet.

TABLE I. Physical requirements of fluorescent mesh cloth

Characteristic	Style 1	Style 2
Weight, oz/sq yd	9.0 to 11.0	6.0 to 8.0
Bursting strength, lbs, min	200	200
Texture		
Wales or warp, min	6	7
Courses or filling, min	7	7

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:13Z
Check the source to verify that this is the current version before use.

3.3.2.1 Color. The color of the fluorescent mesh cloth shall be Fluorescent Orange 430 and shall match the standard sample. The color of the cloth shall be obtained by adding fluorescent dyes or pigments to the coating formula.

3.3.2.1.1 Color matching. The shade of the fluorescent mesh cloth shall match the standard sample when viewed under filtered tungsten lamps that approximate artificial daylight and that have a correlated color temperature of 7500 ± 200K with illumination of 100 ± 20 foot candles. The color shall be a good approximation to the standard sample under incandescent lamplight at 2300 ± 200K.

3.3.2.1.2 Colorfastness. The fluorescent mesh cloth shall show fastness to light equal to or better than the standard sample after 100 hours exposure when tested as specified in 4.4.1. When no standard sample has been established or designated as applicable to colorfastness, the finished cloth shall show "good" fastness to light after 100 hours exposure when tested as specified in 4.4.1.

3.3.3 Binding (used only on the leg band, sleevelet, and arm band).

3.3.3.1 Base cloth. The base cloth for the bias binding shall be an unbleached, undyed, cheesecloth woven from cotton yarns, free from waste and loading materials, carded and drawn into single yarns. The base cloth shall meet the requirements specified in table II when tested as specified in 4.4.1.

TABLE II. Physical requirements of the bias binding base cloth

Characteristic	Requirement
Weight, oz/sq yd	2.0 (min)
Yarns per inch:	
Warp	54 (min)
Filling	40 (min)
Breaking strength, lbs	
Warp	30 (min)
Filling	10 (min)
Weave	Plain (1 by 1)

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:13Z
Check the source to verify that this is the current version before use.

3.3.3.2 Coated cloth. The base cloth specified in 3.3.3.1 shall be coated on one side only with a compound containing a minimum of 2 percent polytetrafluoroethylene and gold dyestuffs and coating agents to meet the requirements specified in table III when tested as specified in 4.4.1.

TABLE III. Physical requirements of the binding coated cloth

Characteristic	Requirement
Overall weight, oz/sq yd	2.9 (min) to 3.1 (max)
Breaking strength, lbs:	
Warp	30 (min)
Filling	10 (min)
Tearing strength, grams:	
Warp	800 (min)
Filling	400 (min)

3.3.3.2.1 Bias binding. The finished and coated cloth shall be cut on the bias.

3.3.4 Unbleached braided elastic webbing. The braided elastic webbing used in the sleevelet shall be unbleached, 3/8 inch wide and shall conform to type II, class 2 of JJ-W-155.

3.3.5 Black elastic webbing. The elastic webbing used in the helmet band shall be black, 1 inch wide and shall conform to class 1 of MIL-W-5664.

3.3.6 Nylon fastener tape. The hook shall be 1 inch wide and the pile shall be 2 inches wide, and the tape fastener shall be black 3230 in color and shall conform to type I, class 1 of MIL-F-21840.

3.3.7 Thread. The thread for all sewing shall be polyester, cotton-covered thread, ticket No. 30, 2 or 3 ply, natural conforming to MIL-T-43548.

3.4 Construction. The construction shall conform in all respects to the drawings listed in section 2 and as specified herein.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:13Z
Check the source to verify that this is the current version before use.

3.4.1 Stitches, seams, and stitchings.

3.4.1.1 Types of stitching. Stitching shall conform to FED-STD-751 as follows:

For all stitching, except overedge stitching and bartacking	Type 301, 8 to 10 stitches per inch
For overedge stitching	Type 504 or 505, 8 to 10 stitches per inch
Bartacking	5/8 inch ± 1/16 inch in length, 1/8 inch wide ± 1/32 inch and shall contain 28 stitches

3.4.1.1.1 Type 301 stitching. Thread breaks in stitching shall be overstitched not less than 1 inch at each break. Stitching shall be backstitched not less than 1 inch at the ends except where ends are turned under in a hem or held down by other stitching. Thread tension shall be maintained so that there will be no loose or tight stitching and the lock will be imbedded in the materials sewed.

3.4.1.1.2 Overedge stitching. Thread breaks in overedge stitching (type 504 or 505) shall be overstitched not less than 3/4 inch at each break.

3.4.1.1.3 Bartacking. Bartacking shall be free of thread breaks and loose stitching.

3.4.1.2 Automatic stitching. Automatic stitching machines may be used to perform any of the required stitch patterns provided the requirements of the stitch pattern, stitches per inch, size and type of thread are met, and at least three or more tying, overlapping, or backstitches are used to secure the ends of the stitching.

3.4.1.3 Thread ends. All thread ends that are visible on the finished item shall be trimmed to a length of not more than 1/4 inch.

3.4.1.4 Seams. Seam allowance shall be maintained with seams properly sewn so that no runoffs, twists, pleats, puckers, or open seams shall result.

3.5 Labels.

3.5.1 Vest, leg band, sleevelet, and arm band. The label shall conform to type VI, class 15 of DDD-L-20 and shall be applied in the location specified on Drawings 2-3-433, 2-3-435, and 2-3-436. The label cloth shall be

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:13Z
Check the source to verify that this is the current version before use.

dyed lemon yellow cable No. 70205 in conformance with the Standard Color Card of America. The fastness to laundering requirements of DDD-L-20 shall apply. The identification marking shall include the applicable national stock number. The label shall contain the cleaning instruction shown in 3.5.3. Exceptions to the class 15 label may be as follows:

a. For the vest, leg band and armband, the required information may be incorporated in a label of approximate size of 1 1/2 inches by 7 3/8 inches, and the identification and instructions may be side by side, with type size of approximately 2/32 to 1/4 inch.

b. For the sleevelet, the required information may be incorporated in an identification label approximately of 1 1/2 inches by 4 inches; and a separate instruction label of the same approximate size (1 1/2 inches by 4 inches) with the type size approximately 2/32 to 1/4 inch. Both identification and instruction labels shall be located behind the reflective stripes.

* 3.5.2 Helmet band. The identification marking shall conform to type IV, class 1 of DDD-L-20, shall include the stock number, and shall be applied in the location as specified on Drawing 2-3-436. An alternate identification marking, embossed marking (rather than direct printing with a black marking medium) may be used on the vinyl reflectorized film cloth (type II, class 1 of MIL-C-43708). Each polyethylene bagged package shall also contain a paper instruction sheet with the cleaning instructions shown in 3.5.3.

3.5.3 Cleaning instructions. Hand wash in warm water (90°F) with mild detergent. Rinse in clean warm water. Do not twist or wring. Drip dry on hanger. Do not dry clean, iron, or use bleach.

3.5.4 Methods of attachment of labels. The sewn on labels shall be applied in either of the following methods:

a. Sewn in place with the same stitching that is used to attach the reflective tape.

b. The label may be sewn on in a separate operation resulting in a double stitch along the two edges of the reflective tape in the label area.

3.6 Workmanship. The safety clothing shall conform to the quality of product established by this document. The occurrence of defects shall not exceed the applicable acceptable quality levels.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:13Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this document where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items must meet all requirements of sections 3 and 5. The inspection set forth in this document shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirement in the document shall not relieve the contractor of the responsibility of assuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling in quality conformance does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to acceptance of defective material.

* 4.1.2 Certificates of compliance. When certificates of compliance are submitted, the Government reserves the right to inspect such items to determine the validity of the certification.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).
b. Quality conformance inspection (see 4.4).

4.3 First article inspection. When a first article is required (see 6.2), it shall be examined for the defects specified in 4.4.3 and 4.4.4. The presence of any defect shall be cause for rejection of the first article.

4.4 Quality conformance inspection. Unless otherwise specified, sampling for inspection shall be performed in accordance with MIL-STD-105.

* 4.4.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced documents unless otherwise excluded, amended, modified, or qualified in this document or applicable purchase document. In addition, testing shall be performed on components listed in table IV for characteristics noted. Unless otherwise indicated, testing shall be conducted

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:13Z
Check the source to verify that this is the current version before use.

in accordance with FED-STD-191. All requirements are applicable to the sample unit. All test reports shall contain the individual values utilized in expressing the final results. Unless otherwise specified in subsidiary documents, sampling shall be in accordance with the following:

Lot size	Sample size
800 or less	2
801 up to and including 22,000	3
22,001 and over	5

The lot shall be unacceptable if one or more sample units fail to meet any test requirement specified. The unit for expressing lot size and sample unit for testing each component shall be in accordance with applicable subsidiary documents and as follows:

Component	Lot size unit expressed as	Sample unit for testing
Fluorescent mesh cloth	Yards	1/3 sq yd
Bias binding coated cloth	Yards	1/3 sq yd

TABLE IV. Component tests

Component	Characteristic	Requirement paragraph	Test method
Fluorescent mesh cloth	Overall weight	3.3.2	5041
	Bursting strength	3.3.2	5120
	Texture	3.3.2	
	- knitted cloth		5070
	- woven cloth		5050
	Fluorescent dyes or pigments	3.3.2.1	1/
	Colorfastness to light	3.3.2.1.2	5660 2/
Bias binding base cloth	Weight	3.3.3.1	5041 1/
	Yarns per inch	3.3.3.1	5050 1/
	Breaking strength	3.3.3.1	5100 1/
	Weave	3.3.3.1	Visual 1/

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:13Z
Check the source to verify that this is the current version before use.

TABLE IV. Test methods - Continued

Component	Characteristic	Requirement paragraph	Test method
Bias binding coated cloth	Overall weight	3.3.3.2	5041
	Breaking strength	3.3.3.2	5102
	Tearing strength	3.3.3.2	D 1424 3/
	Polytetrafluoro-ethylene and gold dyestuffs	3.3.3.2	1/

1/ Unless otherwise specified, a certificate of compliance may be submitted in lieu of testing.

2/ The time of exposure shall be 100 hours.

3/ Refers to ASTM method.

4.4.2 In-process inspection. Inspection shall be made at any point or during any phase of the manufacturing process to determine whether operations or assemblies are in accordance with requirements indicated on the drawings and as specified herein. Cut dimensions of components shall be as specified. Whenever nonconformance is noted, correction shall be made to the items affected and lot in process. The Government reserves the right to exclude from consideration for acceptance any material or service for which in-process inspection has indicated nonconformance.

4.4.3 End item visual examination. The end item shall be examined for the defects listed in table V. The lot size shall be expressed in units of one vest, leg band, sleevelet, arm band, or helmet band, as applicable. The sample unit shall be one vest, leg band, sleevelet, arm band, or helmet band, as applicable. The inspection level shall be II and the acceptable quality level (AQL), expressed in terms of defects per hundred units, shall be 2.5 for major defects and 15.0 for total (major and minor combined) defects.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:13Z
Check the source to verify that this is the current version before use.

TABLE V. End item visual defects

Examine	Defect	Classification	
		Major	Minor
Cloth	Hole (except needle perforations), mend, burn, cut or tear; any smash, weak place, broken or missing yarn, multiple floats, or open place, clearly visible	X	
	Color not as specified	X	
	The fluorescent orange mesh cloth showing uneven or uncoated area	X	
Webbing	Any hole, cut, tear, or smash	X	
	Color not as specified	X	
	Not firmly and tightly woven, edges frayed or scalloped	X	
Tape fastener	Missing hooks or loops	X	
	Hooks (or loops) flattened	X	
	Color not as specified	X	
Thread	Color not as specified	X	
Open seam	One inch or less		X
	More than 1 inch	X	
	NOTE: A seam shall be classified as open when one or more stitches joining a seam are broken or when two or more continuous skipped or run-off stitches occur. On double-stitched seams, a seam shall be considered open when either one or both sides of the seam are open.		
Raw edges (on edge required to be finished)	More than 1/2 inch securely caught in stitching		X
	NOTE: Raw edge not securely caught in stitching shall be classified as an open seam.		

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:13Z
Check the source to verify that this is the current version before use.

TABLE V. End item visual defects - Continued

Examine	Defect	Classification	
		Major	Minor
Run-off (see open seam)			
Seam and stitch type	Wrong seam or stitch type	X	
Stitching margins or gage of stitching	Not as specified		X
Stitch tension	Loose tension, resulting in a loosely secured seam		X
	Tight tension (stitches break when normal strain is applied to seam or stitching)		X
	NOTE: Puckering is evidence of tight tension. When puckering is evident, seam shall be tested by exerting normal pull in length-wise direction of seam.		
Stitches per inch	One stitch less than minimum specified		X
	Two or more stitches less than minimum specified	X	
	One or more stitches in excess of maximum specified		X
	NOTE: Variation in the number of stitches per inch, caused by the operator speeding up the machine and pulling the fabric in order to sew over heavy places or heavy seams or in turning corners, shall be classified as follows: a. Within the minor defect classification no defect b. Within the major defect classification minor defect		

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:13Z
Check the source to verify that this is the current version before use.

TABLE V. End item visual defects - Continued

Examine	Defect	Classification	
		Major	Minor
Stitching ends	Ends of seams produced with 301 stitch type when not caught in other seams or stitching, backstitched less than 1 inch		X
Thread breaks	Overstitched less than 1 inch on stitch type 301; overstitched less than 3/4 inch on stitch type 504 or 505		X
	NOTE: Thread break not overstitched shall be classified as open seam.		
Bartack or box-stitching	Omitted	X	
	Not as specified or not in specified location		X
Components and assembly	Any component omitted, misplaced, or not as specified (unless otherwise specified herein)	X	
	Any operation omitted, (unless otherwise classified herein)	X	
	Needle chews resulting in a continuous cut or tear extending 1/4 inch	X	
	Seams pleated or badly puckered		X
Binding	Twisted or pleated		X
	Improperly or loosely applied		X
	Ends of binding not finished as specified or overlapped less than 1 inch		X
Identification and marking	Omitted, incorrect, illegible, misplaced, or size characters not as specified		X
	Embossed marking of the helmet band (on vinyl reflectorized film cloth) which results in a hole, cut, tear, perforation or weak place	X	

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:13Z
Check the source to verify that this is the current version before use.

TABLE V. End item visual defects - Continued

Examine	Defect	Classification	
		Major	Minor
Cleanness	Grease, oil, dirt, or ink stains, clearly noticeable; thread ends not trimmed to 1/4 inch maximum length		X

4.4.4 End item dimensional examination. The end item shall be examined for the defects listed in table VI. The lot size shall be expressed in units of one vest, leg band, sleevelet, arm band, or helmet band, as applicable. The sample unit shall be one vest, leg band, sleevelet, arm band, or helmet band, as applicable. The inspection level shall be S-3 and the AQL, expressed in terms of defects per hundred units, shall be 2.5 for major defects and 6.5 for total (major and minor combined).

TABLE VI. End item dimensional examination

Examine	Defect	Classification	
		Major	Minor
Overall dimensions	Smaller than nominal dimensions less applicable minus tolerance indicated on drawings, but not smaller than nominal dimensions less twice the applicable minus tolerance		X
	Smaller than nominal dimensions less twice the applicable minus tolerance indicated on drawings	X	
	Larger than nominal dimensions and applicable plus tolerance indicated on drawings		X
Component and location dimensions	Not within specified tolerance		X

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:13Z
Check the source to verify that this is the current version before use.

4.4.5 Packaging examination. The fully packaged end items shall be examined for the defects listed below. The lot size shall be expressed in units of shipping containers. The sample unit shall be one shipping container fully packaged. The inspection level shall be S-2 and the AQL, expressed in terms of defects per hundred units, shall be 2.5.

Examine	Defect
Marking (exterior and interior)	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application
Materials	Any component missing, damaged, or not as specified
Workmanship	Inadequate application of components, such as incomplete sealing or closure of flap, improper taping, loose strapping, or inadequate stapling Bulged or distorted container
Content	Number per container is more or less than required

4.4.6 Palletization examination. The fully packaged and palletized end items shall be examined for the defects listed below. The lot size shall be expressed in units of palletized unit loads. The sample unit shall be one palletized unit load, fully packaged. The inspection level shall be S-1, and the AQL, expressed in terms of defects per hundred units, shall be 6.5.

Examine	Defect
Finished dimensions	Length, width, or height exceeds specified maximum requirement
Palletization	Pallet pattern not as specified Interlocking of loads not as specified Load not bonded as specified
Weight	Exceeds maximum load limits
Marking	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:13Z
Check the source to verify that this is the current version before use.

5. PACKAGING

5.1 Preservation. Preservation shall be level A or Commercial as specified (see 6.2).

* 5.1.1 Level A. Each safety clothing item shall be neatly folded (where applicable) to the size and packaged in the quantities specified in table VII. Each folded item shall be placed in a snug-fitting clear plastic bag conforming to A-A-50083.

TABLE VII. Packaging and packing data

Item	Approximate fold size (inches) Length	Width	Package quantity	Pack quantity
Safety vest	11 1/2	10	1 each	48 each
Leg band	5 1/4	2	1 pair	96 pair
Sleevelet	8 1/2	6	1 pair	96 pair
Arm band	7 1/4	2	1 pair	96 pair
Helmet band	6 1/4	1	12 each	720 each

* 5.1.2 Commercial. Safety clothing items shall be preserved in accordance with ASTM D 3951.

5.2 Packing. Packing shall be level A, B, or Commercial as specified (see 6.2).

* 5.2.1 Level A packing. Safety clothing items of one type only, preserved as specified in 5.1, shall be packed in quantities specified in table VII in a snug-fitting container conforming to style RSC-L, grade V2s of PPP-B-636. The inside of each fiberboard shipping container shall be fitted with a box liner conforming to type CF, class weather-resistant, variety DW, grade V15c of PPP-B-636. Each shipping container shall be closed, waterproofed, and reinforced in accordance with method III as specified in the appendix of PPP-B-636, except that the inspection shall be in accordance with 4.4.5.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:13Z
Check the source to verify that this is the current version before use.

Shipping containers shall be arranged in unit loads in accordance with MIL-L-35078 for the type and class of load specified (see 6.2). Strapping shall be limited to nonmetallic strapping, except for type II, class F loads.

5.2.2 Level B packing. Safety clothing items of one type only, preserved as specified in 5.1, shall be packed in the quantities specified in table VII in a snug-fitting shipping container conforming to style RSC-L, type CF (variety SW) or SF, class domestic, grade 275 of PPP-B-636. The inside of each fiberboard shipping container shall be fitted with a box liner conforming to type CF, class domestic, variety DW, grade 275 of PPP-B-636. Each shipping container shall be closed in accordance with method II as specified in the appendix of PPP-B-636, except that the inspection shall be in accordance with 4.4.5.

5.2.2.1 Weather-resistant fiberboard containers. When specified (see 6.2), the shipping container shall be a grade V3c, V3s, or V4s fiberboard box fabricated in accordance with PPP-B-636, and closed in accordance with method III as specified in the appendix of PPP-B-636, except that the inspection shall be in accordance with 4.4.5.

* 5.2.3 Commercial packing. Safety clothing items, preserved as specified in 5.1, shall be packed in accordance with ASTM D 3951.

* 5.3 Palletization. When specified (see 6.2), safety clothing, packed as specified in 5.2.2 or 5.2.3, shall be palletized on a 4-way entry pallet in accordance with load type Ia of MIL-STD-147. Pallet type shall be type I (4-way entry), type IV, or type V in accordance with MIL-STD-147. Pallets shall be fabricated from wood groups I, II, III, or IV of MIL-STD-731. Each prepared load shall be bonded with primary and secondary straps in accordance with bonding means K and L or film bonding means O or P. Pallet pattern shall be in accordance with appendix of MIL-STD-147. Interlocking of loads shall be effected by reversing the pattern of each course.

* 5.4 Marking. In addition to any special marking required by the contract, unit packs, shipping containers, and palletized unit loads shall be marked in accordance with MIL-STD-129 or ASTM D 3951, as applicable.

5.4.1 Polyethylene bagged packages. Polyethylene bagged packages shall have the required identification information listed below legibly printed or stamped in black directly on the bag across the center face or on a white label inserted within the bag so as to permit ready identification. The bag or label shall only indicate the following information:

STOCK NUMBER
ITEM DESCRIPTION
QUANTITY

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:13Z
Check the source to verify that this is the current version before use.

6. NOTES

6.1 Intended use. The safety ensemble is designed for use by military police, marching troops, and others required to work in areas traversed by vehicles.

6.2 Ordering data. Acquisition documents should specify the following:

a. Title, number, and date of this document.
b. Type and style, if applicable, required (see 1.2).
c. When a first article is required (see 3.2, 4.3, and 6.4).
d. Selection of applicable levels of preservation and packing (see 5.1 and 5.2).
e. Type and class of unit loading required (see 5.2.1).
f. When weather-resistant grade fiberboard shipping containers are required for level B packing (see 5.2.2.1).
g. When palletization is required (see 5.3).

6.3 Standard sample. For access to samples, address the contracting activity issuing the invitation for bids.

6.4 First article. When a first article is required, it shall be inspected and approved under the appropriate provisions of FAR 52.209. The first article should be a preproduction sample. The contracting officer should specify the appropriate type of first article and the number of units to be furnished. The contracting officer should include specific instructions in all acquisition instruments regarding arrangements for selection, inspection, and approval of the first article.

6.5 Recycled material. It is encouraged that recycled material be used when practical as long as it meets the requirements of the specification (see 3.3).

* 6.6 Subject term (key word) listing.

Clothing
Reflectorized
Safety

6.7 Changes from previous issue. The margins of this document are marked with an asterisk (*) to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only, and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content, as written, irrespective of the marginal notations and relationship to the last previous issue.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:13Z
Check the source to verify that this is the current version before use.

Custodians:

Army - GL
Navy - NU
Air Force - 99

Review activities:

Army - MD
Air Force - 82
DLA - CT

User activity:

Air Force - 45

Preparing activity:

Army - GL

Project No. 8415-0573

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:13Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE ARMY

US Army Natick Research, Development, and
Engineering Center
Natick, MA 01760-5014

NO POSTAGE
NECESSARY
IF MAILED
IN THE
UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300
STRNC-ES

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 12062 WASHINGTON D. C.
POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Commander
US Army Natick Research, Development,
and Engineering Center
ATTN: STRNC-ES
Box 14A
Natick, MA 01760-5014

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:13Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
MIL-S-43753C	Safety Clothing, High Visibility

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
	☐ USER
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ MANUFACTURER
	☐ OTHER *(Specify)*: _____

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426

PREVIOUS EDITION IS OBSOLETE.

NATICK OP 1 Apr 84

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:13Z
Check the source to verify that this is the current version before use.