INCH-POUND

MIL-C-14635B
16 July 1990
SUPERSEDING
MIL-C-14635A
26 November 1975

MILITARY SPECIFICATION

COVER, PERSONNEL IDENTIFICATION TAG

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers one type and size of plastic (plasticized polyvinyl chloride) cover sized to fit over the standard personnel identification tag. The cover can be irreversibly marked with the individual's spectacle prescription.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation (see 6.2).

SPECIFICATIONS

FEDERAL

PPP-B-636 - Boxes, Shipping, Fiberboard
PPP-B-676 - Boxes, Setup

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be used in improving this document should be addressed to: U.S. Army Natick Research, Development, and Engineering Center, Natick, MA 01760-5014 by using the Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 8465

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T03:41Z
Check the source to verify that this is the current version before use.

MILITARY

MIL-L-35078 - Loads, Unit: Preparation of Semiperishable Subsistence Items; Clothing, Personal Equipment and Equipage; General Specification for

STANDARDS

FEDERAL

FED-STD-595 - Colors

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129 - Marking for Shipment and Storage
MIL-STD-147 - Palletized Unit Loads
MIL-STD-731 - Quality of Wood Members for Containers and Pallets

(Unless otherwise indicated, copies of federal and military specifications, standards, and handbooks are available from the Standardization Documents Order Desk, Bldg. 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.)

2.1.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues are those cited in the solicitation.

DRAWINGS

U.S. ARMY NATICK RESEARCH, DEVELOPMENT, AND ENGINEERING CENTER

4-1-481 Cover, Personnel Identification Tag

(Copies of drawings are available from the U.S. Army Natick Research, Development, and Engineering Center, ATTN: STRNC-EMSS, Natick, MA 01760-5014.)

2.2 Non-Government publications. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of the documents which are DoD adopted are those listed in the issue of the DODISS cited in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS are the issues of the documents cited in the solicitation (see 6.2).

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

ASTM D 412 - Test Methods for Rubber Properties in Tension

ASTM D 568 - Flammability of Flexible Plastics

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T03:41Z
Check the source to verify that this is the current version before use.

ASTM D 624 - Test Method for Rubber Property - Tear Resistance

ASTM D 3951 - Practice for Commercial Packing

(Applications for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103-1187.)

(Non-Government standards and other publications are normally available from the organizations that prepare or distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 First article. When specified (see 6.2), a sample shall be subjected to first article inspection (see 6.3) in accordance with 4.3.

3.2 Materials. It is encouraged that recycled material be used when practical as long as it meets the requirements of this specification.

3.2.1 Plasticized polyvinyl chloride. The plasticized polyvinyl chloride composition shall be non-toxic (see 3.4) and self-extinguishing, when tested as specified in 4.4.1.2. The material (after curing) shall be soft flexible elastomeric plastic conforming to the requirements specified in table I when tested as specified in 4.4.1.2.

TABLE I. Plasticized polyvinyl chloride

	Minimum	Maximum
Tensile strength at break, p.s.i.	2300	2550
Ultimate elongation, percent	335	450
Tensile stress at 100 percent elongation, p.s.i.	725	875
Tear resistance (pounds per inch of thickness)	225	300

3.2.1.1 Color. After curing, the polyvinyl chloride shall match color 33613 of FED-STD-595.

3.3 Construction. Tag covers shall be molded in accordance with the details and dimensions of Drawing 4-1-481. All lettering on the faces of the cover shall be raised, shall be legible in the end product, and shall be as shown on Drawing 4-1-481 (see 6.4). All excess material shall be removed in final

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T03:41Z
Check the source to verify that this is the current version before use.

processing. The finished cover shall be capable of being irreversibly marked with a standard Government ball point pen using heavy pressure. Marking shall remain legible after washing when tested as specified in 4.4.4. At the option of the contractor, core pins may be used to support the spacer plates in the mold, provided the core pin holes do not interfere with the prescription marking areas on the covers.

3.4 Toxicity. The finished covers shall be both non-toxic and non-allergenic. When the plastic material is tested as specified in 4.4.1.2, there shall be no evidence of inflammation or other adverse skin reaction on the human test subjects. The contractor shall provide for the performance of this test by, or under the supervision of a doctor of medicine.

3.5 Workmanship. The covers shall conform to the quality of product established by this specification and the occurrence of defects shall not exceed the applicable acceptable quality levels.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements (examinations and tests) as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this specification where such inspections are deemed necessary to ensure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items shall meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of ensuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling inspection, as part of manufacturing operations, is an acceptable practice to ascertain conformance to requirements, however, this does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to accept defective material.

4.1.2 Responsibility for dimensional requirements. Unless otherwise specified in the contract or purchase order, the contractor is responsible for ensuring that all specified dimensions have been met. When dimensions cannot be examined on the end item, inspection shall be made at any point, or at all points in the manufacturing process necessary to assure compliance with all dimensional requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T03:41Z
Check the source to verify that this is the current version before use.

4.1.3 Certificates of compliance. When certificates of compliance are submitted, the Government reserves the right to inspect such items to determine the validity of the certification.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).
b. Quality conformance inspection (see 4.4).

4.3 First article inspection. When a first article is required (see 3.1 and 6.2), it shall be examined for the defects specified in 4.4.2 and 4.4.3 and tested for the characteristics specified in 4.4.4. Any nonconformance shall be cause for rejection of the first article.

4.4 Quality conformance inspection. Unless otherwise specified, sampling for inspection shall be performed in accordance with MIL-STD-105.

4.4.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced documents unless otherwise excluded, amended, modified, or qualified in this specification or applicable purchase document.

4.4.1.1 Component and material certification. Polyvinyl chloride may be accepted on the basis of a contractor's certificate of compliance for material identification and self-extinguishing requirements specified in 3.2.1. A certificate of compliance is acceptable for the toxicity requirements specified in 3.4, provided the test data specified in 4.5.2.1 are attached. A certificate of compliance shall be required for each batch of material used.

4.4.1.2 Component testing. The plasticized polyvinyl chloride shall be tested for the characteristics listed in table II. The lot size for the plasticized polyvinyl chloride shall be expressed in units of 1 pound. Except for toxicity, the sample unit shall be four pieces and each piece shall be 18 inches by 6 inches by 0.025 inch and the sample size shall be as follows:

Lot size (pounds)	Sample size (sample units)
800 or less	2
801 to 22,000	3
22,001 and over	5

Except for toxicity and the extent of burning test, the test results shall be expressed as the lot average. All test reports shall contain the individual values utilized in expressing the final results. There shall be no failure to meet the specified requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T03:41Z
Check the source to verify that this is the current version before use.

TABLE II. Component testing

Characteristic	Requirement paragraph	Test method
Extent of burning test	3.2.1	ASTM D 568 1/
Tensile strength at break	3.2.1	ASTM D 412
Ultimate elongation	3.2.1	ASTM D 412
Tensile stress at 100 percent elongation	3.2.1	ASTM D 412
Tear resistance	3.2.1	ASTM D 624 2/
Toxicity test	3.4	4.5.2

1/ The results shall be reported as pass (self-extinguishing) or fail.

2/ Die C specimens shall be used.

4.4.2 End item visual examination. The end items shall be examined for the defects listed in table III. The lot size shall be expressed in units of covers. The sample unit shall be one cover. The inspection level shall be I and the acceptable quality level (AQL), expressed in terms of defects per hundred units, shall be 4.0.

TABLE III. End item visual defects

Examine	Defect
Design and construction	Varies from design or construction shown on Drawing 4-1-481.
Workmanship	Not clean. Objectionable odor. Edges not smooth, i.e., rough edges. Details of lettering missing or not completely molded. Excessive flash not removed. Hole missing. Surfaces contain voids, pockets or any other defect clearly noticeable.
Finish	Not finished as specfied, i.e., does not match the finish and color (see 3.2.1.1).

4.4.3 End item dimensional examination. The end items shall be examined for conformance to the dimensions specified on Drawing 4-1-481. Only those dimensions that can be evaluated without damaging the end items shall be examined. Any dimension not within the specified tolerance shall be

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T03:41Z
Check the source to verify that this is the current version before use.

classified as a defect. The lot size shall be expressed in units of covers. The sample unit shall be one cover. The inspection level shall be S-3 and the AQL, expressed in terms of defects per hundred units, shall be 2.5.

4.4.4 End item testing. The end items shall conform to the marking requirement in 3.3 when tested as specified in 4.5.1. The lot size shall be expressed in units of covers. The sample unit shall be one cover. The inspection level shall be S-1. Any test failure shall be cause for rejection of the lot.

4.4.5 Packaging examination. The fully packaged end items shall be examined for the defects listed below. The lot size shall be expressed in units of shipping containers. The sample unit shall be one shipping container fully packaged. The inspection level shall be S-2 and the AQL, expressed in terms of defects per hundred units, shall be 2.5.

Examine	Defect
Marking (exterior and interior)	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application
Materials	Any component missing, damaged, or not as specified
Workmanship	Inadequate application of components, such as: incomplete sealing or closure of flap, improper taping, loose strapping or inadequate stapling Bulged or distorted container
Content	Number per container is more or less than required

4.4.6 Palletization examination. The fully packaged and pallletized end items shall be examined for the defects listed below. The lot size shall be the expressed in units of palletized unit loads. The sample unit shall be one palletized unit load, fully packaged. The inspection level shall be S-1 and the AQL, expressed in terms of defects per hundred units, shall be 6.5.

Examine	Defect
Finished dimensions	Length, width, or height exceeds specified maximum requirement
Palletization	Pallet pattern not as specified Load not bonded as specified
Weight	Exceeds maximum load limits
Marking	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T03:41Z
Check the source to verify that this is the current version before use.

4.5 Methods of inspection.

4.5.1 Marking test. The finished cover shall be marked by applying heavy pressure with the standard Government ball point pen and allowed to dry for 10 minutes. The cover shall then be washed by hand with detergent and water for 1 minute, rinsed, and dried. The marking shall then be examined to determine compliance with the requirements of 3.3.

4.5.2 Toxicity test. One half-inch squares 0.08 inch thick of each batch of plasticized polyvinyl chloride material used to fabricate the covers shall be applied to the skin of at least 10 human test subjects by adhesive plaster for 72 hours. The skin test areas shall be examined every 24 hours for evidence of inflammation or other adverse skin reactions. If the material unduly irritates the skin, the test patch shall be removed immediately and the lot represented by that batch shall be rejected.

4.5.2.1 Patch test certificate. A certificate or certificates for each lot of tag covers being delivered shall be forwarded to the contracting activity by the contractor to the effect that the covers are both non-toxic and non-allergenic and meet the requirements of 3.4. The certificate(s) shall contain a record of the patch test performed, a listing of the test subjects by name and the results of each 24 hour observation made for each subject. The record of the test and the observation shall be certified by the doctor of medicine who performed or supervised the testing. In addition, the certificate shall include the contractor's statement that the samples used for testing are from the same batch of polyvinyl chloride used for molding the tag covers. When inspection is performed at the source, the contractor shall furnish a copy of the certificate(s) to the cognizant Government inspector.

5. PACKAGING

5.1 Preservation. Preservation shall be level A or commercial, as specified (see 6.2).

5.1.1 Level A preservation. Two hundred covers shall be arranged on edge in two rows of one hundred each and unit packed in a snug-fitting set-up paperboard box conforming to type I, variety 1, class A, style 1, 2 or 3 of PPP-B-676. Inside dimensions of the box shall be approximately 6 inches by 4 1/2 inches by 1 1/2 inches. A divider made of the same paperboard as the body of the box shall be positioned vertically between the rows.

5.1.2 Commercial preservation. Covers shall be preserved in accordance with ASTM D 3951.

5.2 Packing. Packing shall be level A, B or commercial, as specified.

5.2.1 Level A packing. Six thousand covers, preserved as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC, grade V2s of PPP-B-636, [illegible] of the shipping

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T03:41Z
Check the source to verify that this is the current version before use.

and 15 inches in depth. Each shipping container shall be closed in accordance with method III, waterproofed in accordance with method V and reinforced as specified in the appendix of the container specification. Shipping containers shall be arranged in unit loads in accordance with MIL-L-35078 for the type and class of load specified (see 6.2). Strapping shall be limited to nonmetallic strapping, except for type II, class F loads.

5.2.2 Level B packing. Six thousand covers, preserved as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC, type CF (variety DW) or type SF, class domestic of PPP-B-636. Inside dimensions of the shipping container shall be approximately 14 inches in length, 6 1/2 inches in width, and 15 inches in depth. Each shipping container shall be closed in accordance with method II as specified in the appendix of PPP-B-636.

5.2.2.1 Weather-resistant fiberboard containers. When specified (see 6.2), the shipping container shall be grade V3c, V3s, or V4s, fabricated and closed in accordance with method III as specified in the appendix of PPP-B-636.

5.2.3 Commercial packing. Covers preserved as specified in 5.1, shall be packed in accordance with ASTM D 3951.

5.3 Palletization. When specified (see 6.2), covers, packed as specified in 5.2.2 or 5.2.3, shall be palletized on a 4-way entry pallet in accordance with load type Ia of MIL-STD-147. Pallet type shall be type I (4-way entry), type IV or type V in accordance with MIL-STD-147. Pallets shall be fabricated from wood groups I, II, III, or IV of MIL-STD-731. Each prepared load shall be bonded with primary and secondary straps in accordance with bonding means C and D or film bonding means F or G. Pallet pattern shall be number 39 in accordance with the appendix of MIL-STD-147.

5.4 Marking. In addition to any special marking required by the contract or purchase order, unit packs, shipping containers and palletized unit loads shall be marked in accordance with MIL-STD-129 or ASTM D 3951 as applicable.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. The tag cover is intended to be fitted over one standard identification tag and be irreversibly marked with the individual's spectacle prescription.

6.2 Acquisition requirements. Acquisition documents must specify the following:

a. Title, number, and date of this specification.
b. Issue of DODISS to be cited in the solicitation, and if required, the specific issue of individual documents referenced (see 2.1.1 and 2.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T03:41Z
Check the source to verify that this is the current version before use.

c. When a first article is required (see 3.1, 4.3, and 6.3).
d. Levels of preservation and packing (see 5.1 and 5.2).
e. Type and class of unit load (see 5.2.1).
f. When weather-resistant grade fiberboard shipping containers are required for level B packing (see 5.2.2.1).
g. When palletization is required (see 5.3).

6.3 First article. When a first article is required, it shall be inspected and approved under the appropriate provisions of FAR 52.209. The first article should be a preproduction sample. The contracting officer should specify the appropriate type of first article and the number of units to be furnished. The contracting officer should also include specific instructions in acquisition documents regarding arrangements for selection, inspection, and approval of the first article.

6.4 Raised lettering (see 3.3). Lettering on the cover raised 0.010 inch (with a tolerance of +0.005, -0.000 inch) is suggested in molding of the tag covers (see Drawing 4-1-481).

6.5 Subject term (key word) listing.

Dog tags
Eye glasses
Polyvinyl chloride
Prescription
Spectacles

6.6 Changes from previous issue. Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extensiveness of the changes.

Custodians:

Army - GL
Navy - NU
Air Force - 99

Preparing activity:

Army - GL

(Project 8465-0046)

Review activities:

Army - MD
Navy - MC
Air Force - 82
DPSC - CT

User activities:

Army - SM
Navy - MS
Air Force - 45

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T03:41Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	1. DOCUMENT NUMBER MIL-C-14635B	2. DOCUMENT DATE (YYMMDD) 1990 July 16

3. DOCUMENT TITLE
COVER, PERSONNEL IDENTIFICATION TAG

4. NATURE OF CHANGE *(Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)*

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle Initial)	b. ORGANIZATION	
c. ADDRESS (Include Zip Code)	d. TELEPHONE (Include Area Code) (1) Commercial (2) AUTOVON (If applicable)	7. DATE SUBMITTED (YYMMDD)

8. PREPARING ACTIVITY

a. NAME U.S. Army Natick RD&E Center	b. TELEPHONE (Include Area Code) (1) Commercial: 508-651-5221 (2) AUTOVON: 256-5221
c. ADDRESS (Include Zip Code) Commander, U.S. Army Natick RD&E Center ATTN: STRNC-ES Natick, MA 01760-5014	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT: Defense Quality and Standardization Office 5203 Leesburg Pike, Suite 1403, Falls Church, VA 22041-3466 Telephone (703) 756-2340 AUTOVON 289-2340

Source: https://assist.dla.mil -- Downloaded: 2021-07-30 11Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T03:41Z
Check the source to verify that this is the current version before use.