ZZ-H-601E
June 11, 1990
SUPERSEDING
ZZ-H-601D
February 9, 1981

FEDERAL SPECIFICATION

HOSE AND HOSE ASSEMBLIES, RUBBER (YARN OR FABRIC REINFORCED) WATER SERVICE

This specification is approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers yarn, cord or fabric reinforced hose and hose assemblies for general use in water service.

1.2 Classification.

1.2.1 Grades and classes. Hose covered by this specification will be of the following grades and classes as specified (see 6.2):

Grade 1 - Commercial hose.
Grade 3 - Weather and ozone-resistant hose.
Class 1 - General water inner tube.
Class 2 - Potable water inner tube.

1.2.2 Sizes. Hose covered by this specification will be of the sizes (inside diameter), listed in table I, as specified (see 6.2).

2. APPLICABLE DOCUMENTS

2.1 Government documents.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Commanding Officer (Code 156), Naval Construction Battalion Center, Port Hueneme, CA 93043-5000, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 4720

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:26Z
Check the source to verify that this is the current version before use.

2.1.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation (see 6.2).

Federal Specifications

WW-C-440 - Clamp, Hose (Low Pressure).
WW-C-624 - Coupling, Assembly, Hose (Fire, Garden, Water, Suction).

Federal Standards

FED-STD-H28 - Screw-Thread Standards for Federal Service.
FED-STD-162 - Hose, Rubber, Visual Inspection Guide for.

Military Specification

MIL-H-775 - Hose, Hose Assemblies, Rubber, Plastic, Fabric or Metal (Including Tubing); and Associated Hardware, Packaging of.

Military Standard

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.

(Unless otherwise indicated, copies of federal and military specifications, standards, and handbooks are available from the Standardization Documents Order Desk, Bldg. 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094

2.1.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues are those cited in the solicitation.

Federal Regulation

21 CFR 177.2600 - Code of Federal Regulations (CFR), Title 21 - Food and Drugs, Part 177 Indirect food additives: polymers, Sec. 177.2600 Rubber articles intended for repeated use.

"(The Code of Federal Regulations (CFR) and the Federal Register (FR) are for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402. When indicated, reprints of certain regulations may be obtained from the Federal Agency responsible for issuance thereof.)"

2.2 Other publications. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues are those cited in the solicitation.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:26Z
Check the source to verify that this is the current version before use.

National Sanitation Foundation (NSF)

NSF Std. 61 - Drinking Water System Components - Health Effects.

(Application for copies should be addressed to the National Sanitation Foundation, 3475 Plymouth Road, P.O. Box 1468, Ann Arbor, MI 48106.)

ASTM

ASTM D 297 - Rubber Products - Chemical Analysis.
ASTM D 380 - Testing Rubber Hose.
ASTM D 412 - Rubber Properties in Tension.
ASTM D 413 - Rubber Property Adhesion to Flexible Substrate.
ASTM D 573 - Rubber Deterioration in Air Oven.
ASTM D 1149 - Rubber Deterioration - Surface Ozone Cracking in a Chamber (Flat Specimen).

(Application for copies should be addressed to ASTM, 1916 Race Street, Philadelphia, PA 19103.)

(Non-Government standards and other publications are normally available from the organizations that prepare or distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 First article. When specified (see 6.2), the supplier shall furnish a complete hose length or hose assembly for the first article inspection and approval (see 4.2.1 and 6.5).

3.2 Materials. Materials used shall be free from defects which would adversely affect the performance or maintainability of individual components or of the overall assembly. Materials not specified herein shall be of the same quality used for the intended purpose in commercial practice. Unless otherwise specified herein, all equipment, material, and articles incorporated in the products covered by this specification are to be new and fabricated using materials produced from recovered materials to the maximum extent possible without jeopardizing the intended use. The term "recovered materials" means materials which have been collected or recovered from solid waste and reprocessed to become a source of raw materials, as opposed to virgin raw materials. Unless otherwise specified, none of the above shall be interpreted to mean that the use of used or rebuilt products are allowed under this specification.

3.2.1 Rubber.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:26Z
Check the source to verify that this is the current version before use.

3.2.1.1 Grade 1. The rubber compound used in the construction of the cover and the class 1 tube of grade 1 hose shall be compounded from natural rubber, synthetic rubber or a mixture of natural and synthetic rubber.

3.2.1.2 Grade 3. The rubber compound used in the cover of grade 3 hose shall be weather-resistant and ozone-resistant. The rubber compound used in class 1 tube and other parts of the hose shall be compounded from natural rubber, synthetic rubber, or mixtures of natural and synthetic rubber.

3.2.1.3 Class 2 inner tube. Class 2 inner tube material for grades 1 and 3 hose shall be compounded from natural or synthetic rubber materials that are certified as safe for use in the transport of potable water in accordance with National Sanitation Foundation (NSF) Standard 61, or the Food and Drug Administration (FDA), Code of Federal Regulations 177.2600. The cured rubber shall meet the extraction requirements of 3.9 and 4.5.4.

3.2.2 Other material. Other materials shall be as specified hereinafter.

3.3 Construction. The hose shall consist of:

(a) An inner rubber tube.
(b) A ply or plies of cotton or suitable synthetic yarn or fabric.
(c) An outer rubber cover.

3.4 Reinforcement. The reinforcement shall consist of a ply or plies of braided, knit, or helically wound yarn or plies of fabric. Both the fabric and the yarn shall be made from high grade cotton or synthetic fiber. In accordance with good manufacturing practice, the fabric and the yarn shall be free from defects, sufficiently strong to enable the hose to withstand the hydrostatic test pressure specified in table I, and at the same time be soft and pliable.

3.4.1 Reinforcement plies. The reinforcement plies of yarn may be braided or knitted in one or more plies over the tube or helically wound in multiples of two layers with alternate layers wound in opposite directions. If multiple plies of braided or knitted yarn are used, a distinct layer of rubber compound shall be used between the plies to facilitate adhesion to one another and to the tube and cover. A similar layer may be used between the plies of the helically wound reinforcements. When used, the plies of square woven fabric shall be wrapped at a bias of approximately 45° over the tube. The fabric shall overlap no less than 0.50 inch. The plies of fabric shall adhere to each other and, at the same time, adhere to the inner tube and to the outer cover.

3.5 Length. The length of hose up to and including 1 inch inside diameter shall be 25 feet or multiples thereof up to approximately 500 feet; hose 1.25 and 1.50 inches inside diameter shall be 25 feet or multiples thereof up to approximately 250 feet as specified (see 6.2). Hose over 1.50 inches inside diameter shall be 50 feet.

3.5.1 Tolerance. A tolerance of ±2 percent shall be permitted when tested as specified in 4.5.6.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:26Z
Check the source to verify that this is the current version before use.

3.6 Couplings. Unless otherwise specified (see 6.2), hose shall be furnished without couplings. When specified, a female and a male coupling shall be attached on each end of the hose. The couplings shall be capable of withstanding the test pressures specified in table I without leaking or slipping. On each end of the hose shall be attached one of the following couplings, as specified.

(a) Shank type coupling with interlocking clamps. Hose fitted with interlocking couplings (removable) shall include a serrated nipple and two sections of a clamp equipped for gripping and compressing the hose surface against the nipple. The clamp shall have grooved or waffled interior surfaces and shall have holes for fastening with four bolts. For hose with diameter sizes up to and including 3/4-inch, a two bolt clamp shall be furnished. The protecting end of the nipple shall have a recess in the outer surface to engage the fingers of the clamps. The swivel nut used for tightening the female and male portions of the coupling shall be either hexagonal or octagonal.

(b) Shank type couplings and clamps or ferrules. Shank type couplings and clamps or ferrules, when required, shall be in accordance with WW-C-624, type I or type II. Clamps shall conform to type H of WW-C-440.

(c) Internal expansion ring-type. The internal expansion ring-coupling, when required, shall be in accordance with WW-C-624, type III.

3.6.1 Rubber washers. Female couplings shall be fitted with a rubber washer suitable for the purpose.

3.6.2 Threads. The coupling connection ends shall be threaded in accordance with FED-STD-H28.

3.7 Physical requirements. The hose shall conform to the requirements specified in table I.

3.8 Accelerated aging, grades 1 and 3. After accelerated aging in accordance with 4.5.3, the tensile strength shall be not less than 80 percent of the values specified in table I, and the ultimate elongation shall be not less than 50 percent of the values specified in table I.

3.9 Resistance to water. The extractable nonvolatile matter in class 2 inner tube shall not exceed 21 milligrams per square inch when the tubes are tested as specified in 4.5.4.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:26Z
Check the source to verify that this is the current version before use.

TABLE I. Physical requirements for hose and hose assemblies.

Nominal size in inches (inside diameter)	0.25	0.375	0.50	0.625	0.75	1.0
Tolerance, inside diameter, plus or minus	0.031	0.031	0.031	0.031	0.031	0.062
Thickness, minimum:						
Tube	0.050	0.050	0.060	0.060	0.060	0.060
Cover	0.050	0.050	0.050	0.050	0.050	0.050
Number of reinforcement plies (minimum):						
Wrapped	2	2	2	2	2	2
Braided or knit	1	1	1	1	1	2
Helically wound	2	2	2	2	2	2
Hydrostatic test procedure, minimum, pounds per square inch:						
Proof test 1/	300	300	300	300	300	300
Burst pressure	600	600	600	600	600	600
Friction, minimum, pounds						
Between cover and plies	8	8	8	8	8	8
Between tube and plies	6	6	8	8	8	8
Between plies 2/	8	8	8	8	8	8
Tensile strength (before aging) minimum, pounds per square inch:						
Tube	800	800	800	800	800	800
Cover	1000	1000	1000	1000	1000	1000
Ultimate elongation (before aging) minimum percent:						
Tube	150	150	150	150	150	150
Cover	200	200	200	200	200	200

1/ The hydrostatic proof test shall be made only when hose is purchased with couplings. The hose shall not contract in diameter during the test.

2/ When applicable.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:26Z
Check the source to verify that this is the current version before use.

TABLE I. Physical requirements for hose and hose assemblies - Continued.

Nominal size in inches (inside diameter)	1.25	1.50	2.0	2.50	3.0	3.50	4.0
Tolerance, inside diameter, plus or minus	0.062	0.062	0.062	0.062	0.062	0.062	0.062
Thickness, minimum:							
Tube	0.060	0.060	0.062	0.062	0.094	0.094	0.094
Cover	0.050	0.050	0.062	0.062	0.078	0.078	0.078
Number of reinforcement plies (minimum):							
Wrapped	2	2	2	2	2	2	2
Braided or knit	2	2	2	2	2	2	2
Helically wound	2	2	2	2	2	2	2
Hydrostatic test procedure, minimum, pounds per square inch:							
Proof test 1/	250	250	200	200	200	200	200
Burst pressure	500	500	400	400	400	400	400
Friction, minimum, pounds:							
Between cover and plies	8	8	8	8	8	8	8
Between tube and plies	8	8	8	8	8	8	8
Between plies 2/	8	8	8	8	8	8	8
Tensile strength (before aging) minimum, pounds per square inch:							
Tube	800	800	800	800	800	800	800
Cover	1000	1000	1000	1000	1000	1000	1000
Ultimate elongation (before aging) minimum percent:							
Tube	150	150	150	150	150	150	150
Cover	200	200	200	200	200	200	200

1/ The hydrostatic proof test shall be made only when hose is purchased with couplings. The hose shall not contract in diameter during the test.

2/ When applicable.

3.10 Ozone resistance, grade 3. The rubber cover of grade 3 hose shall show no visible cracking under 2X magnification after testing in accordance with 4.5.5.

3.11 Marking of hose.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:26Z
Check the source to verify that this is the current version before use.

3.11.1 General water hose. Each length of hose shall be marked in a color that contrasts with the color of the hose cover. Marking shall be accomplished either by in-laying a rubber or suitable material brand or by applying a suitable composition ink, bonding that marking onto the cover so that the marking cannot be removed except by mechanical means. The marking shall consist of the manufacturer's name or trademark, the quarter and year of manufacture, the word "water", the symbol "ZZ-H-601", the grade, the class of hose and the words "NOT FOR USE WITH POTABLE WATER". Hose shall be marked at regular intervals of not more than 25 feet. Letters shall be at least 0.125-inch high for sizes 1/4-inch to 5/8-inch inside diameter inclusive. Hose in sizes 3/4-inch and larger shall have letters at least 0.25-inch high. An alternative method of marking may be by the application of a continuous embossed strip along the entire length, vulcanizing the hose, and subsequently removing the strip, leaving a continuous relief identification area. Identification shall include the manufacturer's name or trademark, the work "water", the symbol "ZZ-H-601", the grade, the class of hose, and the words "NOT FOR USE WITH POTABLE WATER" shall be repeated at maximum intervals of 36 inches. When the alternative method of marking is used, no color contrast is required.

3.11.2 Potable water hose, class 2. When class 2 is specified (see 6.2), each hose length shall be marked in the same manner as specified in 3.11.1 except that the words "POTABLE WATER USE ONLY" shall be used in place of "NOT FOR USE WITH POTABLE WATER".

3.11.3 Commercial marking. When specified (see 6.2), commercial marking may be substituted for the marking in 3.11.1 or 3.11.2.

3.12 Workmanship. The quality of workmanship shall be such as to produce hose and hose assemblies that are in accordance with the requirements of this specification.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements (examinations and tests) as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to ensure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items must meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of assuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling in quality conformance does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to acceptance of defective material.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:26Z
Check the source to verify that this is the current version before use.

4.1.2 Component and material inspection. Components and materials shall be inspected in accordance with all the requirements specified herein and in applicable referenced documents.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

(a) First article inspection (see 4.2.1)
(b) Quality conformance inspection (see 4.2.2)

4.2.1 First article inspection. The first article inspection shall be performed on one sample hose length when a first article is required (see 3.1, 6.2, and 6.5). This inspection shall include the examination of 4.4 and the tests of 4.5. The first article may be either a first production item or a standard production item from the supplier's current inventory provided the item meets the requirements of the specification and is representative of the design, construction, and manufacturing technique applicable to the remaining items to be furnished under the contract.

4.2.2 Quality conformance inspection. The quality conformance inspection shall include the examination of 4.4, the tests of 4.5, and the preparation for delivery inspection of 4.6. This inspection shall be performed on the samples selected in accordance with 4.3.

4.3 Sampling. Sampling and inspection procedures shall be in accordance with MIL-STD-105. The unit of product shall be one hose length or hose assembly. All hose and hose assemblies of the same grade, class and size offered for delivery at one time shall be considered a lot for the purpose of inspection (see 6.8).

4.3.1 Sampling for tests. A representative sample 3 feet in length shall be cut from lengths selected from each lot. If hose is ordered with couplings (see 3.6), the supplier shall re-attach couplings to the remaining length from which the 3-foot length was cut. After the couplings have been re-attached, the remaining length of the hose shall be used to conduct the hydrostatic proof pressure test specified in 4.5.1. When the remaining length has passed the hydrostatic proof test, it shall be accepted as a full length of hose.

4.4 Examination. Each of the sample hose lengths selected shall be visually and dimensionally examined to determine conformance with all the requirements of this specification not involving tests. The classification of defects in FED-STD-162 shall be used to determine and evaluate defects through visual inspection.

4.5 Tests. Sample hose sections selected shall be subjected to the applicable tests specified in table II and 4.5.1 through 4.5.6.

4.5.1 Hydrostatic proof test, coupled assemblies. When hose is ordered with couplings, samples selected in accordance with 4.3.1 after couplings have been reattached shall be subjected to the hydrostatic proof test pressure specified in table I in accordance with ASTM Test Method D 380. Water shall be used as the test media. Leakage or other evidence of defects shall be cause for rejection.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:26Z
Check the source to verify that this is the current version before use.

TABLE II. Tests.

Test	Test Method No.	Reference Paragraph
Hose size inside diameter	ASTM D 380	Table I
Hose length	ASTM D 380	4.5.6
Thickness of tube and cover	ASTM D 380	Table I
Tensile strength and elongation of tube and cover	ASTM D 412	Table I
Adhesion	ASTM D 413	Table I
Hydrostatic pressure		
Proof pressure test	ASTM D 380	4.5.1
Burst pressure test	ASTM D 380	4.5.2
Accelerated aging grade 1, class 2 and grade 3, class 2	ASTM D 573	4.5.3
Extraction in distilled water grade 3, class 2	ASTM D 297	4.5.4
Ozone resistance grade 3, cover	ASTM D 1149	4.5.5

4.5.2 Burst test. Hose samples selected shall be subjected to the hydrostatic straight bursting test of ASTM Test Method D 380. Water shall be used as the test media. Failure of the hose at a pressure below the minimum burst pressure specified in table I shall be the cause for rejection of the lot.

4.5.3 Accelerated aging test. Hose samples selected shall be subjected to accelerated aging in accordance with ASTM D Test Method D 573, except that the time for aging shall be 70 hours at a temperature of 212° Fahrenheit (F). After aging, the tensile strength shall be not less than 80 percent of the values specified in table I, and the ultimate elongation shall be not less than 50 percent of the values specified in table I. The die for cutting the specimen shall be die F of ASTM D 412.

4.5.4 Extraction of class 2 hose. The inner tube surface of one hose sample selected in accordance with 4.3.1 shall be extracted in distilled water at reflux temperature in accordance with the following procedures:

(a) Remove a 1-inch ring of rubber inner tube and cut or buff away the outer surface until the surface is smooth.

(b) Cut sufficient length of inner tube to obtain approximately 10 grams, based on a minimum thickness of 3/64-inch.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:26Z
Check the source to verify that this is the current version before use.

(c) Subject sample to distilled water at reflux temperature for 7 hours in an extraction apparatus as shown in figure 1 of ASTM Method D 297.

(d) Filter the solution through # 40 filterpaper and collect the extract in a tared container.

(e) Extract the rubber sample in an additional 50-75 cubic centimeters of distilled water at a reflux temperature for 2 more hours and repeat step (d). Combine the extract solutions and evaporate to dryness. The container and residue shall be dried in an oven at 105° ±3° celsius (C) (221° ±5°F) for one hour, cooled in a desiccator and weighed. The weight of the residue shall be recorded. A blank shall be run using the same amount of distilled water. After making allowance for the blank, the weight of the residue shall be recorded to the nearest milligram.

(f) Report the amount of matter extracted from the rubber in milligrams per square inch of surface, determined as follows: Length (inches) x width (inches) x 2 - total surface area (in^2). Milligrams per square inch = weight of extract/total surface area.

4.5.5 Ozone resistance test. Hose samples selected shall be tested in accordance with ASTM Test Method D 1149. The samples shall be mounted in a 20 percent elongated position, conditioned for 24 hours in an ozone-free atmosphere, then exposed for 72 hours at 104°F to an atmosphere containing 50 parts per hundred million (pphm) of ozone. Visible cracking under 2X magnification at the end of such test shall be cause for rejection.

4.5.6 Hose length measurement. Each hose selected shall be measured for length in accordance with ASTM D 380.

4.6 Preparation for delivery inspection. An examination shall be made to determine compliance with the requirements of section 5. The sample unit shall be one unit prepared for shipment; i.e., one shipping container, one reel or one hose length as applicable. Sampling shall be in accordance with MIL-STD-105.

5. PREPARATION FOR DELIVERY

5.1 Preservation packaging, packing, and marking. Preservation, packaging, packing, and marking shall be in accordance with the requirements of MIL-H-775 with the level of preservation and packaging and the level of packing as specified (see 6.2).

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1.1 Grade 1, class 1. Grade 1, class hose is intended for general water discharge services.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:26Z
Check the source to verify that this is the current version before use.

6.1.2 Grade 3, class 1 or class 2. Grade 3, class 1 or class 2 hose is intended for water applications where resistance to deterioration by weather and ozone is required.

6.1.3 Class 2 inner tube. Grade 1 or grade 3 with class 2 inner tube is for use with potable water.

6.2 Ordering Data. Acquisition documents should specify the following:

(a) Title, number, and date of this specification.
(b) Grade, class, and size (see 1.2.1, 1.2.2 and 3.11.2)
(c) Issue of DODISS to be cited in the solicitation, and if required, the specific issue of individual documents referenced (see 2.1.1).
(d) If first article is required (see 3.1).
(e) Length of hose required (see 3.5).
(f) If couplings are required (types) (see 3.6).
(g) When commercial hose marking is acceptable (see 3.11.3).
(h) Levels of preservation-packaging and packing required (see 5.1).

6.3 Working pressure. The maximum working pressures for the hose covered by this specification are shown in table III.

TABLE III. Maximum working pressures.

Sizes	Maximum working pressure
(inches)	(psi)
0.25	150
0.375	150
0.50	150
0.625	150
0.75	150
1.0	150
1.25	125
1.50	125
2.0	100
2.5	100
3.0	100
3.5	100
4.0	100

6.4 Data requirements. When this specification is used in an acquisition and data are required to be delivered, the data requirements should be developed as specified by an approved Data Item Description (DD Form 1664) and delivered in accordance with the approved Contract Data Requirements List (CDRL), incorporated into the contract. When the provisions of DoD FAR Supplement, Part 27, Sub-Part 27.475-1 (DD Form 1423) are invoked and the DD Form 1423 is not used, the data should be delivered by the contractor in accordance with the contract or purchase order requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:26Z
Check the source to verify that this is the current version before use.

6.5 First article. When a first article inspection is required, the item will be tested and should be a first production item or it may be a standard production item from the contractor's current inventory as specified in 4.2.1. The first article should consist of a sample hose, or hose assembly. The contracting officer should include specific instructions in acquisition documents regarding arrangements for examination, test, and approval of the first article.

6.6 Yarn or fabric-reinforced hose. The terms yarn or fabric-reinforced hose, as defined in this specification cover the following types: wrapped, braided, knit, or helically wound reinforcements.

6.7 Part or Identifying Number (PIN). The PIN to be used for hoses acquired to this specification are created as follows:

ZZ-H-601 X X XX XXX

Federal Specification part number _____

Grade number _____

Class number _____

Hose size code number (see 6.7.1) _____

Hose length in feet _____

6.7.1 Hose size. Hose size is designated by a two-digit code number (see table IV).

TABLE IV. Hose size code number.

Hose size code no.	04	06	08	10	12	16	20
Hose ID (inches)	0.25	0.375	0.50	0.625	0.75	1.0	1.25

Hose size code no.	24	32	40	48	56	64	
Hose ID (inches)	1.50	2.0	2.5	3.0	3.5	4.0	

6.8 Sampling Procedures. Recommended inspection level is II and Acceptable Quality Level (AQL) is 2.5 (See 4.3).

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:26Z
Check the source to verify that this is the current version before use.

MILITARY INTERESTS:

Custodians:

Army - ME
Navy - YD
Air Force - 99

Review activities:

Navy - SH
Air Force - 82
DLA - CS

User Activities:

Army - AT
Navy - MC, OS

CIVIL AGENCY COORDINATING ACTIVITIES:

DOT - ACO
GSA - 7FXEG
HHS - FEC

PREPARING ACTIVITY:

Navy - YD

(Project 4720-0771)

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies and other documents referenced herein.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:26Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	1. DOCUMENT NUMBER 22-H-601E	2. DOCUMENT DATE (YYMMDD) 90/06/11

3. DOCUMENT TITLE
Hose and Hose Assemblies, Rubber (Yarn or Fabric Reinforced) Water Service

4. NATURE OF CHANGE (Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed)

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle Initial)	b. ORGANIZATION	
c. ADDRESS (Include Zip Code)	d. TELEPHONE (Include Area Code) (1) Commercial (2) AUTOVON (If applicable)	7. DATE SUBMITTED (YYMMDD)

8. PREPARING ACTIVITY

a. NAME C. R. Lederer Equipment Criteria Development Div.	b. TELEPHONE (Include Area Code) (1) Commercial: (805) 982-5801 ext 452 (2) AUTOVON: 551-5801 ext 452
c. ADDRESS (Include Zip Code) Commanding Officer (156) Naval Construction Battalion Center Port Hueneme, CA 93043-5000	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT: Defense Quality and Standardization Office 5203 Leesburg Pike, Suite 1403, Falls Church, VA 22041-3466 Telephone (703) 756-2340 AUTOVON 289-2340

DD Form 1426, OCT 89

Source: https://assist.dla.mil -- Downloaded: 20201020112202
Check the source to verify that this is the current version before use.