A-A-54584
10 February 1992

COMMERCIAL ITEM DESCRIPTION

RAZOR, SURGICAL PREPARATION

The General Services Administration has authorized the use of this Commercial Item Description as a replacement for Federal Specification GG-R-001308A which is cancelled.

This commercial item description covers a straight safety razor and blades suitable for use in preparing patients for surgical procedures.

Salient characteristics:

The razor and blades covered by this specification shall be of the types and compositions as specified.

Type I - Razor, Surgical Preparation
Type II - Blade, Surgical Preparation Razor

Style 1. Corrosion-resisting steel, coated
Style 2. Corrosion-resisting steel, uncoated

Material.

Razor. The safety razor shall be fabricated from nickel silver containing 10.0 ± 1.0 percent nickel. The sheath of the blade holder and the razor guard shall be 0.20 inch thick. The core of the blade holder shall be 0.114 inch thick. The handle shall be 0.036 inch thick or 3/4 hard Class 3, Type 301 austenitic stainless steel sheet 0.030 inch thick and shall be in accordance with American Society for Testing and Materials (ASTM) Designation F899 for composition only. The pin rivet and washers shall be fabricated of nickel silver or silicon bronze.

Blade. The rib of the blade shall be fabricated from plated carbon steel conforming to 1008 of ASTM A29 for composition only or cold rolled aluminum strip conforming to chemical composition for aluminum alloy 3003 of QQ-A-250/2E. The cutting blade shall be fabricated from corrosion-resisting steel having the following chemical composition.

AMSC N/A FSC 6515

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:36Z
Check the source to verify that this is the current version before use.

	Regular (%)	Alternate (%)
Carbon	0.58 to 0.70	0.90 to 1.05
Silicon	0.15 to 0.25	0.15 to 0.50
Maganese	0.90 to 1.10	0.20 to 0.80
Chromium	12.0 to 14.0	12.0 to 14.7
Phosphorus	0.040 (maximum)	0.025 (maximum)
Sulfur	0.040 (maximum)	0.020 (maximum)

The beveled edge shall be treated with a fluorocarbon-telomer coating such as sintered polytetrafluroethylene.

Design and dimensions. The surgical razor and the blade shall be in accordance with Defense Personnel Support Center (DPSC) Drawing No. 20204 for design and dimensions. The straight razor and blade shall be suitable for use in preparing patients for surgical procedures.

Construction.

Razor. The razor shall be a straight safety razor, and shall consist of a blade holder, a handle and a razor guard. The razor shall properly accommodate the removable and reversible blade (type II).

Blade holder. The blade holder shall consist of a core, a grooved insert, and a sheath.

Core. One end of the core shall be rounded off and the upper surface provided with a crescent-shaped, smooth grip for the fourth finger, and with a slightly depressed serrated thumb grip on the lower side. The upper surface of the serrated thumb grip shall be grooved to receive the inner end of the grooved insert.

Grooved insert. The lower exposed surface of the grooved insert shall have a full length groove of adequate size in the center width, when assembled in the blade holder to hold the rib of the blade securely and to prevent any appreciable side or end movement of the blade. The inner end shall fit securely in the grooved end of the core and the outer end shall be securely held in place by the lip on the end of the sheath.

Sheath. The width of the sheath shall be sufficient to fit tightly over the upper surface of the grooved insert and core and extend down on each side flush with lower surface of the core, except that the sides between the serrated thumb grip and the free end shall be of uniform width, and one side

Source: https://assist.dla.mil -- Downloaded: 202610-26T09:36Z
Check the source to verify that this is the current version before use.

section between the serrated thumb grip and the inner end shall be extended over the lower surface of the core to the opposite side edge. The center portion of the free end shall be provided with a lip to hold the grooved insert securely in place. The upper corners of the free end shall be slightly rounded. The inner ends shall be assembled in the sheath and shall be securely held by crimping.

Handle. The handle and the assembled blade holder shall be attached by a pin rivet and two 5/16 inch washers. The washers shall be placed on the pin rivet between the handle and the holder. The rivet shall hold the parts with sufficient tension for the blade holder to remain folded in the handle to protect the blade when closed, and to stay in an open position during use, but without excessive tension which would prevent the holder from being freely opened and closed.

Razor guard. The razor guard shall be a removable and reversible tooth guard, as shown in the drawing.

Blade. The blade shall be two-piece, consisting of a rib and a cutting blade. The rib shall securely hold the cutting blade. The cutting blade shall have a single cutting edge. The central portion of the cutting blade shall have an optional rectangular hole, provided the hole is required during the manufacturing process, and shall not exceed the maximum limits specified on the drawing.

Finish.

Razor. The razor components fabricated from nickel silver sheet metal shall be chromium plated. All exterior surfaces of the razor shall have a bright polished finish. The outer ends of pin rivet attaching the blade holder in the handle shall be smoothly peened.

Blade. The cutting edge of the blade shall be bilaterally ground and honed to razor sharpness. The final honed bevels shall be flat, smooth and continuous throughout the entire length. Except for the extreme 1/8 inch at either end, the cutting edge shall be free from micro-cracks, and not more than 5 percent of the edge length shall show nicks, notches, or unhoned portions when viewed microscopically at a magnification of 100 diameters. The remainder of the blade shall have a smooth, bright polished finish. The entire blade shall be free from rust and scale.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:36Z
Check the source to verify that this is the current version before use.

Hardness. The cutting blade shall be uniformly hardened to the hardness range shown below for the applicable composition when tested in accordance with ASTM Designation E18 or E92.

Hardness Values for Cutting Blade.

Material	Rockwell Superficial hardness number. 30-N Scale 1/	Vickers hardness. 2/
Style 1 - Corrosion-resisting steel, coated		
Regular (0.58 to 0.70% Carbon)	71-75	550-650
Alternate (0.90 to 1.05% Carbon)	71-75	550-650
Style 2 - Corrosion-resisting steel, uncoated		
Regular (0.58 to 0.70% Carbon)	77-81	690-800
Alternate (0.90 to 1.05% Carbon)	77-81	690-800

1/ Using a 30-kilogram force and a superficial diamond penetrator.

2/ Using a 2-kgf load.

Corrosion-resistance. The razor shall be capable of being sterilized for surgical use. There shall be no evidence of injury to the razor, such as corrosion, scumming or pitting when boil tested in accordance with ASTM Designation F1089.

Identification marking. The razor, the removable tooth guard and the blade rib shall be permanently and legibly marked with the name or trademark of the manufacturer or supplier.

Workmanship. The razor and blades shall be free from defects such as nicks, feathers, pits, jagged edges and burrs which detracts from their appearance or impairs their serviceability.

Unit. Each (EA). One razor (type I) as specified, constitutes one unit. Package (PG). One package containing five blade (type II, Style 1) or fifty blade (type II, style 2), as specified, constitutes one unit.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:36Z
Check the source to verify that this is the current version before use.

Quality Assurance Provisions.

Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of three years after the delivery of the supplies to which such records relate.

Inspection. Inspection, as used herein, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

Sampling for inspection. Sampling for inspection shall be conducted in accordance with MIL-STD-105. Where feasible, the same sample shall be used for the determination of two or more inspection, examination, and test characteristics. The unit of product for inspection, examination, and test purposes shall be one razor and blade. Unless otherwise specified, sampling for examination shall be conducted at inspection level II, except for dimensions which shall be conducted at inspection level S-1, AQL 2.5 (percent defective) and sampling for tests (when applicable) shall be conducted at inspection level S-1. Acceptance number for tests shall be zero (0) for all samples.

Contractor certification. The contractor shall certify that the product offered meets the salient characteristics of this description and conforms to the producers' own drawings, specifications, standards, and quality assurance practices. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Source: https://assist.dla.mil -- Downloaded: 202610-26T09:36Z
Check the source to verify that this is the current version before use.

Tests. Tests shall be conducted to determine compliance with specification requirements.

Chemical analysis. In the absence of contractor certification for the raw material, a chemical analysis shall be conducted. The chemical analysis shall be performed by reagent solutions, combustion methods, nonemission methods, or by spectrochemical analysis. Any ASTM method shall be acceptable.

Metric products. Products manufactured to metric dimensions will be considered on an equal basis with those manufactured using inch/pound units, providing they fall within the tolerances specified using conversion tables contained in the latest revision of Federal Standard No. 376, and all other requirements of this document are met. If a product is manufactured to metric dimensions and those dimensions exceed the tolerances specified in the inch/pound units, a request should be made to the contracting officer to determine if the product is acceptable. The contracting officer has the option of accepting or rejecting the product.

Regulatory requirements.

Federal Food, Drug and Cosmetic Act. If the product covered by this document has been determined by the U.S. Food and Drug Administration to be under its jurisdiction, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of the Federal Food, Drug and Cosmetic Act, as amended, and regulations promulgated thereunder. In addition, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of all other applicable Federal, State, and local statutes, ordinances, and regulations.

Recovered materials. The offeror/contractor is encouraged to use recovered material in accordance with Federal Acquisition Regulation Subpart 23.4 to the maximum extent practical.

Preservation, packaging, packing, labeling, and marking. Unless otherwise specified, preservation, packaging and packing shall be to a degree of protection to preclude damage to containers and/or contents thereof under normal shipping conditions, handling, etc., involving shipment from the supply source to the receiving activity, plus reshipment from receiving activity, and shall conform to applicable carrier's rules and regulations. Intermediate and exterior package quantities and labeling and marking shall be as specified in the contract and/or order.

Source: https://assist.dla.mil -- Downloaded: 202610-26T09:36Z
Check the source to verify that this is the current version before use.

NOTE: The following National Stock Numbers are covered by this document.

National Stock Number	Item Identification
6515-00-754-0425	RAZOR, SURGICAL PREPARATION, Straight, Corrosion-resisting steel
6515-00-754-0426	BLADE, SURGICAL PREPARATION, Razor, 5s
6515-01-147-0210	BLADE, SURGICAL PREPARATION, Razor, 50s

Ordering data. Intermediate/exterior package quantities, labeling, and marking must be as specified in the contract and/or order.

MILITARY INTERESTS:

Custodians:

Army-MD
Navy-MS
Air Force-03

PREPARING ACTIVITY:

DOD-MB

Agent:

DLA-DM

CIVIL AGENCY COORDINATING ACTIVITIES:

VA-OSS
PHS
FDA-MPQAS

PROJECT NO. 6515-5037
LOCATION: KD#1/RAZOR

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:36Z
Check the source to verify that this is the current version before use.