QQ-A-250/5F
INT. AMENDMENT-2
7 June 1983
USED IN LIEU OF
Amendment-1
October 22, 1974

INTERIM AMENDMENT

TO

FEDERAL SPECIFICATION

ALUMINUM ALLOY ALCLAD 2024, PLATE AND SHEET

This interim amendment was developed by the Naval Air Systems Command, Department of the Navy, Washington, DC 20361, based upon current available technical information. It is recommended that Federal agencies use it in procurement and forward recommendations for changes to the preparing activity at the address shown above.

The General Services Administration has authorized the use of this interim amendment as a valid exception to QQ-A-250/5F, dated January 18, 1971.

PAGE 1

Paragraph 1.2.1, delete "T36" and "T86".

Section 2, add the following:

"Federal Standards

FED-STD-184 - Identification Marking of Aluminum, Magnesium and Titanium."

FSC 9535

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:04Z
Check the source to verify that this is the current version before use.

Table I, delete in entirety and substitute:

"Table I. Chemical Composition 1/

Element	CORE 2024 Percent		CLADDING 1230 Percent
	Minimum	Maximum	Maximum (except as noted)
Silicon	-	0.50	2/
Iron	-	0.50	2/
Copper	3.8	4.9	0.10
Manganese	0.30	0.9	0.05
Magnesium	1.2	1.8	0.05
Chromium	-	0.10	-
Nickel	-	-	-
Zinc	-	0.25	0.10
Titanium	-	0.15	0.03
Others, each	-	0.05	0.03 3/
Others, Total 4/	-	0.15	-
Aluminum	Remainder		99.30 Minimum

1/ Analysis shall routinely be made only for the elements specifically mentioned in table I. If, however, the presence of other elements is indicated or suspected in amounts greater than the specified limits, further analysis shall be made to determine that these elements are not present in excess of specified limits

2/ Iron plus silicon 0.7 percent maximum

3/ Vanadium 0.05 percent maximum

4/ The sum of those "others" metallic elements 0.010 percent or more each, expressed to the second decimal before determining the sum"

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:04Z
Check the source to verify that this is the currentversion before use.

PAGE 3

Table II, delete all mechanical property requirements for "T3, T36 and T86" tempers and substitute the following:

"Temper	Widths	Thickness	Tensile strength, minimum	Yield strength at 0.2 percent offset or at extension indicated		Elongation in 2 in. or 4 times D 1/, 2/, minimum
				Minimum	Extension under load	
	Inches	Inches	Psi	Psi	Inch/Inch	Percent
T3 5/	All	0.008 thru 0.009	58,000	39,000	0.0061	10
	All	.010 thru .020	59,000	39,000	.0061	12
	All	.021 thru .062	59,000	39,000	.0061	15
	All	.063 thru .128	61,000	40,000	.0060	15
	All	.129 thru .249	62,000	40,000	.0060	15 "

PAGE 7

Paragraph 3.5, delete in its entirety and substitute the following:

"3.5 Marking. In addition to the marking required in FED-STD-184, plate and sheet in T3, T4, T81, T351, T361, T851 and T861 tempers shall be identified by a lot number marked in at least one location on each piece."

MILITARY INTEREST:

Custodian

Army-MR
Navy-AS
Air Force-20

Review Activities

Army-AR, CR, EA, EC, MI
Navy-OS, SH
Air Force-99
DLA-IS

User Activities

Navy-MC

CIVIL AGENCY COORDINATING ACTIVITIES:

GSA-FSS
NASA-JFK
DOE-BPA

PREPARING ACTIVITY:

NAVY-AS

DoD Project 9535-0347

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:04Z
Check the source to verify that this is the current version before use.