MILITARY SPECIFICATION

PROPELLANT M30
FOR USE IN CHARGE, PROPELLING, 105MM, M200

This specification is approved for use by the US Army Armament Munitions and Chemical Command, and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers M30 Propellant for use in the M200 Propelling Charge.

1.2 Classification. The propellant shall be Type I, cylindrical, multi-perforated grains.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications and standards. Unless otherwise specified, the following specifications and standards of the issue listed in that issue of the Department of Defense Index of Specifications and Standards (DoDISS) specified in the solicitation, form a part of this specification to the extent specified herein.

SPECIFICATIONS

MILITARY

MIL-A-48078 - Ammunition, Standard Quality Assurance Provisions, General Specification for

MIL-C-48360 - Charge, Propelling, M200, For 105MM, Howitzer M119, Loading, Assembling and Packing

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Commander, U S Army Armament Research, Development and Engineering Center, Attn: AMSMC-QA, Dover, New Jersey 07801-5001 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter

AMSC N/A FSC 1376
DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 202640-23T03:39Z
Check the source to verify that this is the currentversion before use.

STANDARDS

MILITARY

MIL-STD-414 - Sampling Procedures and Tables for Inspection by Variables for Percent Defective

MIL-STD-652 - Propellants, Solid for Cannons, Requirements and Packing

2.1.2 Other Government documents, drawings and publications. The following other Government documents drawings and publications form a part of this specification to the extent specified herein.

DRAWINGS

US ARMY RESEARCH DEVELOPMENT AND ENGINEERING CENTER (ARDEC)

9282042 - Charge; Propelling M200 Loading Assembly

9289185 - Cartridge 105MM, HE, M760 with M200 Propelling Charge, 105MM Howitzer M119 Loading and Assembly

(Copies of specifications, standards, handbooks, drawings, and publications required by manufacturers in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting officer.)

2.1.3 Order of precedence. In the event of a conflict between the text of this specification and the reference cited herein, the text of this specification shall take precedence.

3. REQUIREMENTS

3.1 Material. The propellant shall be M30, Type I conforming to the requirements of MIL-STD-652 and Drawing (Dwg) 9282042.

3.2 Ballistic assessment requirements. The propellant when fired in the L20A1 Tube with the M1 projectile (see 4.5) shall comply with the following requirements; at 70 degrees Fahrenheit (^{O}F) and standard weapon conditions. The propellant shall be capable of assessment to a velocity of 2020 $\pm$ 25 feet per second (fps) with an expected average pressure not to exceed 46,500 pounds per square inch (psi) and a charge weight not to exceed 73 ounces (oz) as determined in 4.5.1.1.

Source: https://assist.dla.mil -- Downloaded: 202610-23T03:39Z
Check the source to verify that this is the current version before use.

3.3 Ballistic uniformity requirements. The propellant when fired in the L20A1 Tube with the M1 projectile (see 4.5.1) shall comply with the following requirements when tested as specified in 4.5.1.2.

3.3.1 Uniformity of velocity. The standard deviation of velocity for the lot at 70°F shall not exceed 8.0 fps.

3.3.2 Average pressure. At 70°F and standard weapon conditions, the propellant shall not produce an average pressure greater than 46,500 psi.

3.3.3 Individual maximum pressure (IMP). The propellant shall not produce an individual pressure greater than 57,000 psi when fired at 145°F.

3.4 Initial production. This specification contains provisions for initial production inspection. Requirements for the submission of initial production inspection samples by the contractor shall be as specified in 4.5.1.2.1

3.5 Preproduction inspection. This specification contains provisions for preproduction inspection. Requirements for the submission of preproduction inspection samples by the contractor shall be as specified in 4.3.1.

3.6 Workmanship. The best commercial practices shall be used in the formulation of propellant furnished under this specification, and all other applicable documents. The propellant and its standard ingredients shall be protected from the action of direct sunlight and acid fumes. Unless other specified, no reground propellant or nitrocellulose shall be used in the manufacture of propellant procured under this specification.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection and standard quality assurance provisions. Unless otherwise specified herein or in the contract, the provisions of MIL-A-48078 shall apply and are hereby made a part of this detail specification. Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements, specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T03:39Z
Check the source to verify that this is the current version before use.

4.2 Classification of inspections. The following types of inspection shall be conducted on the unit product:

a. Preproduction Sample Inspection

b. Quality Conformance Inspection.

4.3 Preproduction sample (pilot lots). The preproduction sample is intended to provide the necessary information to establish the propellant granulation needed to meet the required ballistic parameters.

4.3.1 Submission. The Contractor shall select propellant granulations for approval by Government Engineering and Product Assurance, which, from experience, are expected to bracket the requirements of this specification. The contractor shall submit a preproduction sample as designated by the Contracting Officer for evaluation in accordance with 4.3.2, usually consisting of up to three pilot lots of approximately 3000 lb each, representing each of the candidate granulations.

4.3.2 Inspections to be performed. Each of the pilot lots comprising the preproduction sample and submitted in accordance with 4.3.1 may be subjected by the Government to any or all of the requirements of the applicable drawings and specifications.

4.3.3 Rejection. Government Engineering and Product Assurance personnel and the Contractor shall review the pilot lot test data and shall select a granulation which best fits the requirements of this specification. The Technical Agency shall notify the Contracting Officer of the selected granulation. The Contracting Officer shall designate the preproduction sample as acceptable and shall authorize the Contractor to produce the selected granulation for regular production. If the pilot lots submitted fail to meet or bracket the requirements of this specification, a new preproduction sample shall be submitted in accordance with 4.3.1. Until the preproduction sample is designated acceptable, the Contractor is in no way authorized by the Government to initiate regular production, unless otherwise directed by the Contracting Officer. All future production lots should be of the same basic granulation as the selected granulation authorized for regular production.

4.4 Quality conformance inspection.

4.4.1 Inspection lot formation. Inspection lots shall comply with the lot formation provisions of MIL-A-48078.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T03:39Z
Check the source to verify that this is the current version before use.

4.4.2 Examination and testing.

PRECAUTION - This specification covers sampling and testing of chemical, toxic or explosive materials which are potentially hazardous to personnel. Accordingly, it is emphasized that all applicable safety rules, regulations and procedures must be followed in handling and processing these materials.

4.4.2.1 Sampling for laboratory testing (see 3.1). Each lot of propellant shall be sampled and tested for composition form, dimensions and chemical/physical properties in accordance with MIL-STD-652. (see 6.4)

4.4.2.2 Sampling for ballistic testing (see 3.2). Each lot of propellant shall be sampled for Proving Ground tests in accordance with MIL-STD-652.

4.4.2.3 Charge establishment (see 3.2) If the lot does not meet the applicable requirements, testing shall cease and the Test Director shall immediately notify the procuring activity.

4.4.2.4 Velocity uniformity (70°F) (see 3.3.1). If the product of the factor (.73 for initial production, .69 for subsequent production) times the velocity standard deviation of the rounds tested in accordance with 4.5.1.2 exceeds the applicable requirement, apply referral criteria in accordance with 4.5.1.4. If the referral criteria cited do not apply, the lot shall be rejected. The factor makes allowance for the probability that a standard deviation from a smaller sample size exceeds the true standard deviation by chance alone. The standard deviation shall be calculated with (n-1) as the divisor in a standard statistical technique equivalent to that shown in MIL-STD-414.

4.4.2.5 Average pressure (see 3.3.2). If the average pressure obtained exceeds the applicable requirements, apply referral criteria in accordance with 4.5.1.4. If the referral criteria cited do not apply, the lot shall be rejected.

4.4.2.6 Individual maximum pressure (IMP) (see 3.3.3). If any individual pressure observed during the uniformity series, when corrected to standard conditions and recommended charge weight, exceeds the applicable requirements, the lot shall be rejected.

Source: https://assist.dla.mil -- Downloaded: 202610-23T03:39Z
Check the source to verify that this is the current version before use.

4.5 Methods of Inspection.

4.5.1 Proving ground assessments . This test shall be performed at a Government Proving Ground in accordance with the applicable acceptance test procedure using M1, HE projectiles inert loaded within 0.02 lb of an as fired weight of 33.0 lb and fired in an L20A1 Tube with wear no less than 50% of life remaining. All charges shall be temperature conditioned in a large conditioning box, with adequate air circulation to assure uniform conditioning, at the required temperature for a minimum of 24 hours and assurance will be made that, when fired, the charges are at the conditioning temperature. The following tolerances shall apply to all temperature conditionings: -60°F, +5°F; 70°F, ± 2.5°F, 145°F, -5°F. Copper crusher gages (2) shall be used to measure the maximum chamber pressure of each charge. Velocity coils will be used to measure the muzzle velocity of each charge. Test charges shall be assembled in accordance with drawing 9282042 and MIL-C-48360.

4.5.1.1 Charge establishment (see Table I)

4.5.1.1.1 Charge slope method. Three or more groups of rounds loaded with selected charge weights of propellant (weights selected should bracket expected service charge weight) shall be conditioned and fired at 70°F. Three calibration rounds shall also be conditioned and fired at 70°F, prior to the test rounds. From the data obtained, a charge weight shall be calculated which will yield the prescribed service velocity (see 3.2). This calculated charge weight shall then be loaded into rounds for the uniformity series (see 4.5.1.2). The difference between the corrected velocity obtained during the uniformity series and the service velocity shall be compensated for by a final adjustment in charge weight using the slope of the velocity charge weight curve previously established. The resultant will be the recommended charge weight.

4.5.1.1.2 Constant slope method. After ten (10) lots of a given production series have been fired to provide a good knowledge of the propellant characteristics, the charge slope method of assessment may be discontinued and the charge weight determined by the constant slope method. A composite charge weight versus velocity curve and charge weight versus pressure curve can be established from test results generated. This curve can then be used as in 4.5.1.1.1 to calculate the charge weight needed to achieve service velocity. This calculated charge weight is then to be loaded into charges for the uniformity series and final adjustment is to be made as indicated above for the charge slope method (see 4.5.1.1.1). The resultant will be the recommended charge weight.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T03:39Z
Check the source to verify that this is the current version before use.

4.5.1.2 Uniformity (See Table I).

4.5.1.2.1 Initial production. Thirty (30) charges shall be assembled with the calculated charge weight (see 4.5.1.1.1) of propellant. Ten charges each shall be conditioned to -60°F, 70°F, and 145°F (as indicated by thermo-coupled control charge). Charges fired at 70°F shall be fired alternately with calibration charges and shall be corrected to standard weapon/firing conditions. Firing results at all temperatures shall be corrected to standard projectile weight (see 4.5.1) and to recommended charge weight conditions (i.e., the difference between calculated (as fired) charge weight and recommended charge weight). The means and standard deviations of the velocities and pressures at all firing temperatures shall be calculated using corrected results. The initial production lots represent the first three consecutive lots from each manufacturer which have been produced and met the acceptance criteria of this specification.

4.5.1.2.2 Subsequent production. Fourteen (14) charges shall be assembled with the established charge weight of propellant. Seven charges each shall be conditioned to 70°F and 145°F (as indicated by thermocoupled control round). Charges fired at 70°F shall be fired alternately with calibration charges and shall be corrected to standard weapon/firing conditions (i.e., the difference between calibration performance under test conditions and standard conditions). Firing results at both temperatures shall be corrected to standard projectile weight (see 4.5.1) and to recommended charge weight conditions (i.e., the difference between as fired charge weight and recommended charge weight). The means and standard deviations of the velocities and pressures at both firing temperatures shall be calculated using corrected results.

4.5.1.3 Retest criteria. A lot shall be retested whenever any of the following conditions exist or whenever the proving ground deems it necessary.

a. The final adjustment in charge weight exceeds 1.0 ozs of the charge weight used in uniformity firings, retest for uniformity in accordance with 4.5.1.2.

b. If for any reason, the Proving Ground considers that test conditions have detrimentally affected the test results, additional charges as required shall be tested.

4.5.1.4 Referral criteria. A test lot shall be referred to the procuring activity for disposition whenever any of the following conditions exist or whenever the proving ground deems it necessary.

Source: https://assist.dla.mil -- Downloaded: 202610-23T03:39Z
Check the source to verify that this is the current version before use.

a. Calibration rounds fired in any test phase fail to comply with Section 3 of this specification.

b. Calibration correction applied exceeds two percent of the expected muzzle velocity.

c. Calibration components are not available.

d. Number of test or calibration results utilized in calculations is less than specified.

e. Any unusual occurrences during ballistic testing, such as excessive delays between rounds, stickers, poor projectile flights, etc. Each such event shall be reported in detail on the applicable firing record.

f. Test lot fails velocity standard deviation or average pressure requirement at 70°F and any extreme test value is an outlier.

The following test shall be performed to determine if a single test result is an outlier. With a sample size of 7 at a significance level of 0.05, the critical value (T_C) is 0.507. Calculate a test value (T_t) as follows:

For Low Outlier

$$T_t = \frac{(X_2 - X_1)}{(X_7 - X_1)}$$

For High Outlier

$$T_t = \frac{(X_7 - X_6)}{(X_7 - X_1)}$$

Where:

X_1 = test result being tested as low outlier
X_2 = test result adjacent to X_1, after all the test results are ordered from smallest to largest
X_6 = test result adjacent to the largest test result
X_7 = test result being tested as high outlier

X_1 or X_7 is an outlier of T_t is greater than T_C.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T03:39Z
Check the source to verify that this is the current version before use.

With a sample size of 10 at a significance level of 0.05, the critical value (T_c) is .477. Calculate a test value (T_t) as follows:

For Low Outlier

$$T_t = \frac{(X_2 - X_1)}{(X_9 - X_1)}$$

For High Outlier

$$T_t = \frac{(X_{10} - X_9)}{(X_{10} - X_2)}$$

Where:

X_1 = test result being tested as low outlier
X_2 = test result adjacent to X_1, after all the test results are ordered from smallest to largest
X_9 = test result adjacent to largest test result
X_{10} = test result being tested as high outlier

X_1 or X_{10} is an outlier of T_t is greater than T_c.

5. PACKAGING

5.1 Packing and marking. Packing and marking shall be in accordance with MIL-STD-652, except that all propellant designated for use as reference shall be packed level A.

6. NOTES

6.1 Ordering data. Ordering data shall be in accordance with MIL-A-48078 with the following exceptions:

6.1.1 Acquisition requirements. Acquisition requirements of MIL-A-48078 shall apply.

6.1.2 Contract data requirements. One copy of each of the Propellant Description Sheet and the Acceptance Test Summary shall be forwarded to each office designated by the contracting officer. Copies of data item description required by the contractor in connection with specific acquisition functions should be obtained from the procuring activity.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T03:39Z
Check the source to verify that this is the current version before use.

6.2 Proving ground test summary (see Table I).

TABLE I - Proving Ground Summary

TEST PHASE	Temp (°F)	Sample Size Cal	Sample Size Test	Velocity Requirements: Service Vel (fps)	Velocity Requirements: Vel std dev (fps)	Pressure Requirements: Max Avg Press (psi)	Pressure Requirements: PIMP (psi)
Charge Establishment	70	3	9	2020	N/A	46,500	N/A
Uniformity	-60*	N/A	10	N/A	N/A	N/A	N/A
	70*	10	10	2020	8.0	46,500	N/A
	145*	N/A	10	N/A	N/A	N/A	57,000
	70**	7	7	2020	8.0	46,500	N/A
	145**	N/A	7	N/A	N/A	N/A	57,000

* Initial Production Only

** Subsequent Production

6.3 Drawings. Drawings listed in Section 2 of this specification under the heading US Army Armament Research Development and Engineering Center (ARDEC) may also include drawings prepared by, and identified as, Edgewood Arsenal, Frankford Arsenal, Rock Island Arsenal, (ARRADCOM) or Picatinny Arsenal drawings. Technical data originally prepared by these activities is now under the cognizance of ARDEC.

6.4 Surveillance sample. Samples shall be forwarded to US Army Armament Research Development and Engineering Center (ARDEC), Dover, NJ 07801-5001, ATTN: SMCAR-LCE-MP for the propellant surveillance test program in accordance with MIL-STD-652.

6.5 Individual maximum pressure. Individual maximum pressure specified in 3.3.3 is based on firing with an M1 projectile loaded to an as fired weight of 33.0 lbs. Any change in weight or projectile will require an adjustment of this pressure requirement.

Source: https://assist.dla.mil -- Downloaded: 202610-23T03:39Z
Check the source to verify that this is the currentversion before use.

6.6 Test rounds. Test rounds shall be assembled in accordance with drawings 9289085 and 9282042.

Custodian:
Army-AR

Preparing activity:
Army - AR

(Project 1376 -A262)

Source: https://assist.dla.mil -- Downloaded: 202610-23T03:39Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
MIL-P-70539	PROPELLANT M30 FOR USE IN CHARGE, PROPELLING, 105MM, M200

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ USER
	☐ MANUFACTURER
	☐ OTHER *(Specify)*: _____

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

Source: https://assist.dla.mil – Downloaded: 2026-02-23T03:39Z
Check the source to verify that this is the current version before use.