MIL-L-43704
AMENDMENT-1

23 JUL 1975

MILITARY SPECIFICATION

LEATHER, CATTLEHIDE, CHROME TANNED, FATLIQUORED

This amendment forms a part of Military Specification MIL-L-43704, dated 26 May 1970, and is approved for use by all Departments and Agencies of the Department of Defense.

PAGE 2

3.3.5. Delete and substitute:

"3.3.5 Stitch tearing strength. At least 80 percent of the specimens tested shall have stitch tearing strength values of not less than 30 pounds when tested as specified in 4.3."

3.3.6. Delete and substitute:

"3.3.6 Shrinkage temperature. The leather shall not shrink before the temperature reaches 98°C nor shall the leather shrink when subjected to a temperature of 98°C ± 0.5°C for a period of 30 seconds when tested as specified in 4.3."

PAGE 5

4.3, subparagraph "a". Delete and substitute "a. More than three test specimens fail stitch tearing strength requirements."

Table II, footnote 1/. Delete and substitute "1/ A certificate of compliance shall be submitted and will be acceptable for the requirement stated."

Custodians:

Army - GL
Navy - SA
Air Force - 11

Review activities:

Army - MD
Air Force - 82
DSA-CT

Preparing activity:

Army - GL

Project No. 8330-0139

FSC 8330

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:04Z
Check the source to verify that this is the current version before use.