A-A-1042A
April 28, 1986
SUPERSEDING
A-A-1042
June 11, 1980

COMMERCIAL ITEM DESCRIPTION

STEEL SHOT

The General Services Administration, has authorized the use of this commercial item description in preference to Military Specification MIL-S-851C, type I.

This commercial item description covers hardened cast steel shot for use in blast cleaning equipment for general blasting or peening purposes.

Salient characteristics:

1. Shot numbers shall be 930, 780, 660, 550, 460, 390, 330, 280, 230, 190, 170, 130, 110, or 70.
2. The shot shall be in accordance with the Society of Automotive Engineers (SAE) Standard J444.
3. The shot shall be tested in accordance with SAE Standard J445a and exhibit durability as measured by SAE Standard J445a, using either the Average Life Cycle method or Complete Breakdown method. Shot tested by the Average Life Cycle method shall give a minimum of 1250 cycles; shot tested by the Complete Breakdown method shall typically be as shown in Table I.

TABLE I, Complete Breakdown Method

Shot Size	Durability Cycles	Take-out Screen
930 through 390	2400	40 mesh
330 through 130	3250	50 mesh

4. The shot shall be of the following chemical composition:

Carbon	- 1.20% Max.
Silicon	- 1.50% Max.
Manganese	- 1.20% Max.
Phosphorus	- 0.05% Max.
Sulfur	- 0.05% Max.

Workmanship. The shot shall be free from defective and foreign material that will affect its serviceability. Non-magnetic contamination shall be less than 0.5 percent by volume. Grease, oil, and moisture contamination shall be less than 0.5 percent by weight.

The issues of SAE Standards J444 and J445a in effect on the date of the solicitation shall be used to determine compliance with these requirements.

Preservation, packaging, packing, labeling, and marking. The preservation, packaging, packing, labeling, and marking shall be as specified in the contract or order.

FSC 5350

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:11Z
Check the source to verify that this is the current version before use.

Notes.

Purchaser should specify grit size.

SAE Standards are available from the Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15906.

When this commercial item description is used for procurement, the commercial item certification clause must appear in the solicitation.

NSN's are as follows:

Shot No.	NSN
110	5350-00-819-4057
330	5350-00-270-8462

MILITARY INTEREST:

Army - MR

PREPARING ACTIVITY

GSA - FSS

Review Activity:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:11Z
Check the source to verify that this is the current version before use.