[INCH - POUND]

A-A-1964A
January 14, 1992
SUPERSEDING
A-A-1964
October 15, 1982

COMMERCIAL ITEM DESCRIPTION

ENVELOPE, WALLET

The General Services Administration, Federal Supply Service, Engineering Division, New York, NY 10278; has authorized the use of this Commercial Item Description as a replacement for Federal Specification UU-J-390C which has been canceled.

CLASSIFICATION: Envelope wallets covered by this commercial item description shall be one of the following sizes and expansions, as specified (See Section 6).

Size:	I - 9-1/2" x 11-3/4"
	II - 9-1/2" x 14-3/4"
	III - 9-1/2" x 18"
	IV - 10" x 15"
	V - 10" x 16"
	VI - 9-1/2" x 4"
Expansion:	A - 7/8" - 1 fold
	B - 1-3/4" - 2 folds
	C - 2-5/8" - 3 folds
	D - 3-1/2" - 4 folds

1. SALIENT CHARACTERISTICS:

A. Construction. Envelope wallets shall be provided with flaps and full height gussets. Envelopes shall be supplied in the sizes specified (See Section 6). The leaves of the envelopes shall be two-ply with rounded corners. The color of the outer ply shall be red; the color of the inner ply shall be red, salmon or manila as specified. The flap shall be a continuation of the back leaf and shall overlap the front a minimum of 4 inches when fully expanded. For the 9-1/2" x 4" size the flap shall overlap not less than 2 inches. The flap shall be scored horizontally at various locations for folding the flap within the expansive range of the wallet. The gusset shall be one-ply, single piece construction with a reinforcing strip of cloth, polymeric nonwoven material or latex impregnated fiber not less than 5/8 inch wide completely and securely glued to the top of the gusset on the inside face. The reinforcement strip shall be positioned flush with the top of the

DISTRIBUTION STATEMENT A: Approved for public release; distribution is unlimited

FSC 7530

Source: https://assist.dla.mil -- Downloaded: 202610-26T08:18Z
Check the source to verify that this is the current version before use.

gusset, or no more than 1/8 inch below the top of the gusset, and shall extend fully across the inside width of the gusset, without a break in continuity. The gusset shall be the same color as the outer ply of the leaves. The gusset shall be bonded in place between the plies of the leaves. When the plies and gussets are pulled apart, failure shall be entirely in the paper stock and not the adhesive bond.

When specified, the envelope wallets shall be equipped with elastic loops or ties. The ties shall be either cotton cloth or other suitable material, at least six inches long, which can be securely fastened (See Section 6).

B. Dimensions. Dimensions shall be as specified for the applicable Size and Expansion, with a tolerance of ± 1/16 inch, unless stated otherwise.

C. Physical Properties. The leaves and gussets shall be made of material conforming to the requirements in Table 1:

Table 1

Characteristic	Requirement		TAPPI
	Gusset	Leaves (2-ply)	Test Method
Basis weight, min (24 x 36-500)	120 pounds	240 pounds	T-410
Thickness, min	0.009 inch	0.018 inch	T-411
Bursting strength, min	95 psi	190 psi	T-403
Tearing strength, min (avg, both directions)	280 grams	550 grams	T-414
Fold endurance, min			
Machine direction	600	-	T-511
Cross direction	375	-	

D. Workmanship. The envelope wallets shall be free from holes, tears, creases, wrinkles, blisters, lumps, ply separations, exposed glue edges, and free of any defects which may affect the appearance or serviceability of the item.

2. QUALITY ASSURANCE PROVISIONS:

A. Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:18Z
Check the source to verify that this is the current version before use.

performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

B. Sampling for examination and tests shall be performed in accordance with MIL-STD-105, using the plans specified in Table 2, unless otherwise stated. For the purpose of sampling, a lot shall consist of envelope wallets of the same style, expansion and size. The sample unit shall be one envelope wallet for visual/workmanship and dimensional examination and one fully prepared shipping container for preparation for delivery examination, unless specified otherwise.

Table 2

Examine	Inspection Levels	AQLs (% defective)
Visual/Workmanship Defects	I	2.5
Dimensional Defects	S-3	4.0
Tests	per TAPPI method	per TAPPI method
Preparation for Delivery	S-2	2.5

3. REGULATORY REQUIREMENTS: The contractor shall certify that the product offered shall include a minimum of 50% waste paper, as defined in 40 CFR, Part 250. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

4. PACKAGING, PACKING, AND MARKING: Packaging, packing, and marking shall be as specified in the contract or order.

5. Referenced Documents. The issue of the referenced documents in effect on the date of the solicitation or invitation to bid, shall be used to determine compliance with the requirements stated.

A. Code of Federal Regulations

40 CFR Part 250 - Guideline for federal procurement of paper and paper products containing recovered materials

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:18Z
Check the source to verify that this is the current version before use.

Available from: Superintendent of Documents, U.S. Government Printing Office, Washington DC 20402.

B. TAPPI Methods

T 403 - Bursting strength of paper
T 410 - Grammage of paper and paperboard (weight per unit area)
T 411 - Thickness (caliper) of paper, paperboard, and combined board
T 414 - Internal tearing resistance of paper (Elmendorf-type method)
T 511 - Folding endurance of paper (MIT tester)

Available from: Technical Association of the Pulp and Paper Industry, P.O. Box 105113, Atlanta, GA 30348.

C. Military Standard

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes

Available from: Standardization Documents Order Desk, Bldg. 4D, 700 Robbins Ave., Philadelphia, PA 19111-5094.

6. NOTES: Purchasers should include the following information in procurement documents, as applicable:

A. Title, number and date of specification
B. Size and Expansion required (see CLASSIFICATION and 1.A)
C. Color of Inner Stock required (see 1.A)
D. With or without elastic ties or loops (See 1.A)
E. Packaging, Packing, and Marking required (see 4)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:18Z
Check the source to verify that this is the current version before use.

B. Item Identifiers/Reference Part Number System (for cataloging use only):

AA1964 - A 1 This example describes a 9-1/2" x 11-3/4", 7/8" - 1 fold, Envelope Wallet

Expansion:
1) A - 7/8" - 1 fold
2) B - 1-3/4" - 2 folds
3) C - 2-5/8" - 3 folds
4) D - 3-1/2" - 4 folds

Size:
A) I - 9-1/2" x 11-3/4"
B) II - 9-1/2" x 14-3/4"
C) III - 9-1/2" x 18 "
D) IV - 10" x 15"
E) V - 10" x 16"
F) VI - 9-1/2" x 4"

MILITARY INTEREST:

Review Activities

Navy - SA
Air Force - 84

Custodians

Air Force - 99

PREPARING ACTIVITY:

GSA-FSS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:18Z
Check the source to verify that this is the current version before use.