A-A-1975A
April 3, 1986
SUPERSEDING
A-A-1975
March 15, 1982
NN-D-570B
September 15, 1970

COMMERCIAL ITEM DESCRIPTION

DOWEL, WOOD

The General Services Administration has authorized the use of this commercial item description as a replacement for Federal Specification NN-D-570B which is canceled.

This description covers wood rod dowels and glue dowels.

Salient characteristics:

Dimensions. Length shall be as specified below. Diameter shall be as specified in the contract or order. Dimensions are shown in inches, with millimeter equivalents in parentheses.
Shall be of the following types as specified:
Type I - Rod dowel, 36 (914.4) + 1/2 (13) or - 1/16 (1.5) long.
Type II - Glue dowel, 6 (152.4) + or - 1/16 (1.5) long.
Shall be made of ash, beech, birch, maple, oak, sweet gum, tupelo gum, sycamore, or hickory and have a smooth finish.
Shall have moisture contents as follows when tested in accordance with ASTM D2016.
Type I - not greater than 12 percent.
Type II - not greater than 8 percent.
Cross grain or slope of grain shall not exceed one (1) to twelve (12).
Type I dowels shall have no crook exceeding 3/8 (9.5) per 36 (914.4) nor no bow exceeding 3/4 (19) per 36 (914.4).
Type II dowels shall have minimum of two grooves, diametrically opposite each other, or spiral grooves, or both, extending the length of each dowel. The ends of type II dowels shall be slightly chamfered.
The depth of the grooves shall be no less than 0.012 (0.31) inch for 1/2 (13) inch or less in diameter. The depth of grooves shall not be less than 0.019 (0.48) for glue dowels over 1/2 inch.
Shall have a diameter of 1/8 (3.2), 3/16 (4.8), 1/4 (6.3), 5/16 (7.9), 3/8 (9.5), 7/16 (11), 1/2 (13), 5/8 (16), 3/4 (19), 7/8 (22), and 1 (25) inch (mm).
The tolerance on the diameter shall be ± 3 percent.

The issue of ASTM D2016 in effect on the date of solicitation shall be used to determine moisture content.

FSC 5510

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:18Z
Check the source to verify that this is the current version before use.

Inspection. Sampling for inspection shall be in accordance with MIL-STD-105. A lot shall consist of dowels of one type and diameter, made from the same wood species, under the same conditions. The sample unit shall be one dowel. Examine for visual and dimensional defects using inspection levels S-3, AQL 2.5 percent defective. Test for moisture content using level S-2, AQL 1.5 percent defective.

Preservation, packaging, packing, labeling, and marking. The preservation, packaging, packing, labeling, and marking shall be as specified in the contract or order.

Notes.

Purchaser should specify type and diameter.

ASTM Standards are available from the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

Military Standards are available from the Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

The commercial item certification clause is not required when this commercial item description is used for procurement.

NSN's shall be as follows:

Type	Dia.	NSN
I	1/8 (3.2)	5510-00-237-8254
I	3/16 (4.8)	5510-00-223-7182
I	1/4 (6.3)	5510-00-240-0067
I	5/16 (7.9)	5510-00-223-0952
I	3/8 (9.5)	5510-00-240-0068
I	7/16 (11.0)	5510-00-497-5463
I	1/2 (13)	5510-00-240-0069
I	5/8 (15)	5510-00-240-0070
I	3/4 (19)	5510-00-240-0071
I	7/8 (22.0)	5510-00-978-6858
I	1 (25.4)	5510-00-223-0953
I	1-1/18 (28.6)	5510-00-223-0954
I	1-1/4 (31.8)	5510-00-223-0955
I	1-1/2 (38)	5519-00-223-9856

MILITARY INTEREST:

Military coordinating Activity:
DEFENSE SUPPLY CENTER - CS

Custodians
ARMY - ME
AIR FORCE - 99

Review Interest
AIR FORCE - 84

PREPARING ACTIVITY:

GSA - FSS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:18Z
Check the source to verify that this is the current version before use.